

FORM PTO-1360 (REV. 11-2000)		U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE		ATTORNEY'S DOCKET NUMBER ZU-403	
TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371				U.S. APPLICATION NO. (if known, see 37 CFR 1.55) <div style="font-size: 1.2em; font-weight: bold;">09/857687</div>	
INTERNATIONAL APPLICATION NO. PCT/JP00/06945		INTERNATIONAL FILING DATE 5 October 2000		PRIORITY DATE CLAIMED 8 October 1999	
TITLE OF INVENTION <u>Metallocene Compound, Process for Preparing Metallocene Compound</u> <u>Olefin Polymerization Catalyst, Process for Preparing Polyolefin and Polyolefin</u> APPLICANT(S) FOR DO/EO/US <u>Koji KAWAI, et al.</u>					
Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:					
1. <input checked="" type="checkbox"/> This is a FIRST submission of items concerning a filing under 35 U.S.C. 371. 2. <input type="checkbox"/> This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371. 3. <input type="checkbox"/> This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (21) indicated below. 4. <input type="checkbox"/> The US has been elected by the expiration of 19 months from the priority date (Article 31). 5. <input checked="" type="checkbox"/> A copy of the International Application as filed (35 U.S.C. 371(c)(2)) a. <input type="checkbox"/> is attached hereto (required only if not communicated by the International Bureau). b. <input checked="" type="checkbox"/> has been communicated by the International Bureau. c. <input type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US). 6. <input checked="" type="checkbox"/> An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)). a. <input checked="" type="checkbox"/> is attached hereto. b. <input type="checkbox"/> has been previously submitted under 35 U.S.C. 154(d)(4). 7. <input checked="" type="checkbox"/> Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)) a. <input type="checkbox"/> are attached hereto (required only if not communicated by the International Bureau). b. <input type="checkbox"/> have been communicated by the International Bureau. c. <input type="checkbox"/> have not been made; however, the time limit for making such amendments has NOT expired. d. <input checked="" type="checkbox"/> have not been made and will not be made. 8. <input type="checkbox"/> An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371 (c)(3)). 9. <input checked="" type="checkbox"/> An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)). 10. <input type="checkbox"/> An English language translation of the annexes of the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).					
Items 11 to 20 below concern document(s) or information included:					
11. <input type="checkbox"/> An Information Disclosure Statement under 37 CFR 1.97 and 1.98. 12. <input checked="" type="checkbox"/> An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included. 13. <input checked="" type="checkbox"/> A FIRST preliminary amendment. 14. <input type="checkbox"/> A SECOND or SUBSEQUENT preliminary amendment. 15. <input type="checkbox"/> A substitute specification. 16. <input type="checkbox"/> A change of power of attorney and/or address letter. 17. <input type="checkbox"/> A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821 - 1.825. 18. <input type="checkbox"/> A second copy of the published international application under 35 U.S.C. 154(d)(4). 19. <input type="checkbox"/> A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4). 20. <input checked="" type="checkbox"/> Other items or information: <u>Copy of PCT/IB/308</u> <u>One (1) Sheet Formal Drawing</u>					

U.S. APPLICATION NO. 097857687		INTERNATIONAL APPLICATION NO. PCT/JP00/06945		ATTORNEY'S DOCKET NUMBER ZU-403	
21. <input checked="" type="checkbox"/> The following fees are submitted: BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)): Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO \$1000.00 International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO \$860.00 International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO \$710.00 International preliminary examination fee (37 CFR 1.482) paid to USPTO but all claims did not satisfy provisions of PCT Article 33(1)-(4) \$690.00 International preliminary examination fee (37 CFR 1.482) paid to USPTO and all claims satisfied provisions of PCT Article 33(1)-(4) \$100.00 ENTER APPROPRIATE BASIC FEE AMOUNT =				CALCULATIONS PTO USE ONLY <div style="border: 1px solid black; padding: 2px;"> \$ 860.00 </div>	
Surcharge of \$130.00 for furnishing the oath or declaration later than months from the earliest claimed priority date (37 CFR 1.492(e)). <input type="checkbox"/> 20 <input type="checkbox"/> 30				<div style="border: 1px solid black; padding: 2px;"> \$ 0 </div>	
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE	\$	
Total claims	49 - 20 =	29	x \$18.00	\$ 522.00	
Independent claims	7 - 3 =	4	x \$80.00	\$ 320.00	
MULTIPLE DEPENDENT CLAIM(S) (if applicable)				+ \$270.00	
TOTAL OF ABOVE CALCULATIONS =				\$ 1,972.00	
<input checked="" type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27. The fees indicated above are reduced by 1/2.				<div style="border: 1px solid black; padding: 2px;"> \$ 0 </div>	
SUBTOTAL =				\$ 1,972.00	
Processing fee of \$130.00 for furnishing the English translation later than months from the earliest claimed priority date (37 CFR 1.492(f)). <input type="checkbox"/> 20 <input type="checkbox"/> 30				<div style="border: 1px solid black; padding: 2px;"> \$ 0 </div>	
TOTAL NATIONAL FEE =				\$ 1,972.00	
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property +				\$ 40.00	
TOTAL FEES ENCLOSED =				\$ 2,012.00	
				Amount to be refunded:	\$
				charged:	\$
a. <input checked="" type="checkbox"/> A check in the amount of \$ <u>2,012.00</u> to cover the above fees is enclosed. b. <input type="checkbox"/> Please charge my Deposit Account No. _____ in the amount of \$ _____ to cover the above fees. A duplicate copy of this sheet is enclosed. c. <input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. <u>19-1980</u> . A duplicate copy of this sheet is enclosed. d. <input type="checkbox"/> Fees are to be charged to a credit card. WARNING: Information on this form may become public. Credit card information should not be included on this form. Provide credit card information and authorization on PTO-2038.					
NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137 (a) or (b)) must be filed and granted to restore the application to pending status.					
SEND ALL CORRESPONDENCE TO: <div style="display: flex; justify-content: space-between;"> <div style="width: 45%;"> SHERMAN & SHALLOWAY 413 N. Washington Street Alexandria, VA 22314 703-549-2282 </div> <div style="width: 45%; text-align: right;"> SIGNATURE _____ Leonard W. Sherman NAME _____ 19,636 REGISTRATION NUMBER _____ </div> </div>					

ZU-403

PATENT

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re the application of:

Koji KAWAI, et al.

Serial No.: Unassigned

Group:

Filed: Concurrently

Examiner:

FOR: METALLOCENE COMPOUND, PROCESS FOR PREPARING METALLOCENE
COMPOUND, OLEFIN POLYMERIZATION CATALYST, PROCESS FOR PREPARING
POLYOLEFIN AND POLYOLEFIN

Date: June 7, 2001

The Hon. Commissioner of
Patents and Trademarks
Washington, D.C. 20231

PRELIMINARY AMENDMENT

Sir:

Preliminary to examination, please amend the herewith filed
application as follows:

IN THE CLAIMS

Please cancel claims 11-13 in their entirety and without
prejudice.

Please enter the following new claims:

--20. (New) A process for preparing a polyolefin
comprising polymerizing or copolymerizing an olefin in the
presence of the olefin polymerization catalyst of claim 8.

21. (New) The process for preparing a polyolefin as claimed

in claim 20, wherein the metallocene compound is the metallocene compound represented by the formula (1) or (2), and at least 2 kinds of olefins are copolymerized.

22. (New) The process for preparing a polyolefin as claimed in claim 20, wherein the metallocene compound is the metallocene compound represented by the formula (1a) or (2a), and a single olefin is polymerized.

23. (New) A process for preparing a polyolefin comprising polymerizing or copolymerizing an olefin in the presence of the olefin polymerization catalyst of claim 9.

24. (New) The process for preparing a polyolefin as claimed in claim 23, wherein the metallocene compound (A) is the metallocene compound represented by the formula (1) or (2), and at least 2 kinds of olefins are copolymerized.

25. (New) The process for preparing a polyolefin as claimed in claim 23, wherein the metallocene (A) compound is the metallocene compound represented by the formula (1a) or (2a), and a single olefin is polymerized.

26. (New) A process for preparing a polyolefin comprising polymerizing or copolymerizing an olefin in the presence of the olefin polymerization catalyst of claim 10.

27. (New) The process for preparing a polyolefin as claimed in claim 26, wherein the metallocene (A) compound is the metallocene compound represented by the formula (1) or (2), and at least 2 kinds of olefins are copolymerized.

28. (New) The process for preparing a polyolefin as claimed in claim 26, wherein the metallocene (A) compound is the metallocene compound represented by the formula (1a) or (2a), and a single olefin is polymerized.

REMARKS


Entry of the foregoing amendment prior to examination of this application is respectfully requested in view of the following comments.

Claims 11-13 have been cancelled and new claims 20-28 have been added. Accordingly, claims 1-10 and 14-28 are pending in this application.

Claims 11-13 have been cancelled to eliminate their improper multiple dependency. New claims 20-28 correspond to claims 11-13 rewritten in proper single dependent form.

No new matter has been added and applicant respectfully submits that this application is in condition for allowance and an early notice to that effect is earnestly solicited.

Respectfully submitted,


Attorney for Applicants
Leonard W. Sherman
Reg. No. 19,636

SHERMAN & SHALLOWAY
P.O. BOX 788
Alexandria, Virginia 22313
(703) 549-2282

TITLE

METALLOCENE COMPOUND, PROCESS FOR PREPARING
METALLOCENE COMPOUND, OLEFIN POLYMERIZATION CATALYST,
PROCESS FOR PREPARING POLYOLEFIN, AND POLYOLEFIN

5

TECHNICAL FIELD

The present invention relates to a metallocene compound having a specific structure, a process for preparing the metallocene compound, an olefin
10 polymerization catalyst containing the metallocene compound, a process for preparing a polyolefin using the olefin polymerization catalyst, and a polyolefin.

BACKGROUND ART

15 The "metallocene compound" is well known as a homogeneous catalyst for olefin polymerization. Since the isotactic polymerization was reported by W. Kaminsky, et al. (Angew. Chem. Int. Ed. Engl., 24, 507 (1985)), there have been made many improvements in the
20 olefin polymerization process using a metallocene compound, particularly a process for stereoregularly polymerizing an α -olefin. As an example of the improvement, a metallocene compound having a C2 symmetric structure wherein some hydrogen atoms of the cyclopentadienyl group in the ligand part are replaced

09857687-060801

- with alkyl groups has been reported (by Yamazaki, et al., Chemistry Letters, 1853 (1989), Japanese Patent Laid-Open Publication No. 268307/1992). As like attempts, further, a large number of attempts to
- 5 improve the isotactic stereoregularity of an olefin polymer by the use of a metallocene compound having, as a ligand, a bisindenyl derivative having a C2 symmetric structure have been reported (e.g., Angew. Chem. Int. Ed. Engl., 31, 1347 (1992), Organometallics,
- 10 13, 954 (1994)).

- The metallocene compound of the C2 symmetric structure, however, is usually obtained as a mixture of a racemic modification and a mesoisomer, and only the racemic modification provides an isotactic polymer,
- 15 while obtainable from the mesoisomer is only an atactic polymer, so that it is necessary to separate the racemic modification and the mesoisomer from each other in order to selectively obtain the isotactic polymer.

- 20 On the other hand, J.A. Ewen has found that an α -olefin is polymerized with syndiotactic stereoregularity by the use of a metallocene compound having a Cs symmetric structure wherein the cyclopentadienyl group and the fluorenyl group are
- 25 bridged by dimethylmethylene (J. Am. Chem. Soc., 110,

09557687-060801

6255 (1988)). To improve the metallocene compound, an attempt to introduce tert-butyl groups at the 2-position and the 7-position of the fluorenyl group and thereby further control the syndiotactic

- 5 stereoregularity has been made (Japanese Patent Laid-Open Publication No. 69394/1992).

In addition, an attempt to synthesize an isotactic polymer by the use of a metallocene compound having a C1 symmetric structure that is different from the C2
10 symmetric and the Cs symmetric structures has been reported (see, for example, Japanese Patent Laid-Open Publications No. 193796/1991 and No. 122718/1994, EP 0881236).

- The polymerization activities of these metallocene
15 compounds, however, are still insufficient, and hence development of metallocene compounds having excellent polymerization activities and olefin polymerization catalysts containing such metallocene compounds has been desired.

- 20 The metallocene compounds having Cs and C1 symmetric structures have an advantage in that the structural isomers such as a mesoisomer and a racemic modification are not produced, differently from the metallocene compound having a C2 symmetric structure.

09857687-060801


Of the above metallocene compounds, the metallocene compound of the C1 symmetric structure, however, has a problem in that an unnecessary isomer wherein the substituent group is attached at a position different from the intended proper position is produced depending upon the preparation process. When such an isomer is used as, for example, an olefin polymerization catalyst, unfavorable results such as production of an atactic polymer as a by-product are often brought about. Hence, development of a process for selectively preparing a metallocene compound in which such an unnecessary isomer is not included has been desired.

DISCLOSURE OF THE INVENTION


The metallocene compound according to the invention is represented by the following formula (1) or (2):

09857687.050801

5



... (1)



... (2)

10

wherein R^3 is selected from a hydrocarbon group and a silicon-containing hydrocarbon group; R^1 , R^2 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , R^{11} , R^{12} , R^{13} and R^{14} may be the same or different and are each selected from a

15

hydrogen atom, a hydrocarbon group and a silicon-containing hydrocarbon group; of the groups indicated by R^1 to R^{12} , neighboring groups may be bonded to form a ring; in case of the formula (1), a group selected from R^1 , R^4 , R^5 and R^{12} may be bonded to R^{13} or R^{14} to

20


form a ring; A is a divalent hydrocarbon group of 2 to 20 carbon atoms which may contain an unsaturated bond and/or an aromatic ring; A may contain two or more cyclic structures including a ring formed by A in cooperation with Y; Y is a carbon atom or a silicon

25

atom; M is a metal selected from Group 4 of the

periodic table; j is an integer of 1 to 4; Q is selected from a halogen atom, a hydrocarbon group, an anionic ligand and a neutral ligand capable of coordination by a lone pair; and when j is 2 or greater, each Q may be the same or different.

Another embodiment of the metallocene compound of the invention is represented by the following formula (1a) or (2a):



wherein R^3 is selected from a hydrocarbon group and a silicon-containing hydrocarbon group; R^1 , R^2 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , R^{11} , R^{12} , R^{13} and R^{14} may be the same or different and are each selected from a hydrogen atom, a hydrocarbon group and a silicon-containing hydrocarbon group; in case of a compound of the formula (1a), when R^3 is a tert-butyl group or a


trimethylsilyl group and when R^{13} and R^{14} are methyl groups or phenyl groups at the same time, R^6 and R^{11} are not hydrogen atoms at the same time; of the groups indicated by R^1 to R^{12} , neighboring groups may be

- 5 bonded to form a ring; in case of the formula (1a), a group selected from R^1 , R^4 , R^5 and R^{12} may be bonded to R^{13} or R^{14} to form a ring; A is a divalent hydrocarbon group of 2 to 20 carbon atoms which may contain an unsaturated bond and/or an aromatic ring; A
- 10 may contain two or more cyclic structures including a ring formed by A in cooperation with Y; Y is a carbon atom or a silicon atom; M is a metal selected from Group 4 of the periodic table; j is an integer of 1 to 4; Q is selected from a halogen atom, a hydrocarbon
- 15 group, an anionic ligand and a neutral ligand capable of coordination by a lone pair; and when j is 2 or greater, each Q may be the same or different.


A further embodiment of the metallocene compound of the invention is represented by the following

- 20 formula (1b) or (2b):

09857687-060801



... (1b)



... (2b)

10

wherein R²¹ and R²² may be the same or different and are each selected from a hydrocarbon group and a silicon-containing hydrocarbon group; R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, R¹¹, R¹², R¹³ and R¹⁴ may be the same or

15 different and are each selected from a hydrogen atom, a hydrocarbon group and a silicon-containing

hydrocarbon group; of the groups indicated by R⁵ to R¹², neighboring groups may be bonded to form a ring;

A is a divalent hydrocarbon group of 2 to 20 carbon



20 atoms which may contain an unsaturated bond and/or an aromatic ring; A may contain two or more cyclic structures including a ring formed by A in cooperation with Y; M is a metal selected from Group 4 of the periodic table; Y is a carbon atom or a silicon atom;

25 j is an integer of 1 to 4; Q is selected from a

09857687-060301


halogen atom, a hydrocarbon group, an anionic ligand and a neutral ligand capable of coordination by a lone pair; and when j is 2 or greater, each Q may be the same or different.

- 5 The process for preparing a metallocene compound according to the invention comprises selectively preparing a metallocene compound represented by the above formula (1b) or (2b) so as not to include an isomeric compound represented by the following formula
- 10 (3b), (4b), (5b) or (6b):




20

09857687-060801



... (5b)




... (6b)


10

wherein R²¹, R²², R⁵ to R¹⁴, A, M, Y, Q and j have the same meanings as those of R²¹, R²², R⁵ to R¹⁴, A, M, Y, Q and j in the formula (1b) or (2b), respectively.

- In the present invention, it is preferable that a
- 15 ligand precursor represented by the following formula (7b) or (8b) is selectively prepared so as not to include an isomeric compound represented by the following formula (9b), (10b), (11b) or (12b) and the resulting ligand precursor is used as a material to
- 20 selectively prepare the metallocene compound represented by the formula (1b) or (2b);



... (7b)




... (8b)

10

wherein R²¹, R²², R⁵ to R¹⁴, A and Y have the same meanings as those of R²¹, R²², R⁵ to R¹⁴, A and Y in the formula (1b) or (2b), respectively; and the cyclopentadienyl group may be another isomer different


15

in only the position of a double bond in the cyclopentadienyl ring or a mixture thereof;




25


... (9b)



... (10b)



... (11b)



... (12b)


10

wherein R²¹, R²², R⁵ to R¹⁴, A and Y have the same meanings as those of R²¹, R²², R⁵ to R¹⁴, A and Y in the formula (1b) or (2b), respectively; and the cyclopentadienyl group may be another isomer different in only the position of a double bond in the cyclopentadienyl ring or a mixture thereof.

15


In the present invention, further, it is preferable that a precursor compound represented by the following formula (13b) or (14b) is selectively prepared so as not to include an isomeric compound represented by the following formula (15b), (16b), (17b) or (18b) and the resulting precursor compound is used as a material to selectively prepare the ligand precursor represented by the formula (7b) or (8b);

25



5


...(13b)



...(14b)


wherein R²¹, R²², R¹³, R¹⁴, Y and A have the same meanings as those of R²¹, R²², R¹³, R¹⁴, Y and A in

10 the formula (1b) or (2b), respectively;




15


...(15b)



...(16b)



...(17b)



...(18b)


wherein R²¹, R²², R¹³, R¹⁴, Y and A have the same meanings as those of R²¹, R²², R¹³, R¹⁴, Y and A in

20 the formula (1b) or (2b), respectively.


In the present invention, furthermore, it is preferable that cyclopentadiene represented by the following formula (19b) is selectively prepared so as not to include an isomeric compound represented by the

25 following formula (20b) and the resulting

cyclopentadiene is used as a material to selectively prepare the precursor compound represented by the formula (13b) or (14b);



- wherein R²¹ and R²² have the same meanings as those of R²¹ and R²² in the formula (1b) or (2b), respectively;
- 10 and the cyclopentadienyl group may be another isomer different in only the position of a double bond in the cyclopentadienyl ring or a mixture thereof;



- wherein R²¹ and R²² have the same meanings as those of R²¹ and R²² in the formula (1b) or (2b), respectively;
- 20 and the cyclopentadienyl group may be another isomer different in only the position of a double bond in the cyclopentadienyl ring or a mixture thereof.

The olefin polymerization catalyst according to the invention comprises any one of the above-mentioned metallocene compounds.

The olefin polymerization catalyst of the invention may be an olefin polymerization catalyst comprising:

(A) any one of the above-mentioned metallocene
5 compounds, and

(B) at least one compound selected from:

(B-1) an organometallic compound,

(B-2) an organoaluminum oxy-compound, and

(B-3) a compound which reacts with the
10 metallocene compound (A) to form an ion pair.

The olefin polymerization catalyst of the invention may be an olefin polymerization catalyst comprising the above-mentioned olefin polymerization catalyst and (C) a particle carrier.

15 The process for preparing a polyolefin according to the invention comprises polymerizing or copolymerizing an olefin in the presence of any one of the above-mentioned olefin polymerization catalysts.

In the present invention, it is preferable that
20 the metallocene compound (A) is a metallocene compound represented by the formula (1) or (2) and at least 2 kinds of olefins are copolymerized. It is also preferable that the metallocene compound (A) is a metallocene compound represented by the formula (1a)
25 or (2a) and a single olefin is polymerized.

09857687.060801

0357687 00001
10090 2892560

The polyolefin according to the invention comprises recurring units (U₁) derived from one α -olefin selected from α -olefins of 3 to 8 carbon atoms in amounts of 50 to 100 % by mol and recurring units
5 (U₂) other than the recurring units (U₁), said recurring units (U₂) being derived from at least one olefin selected from α -olefins of 2 to 20 carbon atoms, in amounts of 50 to 0 % by mol, and has the following properties:

- 10 (i) the proportion of 2,1-insertion and the proportion of 1,3-insertion are each not more than 0.2 %, (ii) the molecular weight distribution (Mw/Mn) as determined by gel permeation chromatography is in the
15 range of 1 to 3, and (iii) the quantity of a decane-soluble component is not more than 2 % by weight.

The polyolefin preferably comprises recurring units derived from propylene in amounts of 50 to
20 99.5 % by mol and recurring units derived from at least one olefin selected from α -olefins of 2 to 20 carbon atoms other than propylene in amounts of 50 to 0.5 % by mol.

Another embodiment of the polyolefin of the
25 invention is a homopolymer of one α -olefin selected

from α -olefins of 3 to 8 carbon atoms and has the following properties:

- (i) the pentad isotacticity as determined from ^{13}C -NMR spectrum measurement is not less than 85 %,
- 5 (ii) the proportion of 2,1-insertion and the proportion of 1,3-insertion are each not more than 0.2 %,
- (iii) the MFR is in the range of 0.01 to 1000 g/10 min,
- 10 (iv) the molecular weight distribution (M_w/M_n) as determined by gel permeation chromatography is in the range of 1 to 3,
- (v) the quantity of a decane-soluble component is not more than 2 % by weight, and
- 15 (vi) the melting point (T_m) as measured by a differential scanning calorimeter is not lower than 140°C.

The polyolefin is preferably a homopolymer of propylene.

- 20 A further embodiment of the polyolefin of the invention is a polyolefin comprising recurring units (U_1) derived from one α -olefin selected from α -olefins of 3 to 8 carbon atoms in amounts of 95 to 99.5 % by mol and recurring units (U_2) other than the recurring
- 25 units (U_1), said recurring units (U_2) being derived

00357607 000001

from at least one olefin selected from α -olefins of 2 to 20 carbon atoms, in amounts of 5 to 0.05 % by mol, and has the following properties:

- (i) the pentad isotacticity as determined from
5 ^{13}C -NMR spectrum measurement is not less than 80 %,
- (ii) the proportion of 2,1-insertion and the proportion of 1,3-insertion are each not more than 0.2 %,
- (iii) the MFR is in the range of 0.01 to 1000 g/10
10 min,
- (iv) the molecular weight distribution (M_w/M_n) as determined by gel permeation chromatography is in the range of 1 to 3,
- (v) the quantity of a decane-soluble component is
15 not more than 2 % by weight, and
- (vi) the melting point (T_m) as measured by a differential scanning calorimeter is not higher than 145°C.

- The polyolefin preferably comprises recurring
20 units derived from propylene in amounts of 95 to 99.5 % by mol and recurring units derived from at least one olefin selected from α -olefins of 2 to 20 carbon atoms other than propylene in amounts of 5 to 0.5 % by mol.

BRIEF DESCRIPTION OF THE DRAWING

Fig. 1 is a view to explain an embodiment of a process for preparing the olefin polymerization catalyst according to the present invention.

5

BEST MODE FOR CARRYING OUT THE INVENTION


The metallocene compound, the process for preparing the metallocene compound, the olefin polymerization catalyst, the process for preparing a polyolefin, and the polyolefin according to the invention are described in detail hereinafter.

Metallocene compound


The metallocene compound according to the invention is represented by the following formula (1)

15 or (2).

20



... (1)



... (2)

25

In the formula (1) or (2), R^3 is selected from a hydrocarbon group and a silicon-containing hydrocarbon group.

- The hydrocarbon group preferably is, for example,
- 5 an alkyl group of 1 to 20 carbon atoms, an arylalkyl group of 7 to 20 carbon atoms, an aryl group of 6 to 20 carbon atoms or an alkylaryl group of 7 to 20 carbon atoms. R^3 may be a cyclic hydrocarbon group containing a heteroatom (e.g., sulfur or oxygen), such
- 10 as thienyl or furyl.

- Specific examples of such groups include methyl, ethyl, n-propyl, isopropyl, 2-methylpropyl, 1,1-dimethylpropyl, 2,2-dimethylpropyl, 1,1-diethylpropyl, 1-ethyl-1-methylpropyl, 1,1,2,2-tetramethylpropyl,
- 15 sec-butyl, tert-butyl, 1,1-dimethylbutyl, 1,1,3-trimethylbutyl, neopentyl, cyclohexylmethyl, cyclohexyl, 1-methyl-1-cyclohexyl, 1-adamantyl, 2-adamantyl, 2-methyl-2-adamantyl, menthyl, norbornyl, benzyl, 2-phenylethyl, 1-tetrahydronaphthyl, 1-methyl-
- 20 1-tetrahydronaphthyl, phenyl, naphthyl and tolyl.

The silicon-containing hydrocarbon group is preferably an alkylsilyl or arylsilyl group having 1 to 4 silicon atoms and 3 to 20 carbon atoms.

09857687-06001

Specific examples of such groups include trimethylsilyl, tert-butyldimethylsilyl and triphenylsilyl.

- 5 R^3 is preferably a sterically bulky substituent group, more preferably a substituent group of 4 or more carbon atoms.

- 10 In the formula (1) or (2), R^1 , R^2 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , R^{11} , R^{12} , R^{13} and R^{14} may be the same or different and are each selected from a hydrogen atom, a hydrocarbon group and a silicon-containing hydrocarbon group. Preferred examples of the hydrocarbon groups and the silicon-containing hydrocarbon groups include the same ones as described above.

- 15 The neighboring substituent groups of R^1 to R^4 on the cyclopentadienyl ring may be bonded to form a ring. Examples of such substituted cyclopentadienyl groups include indenyl, 2-methylindenyl, tetrahydroindenyl, 2-methyltetrahydroindenyl and 2,4,4-trimethyltetrahydroindenyl.

20 The neighboring substituent groups of R^5 to R^{12} on the fluorene ring may be bonded to form a ring. Examples of such substituted fluorenyl groups include benzofluorenyl, dibenzofluorenyl,

0057607-060801

octahydrodibenzofluorenyl and
octamethyloctahydrodibenzofluorenyl.

- The substituent groups of R⁵ to R¹² on the fluorene ring are preferred to be bilaterally
- 5 symmetric from the viewpoint of ease of synthesis. That is, R⁵ and R¹², R⁶ and R¹¹, R⁷ and R¹⁰, and R⁸ and R⁹ are preferred to be the same groups, and unsubstituted fluorene, 3,6-di-substituted fluorene, 2,7-di-substituted fluorene or 2,3,6,7-tetra-
- 10 substituted fluorene is more preferred. The 3-position, 6-position, 2-position and 7-position of the fluorene ring correspond to R⁷, R¹⁰, R⁶ and R¹¹, respectively.

In the formula (1) or (2), Y is a carbon atom or a silicon atom.


- 15 In the metallocene compound represented by the formula (1), R¹³ and R¹⁴ are bonded to Y and become a bridge part to form a substituted methylene group or a substituted silylene group. Preferred examples thereof include methylene, dimethylmethylene, diethylmethylene,
- 20 diisopropylmethylene, methyl-tert-butylmethylene, di-tert-butylmethylene, dicyclohexylmethylene, methylcyclohexylmethylene, methylphenylmethylene, diphenylmethylene, methylnaphthylmethylene, dinaphthylmethylene, dimethylsilylene,
- 25 diisopropylsilylene, methyl-tert-butylsilylene,

dicyclohexylsilylene, methylcyclohexylsilylene, methylphenylsilylene, diphenylsilylene, methylnaphthylsilylene and dinaphthylsilylene.


- In the metallocene compound represented by the
- 5 formula (1), a substituent group selected from R^1 , R^4 , R^5 and R^{12} may be bonded to R^{13} or R^{14} of the bridge part to form a ring. An example of such structure wherein R^1 and R^{14} are bonded to each other to form a ring is given below. In the metallocene compound
- 10 represented by the following formula (1c), the bridge part and the cyclopentadienyl group are united to form tetrahydropentalene skeleton, while in the metallocene compound represented by the following formula (1d), the bridge part and the cyclopentadienyl group are
- 15 united to form tetrahydroindenyl skeleton. Likewise, the bridge part and the fluorenyl group may be bonded to form a ring.

0057607:060001

5



... (1c)



... (1d)

- 10 In the metallocene compound represented by the formula (2), A is a divalent hydrocarbon group of 2 to 20 carbon atoms which may contain an unsaturated bond and/or an aromatic ring, and Y is bonded to A to form a cycloalkylidene group, a cyclomethylenesilylene group or the like.

- A may contain two or more cyclic structures including a ring formed by A in cooperation with Y. Preferred examples thereof include cyclopropylidene, cyclobutylidene, cyclopentylidene, cyclohexylidene, cycloheptylidene, bicyclo[3,3,1]nonylidene, norbornylidene, adamantylidene, tetrahydronaphthylidene, dihydroindanylidene, cyclodimethylenesilylene, cyclotrimethylenesilylene, cyclotetramethylenesilylene, cyclopentamethylenesilylene,

cyclohexamethylenesilylene and
cycloheptamethylenesilylene.

In the formula (1) or (2), M is a metal selected
from Group 4 of the periodic table and is specifically
5 titanium, zirconium or hafnium.

In the formula (1) or (2), j is an integer of 1 to
4.

In the formula (1) or (2), Q is selected from a
halogen atom, a hydrocarbon group of 1 to 20 carbon
10 atoms, an anionic ligand and a neutral ligand capable
of coordination by a lone pair. When j is 2 or greater,
each Q may be the same or different.

Examples of the halogen atoms include fluorine,
chlorine, bromine and iodine. Examples of the
15 hydrocarbon groups include the same ones as previously
described.

Examples of the anionic ligands include alkoxy
groups, such as methoxy, tert-butoxy and phenoxy;
carboxylate groups, such as acetate and benzoate; and
20 sulfonate groups, such as mesylate and tosylate.

Examples of the neutral ligands capable of
coordination by a lone pair include organophosphorus
compounds, such as trimethylphosphine,
triethylphosphine, triphenylphosphine and
25 diphenylmethylphosphine; and ethers, such as

09857687-060001

tetrahydrofuran, diethyl ether, dioxane and 1,2-dimethoxyethane.

At least one of Q is preferably a halogen atom or an alkyl group.

- 5 Examples of the metallocene compounds represented by the formula (1) or (2) according to the invention are given below.




10 The ligand structure excluding MQ_j (metal part) in the metallocene compound is divided into three parts of Cp (cyclopentadienyl ring part), Bridge (bridge part) and Flu (fluorenyl ring part), and specific examples of these partial structures and specific examples of ligand structures formed by combination of these partial structures are described first.

15



09257587 060801

Examples of Cp



5





10



















15



20











25



09057697.00001

Examples of Bridge








5

	b1
	b2
	b3
	b4
	b5
	b6
	b7
	b8

10

15

20

	b9
	b10
	b11
	b12
	b13
	b14
	b15

09857687-060801








Examples of Flu

5

10

15

20

	c1
	c2
	c3
	c4
	c5
	c6
	c7

Examples of the ligand structures are described in the following table.

No.	Cp	Bridge	Flu
1	a 1	b 1	c 1
2	a 2	b 1	c 1
3	a 3	b 1	c 1
4	a 4	b 1	c 1
5	a 5	b 1	c 1
6	a 6	b 1	c 1
7	a 7	b 1	c 1
8	a 8	b 1	c 1
9	a 9	b 1	c 1
10	a 10	b 1	c 1
11	a 11	b 1	c 1
12	a 12	b 1	c 1
13	a 13	b 1	c 1
14	a 14	b 1	c 1
15	a 15	b 1	c 1
16	a 16	b 1	c 1
17	a 17	b 1	c 1
18	a 18	b 1	c 1
19	a 19	b 1	c 1
20	a 20	b 1	c 1
21	a 21	b 1	c 1
22	a 22	b 1	c 1
23	a 23	b 1	c 1
24	a 24	b 1	c 1
25	a 25	b 1	c 1
26	a 1	b 2	c 1
27	a 2	b 2	c 1
28	a 3	b 2	c 1
29	a 4	b 2	c 1
30	a 5	b 2	c 1
31	a 6	b 2	c 1
32	a 7	b 2	c 1
33	a 8	b 2	c 1
34	a 9	b 2	c 1
35	a 10	b 2	c 1
36	a 11	b 2	c 1
37	a 12	b 2	c 1
38	a 13	b 2	c 1
39	a 14	b 2	c 1
40	a 15	b 2	c 1
41	a 16	b 2	c 1
42	a 17	b 2	c 1
43	a 18	b 2	c 1
44	a 19	b 2	c 1
45	a 20	b 2	c 1

09257587.060801

No.	Cp	Bridge	Flu
46	a 21	b 2	c 1
47	a 22	b 2	c 1
48	a 23	b 2	c 1
49	a 24	b 2	c 1
50	a 25	b 2	c 1
51	a 1	b 3	c 1
52	a 2	b 3	c 1
53	a 3	b 3	c 1
54	a 4	b 3	c 1
55	a 5	b 3	c 1
56	a 6	b 3	c 1
57	a 7	b 3	c 1
58	a 8	b 3	c 1
59	a 9	b 3	c 1
60	a 10	b 3	c 1
61	a 11	b 3	c 1
62	a 12	b 3	c 1
63	a 13	b 3	c 1
64	a 14	b 3	c 1
65	a 15	b 3	c 1
66	a 16	b 3	c 1
67	a 17	b 3	c 1
68	a 18	b 3	c 1
69	a 19	b 3	c 1
70	a 20	b 3	c 1
71	a 21	b 3	c 1
72	a 22	b 3	c 1
73	a 23	b 3	c 1
74	a 24	b 3	c 1
75	a 25	b 3	c 1
76	a 1	b 4	c 1
77	a 2	b 4	c 1
78	a 3	b 4	c 1
79	a 4	b 4	c 1
80	a 5	b 4	c 1
81	a 6	b 4	c 1
82	a 7	b 4	c 1
83	a 8	b 4	c 1
84	a 9	b 4	c 1
85	a 10	b 4	c 1
86	a 11	b 4	c 1
87	a 12	b 4	c 1
88	a 13	b 4	c 1
89	a 14	b 4	c 1
90	a 15	b 4	c 1
91	a 16	b 4	c 1

00857697-050801

No.	Cp	Bridge	Flu
92	a 17	b 4	c 1
93	a 18	b 4	c 1
94	a 19	b 4	c 1
95	a 20	b 4	c 1
96	a 21	b 4	c 1
97	a 22	b 4	c 1
98	a 23	b 4	c 1
99	a 24	b 4	c 1
100	a 25	b 4	c 1
101	a 1	b 5	c 1
102	a 2	b 5	c 1
103	a 3	b 5	c 1
104	a 4	b 5	c 1
105	a 5	b 5	c 1
106	a 6	b 5	c 1
107	a 7	b 5	c 1
108	a 8	b 5	c 1
109	a 9	b 5	c 1
110	a 10	b 5	c 1
111	a 11	b 5	c 1
112	a 12	b 5	c 1
113	a 13	b 5	c 1
114	a 14	b 5	c 1
115	a 15	b 5	c 1
116	a 16	b 5	c 1
117	a 17	b 5	c 1
118	a 18	b 5	c 1
119	a 19	b 5	c 1
120	a 20	b 5	c 1
121	a 21	b 5	c 1
122	a 22	b 5	c 1
123	a 23	b 5	c 1
124	a 24	b 5	c 1
125	a 25	b 5	c 1
126	a 1	b 6	c 1
127	a 2	b 6	c 1
128	a 3	b 6	c 1
129	a 4	b 6	c 1
130	a 5	b 6	c 1
131	a 6	b 6	c 1
132	a 7	b 6	c 1
133	a 8	b 6	c 1
134	a 9	b 6	c 1
135	a 10	b 6	c 1
136	a 11	b 6	c 1
137	a 12	b 6	c 1

09857567.030001

No.	Cp	Bridge	Flu
138	a 13	b 6	c 1
139	a 14	b 6	c 1
140	a 15	b 6	c 1
141	a 16	b 6	c 1
142	a 17	b 6	c 1
143	a 18	b 6	c 1
144	a 19	b 6	c 1
145	a 20	b 6	c 1
146	a 21	b 6	c 1
147	a 22	b 6	c 1
148	a 23	b 6	c 1
149	a 24	b 6	c 1
150	a 25	b 6	c 1
151	a 1	b 7	c 1
152	a 2	b 7	c 1
153	a 3	b 7	c 1
154	a 4	b 7	c 1
155	a 5	b 7	c 1
156	a 6	b 7	c 1
157	a 7	b 7	c 1
158	a 8	b 7	c 1
159	a 9	b 7	c 1
160	a 10	b 7	c 1
161	a 11	b 7	c 1
162	a 12	b 7	c 1
163	a 13	b 7	c 1
164	a 14	b 7	c 1
165	a 15	b 7	c 1
166	a 16	b 7	c 1
167	a 17	b 7	c 1
168	a 18	b 7	c 1
169	a 19	b 7	c 1
170	a 20	b 7	c 1
171	a 21	b 7	c 1
172	a 22	b 7	c 1
173	a 23	b 7	c 1
174	a 24	b 7	c 1
175	a 25	b 7	c 1
176	a 1	b 8	c 1
177	a 2	b 8	c 1
178	a 3	b 8	c 1
179	a 4	b 8	c 1
180	a 5	b 8	c 1
181	a 6	b 8	c 1
182	a 7	b 8	c 1
183	a 8	b 8	c 1

09857687.060801

No.	Cp	Bridge	Flu
184	a 9	b 8	c 1
185	a 10	b 8	c 1
186	a 11	b 8	c 1
187	a 12	b 8	c 1
188	a 13	b 8	c 1
189	a 14	b 8	c 1
190	a 15	b 8	c 1
191	a 16	b 8	c 1
192	a 17	b 8	c 1
193	a 18	b 8	c 1
194	a 19	b 8	c 1
195	a 20	b 8	c 1
196	a 21	b 8	c 1
197	a 22	b 8	c 1
198	a 23	b 8	c 1
199	a 24	b 8	c 1
200	a 25	b 8	c 1
201	a 1	b 9	c 1
202	a 2	b 9	c 1
203	a 3	b 9	c 1
204	a 4	b 9	c 1
205	a 5	b 9	c 1
206	a 6	b 9	c 1
207	a 7	b 9	c 1
208	a 8	b 9	c 1
209	a 9	b 9	c 1
210	a 10	b 9	c 1
211	a 11	b 9	c 1
212	a 12	b 9	c 1
213	a 13	b 9	c 1
214	a 14	b 9	c 1
215	a 15	b 9	c 1
216	a 16	b 9	c 1
217	a 17	b 9	c 1
218	a 18	b 9	c 1
219	a 19	b 9	c 1
220	a 20	b 9	c 1
221	a 21	b 9	c 1
222	a 22	b 9	c 1
223	a 23	b 9	c 1
224	a 24	b 9	c 1
225	a 25	b 9	c 1
226	a 1	b 10	c 1
227	a 2	b 10	c 1
228	a 3	b 10	c 1
229	a 4	b 10	c 1

09857687-080801

No.	Cp	Bridge	Flu
230	a 5	b 10	c 1
231	a 6	b 10	c 1
232	a 7	b 10	c 1
233	a 8	b 10	c 1
234	a 9	b 10	c 1
235	a 10	b 10	c 1
236	a 11	b 10	c 1
237	a 12	b 10	c 1
238	a 13	b 10	c 1
239	a 14	b 10	c 1
240	a 15	b 10	c 1
241	a 16	b 10	c 1
242	a 17	b 10	c 1
243	a 18	b 10	c 1
244	a 19	b 10	c 1
245	a 20	b 10	c 1
246	a 21	b 10	c 1
247	a 22	b 10	c 1
248	a 23	b 10	c 1
249	a 24	b 10	c 1
250	a 25	b 10	c 1
251	a 1	b 11	c 1
252	a 2	b 11	c 1
253	a 3	b 11	c 1
254	a 4	b 11	c 1
255	a 5	b 11	c 1
256	a 6	b 11	c 1
257	a 7	b 11	c 1
258	a 8	b 11	c 1
259	a 9	b 11	c 1
260	a 10	b 11	c 1
261	a 11	b 11	c 1
262	a 12	b 11	c 1
263	a 13	b 11	c 1
264	a 14	b 11	c 1
265	a 15	b 11	c 1
266	a 16	b 11	c 1
267	a 17	b 11	c 1
268	a 18	b 11	c 1
269	a 19	b 11	c 1
270	a 20	b 11	c 1
271	a 21	b 11	c 1
272	a 22	b 11	c 1
273	a 23	b 11	c 1
274	a 24	b 11	c 1
275	a 25	b 11	c 1

09857687.060801

No.	Cp	Bridge	Flu
276	a 1	b 12	c 1
277	a 2	b 12	c 1
278	a 3	b 12	c 1
279	a 4	b 12	c 1
280	a 5	b 12	c 1
281	a 6	b 12	c 1
282	a 7	b 12	c 1
283	a 8	b 12	c 1
284	a 9	b 12	c 1
285	a 10	b 12	c 1
286	a 11	b 12	c 1
287	a 12	b 12	c 1
288	a 13	b 12	c 1
289	a 14	b 12	c 1
290	a 15	b 12	c 1
291	a 16	b 12	c 1
292	a 17	b 12	c 1
293	a 18	b 12	c 1
294	a 19	b 12	c 1
295	a 20	b 12	c 1
296	a 21	b 12	c 1
297	a 22	b 12	c 1
298	a 23	b 12	c 1
299	a 24	b 12	c 1
300	a 25	b 12	c 1
301	a 1	b 13	c 1
302	a 2	b 13	c 1
303	a 3	b 13	c 1
304	a 4	b 13	c 1
305	a 5	b 13	c 1
306	a 6	b 13	c 1
307	a 7	b 13	c 1
308	a 8	b 13	c 1
309	a 9	b 13	c 1
310	a 10	b 13	c 1
311	a 11	b 13	c 1
312	a 12	b 13	c 1
313	a 13	b 13	c 1
314	a 14	b 13	c 1
315	a 15	b 13	c 1
316	a 16	b 13	c 1
317	a 17	b 13	c 1
318	a 18	b 13	c 1
319	a 19	b 13	c 1
320	a 20	b 13	c 1
321	a 21	b 13	c 1

09857687-060801

No.	Cp	Bridge	Flu
322	a 22	b 13	c 1
323	a 23	b 13	c 1
324	a 24	b 13	c 1
325	a 25	b 13	c 1
326	a 1	b 14	c 1
327	a 2	b 14	c 1
328	a 3	b 14	c 1
329	a 4	b 14	c 1
330	a 5	b 14	c 1
331	a 6	b 14	c 1
332	a 7	b 14	c 1
333	a 8	b 14	c 1
334	a 9	b 14	c 1
335	a 10	b 14	c 1
336	a 11	b 14	c 1
337	a 12	b 14	c 1
338	a 13	b 14	c 1
339	a 14	b 14	c 1
340	a 15	b 14	c 1
341	a 16	b 14	c 1
342	a 17	b 14	c 1
343	a 18	b 14	c 1
344	a 19	b 14	c 1
345	a 20	b 14	c 1
346	a 21	b 14	c 1
347	a 22	b 14	c 1
348	a 23	b 14	c 1
349	a 24	b 14	c 1
350	a 25	b 14	c 1
351	a 1	b 15	c 1
352	a 2	b 15	c 1
353	a 3	b 15	c 1
354	a 4	b 15	c 1
355	a 5	b 15	c 1
356	a 6	b 15	c 1
357	a 7	b 15	c 1
358	a 8	b 15	c 1
359	a 9	b 15	c 1
360	a 10	b 15	c 1
361	a 11	b 15	c 1
362	a 12	b 15	c 1
363	a 13	b 15	c 1
364	a 14	b 15	c 1
365	a 15	b 15	c 1
366	a 16	b 15	c 1
367	a 17	b 15	c 1

09857687.060201

No.	Cp	Bridge	Flu
368	a 18	b 15	c 1
369	a 19	b 15	c 1
370	a 20	b 15	c 1
371	a 21	b 15	c 1
372	a 22	b 15	c 1
373	a 23	b 15	c 1
374	a 24	b 15	c 1
375	a 25	b 15	c 1
376	a 1	b 1	c 2
377	a 2	b 1	c 2
378	a 3	b 1	c 2
379	a 4	b 1	c 2
380	a 5	b 1	c 2
381	a 6	b 1	c 2
382	a 7	b 1	c 2
383	a 8	b 1	c 2
384	a 9	b 1	c 2
385	a 10	b 1	c 2
386	a 11	b 1	c 2
387	a 12	b 1	c 2
388	a 13	b 1	c 2
389	a 14	b 1	c 2
390	a 15	b 1	c 2
391	a 16	b 1	c 2
392	a 17	b 1	c 2
393	a 18	b 1	c 2
394	a 19	b 1	c 2
395	a 20	b 1	c 2
396	a 21	b 1	c 2
397	a 22	b 1	c 2
398	a 23	b 1	c 2
399	a 24	b 1	c 2
400	a 25	b 1	c 2
401	a 1	b 2	c 2
402	a 2	b 2	c 2
403	a 3	b 2	c 2
404	a 4	b 2	c 2
405	a 5	b 2	c 2
406	a 6	b 2	c 2
407	a 7	b 2	c 2
408	a 8	b 2	c 2
409	a 9	b 2	c 2
410	a 10	b 2	c 2
411	a 11	b 2	c 2
412	a 12	b 2	c 2
413	a 13	b 2	c 2

09857687.060801

No.	Cp	Bridge	Flu
414	a 14	b 2	c 2
415	a 15	b 2	c 2
416	a 16	b 2	c 2
417	a 17	b 2	c 2
418	a 18	b 2	c 2
419	a 19	b 2	c 2
420	a 20	b 2	c 2
421	a 21	b 2	c 2
422	a 22	b 2	c 2
423	a 23	b 2	c 2
424	a 24	b 2	c 2
425	a 25	b 2	c 2
426	a 1	b 3	c 2
427	a 2	b 3	c 2
428	a 3	b 3	c 2
429	a 4	b 3	c 2
430	a 5	b 3	c 2
431	a 6	b 3	c 2
432	a 7	b 3	c 2
433	a 8	b 3	c 2
434	a 9	b 3	c 2
435	a 10	b 3	c 2
436	a 11	b 3	c 2
437	a 12	b 3	c 2
438	a 13	b 3	c 2
439	a 14	b 3	c 2
440	a 15	b 3	c 2
441	a 16	b 3	c 2
442	a 17	b 3	c 2
443	a 18	b 3	c 2
444	a 19	b 3	c 2
445	a 20	b 3	c 2
446	a 21	b 3	c 2
447	a 22	b 3	c 2
448	a 23	b 3	c 2
449	a 24	b 3	c 2
450	a 25	b 3	c 2
451	a 1	b 4	c 2
452	a 2	b 4	c 2
453	a 3	b 4	c 2
454	a 4	b 4	c 2
455	a 5	b 4	c 2
456	a 6	b 4	c 2
457	a 7	b 4	c 2
458	a 8	b 4	c 2
459	a 9	b 4	c 2

09857687-060801

No.	Cp	Bridge	Flu
460	a 10	b 4	c 2
461	a 11	b 4	c 2
462	a 12	b 4	c 2
463	a 13	b 4	c 2
464	a 14	b 4	c 2
465	a 15	b 4	c 2
466	a 16	b 4	c 2
467	a 17	b 4	c 2
468	a 18	b 4	c 2
469	a 19	b 4	c 2
470	a 20	b 4	c 2
471	a 21	b 4	c 2
472	a 22	b 4	c 2
473	a 23	b 4	c 2
474	a 24	b 4	c 2
475	a 25	b 4	c 2
476	a 1	b 5	c 2
477	a 2	b 5	c 2
478	a 3	b 5	c 2
479	a 4	b 5	c 2
480	a 5	b 5	c 2
481	a 6	b 5	c 2
482	a 7	b 5	c 2
483	a 8	b 5	c 2
484	a 9	b 5	c 2
485	a 10	b 5	c 2
486	a 11	b 5	c 2
487	a 12	b 5	c 2
488	a 13	b 5	c 2
489	a 14	b 5	c 2
490	a 15	b 5	c 2
491	a 16	b 5	c 2
492	a 17	b 5	c 2
493	a 18	b 5	c 2
494	a 19	b 5	c 2
495	a 20	b 5	c 2
496	a 21	b 5	c 2
497	a 22	b 5	c 2
498	a 23	b 5	c 2
499	a 24	b 5	c 2
500	a 25	b 5	c 2
501	a 1	b 6	c 2
502	a 2	b 6	c 2
503	a 3	b 6	c 2
504	a 4	b 6	c 2
505	a 5	b 6	c 2

09857687.060801

No.	Cp	Bridge	Flu
506	a 6	b 6	c 2
507	a 7	b 6	c 2
508	a 8	b 6	c 2
509	a 9	b 6	c 2
510	a 10	b 6	c 2
511	a 11	b 6	c 2
512	a 12	b 6	c 2
513	a 13	b 6	c 2
514	a 14	b 6	c 2
515	a 15	b 6	c 2
516	a 16	b 6	c 2
517	a 17	b 6	c 2
518	a 18	b 6	c 2
519	a 19	b 6	c 2
520	a 20	b 6	c 2
521	a 21	b 6	c 2
522	a 22	b 6	c 2
523	a 23	b 6	c 2
524	a 24	b 6	c 2
525	a 25	b 6	c 2
526	a 1	b 7	c 2
527	a 2	b 7	c 2
528	a 3	b 7	c 2
529	a 4	b 7	c 2
530	a 5	b 7	c 2
531	a 6	b 7	c 2
532	a 7	b 7	c 2
533	a 8	b 7	c 2
534	a 9	b 7	c 2
535	a 10	b 7	c 2
536	a 11	b 7	c 2
537	a 12	b 7	c 2
538	a 13	b 7	c 2
539	a 14	b 7	c 2
540	a 15	b 7	c 2
541	a 16	b 7	c 2
542	a 17	b 7	c 2
543	a 18	b 7	c 2
544	a 19	b 7	c 2
545	a 20	b 7	c 2
546	a 21	b 7	c 2
547	a 22	b 7	c 2
548	a 23	b 7	c 2
549	a 24	b 7	c 2
550	a 25	b 7	c 2
551	a 1	b 8	c 2

09857687.060801

No.	Cp	Bridge	Flu
552	a 2	b 8	c 2
553	a 3	b 8	c 2
554	a 4	b 8	c 2
555	a 5	b 8	c 2
556	a 6	b 8	c 2
557	a 7	b 8	c 2
558	a 8	b 8	c 2
559	a 9	b 8	c 2
560	a 10	b 8	c 2
561	a 11	b 8	c 2
562	a 12	b 8	c 2
563	a 13	b 8	c 2
564	a 14	b 8	c 2
565	a 15	b 8	c 2
566	a 16	b 8	c 2
567	a 17	b 8	c 2
568	a 18	b 8	c 2
569	a 19	b 8	c 2
570	a 20	b 8	c 2
571	a 21	b 8	c 2
572	a 22	b 8	c 2
573	a 23	b 8	c 2
574	a 24	b 8	c 2
575	a 25	b 8	c 2
576	a 1	b 9	c 2
577	a 2	b 9	c 2
578	a 3	b 9	c 2
579	a 4	b 9	c 2
580	a 5	b 9	c 2
581	a 6	b 9	c 2
582	a 7	b 9	c 2
583	a 8	b 9	c 2
584	a 9	b 9	c 2
585	a 10	b 9	c 2
586	a 11	b 9	c 2
587	a 12	b 9	c 2
588	a 13	b 9	c 2
589	a 14	b 9	c 2
590	a 15	b 9	c 2
591	a 16	b 9	c 2
592	a 17	b 9	c 2
593	a 18	b 9	c 2
594	a 19	b 9	c 2
595	a 20	b 9	c 2
596	a 21	b 9	c 2
597	a 22	b 9	c 2

050801.050801

No.	Cp	Bridge	Flu
598	a 23	b 9	c 2
599	a 24	b 9	c 2
600	a 25	b 9	c 2
601	a 1	b 10	c 2
602	a 2	b 10	c 2
603	a 3	b 10	c 2
604	a 4	b 10	c 2
605	a 5	b 10	c 2
606	a 6	b 10	c 2
607	a 7	b 10	c 2
608	a 8	b 10	c 2
609	a 9	b 10	c 2
610	a 10	b 10	c 2
611	a 11	b 10	c 2
612	a 12	b 10	c 2
613	a 13	b 10	c 2
614	a 14	b 10	c 2
615	a 15	b 10	c 2
616	a 16	b 10	c 2
617	a 17	b 10	c 2
618	a 18	b 10	c 2
619	a 19	b 10	c 2
620	a 20	b 10	c 2
621	a 21	b 10	c 2
622	a 22	b 10	c 2
623	a 23	b 10	c 2
624	a 24	b 10	c 2
625	a 25	b 10	c 2
626	a 1	b 11	c 2
627	a 2	b 11	c 2
628	a 3	b 11	c 2
629	a 4	b 11	c 2
630	a 5	b 11	c 2
631	a 6	b 11	c 2
632	a 7	b 11	c 2
633	a 8	b 11	c 2
634	a 9	b 11	c 2
635	a 10	b 11	c 2
636	a 11	b 11	c 2
637	a 12	b 11	c 2
638	a 13	b 11	c 2
639	a 14	b 11	c 2
640	a 15	b 11	c 2
641	a 16	b 11	c 2
642	a 17	b 11	c 2
643	a 18	b 11	c 2

09857687-060801

No.	Cp	Bridge	Flu
644	a 19	b 11	c 2
645	a 20	b 11	c 2
646	a 21	b 11	c 2
647	a 22	b 11	c 2
648	a 23	b 11	c 2
649	a 24	b 11	c 2
650	a 25	b 11	c 2
651	a 1	b 12	c 2
652	a 2	b 12	c 2
653	a 3	b 12	c 2
654	a 4	b 12	c 2
655	a 5	b 12	c 2
656	a 6	b 12	c 2
657	a 7	b 12	c 2
658	a 8	b 12	c 2
659	a 9	b 12	c 2
660	a 10	b 12	c 2
661	a 11	b 12	c 2
662	a 12	b 12	c 2
663	a 13	b 12	c 2
664	a 14	b 12	c 2
665	a 15	b 12	c 2
666	a 16	b 12	c 2
667	a 17	b 12	c 2
668	a 18	b 12	c 2
669	a 19	b 12	c 2
670	a 20	b 12	c 2
671	a 21	b 12	c 2
672	a 22	b 12	c 2
673	a 23	b 12	c 2
674	a 24	b 12	c 2
675	a 25	b 12	c 2
676	a 1	b 13	c 2
677	a 2	b 13	c 2
678	a 3	b 13	c 2
679	a 4	b 13	c 2
680	a 5	b 13	c 2
681	a 6	b 13	c 2
682	a 7	b 13	c 2
683	a 8	b 13	c 2
684	a 9	b 13	c 2
685	a 10	b 13	c 2
686	a 11	b 13	c 2
687	a 12	b 13	c 2
688	a 13	b 13	c 2
689	a 14	b 13	c 2

09857687 060801

No.	Cp	Bridge	Flu
690	a 15	b 13	c 2
691	a 16	b 13	c 2
692	a 17	b 13	c 2
693	a 18	b 13	c 2
694	a 19	b 13	c 2
695	a 20	b 13	c 2
696	a 21	b 13	c 2
697	a 22	b 13	c 2
698	a 23	b 13	c 2
699	a 24	b 13	c 2
700	a 25	b 13	c 2
701	a 1	b 14	c 2
702	a 2	b 14	c 2
703	a 3	b 14	c 2
704	a 4	b 14	c 2
705	a 5	b 14	c 2
706	a 6	b 14	c 2
707	a 7	b 14	c 2
708	a 8	b 14	c 2
709	a 9	b 14	c 2
710	a 10	b 14	c 2
711	a 11	b 14	c 2
712	a 12	b 14	c 2
713	a 13	b 14	c 2
714	a 14	b 14	c 2
715	a 15	b 14	c 2
716	a 16	b 14	c 2
717	a 17	b 14	c 2
718	a 18	b 14	c 2
719	a 19	b 14	c 2
720	a 20	b 14	c 2
721	a 21	b 14	c 2
722	a 22	b 14	c 2
723	a 23	b 14	c 2
724	a 24	b 14	c 2
725	a 25	b 14	c 2
726	a 1	b 15	c 2
727	a 2	b 15	c 2
728	a 3	b 15	c 2
729	a 4	b 15	c 2
730	a 5	b 15	c 2
731	a 6	b 15	c 2
732	a 7	b 15	c 2
733	a 8	b 15	c 2
734	a 9	b 15	c 2
735	a 10	b 15	c 2

No.	Cp	Bridge	Flu
736	a 11	b 15	c 2
737	a 12	b 15	c 2
738	a 13	b 15	c 2
739	a 14	b 15	c 2
740	a 15	b 15	c 2
741	a 16	b 15	c 2
742	a 17	b 15	c 2
743	a 18	b 15	c 2
744	a 19	b 15	c 2
745	a 20	b 15	c 2
746	a 21	b 15	c 2
747	a 22	b 15	c 2
748	a 23	b 15	c 2
749	a 24	b 15	c 2
750	a 25	b 15	c 2
751	a 1	b 1	c 3
752	a 2	b 1	c 3
753	a 3	b 1	c 3
754	a 4	b 1	c 3
755	a 5	b 1	c 3
756	a 6	b 1	c 3
757	a 7	b 1	c 3
758	a 8	b 1	c 3
759	a 9	b 1	c 3
760	a 10	b 1	c 3
761	a 11	b 1	c 3
762	a 12	b 1	c 3
763	a 13	b 1	c 3
764	a 14	b 1	c 3
765	a 15	b 1	c 3
766	a 16	b 1	c 3
767	a 17	b 1	c 3
768	a 18	b 1	c 3
769	a 19	b 1	c 3
770	a 20	b 1	c 3
771	a 21	b 1	c 3
772	a 22	b 1	c 3
773	a 23	b 1	c 3
774	a 24	b 1	c 3
775	a 25	b 1	c 3
776	a 1	b 2	c 3
777	a 2	b 2	c 3
778	a 3	b 2	c 3
779	a 4	b 2	c 3
780	a 5	b 2	c 3
781	a 6	b 2	c 3

09857687-060801

No.	Cp	Bridge	Flu
782	a 7	b 2	c 3
783	a 8	b 2	c 3
784	a 9	b 2	c 3
785	a 10	b 2	c 3
786	a 11	b 2	c 3
787	a 12	b 2	c 3
788	a 13	b 2	c 3
789	a 14	b 2	c 3
790	a 15	b 2	c 3
791	a 16	b 2	c 3
792	a 17	b 2	c 3
793	a 18	b 2	c 3
794	a 19	b 2	c 3
795	a 20	b 2	c 3
796	a 21	b 2	c 3
797	a 22	b 2	c 3
798	a 23	b 2	c 3
799	a 24	b 2	c 3
800	a 25	b 2	c 3
801	a 1	b 3	c 3
802	a 2	b 3	c 3
803	a 3	b 3	c 3
804	a 4	b 3	c 3
805	a 5	b 3	c 3
806	a 6	b 3	c 3
807	a 7	b 3	c 3
808	a 8	b 3	c 3
809	a 9	b 3	c 3
810	a 10	b 3	c 3
811	a 11	b 3	c 3
812	a 12	b 3	c 3
813	a 13	b 3	c 3
814	a 14	b 3	c 3
815	a 15	b 3	c 3
816	a 16	b 3	c 3
817	a 17	b 3	c 3
818	a 18	b 3	c 3
819	a 19	b 3	c 3
820	a 20	b 3	c 3
821	a 21	b 3	c 3
822	a 22	b 3	c 3
823	a 23	b 3	c 3
824	a 24	b 3	c 3
825	a 25	b 3	c 3
826	a 1	b 4	c 3
827	a 2	b 4	c 3

09857687 060801

No.	Cp	Bridge	Flu
828	a 3	b 4	c 3
829	a 4	b 4	c 3
830	a 5	b 4	c 3
831	a 6	b 4	c 3
832	a 7	b 4	c 3
833	a 8	b 4	c 3
834	a 9	b 4	c 3
835	a 10	b 4	c 3
836	a 11	b 4	c 3
837	a 12	b 4	c 3
838	a 13	b 4	c 3
839	a 14	b 4	c 3
840	a 15	b 4	c 3
841	a 16	b 4	c 3
842	a 17	b 4	c 3
843	a 18	b 4	c 3
844	a 19	b 4	c 3
845	a 20	b 4	c 3
846	a 21	b 4	c 3
847	a 22	b 4	c 3
848	a 23	b 4	c 3
849	a 24	b 4	c 3
850	a 25	b 4	c 3
851	a 1	b 5	c 3
852	a 2	b 5	c 3
853	a 3	b 5	c 3
854	a 4	b 5	c 3
855	a 5	b 5	c 3
856	a 6	b 5	c 3
857	a 7	b 5	c 3
858	a 8	b 5	c 3
859	a 9	b 5	c 3
860	a 10	b 5	c 3
861	a 11	b 5	c 3
862	a 12	b 5	c 3
863	a 13	b 5	c 3
864	a 14	b 5	c 3
865	a 15	b 5	c 3
866	a 16	b 5	c 3
867	a 17	b 5	c 3
868	a 18	b 5	c 3
869	a 19	b 5	c 3
870	a 20	b 5	c 3
871	a 21	b 5	c 3
872	a 22	b 5	c 3
873	a 23	b 5	c 3

09857687.060801

No.	Cp	Bridge	Flu
874	a 24	b 5	c 3
875	a 25	b 5	c 3
876	a 1	b 6	c 3
877	a 2	b 6	c 3
878	a 3	b 6	c 3
879	a 4	b 6	c 3
880	a 5	b 6	c 3
881	a 6	b 6	c 3
882	a 7	b 6	c 3
883	a 8	b 6	c 3
884	a 9	b 6	c 3
885	a 10	b 6	c 3
886	a 11	b 6	c 3
887	a 12	b 6	c 3
888	a 13	b 6	c 3
889	a 14	b 6	c 3
890	a 15	b 6	c 3
891	a 16	b 6	c 3
892	a 17	b 6	c 3
893	a 18	b 6	c 3
894	a 19	b 6	c 3
895	a 20	b 6	c 3
896	a 21	b 6	c 3
897	a 22	b 6	c 3
898	a 23	b 6	c 3
899	a 24	b 6	c 3
900	a 25	b 6	c 3
901	a 1	b 7	c 3
902	a 2	b 7	c 3
903	a 3	b 7	c 3
904	a 4	b 7	c 3
905	a 5	b 7	c 3
906	a 6	b 7	c 3
907	a 7	b 7	c 3
908	a 8	b 7	c 3
909	a 9	b 7	c 3
910	a 10	b 7	c 3
911	a 11	b 7	c 3
912	a 12	b 7	c 3
913	a 13	b 7	c 3
914	a 14	b 7	c 3
915	a 15	b 7	c 3
916	a 16	b 7	c 3
917	a 17	b 7	c 3
918	a 18	b 7	c 3
919	a 19	b 7	c 3

09857687.060801

No.	Cp	Bridge	Flu
920	a 20	b 7	c 3
921	a 21	b 7	c 3
922	a 22	b 7	c 3
923	a 23	b 7	c 3
924	a 24	b 7	c 3
925	a 25	b 7	c 3
926	a 1	b 8	c 3
927	a 2	b 8	c 3
928	a 3	b 8	c 3
929	a 4	b 8	c 3
930	a 5	b 8	c 3
931	a 6	b 8	c 3
932	a 7	b 8	c 3
933	a 8	b 8	c 3
934	a 9	b 8	c 3
935	a 10	b 8	c 3
936	a 11	b 8	c 3
937	a 12	b 8	c 3
938	a 13	b 8	c 3
939	a 14	b 8	c 3
940	a 15	b 8	c 3
941	a 16	b 8	c 3
942	a 17	b 8	c 3
943	a 18	b 8	c 3
944	a 19	b 8	c 3
945	a 20	b 8	c 3
946	a 21	b 8	c 3
947	a 22	b 8	c 3
948	a 23	b 8	c 3
949	a 24	b 8	c 3
950	a 25	b 8	c 3
951	a 1	b 9	c 3
952	a 2	b 9	c 3
953	a 3	b 9	c 3
954	a 4	b 9	c 3
955	a 5	b 9	c 3
956	a 6	b 9	c 3
957	a 7	b 9	c 3
958	a 8	b 9	c 3
959	a 9	b 9	c 3
960	a 10	b 9	c 3
961	a 11	b 9	c 3
962	a 12	b 9	c 3
963	a 13	b 9	c 3
964	a 14	b 9	c 3
965	a 15	b 9	c 3

00857537-000001

No.	Cp	Bridge	Flu
966	a 16	b 9	c 3
967	a 17	b 9	c 3
968	a 18	b 9	c 3
969	a 19	b 9	c 3
970	a 20	b 9	c 3
971	a 21	b 9	c 3
972	a 22	b 9	c 3
973	a 23	b 9	c 3
974	a 24	b 9	c 3
975	a 25	b 9	c 3
976	a 1	b 10	c 3
977	a 2	b 10	c 3
978	a 3	b 10	c 3
979	a 4	b 10	c 3
980	a 5	b 10	c 3
981	a 6	b 10	c 3
982	a 7	b 10	c 3
983	a 8	b 10	c 3
984	a 9	b 10	c 3
985	a 10	b 10	c 3
986	a 11	b 10	c 3
987	a 12	b 10	c 3
988	a 13	b 10	c 3
989	a 14	b 10	c 3
990	a 15	b 10	c 3
991	a 16	b 10	c 3
992	a 17	b 10	c 3
993	a 18	b 10	c 3
994	a 19	b 10	c 3
995	a 20	b 10	c 3
996	a 21	b 10	c 3
997	a 22	b 10	c 3
998	a 23	b 10	c 3
999	a 24	b 10	c 3
1000	a 25	b 10	c 3
1001	a 1	b 11	c 3
1002	a 2	b 11	c 3
1003	a 3	b 11	c 3
1004	a 4	b 11	c 3
1005	a 5	b 11	c 3
1006	a 6	b 11	c 3
1007	a 7	b 11	c 3
1008	a 8	b 11	c 3
1009	a 9	b 11	c 3
1010	a 10	b 11	c 3
1011	a 11	b 11	c 3

09857687-060801

No.	Cp	Bridge	Flu
1012	a 12	b 11	c 3
1013	a 13	b 11	c 3
1014	a 14	b 11	c 3
1015	a 15	b 11	c 3
1016	a 16	b 11	c 3
1017	a 17	b 11	c 3
1018	a 18	b 11	c 3
1019	a 19	b 11	c 3
1020	a 20	b 11	c 3
1021	a 21	b 11	c 3
1022	a 22	b 11	c 3
1023	a 23	b 11	c 3
1024	a 24	b 11	c 3
1025	a 25	b 11	c 3
1026	a 1	b 12	c 3
1027	a 2	b 12	c 3
1028	a 3	b 12	c 3
1029	a 4	b 12	c 3
1030	a 5	b 12	c 3
1031	a 6	b 12	c 3
1032	a 7	b 12	c 3
1033	a 8	b 12	c 3
1034	a 9	b 12	c 3
1035	a 10	b 12	c 3
1036	a 11	b 12	c 3
1037	a 12	b 12	c 3
1038	a 13	b 12	c 3
1039	a 14	b 12	c 3
1040	a 15	b 12	c 3
1041	a 16	b 12	c 3
1042	a 17	b 12	c 3
1043	a 18	b 12	c 3
1044	a 19	b 12	c 3
1045	a 20	b 12	c 3
1046	a 21	b 12	c 3
1047	a 22	b 12	c 3
1048	a 23	b 12	c 3
1049	a 24	b 12	c 3
1050	a 25	b 12	c 3
1051	a 1	b 13	c 3
1052	a 2	b 13	c 3
1053	a 3	b 13	c 3
1054	a 4	b 13	c 3
1055	a 5	b 13	c 3
1056	a 6	b 13	c 3
1057	a 7	b 13	c 3

09857587-060301

No.	Cp	Bridge	Flu
1058	a 8	b 13	c 3
1059	a 9	b 13	c 3
1060	a 10	b 13	c 3
1061	a 11	b 13	c 3
1062	a 12	b 13	c 3
1063	a 13	b 13	c 3
1064	a 14	b 13	c 3
1065	a 15	b 13	c 3
1066	a 16	b 13	c 3
1067	a 17	b 13	c 3
1068	a 18	b 13	c 3
1069	a 19	b 13	c 3
1070	a 20	b 13	c 3
1071	a 21	b 13	c 3
1072	a 22	b 13	c 3
1073	a 23	b 13	c 3
1074	a 24	b 13	c 3
1075	a 25	b 13	c 3
1076	a 1	b 14	c 3
1077	a 2	b 14	c 3
1078	a 3	b 14	c 3
1079	a 4	b 14	c 3
1080	a 5	b 14	c 3
1081	a 6	b 14	c 3
1082	a 7	b 14	c 3
1083	a 8	b 14	c 3
1084	a 9	b 14	c 3
1085	a 10	b 14	c 3
1086	a 11	b 14	c 3
1087	a 12	b 14	c 3
1088	a 13	b 14	c 3
1089	a 14	b 14	c 3
1090	a 15	b 14	c 3
1091	a 16	b 14	c 3
1092	a 17	b 14	c 3
1093	a 18	b 14	c 3
1094	a 19	b 14	c 3
1095	a 20	b 14	c 3
1096	a 21	b 14	c 3
1097	a 22	b 14	c 3
1098	a 23	b 14	c 3
1099	a 24	b 14	c 3
1100	a 25	b 14	c 3
1101	a 1	b 15	c 3
1102	a 2	b 15	c 3
1103	a 3	b 15	c 3

09857687-060801

No.	Cp	Bridge	Flu
1104	a 4	b 15	c 3
1105	a 5	b 15	c 3
1106	a 6	b 15	c 3
1107	a 7	b 15	c 3
1108	a 8	b 15	c 3
1109	a 9	b 15	c 3
1110	a 10	b 15	c 3
1111	a 11	b 15	c 3
1112	a 12	b 15	c 3
1113	a 13	b 15	c 3
1114	a 14	b 15	c 3
1115	a 15	b 15	c 3
1116	a 16	b 15	c 3
1117	a 17	b 15	c 3
1118	a 18	b 15	c 3
1119	a 19	b 15	c 3
1120	a 20	b 15	c 3
1121	a 21	b 15	c 3
1122	a 22	b 15	c 3
1123	a 23	b 15	c 3
1124	a 24	b 15	c 3
1125	a 25	b 15	c 3
1126	a 1	b 1	c 4
1127	a 2	b 1	c 4
1128	a 3	b 1	c 4
1129	a 4	b 1	c 4
1130	a 5	b 1	c 4
1131	a 6	b 1	c 4
1132	a 7	b 1	c 4
1133	a 8	b 1	c 4
1134	a 9	b 1	c 4
1135	a 10	b 1	c 4
1136	a 11	b 1	c 4
1137	a 12	b 1	c 4
1138	a 13	b 1	c 4
1139	a 14	b 1	c 4
1140	a 15	b 1	c 4
1141	a 16	b 1	c 4
1142	a 17	b 1	c 4
1143	a 18	b 1	c 4
1144	a 19	b 1	c 4
1145	a 20	b 1	c 4
1146	a 21	b 1	c 4
1147	a 22	b 1	c 4
1148	a 23	b 1	c 4
1149	a 24	b 1	c 4

09857687 060001

No.	Cp	Bridge	Flu
1150	a 25	b 1	c 4
1151	a 1	b 2	c 4
1152	a 2	b 2	c 4
1153	a 3	b 2	c 4
1154	a 4	b 2	c 4
1155	a 5	b 2	c 4
1156	a 6	b 2	c 4
1157	a 7	b 2	c 4
1158	a 8	b 2	c 4
1159	a 9	b 2	c 4
1160	a 10	b 2	c 4
1161	a 11	b 2	c 4
1162	a 12	b 2	c 4
1163	a 13	b 2	c 4
1164	a 14	b 2	c 4
1165	a 15	b 2	c 4
1166	a 16	b 2	c 4
1167	a 17	b 2	c 4
1168	a 18	b 2	c 4
1169	a 19	b 2	c 4
1170	a 20	b 2	c 4
1171	a 21	b 2	c 4
1172	a 22	b 2	c 4
1173	a 23	b 2	c 4
1174	a 24	b 2	c 4
1175	a 25	b 2	c 4
1176	a 1	b 3	c 4
1177	a 2	b 3	c 4
1178	a 3	b 3	c 4
1179	a 4	b 3	c 4
1180	a 5	b 3	c 4
1181	a 6	b 3	c 4
1182	a 7	b 3	c 4
1183	a 8	b 3	c 4
1184	a 9	b 3	c 4
1185	a 10	b 3	c 4
1186	a 11	b 3	c 4
1187	a 12	b 3	c 4
1188	a 13	b 3	c 4
1189	a 14	b 3	c 4
1190	a 15	b 3	c 4
1191	a 16	b 3	c 4
1192	a 17	b 3	c 4
1193	a 18	b 3	c 4
1194	a 19	b 3	c 4
1195	a 20	b 3	c 4

09857687-060801

No.	Cp	Bridge	Flu
1196	a 21	b 3	c 4
1197	a 22	b 3	c 4
1198	a 23	b 3	c 4
1199	a 24	b 3	c 4
1200	a 25	b 3	c 4
1201	a 1	b 4	c 4
1202	a 2	b 4	c 4
1203	a 3	b 4	c 4
1204	a 4	b 4	c 4
1205	a 5	b 4	c 4
1206	a 6	b 4	c 4
1207	a 7	b 4	c 4
1208	a 8	b 4	c 4
1209	a 9	b 4	c 4
1210	a 10	b 4	c 4
1211	a 11	b 4	c 4
1212	a 12	b 4	c 4
1213	a 13	b 4	c 4
1214	a 14	b 4	c 4
1215	a 15	b 4	c 4
1216	a 16	b 4	c 4
1217	a 17	b 4	c 4
1218	a 18	b 4	c 4
1219	a 19	b 4	c 4
1220	a 20	b 4	c 4
1221	a 21	b 4	c 4
1222	a 22	b 4	c 4
1223	a 23	b 4	c 4
1224	a 24	b 4	c 4
1225	a 25	b 4	c 4
1226	a 1	b 5	c 4
1227	a 2	b 5	c 4
1228	a 3	b 5	c 4
1229	a 4	b 5	c 4
1230	a 5	b 5	c 4
1231	a 6	b 5	c 4
1232	a 7	b 5	c 4
1233	a 8	b 5	c 4
1234	a 9	b 5	c 4
1235	a 10	b 5	c 4
1236	a 11	b 5	c 4
1237	a 12	b 5	c 4
1238	a 13	b 5	c 4
1239	a 14	b 5	c 4
1240	a 15	b 5	c 4
1241	a 16	b 5	c 4

09857687 060801

No.	Cp	Bridge	Flu
1242	a 17	b 5	c 4
1243	a 18	b 5	c 4
1244	a 19	b 5	c 4
1245	a 20	b 5	c 4
1246	a 21	b 5	c 4
1247	a 22	b 5	c 4
1248	a 23	b 5	c 4
1249	a 24	b 5	c 4
1250	a 25	b 5	c 4
1251	a 1	b 6	c 4
1252	a 2	b 6	c 4
1253	a 3	b 6	c 4
1254	a 4	b 6	c 4
1255	a 5	b 6	c 4
1256	a 6	b 6	c 4
1257	a 7	b 6	c 4
1258	a 8	b 6	c 4
1259	a 9	b 6	c 4
1260	a 10	b 6	c 4
1261	a 11	b 6	c 4
1262	a 12	b 6	c 4
1263	a 13	b 6	c 4
1264	a 14	b 6	c 4
1265	a 15	b 6	c 4
1266	a 16	b 6	c 4
1267	a 17	b 6	c 4
1268	a 18	b 6	c 4
1269	a 19	b 6	c 4
1270	a 20	b 6	c 4
1271	a 21	b 6	c 4
1272	a 22	b 6	c 4
1273	a 23	b 6	c 4
1274	a 24	b 6	c 4
1275	a 25	b 6	c 4
1276	a 1	b 7	c 4
1277	a 2	b 7	c 4
1278	a 3	b 7	c 4
1279	a 4	b 7	c 4
1280	a 5	b 7	c 4
1281	a 6	b 7	c 4
1282	a 7	b 7	c 4
1283	a 8	b 7	c 4
1284	a 9	b 7	c 4
1285	a 10	b 7	c 4
1286	a 11	b 7	c 4
1287	a 12	b 7	c 4

09857687.060801

No.	Cp	Bridge	Flu
1288	a 13	b 7	c 4
1289	a 14	b 7	c 4
1290	a 15	b 7	c 4
1291	a 16	b 7	c 4
1292	a 17	b 7	c 4
1293	a 18	b 7	c 4
1294	a 19	b 7	c 4
1295	a 20	b 7	c 4
1296	a 21	b 7	c 4
1297	a 22	b 7	c 4
1298	a 23	b 7	c 4
1299	a 24	b 7	c 4
1300	a 25	b 7	c 4
1301	a 1	b 8	c 4
1302	a 2	b 8	c 4
1303	a 3	b 8	c 4
1304	a 4	b 8	c 4
1305	a 5	b 8	c 4
1306	a 6	b 8	c 4
1307	a 7	b 8	c 4
1308	a 8	b 8	c 4
1309	a 9	b 8	c 4
1310	a 10	b 8	c 4
1311	a 11	b 8	c 4
1312	a 12	b 8	c 4
1313	a 13	b 8	c 4
1314	a 14	b 8	c 4
1315	a 15	b 8	c 4
1316	a 16	b 8	c 4
1317	a 17	b 8	c 4
1318	a 18	b 8	c 4
1319	a 19	b 8	c 4
1320	a 20	b 8	c 4
1321	a 21	b 8	c 4
1322	a 22	b 8	c 4
1323	a 23	b 8	c 4
1324	a 24	b 8	c 4
1325	a 25	b 8	c 4
1326	a 1	b 9	c 4
1327	a 2	b 9	c 4
1328	a 3	b 9	c 4
1329	a 4	b 9	c 4
1330	a 5	b 9	c 4
1331	a 6	b 9	c 4
1332	a 7	b 9	c 4
1333	a 8	b 9	c 4

09857687 060801

No.	Cp	Bridge	Flu
1334	a 9	b 9	c 4
1335	a 10	b 9	c 4
1336	a 11	b 9	c 4
1337	a 12	b 9	c 4
1338	a 13	b 9	c 4
1339	a 14	b 9	c 4
1340	a 15	b 9	c 4
1341	a 16	b 9	c 4
1342	a 17	b 9	c 4
1343	a 18	b 9	c 4
1344	a 19	b 9	c 4
1345	a 20	b 9	c 4
1346	a 21	b 9	c 4
1347	a 22	b 9	c 4
1348	a 23	b 9	c 4
1349	a 24	b 9	c 4
1350	a 25	b 9	c 4
1351	a 1	b 10	c 4
1352	a 2	b 10	c 4
1353	a 3	b 10	c 4
1354	a 4	b 10	c 4
1355	a 5	b 10	c 4
1356	a 6	b 10	c 4
1357	a 7	b 10	c 4
1358	a 8	b 10	c 4
1359	a 9	b 10	c 4
1360	a 10	b 10	c 4
1361	a 11	b 10	c 4
1362	a 12	b 10	c 4
1363	a 13	b 10	c 4
1364	a 14	b 10	c 4
1365	a 15	b 10	c 4
1366	a 16	b 10	c 4
1367	a 17	b 10	c 4
1368	a 18	b 10	c 4
1369	a 19	b 10	c 4
1370	a 20	b 10	c 4
1371	a 21	b 10	c 4
1372	a 22	b 10	c 4
1373	a 23	b 10	c 4
1374	a 24	b 10	c 4
1375	a 25	b 10	c 4
1376	a 1	b 11	c 4
1377	a 2	b 11	c 4
1378	a 3	b 11	c 4
1379	a 4	b 11	c 4

09857687 060801

No.	Cp	Bridge	Flu
1380	a 5	b 11	c 4
1381	a 6	b 11	c 4
1382	a 7	b 11	c 4
1383	a 8	b 11	c 4
1384	a 9	b 11	c 4
1385	a 10	b 11	c 4
1386	a 11	b 11	c 4
1387	a 12	b 11	c 4
1388	a 13	b 11	c 4
1389	a 14	b 11	c 4
1390	a 15	b 11	c 4
1391	a 16	b 11	c 4
1392	a 17	b 11	c 4
1393	a 18	b 11	c 4
1394	a 19	b 11	c 4
1395	a 20	b 11	c 4
1396	a 21	b 11	c 4
1397	a 22	b 11	c 4
1398	a 23	b 11	c 4
1399	a 24	b 11	c 4
1400	a 25	b 11	c 4
1401	a 1	b 12	c 4
1402	a 2	b 12	c 4
1403	a 3	b 12	c 4
1404	a 4	b 12	c 4
1405	a 5	b 12	c 4
1406	a 6	b 12	c 4
1407	a 7	b 12	c 4
1408	a 8	b 12	c 4
1409	a 9	b 12	c 4
1410	a 10	b 12	c 4
1411	a 11	b 12	c 4
1412	a 12	b 12	c 4
1413	a 13	b 12	c 4
1414	a 14	b 12	c 4
1415	a 15	b 12	c 4
1416	a 16	b 12	c 4
1417	a 17	b 12	c 4
1418	a 18	b 12	c 4
1419	a 19	b 12	c 4
1420	a 20	b 12	c 4
1421	a 21	b 12	c 4
1422	a 22	b 12	c 4
1423	a 23	b 12	c 4
1424	a 24	b 12	c 4
1425	a 25	b 12	c 4

09857687-060801

No.	Cp	Bridge	Flu
1426	a 1	b 13	c 4
1427	a 2	b 13	c 4
1428	a 3	b 13	c 4
1429	a 4	b 13	c 4
1430	a 5	b 13	c 4
1431	a 6	b 13	c 4
1432	a 7	b 13	c 4
1433	a 8	b 13	c 4
1434	a 9	b 13	c 4
1435	a 10	b 13	c 4
1436	a 11	b 13	c 4
1437	a 12	b 13	c 4
1438	a 13	b 13	c 4
1439	a 14	b 13	c 4
1440	a 15	b 13	c 4
1441	a 16	b 13	c 4
1442	a 17	b 13	c 4
1443	a 18	b 13	c 4
1444	a 19	b 13	c 4
1445	a 20	b 13	c 4
1446	a 21	b 13	c 4
1447	a 22	b 13	c 4
1448	a 23	b 13	c 4
1449	a 24	b 13	c 4
1450	a 25	b 13	c 4
1451	a 1	b 14	c 4
1452	a 2	b 14	c 4
1453	a 3	b 14	c 4
1454	a 4	b 14	c 4
1455	a 5	b 14	c 4
1456	a 6	b 14	c 4
1457	a 7	b 14	c 4
1458	a 8	b 14	c 4
1459	a 9	b 14	c 4
1460	a 10	b 14	c 4
1461	a 11	b 14	c 4
1462	a 12	b 14	c 4
1463	a 13	b 14	c 4
1464	a 14	b 14	c 4
1465	a 15	b 14	c 4
1466	a 16	b 14	c 4
1467	a 17	b 14	c 4
1468	a 18	b 14	c 4
1469	a 19	b 14	c 4
1470	a 20	b 14	c 4
1471	a 21	b 14	c 4

09357687 060801

No.	Cp	Bridge	Flu
1472	a 22	b 14	c 4
1473	a 23	b 14	c 4
1474	a 24	b 14	c 4
1475	a 25	b 14	c 4
1476	a 1	b 15	c 4
1477	a 2	b 15	c 4
1478	a 3	b 15	c 4
1479	a 4	b 15	c 4
1480	a 5	b 15	c 4
1481	a 6	b 15	c 4
1482	a 7	b 15	c 4
1483	a 8	b 15	c 4
1484	a 9	b 15	c 4
1485	a 10	b 15	c 4
1486	a 11	b 15	c 4
1487	a 12	b 15	c 4
1488	a 13	b 15	c 4
1489	a 14	b 15	c 4
1490	a 15	b 15	c 4
1491	a 16	b 15	c 4
1492	a 17	b 15	c 4
1493	a 18	b 15	c 4
1494	a 19	b 15	c 4
1495	a 20	b 15	c 4
1496	a 21	b 15	c 4
1497	a 22	b 15	c 4
1498	a 23	b 15	c 4
1499	a 24	b 15	c 4
1500	a 25	b 15	c 4
1501	a 1	b 1	c 5
1502	a 2	b 1	c 5
1503	a 3	b 1	c 5
1504	a 4	b 1	c 5
1505	a 5	b 1	c 5
1506	a 6	b 1	c 5
1507	a 7	b 1	c 5
1508	a 8	b 1	c 5
1509	a 9	b 1	c 5
1510	a 10	b 1	c 5
1511	a 11	b 1	c 5
1512	a 12	b 1	c 5
1513	a 13	b 1	c 5
1514	a 14	b 1	c 5
1515	a 15	b 1	c 5
1516	a 16	b 1	c 5
1517	a 17	b 1	c 5

09857687.060801

No.	Cp	Bridge	Flu
1518	a 18	b 1	c 5
1519	a 19	b 1	c 5
1520	a 20	b 1	c 5
1521	a 21	b 1	c 5
1522	a 22	b 1	c 5
1523	a 23	b 1	c 5
1524	a 24	b 1	c 5
1525	a 25	b 1	c 5
1526	a 1	b 2	c 5
1527	a 2	b 2	c 5
1528	a 3	b 2	c 5
1529	a 4	b 2	c 5
1530	a 5	b 2	c 5
1531	a 6	b 2	c 5
1532	a 7	b 2	c 5
1533	a 8	b 2	c 5
1534	a 9	b 2	c 5
1535	a 10	b 2	c 5
1536	a 11	b 2	c 5
1537	a 12	b 2	c 5
1538	a 13	b 2	c 5
1539	a 14	b 2	c 5
1540	a 15	b 2	c 5
1541	a 16	b 2	c 5
1542	a 17	b 2	c 5
1543	a 18	b 2	c 5
1544	a 19	b 2	c 5
1545	a 20	b 2	c 5
1546	a 21	b 2	c 5
1547	a 22	b 2	c 5
1548	a 23	b 2	c 5
1549	a 24	b 2	c 5
1550	a 25	b 2	c 5
1551	a 1	b 3	c 5
1552	a 2	b 3	c 5
1553	a 3	b 3	c 5
1554	a 4	b 3	c 5
1555	a 5	b 3	c 5
1556	a 6	b 3	c 5
1557	a 7	b 3	c 5
1558	a 8	b 3	c 5
1559	a 9	b 3	c 5
1560	a 10	b 3	c 5
1561	a 11	b 3	c 5
1562	a 12	b 3	c 5
1563	a 13	b 3	c 5

09857587 060801

No.	Cp	Bridge	Flu
1564	a 14	b 3	c 5
1565	a 15	b 3	c 5
1566	a 16	b 3	c 5
1567	a 17	b 3	c 5
1568	a 18	b 3	c 5
1569	a 19	b 3	c 5
1570	a 20	b 3	c 5
1571	a 21	b 3	c 5
1572	a 22	b 3	c 5
1573	a 23	b 3	c 5
1574	a 24	b 3	c 5
1575	a 25	b 3	c 5
1576	a 1	b 4	c 5
1577	a 2	b 4	c 5
1578	a 3	b 4	c 5
1579	a 4	b 4	c 5
1580	a 5	b 4	c 5
1581	a 6	b 4	c 5
1582	a 7	b 4	c 5
1583	a 8	b 4	c 5
1584	a 9	b 4	c 5
1585	a 10	b 4	c 5
1586	a 11	b 4	c 5
1587	a 12	b 4	c 5
1588	a 13	b 4	c 5
1589	a 14	b 4	c 5
1590	a 15	b 4	c 5
1591	a 16	b 4	c 5
1592	a 17	b 4	c 5
1593	a 18	b 4	c 5
1594	a 19	b 4	c 5
1595	a 20	b 4	c 5
1596	a 21	b 4	c 5
1597	a 22	b 4	c 5
1598	a 23	b 4	c 5
1599	a 24	b 4	c 5
1600	a 25	b 4	c 5
1601	a 1	b 5	c 5
1602	a 2	b 5	c 5
1603	a 3	b 5	c 5
1604	a 4	b 5	c 5
1605	a 5	b 5	c 5
1606	a 6	b 5	c 5
1607	a 7	b 5	c 5
1608	a 8	b 5	c 5
1609	a 9	b 5	c 5

09857587 060801

No.	Cp	Bridge	Flu
1610	a 10	b 5	c 5
1611	a 11	b 5	c 5
1612	a 12	b 5	c 5
1613	a 13	b 5	c 5
1614	a 14	b 5	c 5
1615	a 15	b 5	c 5
1616	a 16	b 5	c 5
1617	a 17	b 5	c 5
1618	a 18	b 5	c 5
1619	a 19	b 5	c 5
1620	a 20	b 5	c 5
1621	a 21	b 5	c 5
1622	a 22	b 5	c 5
1623	a 23	b 5	c 5
1624	a 24	b 5	c 5
1625	a 25	b 5	c 5
1626	a 1	b 6	c 5
1627	a 2	b 6	c 5
1628	a 3	b 6	c 5
1629	a 4	b 6	c 5
1630	a 5	b 6	c 5
1631	a 6	b 6	c 5
1632	a 7	b 6	c 5
1633	a 8	b 6	c 5
1634	a 9	b 6	c 5
1635	a 10	b 6	c 5
1636	a 11	b 6	c 5
1637	a 12	b 6	c 5
1638	a 13	b 6	c 5
1639	a 14	b 6	c 5
1640	a 15	b 6	c 5
1641	a 16	b 6	c 5
1642	a 17	b 6	c 5
1643	a 18	b 6	c 5
1644	a 19	b 6	c 5
1645	a 20	b 6	c 5
1646	a 21	b 6	c 5
1647	a 22	b 6	c 5
1648	a 23	b 6	c 5
1649	a 24	b 6	c 5
1650	a 25	b 6	c 5
1651	a 1	b 7	c 5
1652	a 2	b 7	c 5
1653	a 3	b 7	c 5
1654	a 4	b 7	c 5
1655	a 5	b 7	c 5

09857687-060801

No.	Cp	Bridge	Flu
1656	a 6	b 7	c 5
1657	a 7	b 7	c 5
1658	a 8	b 7	c 5
1659	a 9	b 7	c 5
1660	a 10	b 7	c 5
1661	a 11	b 7	c 5
1662	a 12	b 7	c 5
1663	a 13	b 7	c 5
1664	a 14	b 7	c 5
1665	a 15	b 7	c 5
1666	a 16	b 7	c 5
1667	a 17	b 7	c 5
1668	a 18	b 7	c 5
1669	a 19	b 7	c 5
1670	a 20	b 7	c 5
1671	a 21	b 7	c 5
1672	a 22	b 7	c 5
1673	a 23	b 7	c 5
1674	a 24	b 7	c 5
1675	a 25	b 7	c 5
1676	a 1	b 8	c 5
1677	a 2	b 8	c 5
1678	a 3	b 8	c 5
1679	a 4	b 8	c 5
1680	a 5	b 8	c 5
1681	a 6	b 8	c 5
1682	a 7	b 8	c 5
1683	a 8	b 8	c 5
1684	a 9	b 8	c 5
1685	a 10	b 8	c 5
1686	a 11	b 8	c 5
1687	a 12	b 8	c 5
1688	a 13	b 8	c 5
1689	a 14	b 8	c 5
1690	a 15	b 8	c 5
1691	a 16	b 8	c 5
1692	a 17	b 8	c 5
1693	a 18	b 8	c 5
1694	a 19	b 8	c 5
1695	a 20	b 8	c 5
1696	a 21	b 8	c 5
1697	a 22	b 8	c 5
1698	a 23	b 8	c 5
1699	a 24	b 8	c 5
1700	a 25	b 8	c 5
1701	a 1	b 9	c 5

09857687-060801

No.	Cp	Bridge	Flu
1702	a 2	b 9	c 5
1703	a 3	b 9	c 5
1704	a 4	b 9	c 5
1705	a 5	b 9	c 5
1706	a 6	b 9	c 5
1707	a 7	b 9	c 5
1708	a 8	b 9	c 5
1709	a 9	b 9	c 5
1710	a 10	b 9	c 5
1711	a 11	b 9	c 5
1712	a 12	b 9	c 5
1713	a 13	b 9	c 5
1714	a 14	b 9	c 5
1715	a 15	b 9	c 5
1716	a 16	b 9	c 5
1717	a 17	b 9	c 5
1718	a 18	b 9	c 5
1719	a 19	b 9	c 5
1720	a 20	b 9	c 5
1721	a 21	b 9	c 5
1722	a 22	b 9	c 5
1723	a 23	b 9	c 5
1724	a 24	b 9	c 5
1725	a 25	b 9	c 5
1726	a 1	b 10	c 5
1727	a 2	b 10	c 5
1728	a 3	b 10	c 5
1729	a 4	b 10	c 5
1730	a 5	b 10	c 5
1731	a 6	b 10	c 5
1732	a 7	b 10	c 5
1733	a 8	b 10	c 5
1734	a 9	b 10	c 5
1735	a 10	b 10	c 5
1736	a 11	b 10	c 5
1737	a 12	b 10	c 5
1738	a 13	b 10	c 5
1739	a 14	b 10	c 5
1740	a 15	b 10	c 5
1741	a 16	b 10	c 5
1742	a 17	b 10	c 5
1743	a 18	b 10	c 5
1744	a 19	b 10	c 5
1745	a 20	b 10	c 5
1746	a 21	b 10	c 5
1747	a 22	b 10	c 5

09857637 060801

No.	Cp	Bridge	Flu
1748	a 23	b 10	c 5
1749	a 24	b 10	c 5
1750	a 25	b 10	c 5
1751	a 1	b 11	c 5
1752	a 2	b 11	c 5
1753	a 3	b 11	c 5
1754	a 4	b 11	c 5
1755	a 5	b 11	c 5
1756	a 6	b 11	c 5
1757	a 7	b 11	c 5
1758	a 8	b 11	c 5
1759	a 9	b 11	c 5
1760	a 10	b 11	c 5
1761	a 11	b 11	c 5
1762	a 12	b 11	c 5
1763	a 13	b 11	c 5
1764	a 14	b 11	c 5
1765	a 15	b 11	c 5
1766	a 16	b 11	c 5
1767	a 17	b 11	c 5
1768	a 18	b 11	c 5
1769	a 19	b 11	c 5
1770	a 20	b 11	c 5
1771	a 21	b 11	c 5
1772	a 22	b 11	c 5
1773	a 23	b 11	c 5
1774	a 24	b 11	c 5
1775	a 25	b 11	c 5
1776	a 1	b 12	c 5
1777	a 2	b 12	c 5
1778	a 3	b 12	c 5
1779	a 4	b 12	c 5
1780	a 5	b 12	c 5
1781	a 6	b 12	c 5
1782	a 7	b 12	c 5
1783	a 8	b 12	c 5
1784	a 9	b 12	c 5
1785	a 10	b 12	c 5
1786	a 11	b 12	c 5
1787	a 12	b 12	c 5
1788	a 13	b 12	c 5
1789	a 14	b 12	c 5
1790	a 15	b 12	c 5
1791	a 16	b 12	c 5
1792	a 17	b 12	c 5
1793	a 18	b 12	c 5

09557597, 050801

No.	Cp	Bridge	Flu
1794	a 19	b 12	c 5
1795	a 20	b 12	c 5
1796	a 21	b 12	c 5
1797	a 22	b 12	c 5
1798	a 23	b 12	c 5
1799	a 24	b 12	c 5
1800	a 25	b 12	c 5
1801	a 1	b 13	c 5
1802	a 2	b 13	c 5
1803	a 3	b 13	c 5
1804	a 4	b 13	c 5
1805	a 5	b 13	c 5
1806	a 6	b 13	c 5
1807	a 7	b 13	c 5
1808	a 8	b 13	c 5
1809	a 9	b 13	c 5
1810	a 10	b 13	c 5
1811	a 11	b 13	c 5
1812	a 12	b 13	c 5
1813	a 13	b 13	c 5
1814	a 14	b 13	c 5
1815	a 15	b 13	c 5
1816	a 16	b 13	c 5
1817	a 17	b 13	c 5
1818	a 18	b 13	c 5
1819	a 19	b 13	c 5
1820	a 20	b 13	c 5
1821	a 21	b 13	c 5
1822	a 22	b 13	c 5
1823	a 23	b 13	c 5
1824	a 24	b 13	c 5
1825	a 25	b 13	c 5
1826	a 1	b 14	c 5
1827	a 2	b 14	c 5
1828	a 3	b 14	c 5
1829	a 4	b 14	c 5
1830	a 5	b 14	c 5
1831	a 6	b 14	c 5
1832	a 7	b 14	c 5
1833	a 8	b 14	c 5
1834	a 9	b 14	c 5
1835	a 10	b 14	c 5
1836	a 11	b 14	c 5
1837	a 12	b 14	c 5
1838	a 13	b 14	c 5
1839	a 14	b 14	c 5

03857687.060201

No.	Cp	Bridge	Flu
1840	a 15	b 14	c 5
1841	a 16	b 14	c 5
1842	a 17	b 14	c 5
1843	a 18	b 14	c 5
1844	a 19	b 14	c 5
1845	a 20	b 14	c 5
1846	a 21	b 14	c 5
1847	a 22	b 14	c 5
1848	a 23	b 14	c 5
1849	a 24	b 14	c 5
1850	a 25	b 14	c 5
1851	a 1	b 15	c 5
1852	a 2	b 15	c 5
1853	a 3	b 15	c 5
1854	a 4	b 15	c 5
1855	a 5	b 15	c 5
1856	a 6	b 15	c 5
1857	a 7	b 15	c 5
1858	a 8	b 15	c 5
1859	a 9	b 15	c 5
1860	a 10	b 15	c 5
1861	a 11	b 15	c 5
1862	a 12	b 15	c 5
1863	a 13	b 15	c 5
1864	a 14	b 15	c 5
1865	a 15	b 15	c 5
1866	a 16	b 15	c 5
1867	a 17	b 15	c 5
1868	a 18	b 15	c 5
1869	a 19	b 15	c 5
1870	a 20	b 15	c 5
1871	a 21	b 15	c 5
1872	a 22	b 15	c 5
1873	a 23	b 15	c 5
1874	a 24	b 15	c 5
1875	a 25	b 15	c 5
1876	a 1	b 1	c 6
1877	a 2	b 1	c 6
1878	a 3	b 1	c 6
1879	a 4	b 1	c 6
1880	a 5	b 1	c 6
1881	a 6	b 1	c 6
1882	a 7	b 1	c 6
1883	a 8	b 1	c 6
1884	a 9	b 1	c 6
1885	a 10	b 1	c 6

09857687 060801

No.	Cp	Bridge	Flu
1886	a 11	b 1	c 6
1887	a 12	b 1	c 6
1888	a 13	b 1	c 6
1889	a 14	b 1	c 6
1890	a 15	b 1	c 6
1891	a 16	b 1	c 6
1892	a 17	b 1	c 6
1893	a 18	b 1	c 6
1894	a 19	b 1	c 6
1895	a 20	b 1	c 6
1896	a 21	b 1	c 6
1897	a 22	b 1	c 6
1898	a 23	b 1	c 6
1899	a 24	b 1	c 6
1900	a 25	b 1	c 6
1901	a 1	b 2	c 6
1902	a 2	b 2	c 6
1903	a 3	b 2	c 6
1904	a 4	b 2	c 6
1905	a 5	b 2	c 6
1906	a 6	b 2	c 6
1907	a 7	b 2	c 6
1908	a 8	b 2	c 6
1909	a 9	b 2	c 6
1910	a 10	b 2	c 6
1911	a 11	b 2	c 6
1912	a 12	b 2	c 6
1913	a 13	b 2	c 6
1914	a 14	b 2	c 6
1915	a 15	b 2	c 6
1916	a 16	b 2	c 6
1917	a 17	b 2	c 6
1918	a 18	b 2	c 6
1919	a 19	b 2	c 6
1920	a 20	b 2	c 6
1921	a 21	b 2	c 6
1922	a 22	b 2	c 6
1923	a 23	b 2	c 6
1924	a 24	b 2	c 6
1925	a 25	b 2	c 6
1926	a 1	b 3	c 6
1927	a 2	b 3	c 6
1928	a 3	b 3	c 6
1929	a 4	b 3	c 6
1930	a 5	b 3	c 6
1931	a 6	b 3	c 6

09857587 060801

No.	Cp	Bridge	Flu
1932	a 7	b 3	c 6
1933	a 8	b 3	c 6
1934	a 9	b 3	c 6
1935	a 10	b 3	c 6
1936	a 11	b 3	c 6
1937	a 12	b 3	c 6
1938	a 13	b 3	c 6
1939	a 14	b 3	c 6
1940	a 15	b 3	c 6
1941	a 16	b 3	c 6
1942	a 17	b 3	c 6
1943	a 18	b 3	c 6
1944	a 19	b 3	c 6
1945	a 20	b 3	c 6
1946	a 21	b 3	c 6
1947	a 22	b 3	c 6
1948	a 23	b 3	c 6
1949	a 24	b 3	c 6
1950	a 25	b 3	c 6
1951	a 1	b 4	c 6
1952	a 2	b 4	c 6
1953	a 3	b 4	c 6
1954	a 4	b 4	c 6
1955	a 5	b 4	c 6
1956	a 6	b 4	c 6
1957	a 7	b 4	c 6
1958	a 8	b 4	c 6
1959	a 9	b 4	c 6
1960	a 10	b 4	c 6
1961	a 11	b 4	c 6
1962	a 12	b 4	c 6
1963	a 13	b 4	c 6
1964	a 14	b 4	c 6
1965	a 15	b 4	c 6
1966	a 16	b 4	c 6
1967	a 17	b 4	c 6
1968	a 18	b 4	c 6
1969	a 19	b 4	c 6
1970	a 20	b 4	c 6
1971	a 21	b 4	c 6
1972	a 22	b 4	c 6
1973	a 23	b 4	c 6
1974	a 24	b 4	c 6
1975	a 25	b 4	c 6
1976	a 1	b 5	c 6
1977	a 2	b 5	c 6

09357587-060801

No.	Cp	Bridge	Flu
1978	a 3	b 5	c 6
1979	a 4	b 5	c 6
1980	a 5	b 5	c 6
1981	a 6	b 5	c 6
1982	a 7	b 5	c 6
1983	a 8	b 5	c 6
1984	a 9	b 5	c 6
1985	a 10	b 5	c 6
1986	a 11	b 5	c 6
1987	a 12	b 5	c 6
1988	a 13	b 5	c 6
1989	a 14	b 5	c 6
1990	a 15	b 5	c 6
1991	a 16	b 5	c 6
1992	a 17	b 5	c 6
1993	a 18	b 5	c 6
1994	a 19	b 5	c 6
1995	a 20	b 5	c 6
1996	a 21	b 5	c 6
1997	a 22	b 5	c 6
1998	a 23	b 5	c 6
1999	a 24	b 5	c 6
2000	a 25	b 5	c 6
2001	a 1	b 6	c 6
2002	a 2	b 6	c 6
2003	a 3	b 6	c 6
2004	a 4	b 6	c 6
2005	a 5	b 6	c 6
2006	a 6	b 6	c 6
2007	a 7	b 6	c 6
2008	a 8	b 6	c 6
2009	a 9	b 6	c 6
2010	a 10	b 6	c 6
2011	a 11	b 6	c 6
2012	a 12	b 6	c 6
2013	a 13	b 6	c 6
2014	a 14	b 6	c 6
2015	a 15	b 6	c 6
2016	a 16	b 6	c 6
2017	a 17	b 6	c 6
2018	a 18	b 6	c 6
2019	a 19	b 6	c 6
2020	a 20	b 6	c 6
2021	a 21	b 6	c 6
2022	a 22	b 6	c 6
2023	a 23	b 6	c 6

09857687-060201

No.	Cp	Bridge	Flu
2024	a 24	b 6	c 6
2025	a 25	b 6	c 6
2026	a 1	b 7	c 6
2027	a 2	b 7	c 6
2028	a 3	b 7	c 6
2029	a 4	b 7	c 6
2030	a 5	b 7	c 6
2031	a 6	b 7	c 6
2032	a 7	b 7	c 6
2033	a 8	b 7	c 6
2034	a 9	b 7	c 6
2035	a 10	b 7	c 6
2036	a 11	b 7	c 6
2037	a 12	b 7	c 6
2038	a 13	b 7	c 6
2039	a 14	b 7	c 6
2040	a 15	b 7	c 6
2041	a 16	b 7	c 6
2042	a 17	b 7	c 6
2043	a 18	b 7	c 6
2044	a 19	b 7	c 6
2045	a 20	b 7	c 6
2046	a 21	b 7	c 6
2047	a 22	b 7	c 6
2048	a 23	b 7	c 6
2049	a 24	b 7	c 6
2050	a 25	b 7	c 6
2051	a 1	b 8	c 6
2052	a 2	b 8	c 6
2053	a 3	b 8	c 6
2054	a 4	b 8	c 6
2055	a 5	b 8	c 6
2056	a 6	b 8	c 6
2057	a 7	b 8	c 6
2058	a 8	b 8	c 6
2059	a 9	b 8	c 6
2060	a 10	b 8	c 6
2061	a 11	b 8	c 6
2062	a 12	b 8	c 6
2063	a 13	b 8	c 6
2064	a 14	b 8	c 6
2065	a 15	b 8	c 6
2066	a 16	b 8	c 6
2067	a 17	b 8	c 6
2068	a 18	b 8	c 6
2069	a 19	b 8	c 6

09857687 050801

No.	Cp	Bridge	Flu
2070	a 20	b 8	c 6
2071	a 21	b 8	c 6
2072	a 22	b 8	c 6
2073	a 23	b 8	c 6
2074	a 24	b 8	c 6
2075	a 25	b 8	c 6
2076	a 1	b 9	c 6
2077	a 2	b 9	c 6
2078	a 3	b 9	c 6
2079	a 4	b 9	c 6
2080	a 5	b 9	c 6
2081	a 6	b 9	c 6
2082	a 7	b 9	c 6
2083	a 8	b 9	c 6
2084	a 9	b 9	c 6
2085	a 10	b 9	c 6
2086	a 11	b 9	c 6
2087	a 12	b 9	c 6
2088	a 13	b 9	c 6
2089	a 14	b 9	c 6
2090	a 15	b 9	c 6
2091	a 16	b 9	c 6
2092	a 17	b 9	c 6
2093	a 18	b 9	c 6
2094	a 19	b 9	c 6
2095	a 20	b 9	c 6
2096	a 21	b 9	c 6
2097	a 22	b 9	c 6
2098	a 23	b 9	c 6
2099	a 24	b 9	c 6
2100	a 25	b 9	c 6
2101	a 1	b 10	c 6
2102	a 2	b 10	c 6
2103	a 3	b 10	c 6
2104	a 4	b 10	c 6
2105	a 5	b 10	c 6
2106	a 6	b 10	c 6
2107	a 7	b 10	c 6
2108	a 8	b 10	c 6
2109	a 9	b 10	c 6
2110	a 10	b 10	c 6
2111	a 11	b 10	c 6
2112	a 12	b 10	c 6
2113	a 13	b 10	c 6
2114	a 14	b 10	c 6
2115	a 15	b 10	c 6

09857587 060801

No.	Cp	Bridge	Flu
2116	a 16	b 10	c 6
2117	a 17	b 10	c 6
2118	a 18	b 10	c 6
2119	a 19	b 10	c 6
2120	a 20	b 10	c 6
2121	a 21	b 10	c 6
2122	a 22	b 10	c 6
2123	a 23	b 10	c 6
2124	a 24	b 10	c 6
2125	a 25	b 10	c 6
2126	a 1	b 11	c 6
2127	a 2	b 11	c 6
2128	a 3	b 11	c 6
2129	a 4	b 11	c 6
2130	a 5	b 11	c 6
2131	a 6	b 11	c 6
2132	a 7	b 11	c 6
2133	a 8	b 11	c 6
2134	a 9	b 11	c 6
2135	a 10	b 11	c 6
2136	a 11	b 11	c 6
2137	a 12	b 11	c 6
2138	a 13	b 11	c 6
2139	a 14	b 11	c 6
2140	a 15	b 11	c 6
2141	a 16	b 11	c 6
2142	a 17	b 11	c 6
2143	a 18	b 11	c 6
2144	a 19	b 11	c 6
2145	a 20	b 11	c 6
2146	a 21	b 11	c 6
2147	a 22	b 11	c 6
2148	a 23	b 11	c 6
2149	a 24	b 11	c 6
2150	a 25	b 11	c 6
2151	a 1	b 12	c 6
2152	a 2	b 12	c 6
2153	a 3	b 12	c 6
2154	a 4	b 12	c 6
2155	a 5	b 12	c 6
2156	a 6	b 12	c 6
2157	a 7	b 12	c 6
2158	a 8	b 12	c 6
2159	a 9	b 12	c 6
2160	a 10	b 12	c 6
2161	a 11	b 12	c 6

09857687-060801

No.	Cp	Bridge	Flu
2162	a 12	b 12	c 6
2163	a 13	b 12	c 6
2164	a 14	b 12	c 6
2165	a 15	b 12	c 6
2166	a 16	b 12	c 6
2167	a 17	b 12	c 6
2168	a 18	b 12	c 6
2169	a 19	b 12	c 6
2170	a 20	b 12	c 6
2171	a 21	b 12	c 6
2172	a 22	b 12	c 6
2173	a 23	b 12	c 6
2174	a 24	b 12	c 6
2175	a 25	b 12	c 6
2176	a 1	b 13	c 6
2177	a 2	b 13	c 6
2178	a 3	b 13	c 6
2179	a 4	b 13	c 6
2180	a 5	b 13	c 6
2181	a 6	b 13	c 6
2182	a 7	b 13	c 6
2183	a 8	b 13	c 6
2184	a 9	b 13	c 6
2185	a 10	b 13	c 6
2186	a 11	b 13	c 6
2187	a 12	b 13	c 6
2188	a 13	b 13	c 6
2189	a 14	b 13	c 6
2190	a 15	b 13	c 6
2191	a 16	b 13	c 6
2192	a 17	b 13	c 6
2193	a 18	b 13	c 6
2194	a 19	b 13	c 6
2195	a 20	b 13	c 6
2196	a 21	b 13	c 6
2197	a 22	b 13	c 6
2198	a 23	b 13	c 6
2199	a 24	b 13	c 6
2200	a 25	b 13	c 6
2201	a 1	b 14	c 6
2202	a 2	b 14	c 6
2203	a 3	b 14	c 6
2204	a 4	b 14	c 6
2205	a 5	b 14	c 6
2206	a 6	b 14	c 6
2207	a 7	b 14	c 6

09857687.060801

No.	Cp	Bridge	Flu
2208	a 8	b 14	c 6
2209	a 9	b 14	c 6
2210	a 10	b 14	c 6
2211	a 11	b 14	c 6
2212	a 12	b 14	c 6
2213	a 13	b 14	c 6
2214	a 14	b 14	c 6
2215	a 15	b 14	c 6
2216	a 16	b 14	c 6
2217	a 17	b 14	c 6
2218	a 18	b 14	c 6
2219	a 19	b 14	c 6
2220	a 20	b 14	c 6
2221	a 21	b 14	c 6
2222	a 22	b 14	c 6
2223	a 23	b 14	c 6
2224	a 24	b 14	c 6
2225	a 25	b 14	c 6
2226	a 1	b 15	c 6
2227	a 2	b 15	c 6
2228	a 3	b 15	c 6
2229	a 4	b 15	c 6
2230	a 5	b 15	c 6
2231	a 6	b 15	c 6
2232	a 7	b 15	c 6
2233	a 8	b 15	c 6
2234	a 9	b 15	c 6
2235	a 10	b 15	c 6
2236	a 11	b 15	c 6
2237	a 12	b 15	c 6
2238	a 13	b 15	c 6
2239	a 14	b 15	c 6
2240	a 15	b 15	c 6
2241	a 16	b 15	c 6
2242	a 17	b 15	c 6
2243	a 18	b 15	c 6
2244	a 19	b 15	c 6
2245	a 20	b 15	c 6
2246	a 21	b 15	c 6
2247	a 22	b 15	c 6
2248	a 23	b 15	c 6
2249	a 24	b 15	c 6
2250	a 25	b 15	c 6
2251	a 1	b 1	c 7
2252	a 2	b 1	c 7
2253	a 3	b 1	c 7

09857687-060801

No.	Cp	Bridge	Flu
2254	a 4	b 1	c 7
2255	a 5	b 1	c 7
2256	a 6	b 1	c 7
2257	a 7	b 1	c 7
2258	a 8	b 1	c 7
2259	a 9	b 1	c 7
2260	a 10	b 1	c 7
2261	a 11	b 1	c 7
2262	a 12	b 1	c 7
2263	a 13	b 1	c 7
2264	a 14	b 1	c 7
2265	a 15	b 1	c 7
2266	a 16	b 1	c 7
2267	a 17	b 1	c 7
2268	a 18	b 1	c 7
2269	a 19	b 1	c 7
2270	a 20	b 1	c 7
2271	a 21	b 1	c 7
2272	a 22	b 1	c 7
2273	a 23	b 1	c 7
2274	a 24	b 1	c 7
2275	a 25	b 1	c 7
2276	a 1	b 2	c 7
2277	a 2	b 2	c 7
2278	a 3	b 2	c 7
2279	a 4	b 2	c 7
2280	a 5	b 2	c 7
2281	a 6	b 2	c 7
2282	a 7	b 2	c 7
2283	a 8	b 2	c 7
2284	a 9	b 2	c 7
2285	a 10	b 2	c 7
2286	a 11	b 2	c 7
2287	a 12	b 2	c 7
2288	a 13	b 2	c 7
2289	a 14	b 2	c 7
2290	a 15	b 2	c 7
2291	a 16	b 2	c 7
2292	a 17	b 2	c 7
2293	a 18	b 2	c 7
2294	a 19	b 2	c 7
2295	a 20	b 2	c 7
2296	a 21	b 2	c 7
2297	a 22	b 2	c 7
2298	a 23	b 2	c 7
2299	a 24	b 2	c 7

09857687-060801

No.	Cp	Bridge	Flu
2300	a 25	b 2	c 7
2301	a 1	b 3	c 7
2302	a 2	b 3	c 7
2303	a 3	b 3	c 7
2304	a 4	b 3	c 7
2305	a 5	b 3	c 7
2306	a 6	b 3	c 7
2307	a 7	b 3	c 7
2308	a 8	b 3	c 7
2309	a 9	b 3	c 7
2310	a 10	b 3	c 7
2311	a 11	b 3	c 7
2312	a 12	b 3	c 7
2313	a 13	b 3	c 7
2314	a 14	b 3	c 7
2315	a 15	b 3	c 7
2316	a 16	b 3	c 7
2317	a 17	b 3	c 7
2318	a 18	b 3	c 7
2319	a 19	b 3	c 7
2320	a 20	b 3	c 7
2321	a 21	b 3	c 7
2322	a 22	b 3	c 7
2323	a 23	b 3	c 7
2324	a 24	b 3	c 7
2325	a 25	b 3	c 7
2326	a 1	b 4	c 7
2327	a 2	b 4	c 7
2328	a 3	b 4	c 7
2329	a 4	b 4	c 7
2330	a 5	b 4	c 7
2331	a 6	b 4	c 7
2332	a 7	b 4	c 7
2333	a 8	b 4	c 7
2334	a 9	b 4	c 7
2335	a 10	b 4	c 7
2336	a 11	b 4	c 7
2337	a 12	b 4	c 7
2338	a 13	b 4	c 7
2339	a 14	b 4	c 7
2340	a 15	b 4	c 7
2341	a 16	b 4	c 7
2342	a 17	b 4	c 7
2343	a 18	b 4	c 7
2344	a 19	b 4	c 7
2345	a 20	b 4	c 7

09857687.060801

No.	Cp	Bridge	Flu
2346	a 21	b 4	c 7
2347	a 22	b 4	c 7
2348	a 23	b 4	c 7
2349	a 24	b 4	c 7
2350	a 25	b 4	c 7
2351	a 1	b 5	c 7
2352	a 2	b 5	c 7
2353	a 3	b 5	c 7
2354	a 4	b 5	c 7
2355	a 5	b 5	c 7
2356	a 6	b 5	c 7
2357	a 7	b 5	c 7
2358	a 8	b 5	c 7
2359	a 9	b 5	c 7
2360	a 10	b 5	c 7
2361	a 11	b 5	c 7
2362	a 12	b 5	c 7
2363	a 13	b 5	c 7
2364	a 14	b 5	c 7
2365	a 15	b 5	c 7
2366	a 16	b 5	c 7
2367	a 17	b 5	c 7
2368	a 18	b 5	c 7
2369	a 19	b 5	c 7
2370	a 20	b 5	c 7
2371	a 21	b 5	c 7
2372	a 22	b 5	c 7
2373	a 23	b 5	c 7
2374	a 24	b 5	c 7
2375	a 25	b 5	c 7
2376	a 1	b 6	c 7
2377	a 2	b 6	c 7
2378	a 3	b 6	c 7
2379	a 4	b 6	c 7
2380	a 5	b 6	c 7
2381	a 6	b 6	c 7
2382	a 7	b 6	c 7
2383	a 8	b 6	c 7
2384	a 9	b 6	c 7
2385	a 10	b 6	c 7
2386	a 11	b 6	c 7
2387	a 12	b 6	c 7
2388	a 13	b 6	c 7
2389	a 14	b 6	c 7
2390	a 15	b 6	c 7
2391	a 16	b 6	c 7

09857687.060801

No.	Cp	Bridge	Flu
2392	a 17	b 6	c 7
2393	a 18	b 6	c 7
2394	a 19	b 6	c 7
2395	a 20	b 6	c 7
2396	a 21	b 6	c 7
2397	a 22	b 6	c 7
2398	a 23	b 6	c 7
2399	a 24	b 6	c 7
2400	a 25	b 6	c 7
2401	a 1	b 7	c 7
2402	a 2	b 7	c 7
2403	a 3	b 7	c 7
2404	a 4	b 7	c 7
2405	a 5	b 7	c 7
2406	a 6	b 7	c 7
2407	a 7	b 7	c 7
2408	a 8	b 7	c 7
2409	a 9	b 7	c 7
2410	a 10	b 7	c 7
2411	a 11	b 7	c 7
2412	a 12	b 7	c 7
2413	a 13	b 7	c 7
2414	a 14	b 7	c 7
2415	a 15	b 7	c 7
2416	a 16	b 7	c 7
2417	a 17	b 7	c 7
2418	a 18	b 7	c 7
2419	a 19	b 7	c 7
2420	a 20	b 7	c 7
2421	a 21	b 7	c 7
2422	a 22	b 7	c 7
2423	a 23	b 7	c 7
2424	a 24	b 7	c 7
2425	a 25	b 7	c 7
2426	a 1	b 8	c 7
2427	a 2	b 8	c 7
2428	a 3	b 8	c 7
2429	a 4	b 8	c 7
2430	a 5	b 8	c 7
2431	a 6	b 8	c 7
2432	a 7	b 8	c 7
2433	a 8	b 8	c 7
2434	a 9	b 8	c 7
2435	a 10	b 8	c 7
2436	a 11	b 8	c 7
2437	a 12	b 8	c 7

09857687, 060801

No.	Cp	Bridge	Flu
2438	a 13	b 8	c 7
2439	a 14	b 8	c 7
2440	a 15	b 8	c 7
2441	a 16	b 8	c 7
2442	a 17	b 8	c 7
2443	a 18	b 8	c 7
2444	a 19	b 8	c 7
2445	a 20	b 8	c 7
2446	a 21	b 8	c 7
2447	a 22	b 8	c 7
2448	a 23	b 8	c 7
2449	a 24	b 8	c 7
2450	a 25	b 8	c 7
2451	a 1	b 9	c 7
2452	a 2	b 9	c 7
2453	a 3	b 9	c 7
2454	a 4	b 9	c 7
2455	a 5	b 9	c 7
2456	a 6	b 9	c 7
2457	a 7	b 9	c 7
2458	a 8	b 9	c 7
2459	a 9	b 9	c 7
2460	a 10	b 9	c 7
2461	a 11	b 9	c 7
2462	a 12	b 9	c 7
2463	a 13	b 9	c 7
2464	a 14	b 9	c 7
2465	a 15	b 9	c 7
2466	a 16	b 9	c 7
2467	a 17	b 9	c 7
2468	a 18	b 9	c 7
2469	a 19	b 9	c 7
2470	a 20	b 9	c 7
2471	a 21	b 9	c 7
2472	a 22	b 9	c 7
2473	a 23	b 9	c 7
2474	a 24	b 9	c 7
2475	a 25	b 9	c 7
2476	a 1	b 10	c 7
2477	a 2	b 10	c 7
2478	a 3	b 10	c 7
2479	a 4	b 10	c 7
2480	a 5	b 10	c 7
2481	a 6	b 10	c 7
2482	a 7	b 10	c 7
2483	a 8	b 10	c 7

09857687.060801

No.	Cp	Bridge	Flu
2484	a 9	b 10	c 7
2485	a 10	b 10	c 7
2486	a 11	b 10	c 7
2487	a 12	b 10	c 7
2488	a 13	b 10	c 7
2489	a 14	b 10	c 7
2490	a 15	b 10	c 7
2491	a 16	b 10	c 7
2492	a 17	b 10	c 7
2493	a 18	b 10	c 7
2494	a 19	b 10	c 7
2495	a 20	b 10	c 7
2496	a 21	b 10	c 7
2497	a 22	b 10	c 7
2498	a 23	b 10	c 7
2499	a 24	b 10	c 7
2500	a 25	b 10	c 7
2501	a 1	b 11	c 7
2502	a 2	b 11	c 7
2503	a 3	b 11	c 7
2504	a 4	b 11	c 7
2505	a 5	b 11	c 7
2506	a 6	b 11	c 7
2507	a 7	b 11	c 7
2508	a 8	b 11	c 7
2509	a 9	b 11	c 7
2510	a 10	b 11	c 7
2511	a 11	b 11	c 7
2512	a 12	b 11	c 7
2513	a 13	b 11	c 7
2514	a 14	b 11	c 7
2515	a 15	b 11	c 7
2516	a 16	b 11	c 7
2517	a 17	b 11	c 7
2518	a 18	b 11	c 7
2519	a 19	b 11	c 7
2520	a 20	b 11	c 7
2521	a 21	b 11	c 7
2522	a 22	b 11	c 7
2523	a 23	b 11	c 7
2524	a 24	b 11	c 7
2525	a 25	b 11	c 7
2526	a 1	b 12	c 7
2527	a 2	b 12	c 7
2528	a 3	b 12	c 7
2529	a 4	b 12	c 7

T08090728975860

No.	Cp	Bridge	Flu
2530	a 5	b 12	c 7
2531	a 6	b 12	c 7
2532	a 7	b 12	c 7
2533	a 8	b 12	c 7
2534	a 9	b 12	c 7
2535	a 10	b 12	c 7
2536	a 11	b 12	c 7
2537	a 12	b 12	c 7
2538	a 13	b 12	c 7
2539	a 14	b 12	c 7
2540	a 15	b 12	c 7
2541	a 16	b 12	c 7
2542	a 17	b 12	c 7
2543	a 18	b 12	c 7
2544	a 19	b 12	c 7
2545	a 20	b 12	c 7
2546	a 21	b 12	c 7
2547	a 22	b 12	c 7
2548	a 23	b 12	c 7
2549	a 24	b 12	c 7
2550	a 25	b 12	c 7
2551	a 1	b 13	c 7
2552	a 2	b 13	c 7
2553	a 3	b 13	c 7
2554	a 4	b 13	c 7
2555	a 5	b 13	c 7
2556	a 6	b 13	c 7
2557	a 7	b 13	c 7
2558	a 8	b 13	c 7
2559	a 9	b 13	c 7
2560	a 10	b 13	c 7
2561	a 11	b 13	c 7
2562	a 12	b 13	c 7
2563	a 13	b 13	c 7
2564	a 14	b 13	c 7
2565	a 15	b 13	c 7
2566	a 16	b 13	c 7
2567	a 17	b 13	c 7
2568	a 18	b 13	c 7
2569	a 19	b 13	c 7
2570	a 20	b 13	c 7
2571	a 21	b 13	c 7
2572	a 22	b 13	c 7
2573	a 23	b 13	c 7
2574	a 24	b 13	c 7
2575	a 25	b 13	c 7

09357687.060801


No.	Cp	Bridge	Flu
2576	a 1	b 14	c 7
2577	a 2	b 14	c 7
2578	a 3	b 14	c 7
2579	a 4	b 14	c 7
2580	a 5	b 14	c 7
2581	a 6	b 14	c 7
2582	a 7	b 14	c 7
2583	a 8	b 14	c 7
2584	a 9	b 14	c 7
2585	a 10	b 14	c 7
2586	a 11	b 14	c 7
2587	a 12	b 14	c 7
2588	a 13	b 14	c 7
2589	a 14	b 14	c 7
2590	a 15	b 14	c 7
2591	a 16	b 14	c 7
2592	a 17	b 14	c 7
2593	a 18	b 14	c 7
2594	a 19	b 14	c 7
2595	a 20	b 14	c 7
2596	a 21	b 14	c 7
2597	a 22	b 14	c 7
2598	a 23	b 14	c 7
2599	a 24	b 14	c 7
2600	a 25	b 14	c 7
2601	a 1	b 15	c 7
2602	a 2	b 15	c 7
2603	a 3	b 15	c 7
2604	a 4	b 15	c 7
2605	a 5	b 15	c 7
2606	a 6	b 15	c 7
2607	a 7	b 15	c 7
2608	a 8	b 15	c 7
2609	a 9	b 15	c 7
2610	a 10	b 15	c 7
2611	a 11	b 15	c 7
2612	a 12	b 15	c 7
2613	a 13	b 15	c 7
2614	a 14	b 15	c 7
2615	a 15	b 15	c 7
2616	a 16	b 15	c 7
2617	a 17	b 15	c 7
2618	a 18	b 15	c 7
2619	a 19	b 15	c 7
2620	a 20	b 15	c 7
2621	a 21	b 15	c 7

09857687-060801

No.	Cp	Bridge	Flu
2622	a 22	b 15	c 7
2623	a 23	b 15	c 7
2624	a 24	b 15	c 7
2625	a 25	b 15	c 7

- According to the above table, the ligand structure
- 5 of No. 752 means a combination of a2-b1-c3, so that when the metal part MQ_j is ZrCl₂, the following metallocene compound is exemplified.

10




15

- Specific examples of MQ_j include ZrCl₂, ZrBr₂, ZrMe₂, Zr(OTs)₂, Zr(OMs)₂, Zr(OTf)₂, TiCl₂, TiBr₂, TiMe₂, Ti(OTs)₂, Ti(OMs)₂, Ti(OTf)₂, HfCl₂, HfBr₂, HfMe₂, Hf(OTs)₂, Hf(OMs)₂ and Hf(OTf)₂, wherein Ts
- 20 indicates a p-toluenesulfonyl group, Ms indicates a methanesulfonyl group, and Tf indicates a trifluoromethanesulfonyl group.

T08080-78758601

Examples of the metallocene compounds wherein the substituent group on the Cp ring and the substituent group on the bridge part are bonded to form a ring include the following compounds.

5



Preferred examples of the metallocene compounds represented by the formula (1) or (2) according to the invention include:

a metallocene compound of the formula (1) wherein R^1 , R^{13} and R^{14} are each methyl, R^3 is tert-butyl, R^2 , R^4 , R^5 , R^7 , R^8 , R^9 , R^{10} and R^{12} are each hydrogen, R^6 and R^{11} are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

a metallocene compound of the formula (1) wherein R^{13} and R^{14} are each methyl, R^3 is 1-methyl-1-cyclohexyl, R^1 , R^2 , R^4 , R^5 , R^6 , R^8 , R^9 , R^{11} and R^{12} are each hydrogen, R^7 and R^{10} are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

a metallocene compound of the formula (1) wherein R^{13} and R^{14} are each methyl, R^3 is tert-butyl, R^1 , R^2 , R^4 , R^5 , R^8 , R^9 and R^{12} are each hydrogen, R^6 and R^7 are bonded to form $-(C(CH_3)_2CH_2CH_2C(CH_3)_2)-$ and

- 5 thereby form a ring, R^{10} and R^{11} are bonded to form $-(C(CH_3)_2CH_2CH_2C(CH_3)_2)-$ and thereby form a ring, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

- a metallocene compound of the formula (1) wherein R^{13} and R^{14} are each methyl, R^3 is trimethylsilyl, R^1 , R^2 , R^4 , R^5 , R^8 , R^9 and R^{12} are each hydrogen, R^6 and R^7 are bonded to form $-(C(CH_3)_2CH_2CH_2C(CH_3)_2)-$ and thereby form a ring, R^{10} and R^{11} are bonded to form $-(C(CH_3)_2CH_2CH_2C(CH_3)_2)-$ and thereby form a ring, M is zirconium, Y is carbon, Q is chlorine, and j is 2;
- 10

- 15 a metallocene compound of the formula (1) wherein R^{13} and R^{14} are each methyl, R^3 is 1,1-dimethylpropyl, R^1 , R^2 , R^4 , R^5 , R^6 , R^8 , R^9 , R^{11} and R^{12} are each hydrogen, R^7 and R^{10} are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

- 20 a metallocene compound of the formula (1) wherein R^{13} and R^{14} are each methyl, R^3 is 1-ethyl-1-methylpropyl, R^1 , R^2 , R^4 , R^5 , R^6 , R^8 , R^9 , R^{11} and R^{12} are each hydrogen, R^7 and R^{10} are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

09657687-060801

a metallocene compound of the formula (1) wherein
R¹³ and R¹⁴ are each methyl, R³ is 1,1,3-
trimethylbutyl, R¹, R², R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹ and
R¹² are each hydrogen, R⁷ and R¹⁰ are each tert-butyl,
5 M is zirconium, Y is carbon, Q is chlorine, and j is
2;

a metallocene compound of the formula (1) wherein
R¹³ and R¹⁴ are each methyl, R³ is 1,1-dimethylbutyl,
R¹, R², R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹ and R¹² are each
10 hydrogen, R⁷ and R¹⁰ are each tert-butyl, M is
zirconium, Y is carbon, Q is chlorine, and j is 2;

a metallocene compound of the formula (1) wherein
R¹³ and R¹⁴ are each methyl, R³ is tert-butyl, R¹, R²,
R⁴, R⁵, R⁷, R⁸, R⁹, R¹⁰ and R¹² are each hydrogen, R⁶
15 and R¹¹ are each tert-butyl, M is zirconium, Y is
carbon, Q is chlorine, and j is 2;

a metallocene compound of the formula (1) wherein
R³, R¹³ and R¹⁴ are each phenyl, R¹, R², R⁴, R⁵, R⁸,
R⁹ and R¹² are each hydrogen, R⁶ and R⁷ are bonded to
20 form $-(C(CH_3)_2CH_2CH_2C(CH_3)_2)-$ and thereby form a ring,
R¹⁰ and R¹¹ are bonded to form -
 $(C(CH_3)_2CH_2CH_2C(CH_3)_2)-$ and thereby form a ring, M is
zirconium, Y is carbon, Q is chlorine, and j is 2;

a metallocene compound of the formula (1) wherein
25 R³ is trimethylsilyl, R¹³ and R¹⁴ are each phenyl, R¹,

09857687.060801

R², R⁴, R⁵, R⁸, R⁹ and R¹² are each hydrogen, R⁶ and R⁷ are bonded to form -(C(CH₃)₂CH₂CH₂C(CH₃)₂)- and thereby form a ring, R¹⁰ and R¹¹ are bonded to form -(C(CH₃)₂CH₂CH₂C(CH₃)₂)- and thereby form a ring, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

- 5 a metallocene compound of the formula (1) wherein R¹³ is methyl, R¹⁴ is phenyl, R³ is tert-butyl, R¹, R², R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹ and R¹² are each hydrogen, R⁷ and R¹⁰ are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

- 10 a metallocene compound of the formula (1) wherein R¹³ and R¹⁴ are each ethyl, R³ is tert-butyl, R¹, R², R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹ and R¹² are each hydrogen, R⁷ and R¹⁰ are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

- 15 a metallocene compound of the formula (2) wherein R¹ is methyl, R³ is tert-butyl, R², R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, R¹¹ and R¹² are each hydrogen, M is zirconium, Y is carbon, Q is chlorine, j is 2, and A is -(CH₂)₅-;

- 20 a metallocene compound of the formula (2) wherein R¹ is methyl, R³ is tert-butyl, R², R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹ and R¹² are each hydrogen, R⁷ and R¹⁰ are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, j is 2, and A is -(CH₂)₅-;

09857697.060801

a metallocene compound of the formula (2) wherein
R³ is trimethylsilyl, R¹, R², R⁴, R⁵, R⁷, R⁸, R⁹, R¹⁰
and R¹² are each hydrogen, R⁶ and R¹¹ are each tert-
butyl, M is zirconium, Y is carbon, Q is chlorine, j
5 is 2, and A is -(CH₂)₅-;

a metallocene compound of the formula (2) wherein
R³ is trimethylsilyl, R¹, R², R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹
and R¹² are each hydrogen, R⁷ and R¹⁰ are each tert-
butyl, M is zirconium, Y is carbon, Q is chlorine, j
10 is 2, and A is -(CH₂)₅-;

a metallocene compound of the formula (2) wherein
R³ is tert-butyl, R¹, R², R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹ and
R¹² are each hydrogen, R⁷ and R¹⁰ are each tert-butyl,
M is zirconium, Y is carbon, Q is chlorine, j is 2,
15 and A is -(CH₂)₄-;

a metallocene compound of the formula (2) wherein
R³ is 1,1-dimethylpropyl, R¹, R², R⁴, R⁵, R⁶, R⁸, R⁹,
R¹¹ and R¹² are each hydrogen, R⁷ and R¹⁰ are each
tert-butyl, M is zirconium, Y is carbon, Q is chlorine,
20 j is 2, and A is -(CH₂)₅-;

a metallocene compound of the formula (2) wherein
R³ is tert-butyl, R¹, R², R⁴, R⁵, R⁸, R⁹ and R¹² are
each hydrogen, R⁶ and R⁷ are bonded to form -
(C(CH₃)₂CH₂CH₂C(CH₃)₂)- and thereby form a ring, R¹⁰
25 and R¹¹ are bonded to form -(C(CH₃)₂CH₂CH₂C(CH₃)₂)-

09857687-060801

and thereby form a ring, M is zirconium, Y is carbon, Q is chlorine, j is 2, and A is $-(CH_2)_4-$;

- a metallocene compound of the formula (1) wherein
- 5 R¹, R¹³ and R¹⁴ are each methyl, R³ is tert-butyl, R², R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹ and R¹² are each hydrogen, R⁷ and R¹⁰ are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

- a metallocene compound of the formula (1) wherein
- 10 R¹³ and R¹⁴ are each methyl, R³ is tert-butyl, R¹, R², R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹ and R¹² are each hydrogen, R⁷ and R¹⁰ are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

- a metallocene compound of the formula (1) wherein
- 15 R¹, R¹³ and R¹⁴ are each methyl, R³ is tert-butyl, R², R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, R¹¹ and R¹² are each hydrogen, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

- a metallocene compound of the formula (1) wherein
- 20 R¹³ and R¹⁴ are each methyl, R³ is trimethylsilyl, R¹, R², R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹ and R¹² are each hydrogen, R⁷ and R¹⁰ are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, and j is 2; and

- a metallocene compound of the formula (1) wherein
- 25 R¹³ and R¹⁴ are each phenyl, R³ is trimethylsilyl, R¹, R², R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹ and R¹² are each hydrogen,

09857687.060201


R⁷ and R¹⁰ are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, and j is 2.

There is no specific limitation on the process for preparing the metallocene compound represented by the
5 formula (1) or (2), and the compound can be prepared by, for example, the below-described process.




First, the ligand precursor (5) used as starting material for preparing the metallocene compound represented by the formula (1) can be prepared through
10 the following step (A) or (B).

09557667-060001

[A]



[B]



20

09857687-060801




In the compounds shown in the above steps (A) and (B), R^1 to R^{14} and Y have the same meanings as those of R^1 to R^{14} and Y in the formula (1), respectively, L is an alkali metal, and Z^1 and Z^2 may be the same or
5 different and are each a halogen or an anionic ligand.

With regard to the cyclopentadiene (7), the precursor compound (10) and the ligand precursor (5), presence of isomers different in only the position of a double bond in the cyclopentadienyl ring can be
10 thought, but only one example is shown. Each of them may be another isomer different in only the position of a double bond in the cyclopentadienyl ring or a mixture thereof.

The ligand precursor (6) used as starting material
15 for preparing the metallocene compound represented by the formula (2) can be prepared through the following step (C) or (D).

09657687-060801




[C]



20

09857687.060801

[D]




In the compounds shown in the above steps (C) and (D), R^1 to R^4 , Y and A have the same meanings as those of R^1 to R^4 , Y and A in the formula (2), respectively, L is an alkali metal, and Z^1 and Z^2 may be the same or different and are each a halogen or an anionic ligand.

With regard to the cyclopentadiene (7), the precursor compound (18) and the ligand precursor (6), presence of isomers different in only the position of a double bond in the cyclopentadienyl ring can be thought, but only one example is shown. Each of them may be another isomer different in only the position of a double bond in the cyclopentadienyl ring or a mixture thereof.

The cyclopentadiene (7) that is a precursor common to the metallocene compounds represented by the formulas (1) and (2) can be prepared through, for example, the following step (E) or (F).

20 [E]




In the compounds shown in the step (E), R^1 , R^2 , R^3 and R^4 have the same meanings as those of R^1 , R^2 , R^3

and R^4 in the formula (1) or (2), respectively, M^1 is an alkali metal or an alkaline earth metal, Z^3 is the same as R^3 or is a halogen or an anionic ligand, and e is a valence of M^1 .

5

[F]




10

In the compounds shown in the step (F), R^1 , R^2 , R^3 and R^4 have the same meanings as those of R^1 , R^2 , R^3 and R^4 in the formula (1) or (2), respectively, L is an alkali metal, and Z^1 is a halogen or an anionic ligand.

15

When R^3 is a substituent group represented by $CR^{15}R^{16}R^{17}$, the cyclopentadiene (7) can be prepared also through the following step (G).

20 [G]



25

In the step (G), R^1 , R^2 and R^4 have the same meanings as those of R^1 , R^2 and R^4 in the formula (1) or (2), respectively, R^{15} , R^{16} and R^{17} are each selected from a hydrogen atom, a hydrocarbon group and
5 a silicon-containing hydrocarbon group and may be the same or different, and L is an alkali metal.

In the steps (E) to (G), though, examples of methods to introduce the substituent group R^3 are shown, the substituent groups R^1 , R^2 and R^4 can also
10 be introduced similarly to those methods.

The alkali metal used for the reactions in the steps (A) to (G) is lithium, sodium or potassium, and the alkaline earth metal is magnesium or calcium. The halogen is fluorine, chlorine, bromine or iodine.
15 Examples of the anionic ligands include alkoxy groups, such as methoxy, tert-butoxy and phenoxy; carboxylate groups, such as acetate and benzoate; and sulfonate groups, such as mesylate and tosylate.

Next, an example of the process for preparing a
20 metallocene compound from the ligand precursor represented by the formula (5) or (6) is described.

In the first place, the ligand precursor represented by the formula (5) or (6) that is obtained by the reaction of the step (A), (B), (C) or (D) is
25 brought into contact with an alkali metal, an alkali

00857667-060801

metal hydride or an organic alkali metal in an organic solvent at a reaction temperature of -80 to 200°C to prepare a di-alkali metal salt.

- Examples of the organic solvents used for the
- 5 above reaction include aliphatic hydrocarbons, such as pentane, hexane, heptane, cyclohexane and decalin; aromatic hydrocarbons, such as benzene, toluene and xylene; ethers, such as THF (tetrahydrofuran), diethyl ether, dioxane and 1,2-dimethoxyethane; and
- 10 halogenated hydrocarbons, such as dichloromethane and chloroform.

Examples of the alkali metals used for the reaction include lithium, sodium and potassium.

- Examples of the alkali metal hydrides include sodium
- 15 hydride and potassium hydride. Examples of the organic alkali metals include methyllithium, butyllithium and phenyllithium.

- In the next place, the di-alkali metal salt is allowed to react, in an organic solvent, with a
- 20 compound represented by the following formula (30):



(30)

- wherein M is a metal selected from Group 4 of the
- 25 periodic table, each Z may be the same or different

0057607, 060801

and is selected from a halogen, an anionic ligand and a neutral ligand capable of coordination by a lone pair, and k is an integer of 3 to 6.

Thus, the metallocene compound represented by the
5 formula (1) or (2) can be synthesized.

Preferred examples of the compounds represented by the formula (30) include trivalent or tetravalent titanium fluoride, chloride, bromide or iodide; tetravalent zirconium fluoride, chloride, bromide or
10 iodide; tetravalent hafnium fluoride, chloride, bromide or iodide; and complexes of these compounds with ethers such as THF, diethyl ether, dioxane and 1,2-dimethoxyethane.

Examples of the organic solvents used include the
15 same ones as previously described.


The reaction of the di-alkali metal salt with the compound represented by the formula (30) is preferably an equimolar reaction, and can be carried out in the aforesaid organic solvent at a reaction temperature of
20 -80 to 200°C.

The metallocene compound obtained by the reaction can be isolated and purified by, for example, extraction, recrystallization or sublimation.

Next, the metallocene compound represented by the
25 formula (1a) or (2a) is described.

09857687-060601

Another embodiment of the metallocene compound of the invention is represented by the following formula (1a) or (2a).



- In the formula (1a) or (2a), R^3 has the same meaning as that of R^3 in the formula (1) or (2); R^1 , R^2 , and R^4 to R^{14} have the same meanings as those of R^1 , R^2 , and R^4 to R^{14} in the formula (1) or (2), respectively; and A, Y, M, Q and j have the same meanings as those of A, Y, M, Q and j in the formula (1) or (2), respectively. In case of the compound of the formula (1a) wherein R^3 is tert-butyl or trimethylsilyl and R^{13} and R^{14} are methyl groups or phenyl groups at the same time, R^6 and R^{11} are not hydrogen atoms at the same time.

R^3 is preferably a sterically bulky substituent group, more preferably a substituent group of 4 or more carbon atoms.

- Examples of the metallocene compounds represented
- 5 by the formula (1a) or (2a) according to the invention are given below.

- Examples of the ligand structure excluding MQ_j (metal part) in the metallocene compound are described first. Examples of Cp (cyclopentadienyl ring part),
- 10 Bridge (bridge part) and Flu (fluorenyl ring part) are the same as those previously described with respect to the metallocene compound represented by the formula (1) or (2).

09857587-060801

No.	Cp	Bridge	Flu
1	a 1	b 1	c 1
2	a 2	b 1	c 1
3	a 3	b 1	c 1
4	a 4	b 1	c 1
5	a 5	b 1	c 1
6	a 6	b 1	c 1
7	a 7	b 1	c 1
8	a 8	b 1	c 1
9	a 9	b 1	c 1
10	a 10	b 1	c 1
11	a 11	b 1	c 1
12	a 12	b 1	c 1
13	a 13	b 1	c 1
14	a 14	b 1	c 1
15	a 15	b 1	c 1
16	a 16	b 1	c 1
17	a 17	b 1	c 1
18	a 18	b 1	c 1
19	a 19	b 1	c 1
20	a 20	b 1	c 1
21	a 21	b 1	c 1
22	a 22	b 1	c 1
23	a 23	b 1	c 1
24	a 24	b 1	c 1
25	a 25	b 1	c 1
26	a 1	b 2	c 1
27	a 2	b 2	c 1
28	a 3	b 2	c 1
29	a 4	b 2	c 1
30	a 5	b 2	c 1
31	a 6	b 2	c 1
32	a 7	b 2	c 1
33	a 8	b 2	c 1
34	a 9	b 2	c 1
35	a 10	b 2	c 1
36	a 11	b 2	c 1
37	a 12	b 2	c 1
38	a 13	b 2	c 1
39	a 14	b 2	c 1
40	a 15	b 2	c 1
41	a 16	b 2	c 1
42	a 17	b 2	c 1
43	a 18	b 2	c 1
44	a 19	b 2	c 1
45	a 20	b 2	c 1

09857687.060801

No.	Cp	Bridge	Flu
46	a 21	b 2	c 1
47	a 22	b 2	c 1
48	a 23	b 2	c 1
49	a 24	b 2	c 1
50	a 25	b 2	c 1
51	a 1	b 3	c 1
52	a 2	b 3	c 1
53	a 3	b 3	c 1
54	a 4	b 3	c 1
55	a 5	b 3	c 1
56	a 6	b 3	c 1
57	a 7	b 3	c 1
58	a 8	b 3	c 1
59	a 9	b 3	c 1
60	a 10	b 3	c 1
61	a 11	b 3	c 1
62	a 12	b 3	c 1
63	a 13	b 3	c 1
64	a 14	b 3	c 1
65	a 15	b 3	c 1
66	a 16	b 3	c 1
67	a 17	b 3	c 1
68	a 18	b 3	c 1
69	a 19	b 3	c 1
70	a 20	b 3	c 1
71	a 21	b 3	c 1
72	a 22	b 3	c 1
73	a 23	b 3	c 1
74	a 24	b 3	c 1
75	a 25	b 3	c 1
76	a 1	b 4	c 1
77	a 2	b 4	c 1
78	a 3	b 4	c 1
79	a 4	b 4	c 1
80	a 5	b 4	c 1
81	a 6	b 4	c 1
82	a 7	b 4	c 1
83	a 8	b 4	c 1
84	a 9	b 4	c 1
85	a 10	b 4	c 1
86	a 11	b 4	c 1
87	a 12	b 4	c 1
88	a 13	b 4	c 1
89	a 14	b 4	c 1
90	a 15	b 4	c 1
91	a 16	b 4	c 1

09857687 060801

No.	Cp	Bridge	Flu
92	a 17	b 4	c 1
93	a 18	b 4	c 1
94	a 19	b 4	c 1
95	a 20	b 4	c 1
96	a 21	b 4	c 1
97	a 22	b 4	c 1
98	a 23	b 4	c 1
99	a 24	b 4	c 1
100	a 25	b 4	c 1
101	a 1	b 5	c 1
102	a 2	b 5	c 1
103	a 3	b 5	c 1
104	a 4	b 5	c 1
105	a 5	b 5	c 1
106	a 6	b 5	c 1
107	a 7	b 5	c 1
108	a 8	b 5	c 1
109	a 9	b 5	c 1
110	a 10	b 5	c 1
111	a 11	b 5	c 1
112	a 12	b 5	c 1
113	a 13	b 5	c 1
114	a 14	b 5	c 1
115	a 15	b 5	c 1
116	a 16	b 5	c 1
117	a 17	b 5	c 1
118	a 18	b 5	c 1
119	a 19	b 5	c 1
120	a 20	b 5	c 1
121	a 21	b 5	c 1
122	a 22	b 5	c 1
123	a 23	b 5	c 1
124	a 24	b 5	c 1
125	a 25	b 5	c 1
126	a 1	b 6	c 1
127	a 2	b 6	c 1
128	a 3	b 6	c 1
129	a 4	b 6	c 1
130	a 5	b 6	c 1
131	a 6	b 6	c 1
132	a 7	b 6	c 1
133	a 8	b 6	c 1
134	a 9	b 6	c 1
135	a 10	b 6	c 1
136	a 11	b 6	c 1
137	a 12	b 6	c 1

09857687.060801

No.	Cp	Bridge	Flu
138	a 13	b 6	c 1
139	a 14	b 6	c 1
140	a 15	b 6	c 1
141	a 16	b 6	c 1
142	a 17	b 6	c 1
143	a 18	b 6	c 1
144	a 19	b 6	c 1
145	a 20	b 6	c 1
146	a 21	b 6	c 1
147	a 22	b 6	c 1
148	a 23	b 6	c 1
149	a 24	b 6	c 1
150	a 25	b 6	c 1
151	a 1	b 7	c 1
152	a 2	b 7	c 1
153	a 3	b 7	c 1
154	a 4	b 7	c 1
155	a 5	b 7	c 1
156	a 6	b 7	c 1
157	a 7	b 7	c 1
158	a 8	b 7	c 1
159	a 9	b 7	c 1
160	a 10	b 7	c 1
161	a 11	b 7	c 1
162	a 12	b 7	c 1
163	a 13	b 7	c 1
164	a 14	b 7	c 1
165	a 15	b 7	c 1
166	a 16	b 7	c 1
167	a 17	b 7	c 1
168	a 18	b 7	c 1
169	a 19	b 7	c 1
170	a 20	b 7	c 1
171	a 21	b 7	c 1
172	a 22	b 7	c 1
173	a 23	b 7	c 1
174	a 24	b 7	c 1
175	a 25	b 7	c 1
176	a 5	b 8	c 1
177	a 6	b 8	c 1
178	a 7	b 8	c 1
179	a 8	b 8	c 1
180	a 9	b 8	c 1
181	a 10	b 8	c 1
182	a 11	b 8	c 1
183	a 12	b 8	c 1

09857687 060801

No.	Cp	Bridge	Flu
184	a 13	b 8	c 1
185	a 14	b 8	c 1
186	a 15	b 8	c 1
187	a 16	b 8	c 1
188	a 17	b 8	c 1
189	a 18	b 8	c 1
190	a 19	b 8	c 1
191	a 20	b 8	c 1
192	a 21	b 8	c 1
193	a 22	b 8	c 1
194	a 23	b 8	c 1
195	a 24	b 8	c 1
196	a 25	b 8	c 1
197	a 5	b 9	c 1
198	a 6	b 9	c 1
199	a 7	b 9	c 1
200	a 8	b 9	c 1
201	a 9	b 9	c 1
202	a 10	b 9	c 1
203	a 11	b 9	c 1
204	a 12	b 9	c 1
205	a 13	b 9	c 1
206	a 14	b 9	c 1
207	a 15	b 9	c 1
208	a 16	b 9	c 1
209	a 17	b 9	c 1
210	a 18	b 9	c 1
211	a 19	b 9	c 1
212	a 20	b 9	c 1
213	a 21	b 9	c 1
214	a 22	b 9	c 1
215	a 23	b 9	c 1
216	a 24	b 9	c 1
217	a 25	b 9	c 1
218	a 5	b 10	c 1
219	a 6	b 10	c 1
220	a 7	b 10	c 1
221	a 8	b 10	c 1
222	a 9	b 10	c 1
223	a 10	b 10	c 1
224	a 11	b 10	c 1
225	a 12	b 10	c 1
226	a 13	b 10	c 1
227	a 14	b 10	c 1
228	a 15	b 10	c 1
229	a 16	b 10	c 1

09557687.060601

No.	Cp	Bridge	Flu
230	a 17	b 10	c 1
231	a 18	b 10	c 1
232	a 19	b 10	c 1
233	a 20	b 10	c 1
234	a 21	b 10	c 1
235	a 22	b 10	c 1
236	a 23	b 10	c 1
237	a 24	b 10	c 1
238	a 25	b 10	c 1
239	a 5	b 11	c 1
240	a 6	b 11	c 1
241	a 7	b 11	c 1
242	a 8	b 11	c 1
243	a 9	b 11	c 1
244	a 10	b 11	c 1
245	a 11	b 11	c 1
246	a 12	b 11	c 1
247	a 13	b 11	c 1
248	a 14	b 11	c 1
249	a 15	b 11	c 1
250	a 16	b 11	c 1
251	a 17	b 11	c 1
252	a 18	b 11	c 1
253	a 19	b 11	c 1
254	a 20	b 11	c 1
255	a 21	b 11	c 1
256	a 22	b 11	c 1
257	a 23	b 11	c 1
258	a 24	b 11	c 1
259	a 25	b 11	c 1
260	a 1	b 12	c 1
261	a 2	b 12	c 1
262	a 3	b 12	c 1
263	a 4	b 12	c 1
264	a 5	b 12	c 1
265	a 6	b 12	c 1
266	a 7	b 12	c 1
267	a 8	b 12	c 1
268	a 9	b 12	c 1
269	a 10	b 12	c 1
270	a 11	b 12	c 1
271	a 12	b 12	c 1
272	a 13	b 12	c 1
273	a 14	b 12	c 1
274	a 15	b 12	c 1
275	a 16	b 12	c 1

09857587-060801

No.	Cp	Bridge	Flu
276	a 17	b 12	c 1
277	a 18	b 12	c 1
278	a 19	b 12	c 1
279	a 20	b 12	c 1
280	a 21	b 12	c 1
281	a 22	b 12	c 1
282	a 23	b 12	c 1
283	a 24	b 12	c 1
284	a 25	b 12	c 1
285	a 1	b 13	c 1
286	a 2	b 13	c 1
287	a 3	b 13	c 1
288	a 4	b 13	c 1
289	a 5	b 13	c 1
290	a 6	b 13	c 1
291	a 7	b 13	c 1
292	a 8	b 13	c 1
293	a 9	b 13	c 1
294	a 10	b 13	c 1
295	a 11	b 13	c 1
296	a 12	b 13	c 1
297	a 13	b 13	c 1
298	a 14	b 13	c 1
299	a 15	b 13	c 1
300	a 16	b 13	c 1
301	a 17	b 13	c 1
302	a 18	b 13	c 1
303	a 19	b 13	c 1
304	a 20	b 13	c 1
305	a 21	b 13	c 1
306	a 22	b 13	c 1
307	a 23	b 13	c 1
308	a 24	b 13	c 1
309	a 25	b 13	c 1
310	a 1	b 14	c 1
311	a 2	b 14	c 1
312	a 3	b 14	c 1
313	a 4	b 14	c 1
314	a 5	b 14	c 1
315	a 6	b 14	c 1
316	a 7	b 14	c 1
317	a 8	b 14	c 1
318	a 9	b 14	c 1
319	a 10	b 14	c 1
320	a 11	b 14	c 1
321	a 12	b 14	c 1

09657687.060601

No.	Cp	Bridge	Flu
322	a 13	b 14	c 1
323	a 14	b 14	c 1
324	a 15	b 14	c 1
325	a 16	b 14	c 1
326	a 17	b 14	c 1
327	a 18	b 14	c 1
328	a 19	b 14	c 1
329	a 20	b 14	c 1
330	a 21	b 14	c 1
331	a 22	b 14	c 1
332	a 23	b 14	c 1
333	a 24	b 14	c 1
334	a 25	b 14	c 1
335	a 1	b 15	c 1
336	a 2	b 15	c 1
337	a 3	b 15	c 1
338	a 4	b 15	c 1
339	a 5	b 15	c 1
340	a 6	b 15	c 1
341	a 7	b 15	c 1
342	a 8	b 15	c 1
343	a 9	b 15	c 1
344	a 10	b 15	c 1
345	a 11	b 15	c 1
346	a 12	b 15	c 1
347	a 13	b 15	c 1
348	a 14	b 15	c 1
349	a 15	b 15	c 1
350	a 16	b 15	c 1
351	a 17	b 15	c 1
352	a 18	b 15	c 1
353	a 19	b 15	c 1
354	a 20	b 15	c 1
355	a 21	b 15	c 1
356	a 22	b 15	c 1
357	a 23	b 15	c 1
358	a 24	b 15	c 1
359	a 25	b 15	c 1
360	a 1	b 1	c 2
361	a 2	b 1	c 2
362	a 3	b 1	c 2
363	a 4	b 1	c 2
364	a 5	b 1	c 2
365	a 6	b 1	c 2
366	a 7	b 1	c 2
367	a 8	b 1	c 2

09857687.060801

No.	Cp	Bridge	Flu
368	a 9	b 1	c 2
369	a 10	b 1	c 2
370	a 11	b 1	c 2
371	a 12	b 1	c 2
372	a 13	b 1	c 2
373	a 14	b 1	c 2
374	a 15	b 1	c 2
375	a 16	b 1	c 2
376	a 17	b 1	c 2
377	a 18	b 1	c 2
378	a 19	b 1	c 2
379	a 20	b 1	c 2
380	a 21	b 1	c 2
381	a 22	b 1	c 2
382	a 23	b 1	c 2
383	a 24	b 1	c 2
384	a 25	b 1	c 2
385	a 1	b 2	c 2
386	a 2	b 2	c 2
387	a 3	b 2	c 2
388	a 4	b 2	c 2
389	a 5	b 2	c 2
390	a 6	b 2	c 2
391	a 7	b 2	c 2
392	a 8	b 2	c 2
393	a 9	b 2	c 2
394	a 10	b 2	c 2
395	a 11	b 2	c 2
396	a 12	b 2	c 2
397	a 13	b 2	c 2
398	a 14	b 2	c 2
399	a 15	b 2	c 2
400	a 16	b 2	c 2
401	a 17	b 2	c 2
402	a 18	b 2	c 2
403	a 19	b 2	c 2
404	a 20	b 2	c 2
405	a 21	b 2	c 2
406	a 22	b 2	c 2
407	a 23	b 2	c 2
408	a 24	b 2	c 2
409	a 25	b 2	c 2
410	a 1	b 3	c 2
411	a 2	b 3	c 2
412	a 3	b 3	c 2
413	a 4	b 3	c 2

09857687 060801

No.	Cp	Bridge	Flu
414	a 5	b 3	c 2
415	a 6	b 3	c 2
416	a 7	b 3	c 2
417	a 8	b 3	c 2
418	a 9	b 3	c 2
419	a 10	b 3	c 2
420	a 11	b 3	c 2
421	a 12	b 3	c 2
422	a 13	b 3	c 2
423	a 14	b 3	c 2
424	a 15	b 3	c 2
425	a 16	b 3	c 2
426	a 17	b 3	c 2
427	a 18	b 3	c 2
428	a 19	b 3	c 2
429	a 20	b 3	c 2
430	a 21	b 3	c 2
431	a 22	b 3	c 2
432	a 23	b 3	c 2
433	a 24	b 3	c 2
434	a 25	b 3	c 2
435	a 1	b 4	c 2
436	a 2	b 4	c 2
437	a 3	b 4	c 2
438	a 4	b 4	c 2
439	a 5	b 4	c 2
440	a 6	b 4	c 2
441	a 7	b 4	c 2
442	a 8	b 4	c 2
443	a 9	b 4	c 2
444	a 10	b 4	c 2
445	a 11	b 4	c 2
446	a 12	b 4	c 2
447	a 13	b 4	c 2
448	a 14	b 4	c 2
449	a 15	b 4	c 2
450	a 16	b 4	c 2
451	a 17	b 4	c 2
452	a 18	b 4	c 2
453	a 19	b 4	c 2
454	a 20	b 4	c 2
455	a 21	b 4	c 2
456	a 22	b 4	c 2
457	a 23	b 4	c 2
458	a 24	b 4	c 2
459	a 25	b 4	c 2

09857637.060801

No.	Cp	Bridge	Flu
460	a 1	b 5	c 2
461	a 2	b 5	c 2
462	a 3	b 5	c 2
463	a 4	b 5	c 2
464	a 5	b 5	c 2
465	a 6	b 5	c 2
466	a 7	b 5	c 2
467	a 8	b 5	c 2
468	a 9	b 5	c 2
469	a 10	b 5	c 2
470	a 11	b 5	c 2
471	a 12	b 5	c 2
472	a 13	b 5	c 2
473	a 14	b 5	c 2
474	a 15	b 5	c 2
475	a 16	b 5	c 2
476	a 17	b 5	c 2
477	a 18	b 5	c 2
478	a 19	b 5	c 2
479	a 20	b 5	c 2
480	a 21	b 5	c 2
481	a 22	b 5	c 2
482	a 23	b 5	c 2
483	a 24	b 5	c 2
484	a 25	b 5	c 2
485	a 1	b 6	c 2
486	a 2	b 6	c 2
487	a 3	b 6	c 2
488	a 4	b 6	c 2
489	a 5	b 6	c 2
490	a 6	b 6	c 2
491	a 7	b 6	c 2
492	a 8	b 6	c 2
493	a 9	b 6	c 2
494	a 10	b 6	c 2
495	a 11	b 6	c 2
496	a 12	b 6	c 2
497	a 13	b 6	c 2
498	a 14	b 6	c 2
499	a 15	b 6	c 2
500	a 16	b 6	c 2
501	a 17	b 6	c 2
502	a 18	b 6	c 2
503	a 19	b 6	c 2
504	a 20	b 6	c 2
505	a 21	b 6	c 2

09857607 060801

No.	Cp	Bridge	Flu
506	a 22	b 6	c 2
507	a 23	b 6	c 2
508	a 24	b 6	c 2
509	a 25	b 6	c 2
510	a 1	b 7	c 2
511	a 2	b 7	c 2
512	a 3	b 7	c 2
513	a 4	b 7	c 2
514	a 5	b 7	c 2
515	a 6	b 7	c 2
516	a 7	b 7	c 2
517	a 8	b 7	c 2
518	a 9	b 7	c 2
519	a 10	b 7	c 2
520	a 11	b 7	c 2
521	a 12	b 7	c 2
522	a 13	b 7	c 2
523	a 14	b 7	c 2
524	a 15	b 7	c 2
525	a 16	b 7	c 2
526	a 17	b 7	c 2
527	a 18	b 7	c 2
528	a 19	b 7	c 2
529	a 20	b 7	c 2
530	a 21	b 7	c 2
531	a 22	b 7	c 2
532	a 23	b 7	c 2
533	a 24	b 7	c 2
534	a 25	b 7	c 2
535	a 1	b 8	c 2
536	a 2	b 8	c 2
537	a 3	b 8	c 2
538	a 4	b 8	c 2
539	a 5	b 8	c 2
540	a 6	b 8	c 2
541	a 7	b 8	c 2
542	a 8	b 8	c 2
543	a 9	b 8	c 2
544	a 10	b 8	c 2
545	a 11	b 8	c 2
546	a 12	b 8	c 2
547	a 13	b 8	c 2
548	a 14	b 8	c 2
549	a 15	b 8	c 2
550	a 16	b 8	c 2
551	a 17	b 8	c 2

09857667.060801

No.	Cp	Bridge	Flu
552	a 18	b 8	c 2
553	a 19	b 8	c 2
554	a 20	b 8	c 2
555	a 21	b 8	c 2
556	a 22	b 8	c 2
557	a 23	b 8	c 2
558	a 24	b 8	c 2
559	a 25	b 8	c 2
560	a 1	b 9	c 2
561	a 2	b 9	c 2
562	a 3	b 9	c 2
563	a 4	b 9	c 2
564	a 5	b 9	c 2
565	a 6	b 9	c 2
566	a 7	b 9	c 2
567	a 8	b 9	c 2
568	a 9	b 9	c 2
569	a 10	b 9	c 2
570	a 11	b 9	c 2
571	a 12	b 9	c 2
572	a 13	b 9	c 2
573	a 14	b 9	c 2
574	a 15	b 9	c 2
575	a 16	b 9	c 2
576	a 17	b 9	c 2
577	a 18	b 9	c 2
578	a 19	b 9	c 2
579	a 20	b 9	c 2
580	a 21	b 9	c 2
581	a 22	b 9	c 2
582	a 23	b 9	c 2
583	a 24	b 9	c 2
584	a 25	b 9	c 2
585	a 1	b 10	c 2
586	a 2	b 10	c 2
587	a 3	b 10	c 2
588	a 4	b 10	c 2
589	a 5	b 10	c 2
590	a 6	b 10	c 2
591	a 7	b 10	c 2
592	a 8	b 10	c 2
593	a 9	b 10	c 2
594	a 10	b 10	c 2
595	a 11	b 10	c 2
596	a 12	b 10	c 2
597	a 13	b 10	c 2

10909072995860

No.	Cp	Bridge	Flu
598	a 14	b 10	c 2
599	a 15	b 10	c 2
600	a 16	b 10	c 2
601	a 17	b 10	c 2
602	a 18	b 10	c 2
603	a 19	b 10	c 2
604	a 20	b 10	c 2
605	a 21	b 10	c 2
606	a 22	b 10	c 2
607	a 23	b 10	c 2
608	a 24	b 10	c 2
609	a 25	b 10	c 2
610	a 1	b 11	c 2
611	a 2	b 11	c 2
612	a 3	b 11	c 2
613	a 4	b 11	c 2
614	a 5	b 11	c 2
615	a 6	b 11	c 2
616	a 7	b 11	c 2
617	a 8	b 11	c 2
618	a 9	b 11	c 2
619	a 10	b 11	c 2
620	a 11	b 11	c 2
621	a 12	b 11	c 2
622	a 13	b 11	c 2
623	a 14	b 11	c 2
624	a 15	b 11	c 2
625	a 16	b 11	c 2
626	a 17	b 11	c 2
627	a 18	b 11	c 2
628	a 19	b 11	c 2
629	a 20	b 11	c 2
630	a 21	b 11	c 2
631	a 22	b 11	c 2
632	a 23	b 11	c 2
633	a 24	b 11	c 2
634	a 25	b 11	c 2
635	a 1	b 12	c 2
636	a 2	b 12	c 2
637	a 3	b 12	c 2
638	a 4	b 12	c 2
639	a 5	b 12	c 2
640	a 6	b 12	c 2
641	a 7	b 12	c 2
642	a 8	b 12	c 2
643	a 9	b 12	c 2

09257687-060801

No.	Cp	Bridge	Flu
644	a 10	b 12	c 2
645	a 11	b 12	c 2
646	a 12	b 12	c 2
647	a 13	b 12	c 2
648	a 14	b 12	c 2
649	a 15	b 12	c 2
650	a 16	b 12	c 2
651	a 17	b 12	c 2
652	a 18	b 12	c 2
653	a 19	b 12	c 2
654	a 20	b 12	c 2
655	a 21	b 12	c 2
656	a 22	b 12	c 2
657	a 23	b 12	c 2
658	a 24	b 12	c 2
659	a 25	b 12	c 2
660	a 1	b 13	c 2
661	a 2	b 13	c 2
662	a 3	b 13	c 2
663	a 4	b 13	c 2
664	a 5	b 13	c 2
665	a 6	b 13	c 2
666	a 7	b 13	c 2
667	a 8	b 13	c 2
668	a 9	b 13	c 2
669	a 10	b 13	c 2
670	a 11	b 13	c 2
671	a 12	b 13	c 2
672	a 13	b 13	c 2
673	a 14	b 13	c 2
674	a 15	b 13	c 2
675	a 16	b 13	c 2
676	a 17	b 13	c 2
677	a 18	b 13	c 2
678	a 19	b 13	c 2
679	a 20	b 13	c 2
680	a 21	b 13	c 2
681	a 22	b 13	c 2
682	a 23	b 13	c 2
683	a 24	b 13	c 2
684	a 25	b 13	c 2
685	a 1	b 14	c 2
686	a 2	b 14	c 2
687	a 3	b 14	c 2
688	a 4	b 14	c 2
689	a 5	b 14	c 2

0957687-060801

No.	Cp	Bridge	Flu
690	a 6	b 14	c 2
691	a 7	b 14	c 2
692	a 8	b 14	c 2
693	a 9	b 14	c 2
694	a 10	b 14	c 2
695	a 11	b 14	c 2
696	a 12	b 14	c 2
697	a 13	b 14	c 2
698	a 14	b 14	c 2
699	a 15	b 14	c 2
700	a 16	b 14	c 2
701	a 17	b 14	c 2
702	a 18	b 14	c 2
703	a 19	b 14	c 2
704	a 20	b 14	c 2
705	a 21	b 14	c 2
706	a 22	b 14	c 2
707	a 23	b 14	c 2
708	a 24	b 14	c 2
709	a 25	b 14	c 2
710	a 1	b 15	c 2
711	a 2	b 15	c 2
712	a 3	b 15	c 2
713	a 4	b 15	c 2
714	a 5	b 15	c 2
715	a 6	b 15	c 2
716	a 7	b 15	c 2
717	a 8	b 15	c 2
718	a 9	b 15	c 2
719	a 10	b 15	c 2
720	a 11	b 15	c 2
721	a 12	b 15	c 2
722	a 13	b 15	c 2
723	a 14	b 15	c 2
724	a 15	b 15	c 2
725	a 16	b 15	c 2
726	a 17	b 15	c 2
727	a 18	b 15	c 2
728	a 19	b 15	c 2
729	a 20	b 15	c 2
730	a 21	b 15	c 2
731	a 22	b 15	c 2
732	a 23	b 15	c 2
733	a 24	b 15	c 2
734	a 25	b 15	c 2
735	a 1	b 1	c 3

09857687.060801

No.	Cp	Bridge	Flu
736	a 2	b 1	c 3
737	a 3	b 1	c 3
738	a 4	b 1	c 3
739	a 5	b 1	c 3
740	a 6	b 1	c 3
741	a 7	b 1	c 3
742	a 8	b 1	c 3
743	a 9	b 1	c 3
744	a 10	b 1	c 3
745	a 11	b 1	c 3
746	a 12	b 1	c 3
747	a 13	b 1	c 3
748	a 14	b 1	c 3
749	a 15	b 1	c 3
750	a 16	b 1	c 3
751	a 17	b 1	c 3
752	a 18	b 1	c 3
753	a 19	b 1	c 3
754	a 20	b 1	c 3
755	a 21	b 1	c 3
756	a 22	b 1	c 3
757	a 23	b 1	c 3
758	a 24	b 1	c 3
759	a 25	b 1	c 3
760	a 1	b 2	c 3
761	a 2	b 2	c 3
762	a 3	b 2	c 3
763	a 4	b 2	c 3
764	a 5	b 2	c 3
765	a 6	b 2	c 3
766	a 7	b 2	c 3
767	a 8	b 2	c 3
768	a 9	b 2	c 3
769	a 10	b 2	c 3
770	a 11	b 2	c 3
771	a 12	b 2	c 3
772	a 13	b 2	c 3
773	a 14	b 2	c 3
774	a 15	b 2	c 3
775	a 16	b 2	c 3
776	a 17	b 2	c 3
777	a 18	b 2	c 3
778	a 19	b 2	c 3
779	a 20	b 2	c 3
780	a 21	b 2	c 3
781	a 22	b 2	c 3

09857687.060801

No.	Cp	Bridge	Flu
782	a 23	b 2	c 3
783	a 24	b 2	c 3
784	a 25	b 2	c 3
785	a 1	b 3	c 3
786	a 2	b 3	c 3
787	a 3	b 3	c 3
788	a 4	b 3	c 3
789	a 5	b 3	c 3
790	a 6	b 3	c 3
791	a 7	b 3	c 3
792	a 8	b 3	c 3
793	a 9	b 3	c 3
794	a 10	b 3	c 3
795	a 11	b 3	c 3
796	a 12	b 3	c 3
797	a 13	b 3	c 3
798	a 14	b 3	c 3
799	a 15	b 3	c 3
800	a 16	b 3	c 3
801	a 17	b 3	c 3
802	a 18	b 3	c 3
803	a 19	b 3	c 3
804	a 20	b 3	c 3
805	a 21	b 3	c 3
806	a 22	b 3	c 3
807	a 23	b 3	c 3
808	a 24	b 3	c 3
809	a 25	b 3	c 3
810	a 1	b 4	c 3
811	a 2	b 4	c 3
812	a 3	b 4	c 3
813	a 4	b 4	c 3
814	a 5	b 4	c 3
815	a 6	b 4	c 3
816	a 7	b 4	c 3
817	a 8	b 4	c 3
818	a 9	b 4	c 3
819	a 10	b 4	c 3
820	a 11	b 4	c 3
821	a 12	b 4	c 3
822	a 13	b 4	c 3
823	a 14	b 4	c 3
824	a 15	b 4	c 3
825	a 16	b 4	c 3
826	a 17	b 4	c 3
827	a 18	b 4	c 3

06057687-060601

No.	Cp	Bridge	Flu
828	a 19	b 4	c 3
829	a 20	b 4	c 3
830	a 21	b 4	c 3
831	a 22	b 4	c 3
832	a 23	b 4	c 3
833	a 24	b 4	c 3
834	a 25	b 4	c 3
835	a 1	b 5	c 3
836	a 2	b 5	c 3
837	a 3	b 5	c 3
838	a 4	b 5	c 3
839	a 5	b 5	c 3
840	a 6	b 5	c 3
841	a 7	b 5	c 3
842	a 8	b 5	c 3
843	a 9	b 5	c 3
844	a 10	b 5	c 3
845	a 11	b 5	c 3
846	a 12	b 5	c 3
847	a 13	b 5	c 3
848	a 14	b 5	c 3
849	a 15	b 5	c 3
850	a 16	b 5	c 3
851	a 17	b 5	c 3
852	a 18	b 5	c 3
853	a 19	b 5	c 3
854	a 20	b 5	c 3
855	a 21	b 5	c 3
856	a 22	b 5	c 3
857	a 23	b 5	c 3
858	a 24	b 5	c 3
859	a 25	b 5	c 3
860	a 1	b 6	c 3
861	a 2	b 6	c 3
862	a 3	b 6	c 3
863	a 4	b 6	c 3
864	a 5	b 6	c 3
865	a 6	b 6	c 3
866	a 7	b 6	c 3
867	a 8	b 6	c 3
868	a 9	b 6	c 3
869	a 10	b 6	c 3
870	a 11	b 6	c 3
871	a 12	b 6	c 3
872	a 13	b 6	c 3
873	a 14	b 6	c 3

09857687-060801

No.	Cp	Bridge	Flu
874	a 15	b 6	c 3
875	a 16	b 6	c 3
876	a 17	b 6	c 3
877	a 18	b 6	c 3
878	a 19	b 6	c 3
879	a 20	b 6	c 3
880	a 21	b 6	c 3
881	a 22	b 6	c 3
882	a 23	b 6	c 3
883	a 24	b 6	c 3
884	a 25	b 6	c 3
885	a 1	b 7	c 3
886	a 2	b 7	c 3
887	a 3	b 7	c 3
888	a 4	b 7	c 3
889	a 5	b 7	c 3
890	a 6	b 7	c 3
891	a 7	b 7	c 3
892	a 8	b 7	c 3
893	a 9	b 7	c 3
894	a 10	b 7	c 3
895	a 11	b 7	c 3
896	a 12	b 7	c 3
897	a 13	b 7	c 3
898	a 14	b 7	c 3
899	a 15	b 7	c 3
900	a 16	b 7	c 3
901	a 17	b 7	c 3
902	a 18	b 7	c 3
903	a 19	b 7	c 3
904	a 20	b 7	c 3
905	a 21	b 7	c 3
906	a 22	b 7	c 3
907	a 23	b 7	c 3
908	a 24	b 7	c 3
909	a 25	b 7	c 3
910	a 5	b 8	c 3
911	a 6	b 8	c 3
912	a 7	b 8	c 3
913	a 8	b 8	c 3
914	a 9	b 8	c 3
915	a 10	b 8	c 3
916	a 11	b 8	c 3
917	a 12	b 8	c 3
918	a 13	b 8	c 3
919	a 14	b 8	c 3

09857587 060801

No.	Cp	Bridge	Flu
920	a 15	b 8	c 3
921	a 16	b 8	c 3
922	a 17	b 8	c 3
923	a 18	b 8	c 3
924	a 19	b 8	c 3
925	a 20	b 8	c 3
926	a 21	b 8	c 3
927	a 22	b 8	c 3
928	a 23	b 8	c 3
929	a 24	b 8	c 3
930	a 25	b 8	c 3
931	a 5	b 9	c 3
932	a 6	b 9	c 3
933	a 7	b 9	c 3
934	a 8	b 9	c 3
935	a 9	b 9	c 3
936	a 10	b 9	c 3
937	a 11	b 9	c 3
938	a 12	b 9	c 3
939	a 13	b 9	c 3
940	a 14	b 9	c 3
941	a 15	b 9	c 3
942	a 16	b 9	c 3
943	a 17	b 9	c 3
944	a 18	b 9	c 3
945	a 19	b 9	c 3
946	a 20	b 9	c 3
947	a 21	b 9	c 3
948	a 22	b 9	c 3
949	a 23	b 9	c 3
950	a 24	b 9	c 3
951	a 25	b 9	c 3
952	a 5	b 10	c 3
953	a 6	b 10	c 3
954	a 7	b 10	c 3
955	a 8	b 10	c 3
956	a 9	b 10	c 3
957	a 10	b 10	c 3
958	a 11	b 10	c 3
959	a 12	b 10	c 3
960	a 13	b 10	c 3
961	a 14	b 10	c 3
962	a 15	b 10	c 3
963	a 16	b 10	c 3
964	a 17	b 10	c 3
965	a 18	b 10	c 3

09857687 060801

No.	Cp	Bridge	Flu
966	a 19	b 10	c 3
967	a 20	b 10	c 3
968	a 21	b 10	c 3
969	a 22	b 10	c 3
970	a 23	b 10	c 3
971	a 24	b 10	c 3
972	a 25	b 10	c 3
973	a 5	b 11	c 3
974	a 6	b 11	c 3
975	a 7	b 11	c 3
976	a 8	b 11	c 3
977	a 9	b 11	c 3
978	a 10	b 11	c 3
979	a 11	b 11	c 3
980	a 12	b 11	c 3
981	a 13	b 11	c 3
982	a 14	b 11	c 3
983	a 15	b 11	c 3
984	a 16	b 11	c 3
985	a 17	b 11	c 3
986	a 18	b 11	c 3
987	a 19	b 11	c 3
988	a 20	b 11	c 3
989	a 21	b 11	c 3
990	a 22	b 11	c 3
991	a 23	b 11	c 3
992	a 24	b 11	c 3
993	a 25	b 11	c 3
994	a 1	b 12	c 3
995	a 2	b 12	c 3
996	a 3	b 12	c 3
997	a 4	b 12	c 3
998	a 5	b 12	c 3
999	a 6	b 12	c 3
1000	a 7	b 12	c 3
1001	a 8	b 12	c 3
1002	a 9	b 12	c 3
1003	a 10	b 12	c 3
1004	a 11	b 12	c 3
1005	a 12	b 12	c 3
1006	a 13	b 12	c 3
1007	a 14	b 12	c 3
1008	a 15	b 12	c 3
1009	a 16	b 12	c 3
1010	a 17	b 12	c 3
1011	a 18	b 12	c 3

09057607 060801

No.	Cp	Bridge	Flu
1012	a 19	b 12	c 3
1013	a 20	b 12	c 3
1014	a 21	b 12	c 3
1015	a 22	b 12	c 3
1016	a 23	b 12	c 3
1017	a 24	b 12	c 3
1018	a 25	b 12	c 3
1019	a 1	b 13	c 3
1020	a 2	b 13	c 3
1021	a 3	b 13	c 3
1022	a 4	b 13	c 3
1023	a 5	b 13	c 3
1024	a 6	b 13	c 3
1025	a 7	b 13	c 3
1026	a 8	b 13	c 3
1027	a 9	b 13	c 3
1028	a 10	b 13	c 3
1029	a 11	b 13	c 3
1030	a 12	b 13	c 3
1031	a 13	b 13	c 3
1032	a 14	b 13	c 3
1033	a 15	b 13	c 3
1034	a 16	b 13	c 3
1035	a 17	b 13	c 3
1036	a 18	b 13	c 3
1037	a 19	b 13	c 3
1038	a 20	b 13	c 3
1039	a 21	b 13	c 3
1040	a 22	b 13	c 3
1041	a 23	b 13	c 3
1042	a 24	b 13	c 3
1043	a 25	b 13	c 3
1044	a 1	b 14	c 3
1045	a 2	b 14	c 3
1046	a 3	b 14	c 3
1047	a 4	b 14	c 3
1048	a 5	b 14	c 3
1049	a 6	b 14	c 3
1050	a 7	b 14	c 3
1051	a 8	b 14	c 3
1052	a 9	b 14	c 3
1053	a 10	b 14	c 3
1054	a 11	b 14	c 3
1055	a 12	b 14	c 3
1056	a 13	b 14	c 3
1057	a 14	b 14	c 3

00057687 060801

No.	Cp	Bridge	Flu
1058	a 15	b 14	c 3
1059	a 16	b 14	c 3
1060	a 17	b 14	c 3
1061	a 18	b 14	c 3
1062	a 19	b 14	c 3
1063	a 20	b 14	c 3
1064	a 21	b 14	c 3
1065	a 22	b 14	c 3
1066	a 23	b 14	c 3
1067	a 24	b 14	c 3
1068	a 25	b 14	c 3
1069	a 1	b 15	c 3
1070	a 2	b 15	c 3
1071	a 3	b 15	c 3
1072	a 4	b 15	c 3
1073	a 5	b 15	c 3
1074	a 6	b 15	c 3
1075	a 7	b 15	c 3
1076	a 8	b 15	c 3
1077	a 9	b 15	c 3
1078	a 10	b 15	c 3
1079	a 11	b 15	c 3
1080	a 12	b 15	c 3
1081	a 13	b 15	c 3
1082	a 14	b 15	c 3
1083	a 15	b 15	c 3
1084	a 16	b 15	c 3
1085	a 17	b 15	c 3
1086	a 18	b 15	c 3
1087	a 19	b 15	c 3
1088	a 20	b 15	c 3
1089	a 21	b 15	c 3
1090	a 22	b 15	c 3
1091	a 23	b 15	c 3
1092	a 24	b 15	c 3
1093	a 25	b 15	c 3
1094	a 1	b 1	c 4
1095	a 2	b 1	c 4
1096	a 3	b 1	c 4
1097	a 4	b 1	c 4
1098	a 5	b 1	c 4
1099	a 6	b 1	c 4
1100	a 7	b 1	c 4
1101	a 8	b 1	c 4
1102	a 9	b 1	c 4
1103	a 10	b 1	c 4

09357687-060801

No.	Cp	Bridge	Flu
1104	a 11	b 1	c 4
1105	a 12	b 1	c 4
1106	a 13	b 1	c 4
1107	a 14	b 1	c 4
1108	a 15	b 1	c 4
1109	a 16	b 1	c 4
1110	a 17	b 1	c 4
1111	a 18	b 1	c 4
1112	a 19	b 1	c 4
1113	a 20	b 1	c 4
1114	a 21	b 1	c 4
1115	a 22	b 1	c 4
1116	a 23	b 1	c 4
1117	a 24	b 1	c 4
1118	a 25	b 1	c 4
1119	a 1	b 2	c 4
1120	a 2	b 2	c 4
1121	a 3	b 2	c 4
1122	a 4	b 2	c 4
1123	a 5	b 2	c 4
1124	a 6	b 2	c 4
1125	a 7	b 2	c 4
1126	a 8	b 2	c 4
1127	a 9	b 2	c 4
1128	a 10	b 2	c 4
1129	a 11	b 2	c 4
1130	a 12	b 2	c 4
1131	a 13	b 2	c 4
1132	a 14	b 2	c 4
1133	a 15	b 2	c 4
1134	a 16	b 2	c 4
1135	a 17	b 2	c 4
1136	a 18	b 2	c 4
1137	a 19	b 2	c 4
1138	a 20	b 2	c 4
1139	a 21	b 2	c 4
1140	a 22	b 2	c 4
1141	a 23	b 2	c 4
1142	a 24	b 2	c 4
1143	a 25	b 2	c 4
1144	a 1	b 3	c 4
1145	a 2	b 3	c 4
1146	a 3	b 3	c 4
1147	a 4	b 3	c 4
1148	a 5	b 3	c 4
1149	a 6	b 3	c 4

09857687.060801

No.	Cp	Bridge	Flu
1150	a 7	b 3	c 4
1151	a 8	b 3	c 4
1152	a 9	b 3	c 4
1153	a 10	b 3	c 4
1154	a 11	b 3	c 4
1155	a 12	b 3	c 4
1156	a 13	b 3	c 4
1157	a 14	b 3	c 4
1158	a 15	b 3	c 4
1159	a 16	b 3	c 4
1160	a 17	b 3	c 4
1161	a 18	b 3	c 4
1162	a 19	b 3	c 4
1163	a 20	b 3	c 4
1164	a 21	b 3	c 4
1165	a 22	b 3	c 4
1166	a 23	b 3	c 4
1167	a 24	b 3	c 4
1168	a 25	b 3	c 4
1169	a 1	b 4	c 4
1170	a 2	b 4	c 4
1171	a 3	b 4	c 4
1172	a 4	b 4	c 4
1173	a 5	b 4	c 4
1174	a 6	b 4	c 4
1175	a 7	b 4	c 4
1176	a 8	b 4	c 4
1177	a 9	b 4	c 4
1178	a 10	b 4	c 4
1179	a 11	b 4	c 4
1180	a 12	b 4	c 4
1181	a 13	b 4	c 4
1182	a 14	b 4	c 4
1183	a 15	b 4	c 4
1184	a 16	b 4	c 4
1185	a 17	b 4	c 4
1186	a 18	b 4	c 4
1187	a 19	b 4	c 4
1188	a 20	b 4	c 4
1189	a 21	b 4	c 4
1190	a 22	b 4	c 4
1191	a 23	b 4	c 4
1192	a 24	b 4	c 4
1193	a 25	b 4	c 4
1194	a 1	b 5	c 4
1195	a 2	b 5	c 4

09857687 060901

No.	Cp	Bridge	Flu
1196	a 3	b 5	c 4
1197	a 4	b 5	c 4
1198	a 5	b 5	c 4
1199	a 6	b 5	c 4
1200	a 7	b 5	c 4
1201	a 8	b 5	c 4
1202	a 9	b 5	c 4
1203	a 10	b 5	c 4
1204	a 11	b 5	c 4
1205	a 12	b 5	c 4
1206	a 13	b 5	c 4
1207	a 14	b 5	c 4
1208	a 15	b 5	c 4
1209	a 16	b 5	c 4
1210	a 17	b 5	c 4
1211	a 18	b 5	c 4
1212	a 19	b 5	c 4
1213	a 20	b 5	c 4
1214	a 21	b 5	c 4
1215	a 22	b 5	c 4
1216	a 23	b 5	c 4
1217	a 24	b 5	c 4
1218	a 25	b 5	c 4
1219	a 1	b 6	c 4
1220	a 2	b 6	c 4
1221	a 3	b 6	c 4
1222	a 4	b 6	c 4
1223	a 5	b 6	c 4
1224	a 6	b 6	c 4
1225	a 7	b 6	c 4
1226	a 8	b 6	c 4
1227	a 9	b 6	c 4
1228	a 10	b 6	c 4
1229	a 11	b 6	c 4
1230	a 12	b 6	c 4
1231	a 13	b 6	c 4
1232	a 14	b 6	c 4
1233	a 15	b 6	c 4
1234	a 16	b 6	c 4
1235	a 17	b 6	c 4
1236	a 18	b 6	c 4
1237	a 19	b 6	c 4
1238	a 20	b 6	c 4
1239	a 21	b 6	c 4
1240	a 22	b 6	c 4
1241	a 23	b 6	c 4

09857687 060601

No.	Cp	Bridge	Flu
1242	a 24	b 6	c 4
1243	a 25	b 6	c 4
1244	a 1	b 7	c 4
1245	a 2	b 7	c 4
1246	a 3	b 7	c 4
1247	a 4	b 7	c 4
1248	a 5	b 7	c 4
1249	a 6	b 7	c 4
1250	a 7	b 7	c 4
1251	a 8	b 7	c 4
1252	a 9	b 7	c 4
1253	a 10	b 7	c 4
1254	a 11	b 7	c 4
1255	a 12	b 7	c 4
1256	a 13	b 7	c 4
1257	a 14	b 7	c 4
1258	a 15	b 7	c 4
1259	a 16	b 7	c 4
1260	a 17	b 7	c 4
1261	a 18	b 7	c 4
1262	a 19	b 7	c 4
1263	a 20	b 7	c 4
1264	a 21	b 7	c 4
1265	a 22	b 7	c 4
1266	a 23	b 7	c 4
1267	a 24	b 7	c 4
1268	a 25	b 7	c 4
1269	a 5	b 8	c 4
1270	a 6	b 8	c 4
1271	a 7	b 8	c 4
1272	a 8	b 8	c 4
1273	a 9	b 8	c 4
1274	a 10	b 8	c 4
1275	a 11	b 8	c 4
1276	a 12	b 8	c 4
1277	a 13	b 8	c 4
1278	a 14	b 8	c 4
1279	a 15	b 8	c 4
1280	a 16	b 8	c 4
1281	a 17	b 8	c 4
1282	a 18	b 8	c 4
1283	a 19	b 8	c 4
1284	a 20	b 8	c 4
1285	a 21	b 8	c 4
1286	a 22	b 8	c 4
1287	a 23	b 8	c 4

09857687-060801

No.	Cp	Bridge	Flu
1288	a 24	b 8	c 4
1289	a 25	b 8	c 4
1290	a 5	b 9	c 4
1291	a 6	b 9	c 4
1292	a 7	b 9	c 4
1293	a 8	b 9	c 4
1294	a 9	b 9	c 4
1295	a 10	b 9	c 4
1296	a 11	b 9	c 4
1297	a 12	b 9	c 4
1298	a 13	b 9	c 4
1299	a 14	b 9	c 4
1300	a 15	b 9	c 4
1301	a 16	b 9	c 4
1302	a 17	b 9	c 4
1303	a 18	b 9	c 4
1304	a 19	b 9	c 4
1305	a 20	b 9	c 4
1306	a 21	b 9	c 4
1307	a 22	b 9	c 4
1308	a 23	b 9	c 4
1309	a 24	b 9	c 4
1310	a 25	b 9	c 4
1311	a 5	b 10	c 4
1312	a 6	b 10	c 4
1313	a 7	b 10	c 4
1314	a 8	b 10	c 4
1315	a 9	b 10	c 4
1316	a 10	b 10	c 4
1317	a 11	b 10	c 4
1318	a 12	b 10	c 4
1319	a 13	b 10	c 4
1320	a 14	b 10	c 4
1321	a 15	b 10	c 4
1322	a 16	b 10	c 4
1323	a 17	b 10	c 4
1324	a 18	b 10	c 4
1325	a 19	b 10	c 4
1326	a 20	b 10	c 4
1327	a 21	b 10	c 4
1328	a 22	b 10	c 4
1329	a 23	b 10	c 4
1330	a 24	b 10	c 4
1331	a 25	b 10	c 4
1332	a 5	b 11	c 4
1333	a 6	b 11	c 4

09857687.060801

No.	Cp	Bridge	Flu
1334	a 7	b 11	c 4
1335	a 8	b 11	c 4
1336	a 9	b 11	c 4
1337	a 10	b 11	c 4
1338	a 11	b 11	c 4
1339	a 12	b 11	c 4
1340	a 13	b 11	c 4
1341	a 14	b 11	c 4
1342	a 15	b 11	c 4
1343	a 16	b 11	c 4
1344	a 17	b 11	c 4
1345	a 18	b 11	c 4
1346	a 19	b 11	c 4
1347	a 20	b 11	c 4
1348	a 21	b 11	c 4
1349	a 22	b 11	c 4
1350	a 23	b 11	c 4
1351	a 24	b 11	c 4
1352	a 25	b 11	c 4
1353	a 1	b 12	c 4
1354	a 2	b 12	c 4
1355	a 3	b 12	c 4
1356	a 4	b 12	c 4
1357	a 5	b 12	c 4
1358	a 6	b 12	c 4
1359	a 7	b 12	c 4
1360	a 8	b 12	c 4
1361	a 9	b 12	c 4
1362	a 10	b 12	c 4
1363	a 11	b 12	c 4
1364	a 12	b 12	c 4
1365	a 13	b 12	c 4
1366	a 14	b 12	c 4
1367	a 15	b 12	c 4
1368	a 16	b 12	c 4
1369	a 17	b 12	c 4
1370	a 18	b 12	c 4
1371	a 19	b 12	c 4
1372	a 20	b 12	c 4
1373	a 21	b 12	c 4
1374	a 22	b 12	c 4
1375	a 23	b 12	c 4
1376	a 24	b 12	c 4
1377	a 25	b 12	c 4
1378	a 1	b 13	c 4
1379	a 2	b 13	c 4

09857587:060801

No.	Cp	Bridge	Flu
1380	a 3	b 13	c 4
1381	a 4	b 13	c 4
1382	a 5	b 13	c 4
1383	a 6	b 13	c 4
1384	a 7	b 13	c 4
1385	a 8	b 13	c 4
1386	a 9	b 13	c 4
1387	a 10	b 13	c 4
1388	a 11	b 13	c 4
1389	a 12	b 13	c 4
1390	a 13	b 13	c 4
1391	a 14	b 13	c 4
1392	a 15	b 13	c 4
1393	a 16	b 13	c 4
1394	a 17	b 13	c 4
1395	a 18	b 13	c 4
1396	a 19	b 13	c 4
1397	a 20	b 13	c 4
1398	a 21	b 13	c 4
1399	a 22	b 13	c 4
1400	a 23	b 13	c 4
1401	a 24	b 13	c 4
1402	a 25	b 13	c 4
1403	a 1	b 14	c 4
1404	a 2	b 14	c 4
1405	a 3	b 14	c 4
1406	a 4	b 14	c 4
1407	a 5	b 14	c 4
1408	a 6	b 14	c 4
1409	a 7	b 14	c 4
1410	a 8	b 14	c 4
1411	a 9	b 14	c 4
1412	a 10	b 14	c 4
1413	a 11	b 14	c 4
1414	a 12	b 14	c 4
1415	a 13	b 14	c 4
1416	a 14	b 14	c 4
1417	a 15	b 14	c 4
1418	a 16	b 14	c 4
1419	a 17	b 14	c 4
1420	a 18	b 14	c 4
1421	a 19	b 14	c 4
1422	a 20	b 14	c 4
1423	a 21	b 14	c 4
1424	a 22	b 14	c 4
1425	a 23	b 14	c 4

09857687-060801

No.	Cp	Bridge	Flu
1426	a 24	b 14	c 4
1427	a 25	b 14	c 4
1428	a 1	b 15	c 4
1429	a 2	b 15	c 4
1430	a 3	b 15	c 4
1431	a 4	b 15	c 4
1432	a 5	b 15	c 4
1433	a 6	b 15	c 4
1434	a 7	b 15	c 4
1435	a 8	b 15	c 4
1436	a 9	b 15	c 4
1437	a 10	b 15	c 4
1438	a 11	b 15	c 4
1439	a 12	b 15	c 4
1440	a 13	b 15	c 4
1441	a 14	b 15	c 4
1442	a 15	b 15	c 4
1443	a 16	b 15	c 4
1444	a 17	b 15	c 4
1445	a 18	b 15	c 4
1446	a 19	b 15	c 4
1447	a 20	b 15	c 4
1448	a 21	b 15	c 4
1449	a 22	b 15	c 4
1450	a 23	b 15	c 4
1451	a 24	b 15	c 4
1452	a 25	b 15	c 4
1453	a 1	b 1	c 5
1454	a 2	b 1	c 5
1455	a 3	b 1	c 5
1456	a 4	b 1	c 5
1457	a 5	b 1	c 5
1458	a 6	b 1	c 5
1459	a 7	b 1	c 5
1460	a 8	b 1	c 5
1461	a 9	b 1	c 5
1462	a 10	b 1	c 5
1463	a 11	b 1	c 5
1464	a 12	b 1	c 5
1465	a 13	b 1	c 5
1466	a 14	b 1	c 5
1467	a 15	b 1	c 5
1468	a 16	b 1	c 5
1469	a 17	b 1	c 5
1470	a 18	b 1	c 5
1471	a 19	b 1	c 5

09857687 060801

No.	Cp	Bridge	Flu
1472	a 20	b 1	c 5
1473	a 21	b 1	c 5
1474	a 22	b 1	c 5
1475	a 23	b 1	c 5
1476	a 24	b 1	c 5
1477	a 25	b 1	c 5
1478	a 1	b 2	c 5
1479	a 2	b 2	c 5
1480	a 3	b 2	c 5
1481	a 4	b 2	c 5
1482	a 5	b 2	c 5
1483	a 6	b 2	c 5
1484	a 7	b 2	c 5
1485	a 8	b 2	c 5
1486	a 9	b 2	c 5
1487	a 10	b 2	c 5
1488	a 11	b 2	c 5
1489	a 12	b 2	c 5
1490	a 13	b 2	c 5
1491	a 14	b 2	c 5
1492	a 15	b 2	c 5
1493	a 16	b 2	c 5
1494	a 17	b 2	c 5
1495	a 18	b 2	c 5
1496	a 19	b 2	c 5
1497	a 20	b 2	c 5
1498	a 21	b 2	c 5
1499	a 22	b 2	c 5
1500	a 23	b 2	c 5
1501	a 24	b 2	c 5
1502	a 25	b 2	c 5
1503	a 1	b 3	c 5
1504	a 2	b 3	c 5
1505	a 3	b 3	c 5
1506	a 4	b 3	c 5
1507	a 5	b 3	c 5
1508	a 6	b 3	c 5
1509	a 7	b 3	c 5
1510	a 8	b 3	c 5
1511	a 9	b 3	c 5
1512	a 10	b 3	c 5
1513	a 11	b 3	c 5
1514	a 12	b 3	c 5
1515	a 13	b 3	c 5
1516	a 14	b 3	c 5
1517	a 15	b 3	c 5

00857687-060801

No.	Cp	Bridge	Flu
1518	a 16	b 3	c 5
1519	a 17	b 3	c 5
1520	a 18	b 3	c 5
1521	a 19	b 3	c 5
1522	a 20	b 3	c 5
1523	a 21	b 3	c 5
1524	a 22	b 3	c 5
1525	a 23	b 3	c 5
1526	a 24	b 3	c 5
1527	a 25	b 3	c 5
1528	a 1	b 4	c 5
1529	a 2	b 4	c 5
1530	a 3	b 4	c 5
1531	a 4	b 4	c 5
1532	a 5	b 4	c 5
1533	a 6	b 4	c 5
1534	a 7	b 4	c 5
1535	a 8	b 4	c 5
1536	a 9	b 4	c 5
1537	a 10	b 4	c 5
1538	a 11	b 4	c 5
1539	a 12	b 4	c 5
1540	a 13	b 4	c 5
1541	a 14	b 4	c 5
1542	a 15	b 4	c 5
1543	a 16	b 4	c 5
1544	a 17	b 4	c 5
1545	a 18	b 4	c 5
1546	a 19	b 4	c 5
1547	a 20	b 4	c 5
1548	a 21	b 4	c 5
1549	a 22	b 4	c 5
1550	a 23	b 4	c 5
1551	a 24	b 4	c 5
1552	a 25	b 4	c 5
1553	a 1	b 5	c 5
1554	a 2	b 5	c 5
1555	a 3	b 5	c 5
1556	a 4	b 5	c 5
1557	a 5	b 5	c 5
1558	a 6	b 5	c 5
1559	a 7	b 5	c 5
1560	a 8	b 5	c 5
1561	a 9	b 5	c 5
1562	a 10	b 5	c 5
1563	a 11	b 5	c 5

0957537 060201

No.	Cp	Bridge	Flu
1564	a 12	b 5	c 5
1565	a 13	b 5	c 5
1566	a 14	b 5	c 5
1567	a 15	b 5	c 5
1568	a 16	b 5	c 5
1569	a 17	b 5	c 5
1570	a 18	b 5	c 5
1571	a 19	b 5	c 5
1572	a 20	b 5	c 5
1573	a 21	b 5	c 5
1574	a 22	b 5	c 5
1575	a 23	b 5	c 5
1576	a 24	b 5	c 5
1577	a 25	b 5	c 5
1578	a 1	b 6	c 5
1579	a 2	b 6	c 5
1580	a 3	b 6	c 5
1581	a 4	b 6	c 5
1582	a 5	b 6	c 5
1583	a 6	b 6	c 5
1584	a 7	b 6	c 5
1585	a 8	b 6	c 5
1586	a 9	b 6	c 5
1587	a 10	b 6	c 5
1588	a 11	b 6	c 5
1589	a 12	b 6	c 5
1590	a 13	b 6	c 5
1591	a 14	b 6	c 5
1592	a 15	b 6	c 5
1593	a 16	b 6	c 5
1594	a 17	b 6	c 5
1595	a 18	b 6	c 5
1596	a 19	b 6	c 5
1597	a 20	b 6	c 5
1598	a 21	b 6	c 5
1599	a 22	b 6	c 5
1600	a 23	b 6	c 5
1601	a 24	b 6	c 5
1602	a 25	b 6	c 5
1603	a 1	b 7	c 5
1604	a 2	b 7	c 5
1605	a 3	b 7	c 5
1606	a 4	b 7	c 5
1607	a 5	b 7	c 5
1608	a 6	b 7	c 5
1609	a 7	b 7	c 5

0957637 060801

No.	Cp	Bridge	Flu
1610	a 8	b 7	c 5
1611	a 9	b 7	c 5
1612	a 10	b 7	c 5
1613	a 11	b 7	c 5
1614	a 12	b 7	c 5
1615	a 13	b 7	c 5
1616	a 14	b 7	c 5
1617	a 15	b 7	c 5
1618	a 16	b 7	c 5
1619	a 17	b 7	c 5
1620	a 18	b 7	c 5
1621	a 19	b 7	c 5
1622	a 20	b 7	c 5
1623	a 21	b 7	c 5
1624	a 22	b 7	c 5
1625	a 23	b 7	c 5
1626	a 24	b 7	c 5
1627	a 25	b 7	c 5
1628	a 5	b 8	c 5
1629	a 6	b 8	c 5
1630	a 7	b 8	c 5
1631	a 8	b 8	c 5
1632	a 9	b 8	c 5
1633	a 10	b 8	c 5
1634	a 11	b 8	c 5
1635	a 12	b 8	c 5
1636	a 13	b 8	c 5
1637	a 14	b 8	c 5
1638	a 15	b 8	c 5
1639	a 16	b 8	c 5
1640	a 17	b 8	c 5
1641	a 18	b 8	c 5
1642	a 19	b 8	c 5
1643	a 20	b 8	c 5
1644	a 21	b 8	c 5
1645	a 22	b 8	c 5
1646	a 23	b 8	c 5
1647	a 24	b 8	c 5
1648	a 25	b 8	c 5
1649	a 5	b 9	c 5
1650	a 6	b 9	c 5
1651	a 7	b 9	c 5
1652	a 8	b 9	c 5
1653	a 9	b 9	c 5
1654	a 10	b 9	c 5
1655	a 11	b 9	c 5

09857687.060801

No.	Cp	Bridge	Flu
1656	a 12	b 9	c 5
1657	a 13	b 9	c 5
1658	a 14	b 9	c 5
1659	a 15	b 9	c 5
1660	a 16	b 9	c 5
1661	a 17	b 9	c 5
1662	a 18	b 9	c 5
1663	a 19	b 9	c 5
1664	a 20	b 9	c 5
1665	a 21	b 9	c 5
1666	a 22	b 9	c 5
1667	a 23	b 9	c 5
1668	a 24	b 9	c 5
1669	a 25	b 9	c 5
1670	a 5	b 10	c 5
1671	a 6	b 10	c 5
1672	a 7	b 10	c 5
1673	a 8	b 10	c 5
1674	a 9	b 10	c 5
1675	a 10	b 10	c 5
1676	a 11	b 10	c 5
1677	a 12	b 10	c 5
1678	a 13	b 10	c 5
1679	a 14	b 10	c 5
1680	a 15	b 10	c 5
1681	a 16	b 10	c 5
1682	a 17	b 10	c 5
1683	a 18	b 10	c 5
1684	a 19	b 10	c 5
1685	a 20	b 10	c 5
1686	a 21	b 10	c 5
1687	a 22	b 10	c 5
1688	a 23	b 10	c 5
1689	a 24	b 10	c 5
1690	a 25	b 10	c 5
1691	a 5	b 11	c 5
1692	a 6	b 11	c 5
1693	a 7	b 11	c 5
1694	a 8	b 11	c 5
1695	a 9	b 11	c 5
1696	a 10	b 11	c 5
1697	a 11	b 11	c 5
1698	a 12	b 11	c 5
1699	a 13	b 11	c 5
1700	a 14	b 11	c 5
1701	a 15	b 11	c 5

09857687 060801

No.	Cp	Bridge	Flu
1702	a 16	b 11	c 5
1703	a 17	b 11	c 5
1704	a 18	b 11	c 5
1705	a 19	b 11	c 5
1706	a 20	b 11	c 5
1707	a 21	b 11	c 5
1708	a 22	b 11	c 5
1709	a 23	b 11	c 5
1710	a 24	b 11	c 5
1711	a 25	b 11	c 5
1712	a 1	b 12	c 5
1713	a 2	b 12	c 5
1714	a 3	b 12	c 5
1715	a 4	b 12	c 5
1716	a 5	b 12	c 5
1717	a 6	b 12	c 5
1718	a 7	b 12	c 5
1719	a 8	b 12	c 5
1720	a 9	b 12	c 5
1721	a 10	b 12	c 5
1722	a 11	b 12	c 5
1723	a 12	b 12	c 5
1724	a 13	b 12	c 5
1725	a 14	b 12	c 5
1726	a 15	b 12	c 5
1727	a 16	b 12	c 5
1728	a 17	b 12	c 5
1729	a 18	b 12	c 5
1730	a 19	b 12	c 5
1731	a 20	b 12	c 5
1732	a 21	b 12	c 5
1733	a 22	b 12	c 5
1734	a 23	b 12	c 5
1735	a 24	b 12	c 5
1736	a 25	b 12	c 5
1737	a 1	b 13	c 5
1738	a 2	b 13	c 5
1739	a 3	b 13	c 5
1740	a 4	b 13	c 5
1741	a 5	b 13	c 5
1742	a 6	b 13	c 5
1743	a 7	b 13	c 5
1744	a 8	b 13	c 5
1745	a 9	b 13	c 5
1746	a 10	b 13	c 5
1747	a 11	b 13	c 5

108090° 28925860

No.	Cp	Bridge	Flu
1748	a 12	b 13	c 5
1749	a 13	b 13	c 5
1750	a 14	b 13	c 5
1751	a 15	b 13	c 5
1752	a 16	b 13	c 5
1753	a 17	b 13	c 5
1754	a 18	b 13	c 5
1755	a 19	b 13	c 5
1756	a 20	b 13	c 5
1757	a 21	b 13	c 5
1758	a 22	b 13	c 5
1759	a 23	b 13	c 5
1760	a 24	b 13	c 5
1761	a 25	b 13	c 5
1762	a 1	b 14	c 5
1763	a 2	b 14	c 5
1764	a 3	b 14	c 5
1765	a 4	b 14	c 5
1766	a 5	b 14	c 5
1767	a 6	b 14	c 5
1768	a 7	b 14	c 5
1769	a 8	b 14	c 5
1770	a 9	b 14	c 5
1771	a 10	b 14	c 5
1772	a 11	b 14	c 5
1773	a 12	b 14	c 5
1774	a 13	b 14	c 5
1775	a 14	b 14	c 5
1776	a 15	b 14	c 5
1777	a 16	b 14	c 5
1778	a 17	b 14	c 5
1779	a 18	b 14	c 5
1780	a 19	b 14	c 5
1781	a 20	b 14	c 5
1782	a 21	b 14	c 5
1783	a 22	b 14	c 5
1784	a 23	b 14	c 5
1785	a 24	b 14	c 5
1786	a 25	b 14	c 5
1787	a 1	b 15	c 5
1788	a 2	b 15	c 5
1789	a 3	b 15	c 5
1790	a 4	b 15	c 5
1791	a 5	b 15	c 5
1792	a 6	b 15	c 5
1793	a 7	b 15	c 5

09857587-050901

No.	Cp	Bridge	Flu
1794	a 8	b 15	c 5
1795	a 9	b 15	c 5
1796	a 10	b 15	c 5
1797	a 11	b 15	c 5
1798	a 12	b 15	c 5
1799	a 13	b 15	c 5
1800	a 14	b 15	c 5
1801	a 15	b 15	c 5
1802	a 16	b 15	c 5
1803	a 17	b 15	c 5
1804	a 18	b 15	c 5
1805	a 19	b 15	c 5
1806	a 20	b 15	c 5
1807	a 21	b 15	c 5
1808	a 22	b 15	c 5
1809	a 23	b 15	c 5
1810	a 24	b 15	c 5
1811	a 25	b 15	c 5
1812	a 1	b 1	c 6
1813	a 2	b 1	c 6
1814	a 3	b 1	c 6
1815	a 4	b 1	c 6
1816	a 5	b 1	c 6
1817	a 6	b 1	c 6
1818	a 7	b 1	c 6
1819	a 8	b 1	c 6
1820	a 9	b 1	c 6
1821	a 10	b 1	c 6
1822	a 11	b 1	c 6
1823	a 12	b 1	c 6
1824	a 13	b 1	c 6
1825	a 14	b 1	c 6
1826	a 15	b 1	c 6
1827	a 16	b 1	c 6
1828	a 17	b 1	c 6
1829	a 18	b 1	c 6
1830	a 19	b 1	c 6
1831	a 20	b 1	c 6
1832	a 21	b 1	c 6
1833	a 22	b 1	c 6
1834	a 23	b 1	c 6
1835	a 24	b 1	c 6
1836	a 25	b 1	c 6
1837	a 1	b 2	c 6
1838	a 2	b 2	c 6
1839	a 3	b 2	c 6

10857687.060801

No.	Cp	Bridge	Flu
1840	a 4	b 2	c 6
1841	a 5	b 2	c 6
1842	a 6	b 2	c 6
1843	a 7	b 2	c 6
1844	a 8	b 2	c 6
1845	a 9	b 2	c 6
1846	a 10	b 2	c 6
1847	a 11	b 2	c 6
1848	a 12	b 2	c 6
1849	a 13	b 2	c 6
1850	a 14	b 2	c 6
1851	a 15	b 2	c 6
1852	a 16	b 2	c 6
1853	a 17	b 2	c 6
1854	a 18	b 2	c 6
1855	a 19	b 2	c 6
1856	a 20	b 2	c 6
1857	a 21	b 2	c 6
1858	a 22	b 2	c 6
1859	a 23	b 2	c 6
1860	a 24	b 2	c 6
1861	a 25	b 2	c 6
1862	a 1	b 3	c 6
1863	a 2	b 3	c 6
1864	a 3	b 3	c 6
1865	a 4	b 3	c 6
1866	a 5	b 3	c 6
1867	a 6	b 3	c 6
1868	a 7	b 3	c 6
1869	a 8	b 3	c 6
1870	a 9	b 3	c 6
1871	a 10	b 3	c 6
1872	a 11	b 3	c 6
1873	a 12	b 3	c 6
1874	a 13	b 3	c 6
1875	a 14	b 3	c 6
1876	a 15	b 3	c 6
1877	a 16	b 3	c 6
1878	a 17	b 3	c 6
1879	a 18	b 3	c 6
1880	a 19	b 3	c 6
1881	a 20	b 3	c 6
1882	a 21	b 3	c 6
1883	a 22	b 3	c 6
1884	a 23	b 3	c 6
1885	a 24	b 3	c 6

10809072975860

No.	Cp	Bridge	Flu
1886	a 25	b 3	c 6
1887	a 1	b 4	c 6
1888	a 2	b 4	c 6
1889	a 3	b 4	c 6
1890	a 4	b 4	c 6
1891	a 5	b 4	c 6
1892	a 6	b 4	c 6
1893	a 7	b 4	c 6
1894	a 8	b 4	c 6
1895	a 9	b 4	c 6
1896	a 10	b 4	c 6
1897	a 11	b 4	c 6
1898	a 12	b 4	c 6
1899	a 13	b 4	c 6
1900	a 14	b 4	c 6
1901	a 15	b 4	c 6
1902	a 16	b 4	c 6
1903	a 17	b 4	c 6
1904	a 18	b 4	c 6
1905	a 19	b 4	c 6
1906	a 20	b 4	c 6
1907	a 21	b 4	c 6
1908	a 22	b 4	c 6
1909	a 23	b 4	c 6
1910	a 24	b 4	c 6
1911	a 25	b 4	c 6
1912	a 1	b 5	c 6
1913	a 2	b 5	c 6
1914	a 3	b 5	c 6
1915	a 4	b 5	c 6
1916	a 5	b 5	c 6
1917	a 6	b 5	c 6
1918	a 7	b 5	c 6
1919	a 8	b 5	c 6
1920	a 9	b 5	c 6
1921	a 10	b 5	c 6
1922	a 11	b 5	c 6
1923	a 12	b 5	c 6
1924	a 13	b 5	c 6
1925	a 14	b 5	c 6
1926	a 15	b 5	c 6
1927	a 16	b 5	c 6
1928	a 17	b 5	c 6
1929	a 18	b 5	c 6
1930	a 19	b 5	c 6
1931	a 20	b 5	c 6

09857687 060801

No.	Cp	Bridge	Flu
1932	a 21	b 5	c 6
1933	a 22	b 5	c 6
1934	a 23	b 5	c 6
1935	a 24	b 5	c 6
1936	a 25	b 5	c 6
1937	a 1	b 6	c 6
1938	a 2	b 6	c 6
1939	a 3	b 6	c 6
1940	a 4	b 6	c 6
1941	a 5	b 6	c 6
1942	a 6	b 6	c 6
1943	a 7	b 6	c 6
1944	a 8	b 6	c 6
1945	a 9	b 6	c 6
1946	a 10	b 6	c 6
1947	a 11	b 6	c 6
1948	a 12	b 6	c 6
1949	a 13	b 6	c 6
1950	a 14	b 6	c 6
1951	a 15	b 6	c 6
1952	a 16	b 6	c 6
1953	a 17	b 6	c 6
1954	a 18	b 6	c 6
1955	a 19	b 6	c 6
1956	a 20	b 6	c 6
1957	a 21	b 6	c 6
1958	a 22	b 6	c 6
1959	a 23	b 6	c 6
1960	a 24	b 6	c 6
1961	a 25	b 6	c 6
1962	a 1	b 7	c 6
1963	a 2	b 7	c 6
1964	a 3	b 7	c 6
1965	a 4	b 7	c 6
1966	a 5	b 7	c 6
1967	a 6	b 7	c 6
1968	a 7	b 7	c 6
1969	a 8	b 7	c 6
1970	a 9	b 7	c 6
1971	a 10	b 7	c 6
1972	a 11	b 7	c 6
1973	a 12	b 7	c 6
1974	a 13	b 7	c 6
1975	a 14	b 7	c 6
1976	a 15	b 7	c 6
1977	a 16	b 7	c 6

09857687 060801

No.	Cp	Bridge	Flu
1978	a 17	b 7	c 6
1979	a 18	b 7	c 6
1980	a 19	b 7	c 6
1981	a 20	b 7	c 6
1982	a 21	b 7	c 6
1983	a 22	b 7	c 6
1984	a 23	b 7	c 6
1985	a 24	b 7	c 6
1986	a 25	b 7	c 6
1987	a 1	b 8	c 6
1988	a 2	b 8	c 6
1989	a 3	b 8	c 6
1990	a 4	b 8	c 6
1991	a 5	b 8	c 6
1992	a 6	b 8	c 6
1993	a 7	b 8	c 6
1994	a 8	b 8	c 6
1995	a 9	b 8	c 6
1996	a 10	b 8	c 6
1997	a 11	b 8	c 6
1998	a 12	b 8	c 6
1999	a 13	b 8	c 6
2000	a 14	b 8	c 6
2001	a 15	b 8	c 6
2002	a 16	b 8	c 6
2003	a 17	b 8	c 6
2004	a 18	b 8	c 6
2005	a 19	b 8	c 6
2006	a 20	b 8	c 6
2007	a 21	b 8	c 6
2008	a 22	b 8	c 6
2009	a 23	b 8	c 6
2010	a 24	b 8	c 6
2011	a 25	b 8	c 6
2012	a 1	b 9	c 6
2013	a 2	b 9	c 6
2014	a 3	b 9	c 6
2015	a 4	b 9	c 6
2016	a 5	b 9	c 6
2017	a 6	b 9	c 6
2018	a 7	b 9	c 6
2019	a 8	b 9	c 6
2020	a 9	b 9	c 6
2021	a 10	b 9	c 6
2022	a 11	b 9	c 6
2023	a 12	b 9	c 6

09857687, 060801

No.	Cp	Bridge	Flu
2024	a 13	b 9	c 6
2025	a 14	b 9	c 6
2026	a 15	b 9	c 6
2027	a 16	b 9	c 6
2028	a 17	b 9	c 6
2029	a 18	b 9	c 6
2030	a 19	b 9	c 6
2031	a 20	b 9	c 6
2032	a 21	b 9	c 6
2033	a 22	b 9	c 6
2034	a 23	b 9	c 6
2035	a 24	b 9	c 6
2036	a 25	b 9	c 6
2037	a 1	b 10	c 6
2038	a 2	b 10	c 6
2039	a 3	b 10	c 6
2040	a 4	b 10	c 6
2041	a 5	b 10	c 6
2042	a 6	b 10	c 6
2043	a 7	b 10	c 6
2044	a 8	b 10	c 6
2045	a 9	b 10	c 6
2046	a 10	b 10	c 6
2047	a 11	b 10	c 6
2048	a 12	b 10	c 6
2049	a 13	b 10	c 6
2050	a 14	b 10	c 6
2051	a 15	b 10	c 6
2052	a 16	b 10	c 6
2053	a 17	b 10	c 6
2054	a 18	b 10	c 6
2055	a 19	b 10	c 6
2056	a 20	b 10	c 6
2057	a 21	b 10	c 6
2058	a 22	b 10	c 6
2059	a 23	b 10	c 6
2060	a 24	b 10	c 6
2061	a 25	b 10	c 6
2062	a 1	b 11	c 6
2063	a 2	b 11	c 6
2064	a 3	b 11	c 6
2065	a 4	b 11	c 6
2066	a 5	b 11	c 6
2067	a 6	b 11	c 6
2068	a 7	b 11	c 6
2069	a 8	b 11	c 6

00857587.060801

No.	Cp	Bridge	Flu
2070	a 9	b 11	c 6
2071	a 10	b 11	c 6
2072	a 11	b 11	c 6
2073	a 12	b 11	c 6
2074	a 13	b 11	c 6
2075	a 14	b 11	c 6
2076	a 15	b 11	c 6
2077	a 16	b 11	c 6
2078	a 17	b 11	c 6
2079	a 18	b 11	c 6
2080	a 19	b 11	c 6
2081	a 20	b 11	c 6
2082	a 21	b 11	c 6
2083	a 22	b 11	c 6
2084	a 23	b 11	c 6
2085	a 24	b 11	c 6
2086	a 25	b 11	c 6
2087	a 1	b 12	c 6
2088	a 2	b 12	c 6
2089	a 3	b 12	c 6
2090	a 4	b 12	c 6
2091	a 5	b 12	c 6
2092	a 6	b 12	c 6
2093	a 7	b 12	c 6
2094	a 8	b 12	c 6
2095	a 9	b 12	c 6
2096	a 10	b 12	c 6
2097	a 11	b 12	c 6
2098	a 12	b 12	c 6
2099	a 13	b 12	c 6
2100	a 14	b 12	c 6
2101	a 15	b 12	c 6
2102	a 16	b 12	c 6
2103	a 17	b 12	c 6
2104	a 18	b 12	c 6
2105	a 19	b 12	c 6
2106	a 20	b 12	c 6
2107	a 21	b 12	c 6
2108	a 22	b 12	c 6
2109	a 23	b 12	c 6
2110	a 24	b 12	c 6
2111	a 25	b 12	c 6
2112	a 1	b 13	c 6
2113	a 2	b 13	c 6
2114	a 3	b 13	c 6
2115	a 4	b 13	c 6

09357687 060801

No.	Cp	Bridge	Flu
2116	a 5	b 13	c 6
2117	a 6	b 13	c 6
2118	a 7	b 13	c 6
2119	a 8	b 13	c 6
2120	a 9	b 13	c 6
2121	a 10	b 13	c 6
2122	a 11	b 13	c 6
2123	a 12	b 13	c 6
2124	a 13	b 13	c 6
2125	a 14	b 13	c 6
2126	a 15	b 13	c 6
2127	a 16	b 13	c 6
2128	a 17	b 13	c 6
2129	a 18	b 13	c 6
2130	a 19	b 13	c 6
2131	a 20	b 13	c 6
2132	a 21	b 13	c 6
2133	a 22	b 13	c 6
2134	a 23	b 13	c 6
2135	a 24	b 13	c 6
2136	a 25	b 13	c 6
2137	a 1	b 14	c 6
2138	a 2	b 14	c 6
2139	a 3	b 14	c 6
2140	a 4	b 14	c 6
2141	a 5	b 14	c 6
2142	a 6	b 14	c 6
2143	a 7	b 14	c 6
2144	a 8	b 14	c 6
2145	a 9	b 14	c 6
2146	a 10	b 14	c 6
2147	a 11	b 14	c 6
2148	a 12	b 14	c 6
2149	a 13	b 14	c 6
2150	a 14	b 14	c 6
2151	a 15	b 14	c 6
2152	a 16	b 14	c 6
2153	a 17	b 14	c 6
2154	a 18	b 14	c 6
2155	a 19	b 14	c 6
2156	a 20	b 14	c 6
2157	a 21	b 14	c 6
2158	a 22	b 14	c 6
2159	a 23	b 14	c 6
2160	a 24	b 14	c 6
2161	a 25	b 14	c 6

09857687 060801

No.	Cp	Bridge	Flu
2162	a 1	b 15	c 6
2163	a 2	b 15	c 6
2164	a 3	b 15	c 6
2165	a 4	b 15	c 6
2166	a 5	b 15	c 6
2167	a 6	b 15	c 6
2168	a 7	b 15	c 6
2169	a 8	b 15	c 6
2170	a 9	b 15	c 6
2171	a 10	b 15	c 6
2172	a 11	b 15	c 6
2173	a 12	b 15	c 6
2174	a 13	b 15	c 6
2175	a 14	b 15	c 6
2176	a 15	b 15	c 6
2177	a 16	b 15	c 6
2178	a 17	b 15	c 6
2179	a 18	b 15	c 6
2180	a 19	b 15	c 6
2181	a 20	b 15	c 6
2182	a 21	b 15	c 6
2183	a 22	b 15	c 6
2184	a 23	b 15	c 6
2185	a 24	b 15	c 6
2186	a 25	b 15	c 6
2187	a 1	b 1	c 7
2188	a 2	b 1	c 7
2189	a 3	b 1	c 7
2190	a 4	b 1	c 7
2191	a 5	b 1	c 7
2192	a 6	b 1	c 7
2193	a 7	b 1	c 7
2194	a 8	b 1	c 7
2195	a 9	b 1	c 7
2196	a 10	b 1	c 7
2197	a 11	b 1	c 7
2198	a 12	b 1	c 7
2199	a 13	b 1	c 7
2200	a 14	b 1	c 7
2201	a 15	b 1	c 7
2202	a 16	b 1	c 7
2203	a 17	b 1	c 7
2204	a 18	b 1	c 7
2205	a 19	b 1	c 7
2206	a 20	b 1	c 7
2207	a 21	b 1	c 7

09857687 060601

No.	Cp	Bridge	Flu
2208	a 22	b 1	c 7
2209	a 23	b 1	c 7
2210	a 24	b 1	c 7
2211	a 25	b 1	c 7
2212	a 1	b 2	c 7
2213	a 2	b 2	c 7
2214	a 3	b 2	c 7
2215	a 4	b 2	c 7
2216	a 5	b 2	c 7
2217	a 6	b 2	c 7
2218	a 7	b 2	c 7
2219	a 8	b 2	c 7
2220	a 9	b 2	c 7
2221	a 10	b 2	c 7
2222	a 11	b 2	c 7
2223	a 12	b 2	c 7
2224	a 13	b 2	c 7
2225	a 14	b 2	c 7
2226	a 15	b 2	c 7
2227	a 16	b 2	c 7
2228	a 17	b 2	c 7
2229	a 18	b 2	c 7
2230	a 19	b 2	c 7
2231	a 20	b 2	c 7
2232	a 21	b 2	c 7
2233	a 22	b 2	c 7
2234	a 23	b 2	c 7
2235	a 24	b 2	c 7
2236	a 25	b 2	c 7
2237	a 1	b 3	c 7
2238	a 2	b 3	c 7
2239	a 3	b 3	c 7
2240	a 4	b 3	c 7
2241	a 5	b 3	c 7
2242	a 6	b 3	c 7
2243	a 7	b 3	c 7
2244	a 8	b 3	c 7
2245	a 9	b 3	c 7
2246	a 10	b 3	c 7
2247	a 11	b 3	c 7
2248	a 12	b 3	c 7
2249	a 13	b 3	c 7
2250	a 14	b 3	c 7
2251	a 15	b 3	c 7
2252	a 16	b 3	c 7
2253	a 17	b 3	c 7

09857687.060801

No.	Cp	Bridge	Flu
2254	a 18	b 3	c 7
2255	a 19	b 3	c 7
2256	a 20	b 3	c 7
2257	a 21	b 3	c 7
2258	a 22	b 3	c 7
2259	a 23	b 3	c 7
2260	a 24	b 3	c 7
2261	a 25	b 3	c 7
2262	a 1	b 4	c 7
2263	a 2	b 4	c 7
2264	a 3	b 4	c 7
2265	a 4	b 4	c 7
2266	a 5	b 4	c 7
2267	a 6	b 4	c 7
2268	a 7	b 4	c 7
2269	a 8	b 4	c 7
2270	a 9	b 4	c 7
2271	a 10	b 4	c 7
2272	a 11	b 4	c 7
2273	a 12	b 4	c 7
2274	a 13	b 4	c 7
2275	a 14	b 4	c 7
2276	a 15	b 4	c 7
2277	a 16	b 4	c 7
2278	a 17	b 4	c 7
2279	a 18	b 4	c 7
2280	a 19	b 4	c 7
2281	a 20	b 4	c 7
2282	a 21	b 4	c 7
2283	a 22	b 4	c 7
2284	a 23	b 4	c 7
2285	a 24	b 4	c 7
2286	a 25	b 4	c 7
2287	a 1	b 5	c 7
2288	a 2	b 5	c 7
2289	a 3	b 5	c 7
2290	a 4	b 5	c 7
2291	a 5	b 5	c 7
2292	a 6	b 5	c 7
2293	a 7	b 5	c 7
2294	a 8	b 5	c 7
2295	a 9	b 5	c 7
2296	a 10	b 5	c 7
2297	a 11	b 5	c 7
2298	a 12	b 5	c 7
2299	a 13	b 5	c 7

09857687-060801

No.	Cp	Bridge	Flu
2300	a 14	b 5	c 7
2301	a 15	b 5	c 7
2302	a 16	b 5	c 7
2303	a 17	b 5	c 7
2304	a 18	b 5	c 7
2305	a 19	b 5	c 7
2306	a 20	b 5	c 7
2307	a 21	b 5	c 7
2308	a 22	b 5	c 7
2309	a 23	b 5	c 7
2310	a 24	b 5	c 7
2311	a 25	b 5	c 7
2312	a 1	b 6	c 7
2313	a 2	b 6	c 7
2314	a 3	b 6	c 7
2315	a 4	b 6	c 7
2316	a 5	b 6	c 7
2317	a 6	b 6	c 7
2318	a 7	b 6	c 7
2319	a 8	b 6	c 7
2320	a 9	b 6	c 7
2321	a 10	b 6	c 7
2322	a 11	b 6	c 7
2323	a 12	b 6	c 7
2324	a 13	b 6	c 7
2325	a 14	b 6	c 7
2326	a 15	b 6	c 7
2327	a 16	b 6	c 7
2328	a 17	b 6	c 7
2329	a 18	b 6	c 7
2330	a 19	b 6	c 7
2331	a 20	b 6	c 7
2332	a 21	b 6	c 7
2333	a 22	b 6	c 7
2334	a 23	b 6	c 7
2335	a 24	b 6	c 7
2336	a 25	b 6	c 7
2337	a 1	b 7	c 7
2338	a 2	b 7	c 7
2339	a 3	b 7	c 7
2340	a 4	b 7	c 7
2341	a 5	b 7	c 7
2342	a 6	b 7	c 7
2343	a 7	b 7	c 7
2344	a 8	b 7	c 7
2345	a 9	b 7	c 7

09857687.060801

No.	Cp	Bridge	Flu
2346	a 10	b 7	c 7
2347	a 11	b 7	c 7
2348	a 12	b 7	c 7
2349	a 13	b 7	c 7
2350	a 14	b 7	c 7
2351	a 15	b 7	c 7
2352	a 16	b 7	c 7
2353	a 17	b 7	c 7
2354	a 18	b 7	c 7
2355	a 19	b 7	c 7
2356	a 20	b 7	c 7
2357	a 21	b 7	c 7
2358	a 22	b 7	c 7
2359	a 23	b 7	c 7
2360	a 24	b 7	c 7
2361	a 25	b 7	c 7
2362	a 1	b 8	c 7
2363	a 2	b 8	c 7
2364	a 3	b 8	c 7
2365	a 4	b 8	c 7
2366	a 5	b 8	c 7
2367	a 6	b 8	c 7
2368	a 7	b 8	c 7
2369	a 8	b 8	c 7
2370	a 9	b 8	c 7
2371	a 10	b 8	c 7
2372	a 11	b 8	c 7
2373	a 12	b 8	c 7
2374	a 13	b 8	c 7
2375	a 14	b 8	c 7
2376	a 15	b 8	c 7
2377	a 16	b 8	c 7
2378	a 17	b 8	c 7
2379	a 18	b 8	c 7
2380	a 19	b 8	c 7
2381	a 20	b 8	c 7
2382	a 21	b 8	c 7
2383	a 22	b 8	c 7
2384	a 23	b 8	c 7
2385	a 24	b 8	c 7
2386	a 25	b 8	c 7
2387	a 1	b 9	c 7
2388	a 2	b 9	c 7
2389	a 3	b 9	c 7
2390	a 4	b 9	c 7
2391	a 5	b 9	c 7

09557687-060801

No.	Cp	Bridge	Flu
2392	a 6	b 9	c 7
2393	a 7	b 9	c 7
2394	a 8	b 9	c 7
2395	a 9	b 9	c 7
2396	a 10	b 9	c 7
2397	a 11	b 9	c 7
2398	a 12	b 9	c 7
2399	a 13	b 9	c 7
2400	a 14	b 9	c 7
2401	a 15	b 9	c 7
2402	a 16	b 9	c 7
2403	a 17	b 9	c 7
2404	a 18	b 9	c 7
2405	a 19	b 9	c 7
2406	a 20	b 9	c 7
2407	a 21	b 9	c 7
2408	a 22	b 9	c 7
2409	a 23	b 9	c 7
2410	a 24	b 9	c 7
2411	a 25	b 9	c 7
2412	a 1	b 10	c 7
2413	a 2	b 10	c 7
2414	a 3	b 10	c 7
2415	a 4	b 10	c 7
2416	a 5	b 10	c 7
2417	a 6	b 10	c 7
2418	a 7	b 10	c 7
2419	a 8	b 10	c 7
2420	a 9	b 10	c 7
2421	a 10	b 10	c 7
2422	a 11	b 10	c 7
2423	a 12	b 10	c 7
2424	a 13	b 10	c 7
2425	a 14	b 10	c 7
2426	a 15	b 10	c 7
2427	a 16	b 10	c 7
2428	a 17	b 10	c 7
2429	a 18	b 10	c 7
2430	a 19	b 10	c 7
2431	a 20	b 10	c 7
2432	a 21	b 10	c 7
2433	a 22	b 10	c 7
2434	a 23	b 10	c 7
2435	a 24	b 10	c 7
2436	a 25	b 10	c 7
2437	a 1	b 11	c 7

09857687 060801

No.	Cp	Bridge	Flu
2438	a 2	b 11	c 7
2439	a 3	b 11	c 7
2440	a 4	b 11	c 7
2441	a 5	b 11	c 7
2442	a 6	b 11	c 7
2443	a 7	b 11	c 7
2444	a 8	b 11	c 7
2445	a 9	b 11	c 7
2446	a 10	b 11	c 7
2447	a 11	b 11	c 7
2448	a 12	b 11	c 7
2449	a 13	b 11	c 7
2450	a 14	b 11	c 7
2451	a 15	b 11	c 7
2452	a 16	b 11	c 7
2453	a 17	b 11	c 7
2454	a 18	b 11	c 7
2455	a 19	b 11	c 7
2456	a 20	b 11	c 7
2457	a 21	b 11	c 7
2458	a 22	b 11	c 7
2459	a 23	b 11	c 7
2460	a 24	b 11	c 7
2461	a 25	b 11	c 7
2462	a 1	b 12	c 7
2463	a 2	b 12	c 7
2464	a 3	b 12	c 7
2465	a 4	b 12	c 7
2466	a 5	b 12	c 7
2467	a 6	b 12	c 7
2468	a 7	b 12	c 7
2469	a 8	b 12	c 7
2470	a 9	b 12	c 7
2471	a 10	b 12	c 7
2472	a 11	b 12	c 7
2473	a 12	b 12	c 7
2474	a 13	b 12	c 7
2475	a 14	b 12	c 7
2476	a 15	b 12	c 7
2477	a 16	b 12	c 7
2478	a 17	b 12	c 7
2479	a 18	b 12	c 7
2480	a 19	b 12	c 7
2481	a 20	b 12	c 7
2482	a 21	b 12	c 7
2483	a 22	b 12	c 7

102090 28925860 09857687 050801

No.	Cp	Bridge	Flu
2484	a 23	b 12	c 7
2485	a 24	b 12	c 7
2486	a 25	b 12	c 7
2487	a 1	b 13	c 7
2488	a 2	b 13	c 7
2489	a 3	b 13	c 7
2490	a 4	b 13	c 7
2491	a 5	b 13	c 7
2492	a 6	b 13	c 7
2493	a 7	b 13	c 7
2494	a 8	b 13	c 7
2495	a 9	b 13	c 7
2496	a 10	b 13	c 7
2497	a 11	b 13	c 7
2498	a 12	b 13	c 7
2499	a 13	b 13	c 7
2500	a 14	b 13	c 7
2501	a 15	b 13	c 7
2502	a 16	b 13	c 7
2503	a 17	b 13	c 7
2504	a 18	b 13	c 7
2505	a 19	b 13	c 7
2506	a 20	b 13	c 7
2507	a 21	b 13	c 7
2508	a 22	b 13	c 7
2509	a 23	b 13	c 7
2510	a 24	b 13	c 7
2511	a 25	b 13	c 7
2512	a 1	b 14	c 7
2513	a 2	b 14	c 7
2514	a 3	b 14	c 7
2515	a 4	b 14	c 7
2516	a 5	b 14	c 7
2517	a 6	b 14	c 7
2518	a 7	b 14	c 7
2519	a 8	b 14	c 7
2520	a 9	b 14	c 7
2521	a 10	b 14	c 7
2522	a 11	b 14	c 7
2523	a 12	b 14	c 7
2524	a 13	b 14	c 7
2525	a 14	b 14	c 7
2526	a 15	b 14	c 7
2527	a 16	b 14	c 7
2528	a 17	b 14	c 7
2529	a 18	b 14	c 7

09857587.050801


No.	Cp	Bridge	Flu
2530	a 19	b 14	c 7
2531	a 20	b 14	c 7
2532	a 21	b 14	c 7
2533	a 22	b 14	c 7
2534	a 23	b 14	c 7
2535	a 24	b 14	c 7
2536	a 25	b 14	c 7
2537	a 1	b 15	c 7
2538	a 2	b 15	c 7
2539	a 3	b 15	c 7
2540	a 4	b 15	c 7
2541	a 5	b 15	c 7
2542	a 6	b 15	c 7
2543	a 7	b 15	c 7
2544	a 8	b 15	c 7
2545	a 9	b 15	c 7
2546	a 10	b 15	c 7
2547	a 11	b 15	c 7
2548	a 12	b 15	c 7
2549	a 13	b 15	c 7
2550	a 14	b 15	c 7
2551	a 15	b 15	c 7
2552	a 16	b 15	c 7
2553	a 17	b 15	c 7
2554	a 18	b 15	c 7
2555	a 19	b 15	c 7
2556	a 20	b 15	c 7
2557	a 21	b 15	c 7
2558	a 22	b 15	c 7
2559	a 23	b 15	c 7
2560	a 24	b 15	c 7
2561	a 25	b 15	c 7

According to the above table, the ligand structure of No. 736 means a combination of a2-b1-c3, so that

- 5 when the metal part MQ_j is ZrCl₂, the following metallocene compound is exemplified.

09857687-060801

5




Specific examples of MQ₃ include ZrCl₂, ZrBr₂,

- 10 ZrMe₂, Zr(OTs)₂, Zr(OMs)₂, Zr(OTf)₂, TiCl₂, TiBr₂,
TiMe₂, Ti(OTs)₂, Ti(OMs)₂, Ti(OTf)₂, HfCl₂, HfBr₂,
HfMe₂, Hf(OTs)₂, Hf(OMs)₂ and Hf(OTf)₂.

Examples of the metallocene compounds wherein the
substituent group on the Cp ring and the substituent

- 15 group on the bridge part are bonded to form a ring
include the following compounds.

20



Preferred examples of the metallocene compounds represented by the formula (1a) or (2a) according to the invention include:

- a metallocene compound of the formula (1a) wherein
- 5 R¹, R¹³ and R¹⁴ are each methyl, R³ is tert-butyl, R², R⁴, R⁵, R⁷, R⁸, R⁹, R¹⁰ and R¹² are each hydrogen, R⁶ and R¹¹ are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

- a metallocene compound of the formula (1a) wherein
- 10 R¹³ and R¹⁴ are each methyl, R³ is 1-methyl-1-cyclohexyl, R¹, R², R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹ and R¹² are each hydrogen, R⁷ and R¹⁰ are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

- a metallocene compound of the formula (1a) wherein
- 15 R¹³ and R¹⁴ are each methyl, R³ is tert-butyl, R¹, R², R⁴, R⁵, R⁸, R⁹ and R¹² are each hydrogen, R⁶ and R⁷ are bonded to form $-(C(CH_3)_2CH_2CH_2C(CH_3)_2)-$ and thereby form a ring, R¹⁰ and R¹¹ are bonded to form $-(C(CH_3)_2CH_2CH_2C(CH_3)_2)-$ and thereby form a ring, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

- a metallocene compound of the formula (1a) wherein
- 20 R¹³ and R¹⁴ are each methyl, R³ is trimethylsilyl, R¹, R², R⁴, R⁵, R⁸, R⁹ and R¹² are each hydrogen, R⁶ and R⁷ are bonded to form $-(C(CH_3)_2CH_2CH_2C(CH_3)_2)-$ and thereby form a ring, R¹⁰ and R¹¹ are bonded to form -

09857687 060801
100990 2975960

(C(CH₃)₂CH₂CH₂C(CH₃)₂)- and thereby form a ring, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

a metallocene compound of the formula (1a) wherein R¹³ and R¹⁴ are each methyl, R³ is 1,1-dimethylpropyl, 5 R¹, R², R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹ and R¹² are each hydrogen, R⁷ and R¹⁰ are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

a metallocene compound of the formula (1a) wherein R¹³ and R¹⁴ are each methyl, R³ is 1-ethyl-1- 10 methylpropyl, R¹, R², R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹ and R¹² are each hydrogen, R⁷ and R¹⁰ are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

a metallocene compound of the formula (1a) wherein R¹³ and R¹⁴ are each methyl, R³ is 1,1,3- 15 trimethylbutyl, R¹, R², R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹ and R¹² are each hydrogen, R⁷ and R¹⁰ are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

a metallocene compound of the formula (1a) wherein 20 R¹³ and R¹⁴ are each methyl, R³ is 1,1-dimethylbutyl, R¹, R², R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹ and R¹² are each hydrogen, R⁷ and R¹⁰ are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

a metallocene compound of the formula (1a) wherein 25 R¹³ and R¹⁴ are each methyl, R³ is tert-butyl, R¹, R²,

09857687-060801

R⁴, R⁵, R⁷, R⁸, R⁹, R¹⁰ and R¹² are each hydrogen, R⁶ and R¹¹ are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

- a metallocene compound of the formula (1a) wherein
- 5 R³, R¹³ and R¹⁴ are each phenyl, R¹, R², R⁴, R⁵, R⁸, R⁹ and R¹² are each hydrogen, R⁶ and R⁷ are bonded to form $-(C(CH_3)_2CH_2CH_2C(CH_3)_2)-$ and thereby form a ring, R¹⁰ and R¹¹ are bonded to form $-(C(CH_3)_2CH_2CH_2C(CH_3)_2)-$ and thereby form a ring, M is
- 10 zirconium, Y is carbon, Q is chlorine, and j is 2;

- a metallocene compound of the formula (1a) wherein
- R³ is trimethylsilyl, R¹³ and R¹⁴ are each phenyl, R¹, R², R⁴, R⁵, R⁸, R⁹ and R¹² are each hydrogen, R⁶ and R⁷ are bonded to form $-(C(CH_3)_2CH_2CH_2C(CH_3)_2)-$ and
- 15 thereby form a ring, R¹⁰ and R¹¹ are bonded to form $-(C(CH_3)_2CH_2CH_2C(CH_3)_2)-$ and thereby form a ring, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

- a metallocene compound of the formula (1a) wherein
- R¹³ is methyl, R¹⁴ is phenyl, R³ is tert-butyl, R¹, R²,
- 20 R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹ and R¹² are each hydrogen, R⁷ and R¹⁰ are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

- a metallocene compound of the formula (1a) wherein
- R¹³ and R¹⁴ are each ethyl, R³ is tert-butyl, R¹, R²,
- 25 R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹ and R¹² are each hydrogen, R⁷

09857687.060801

and R¹⁰ are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

a metallocene compound of the formula (2a) wherein R¹ is methyl, R³ is tert-butyl, R², R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, R¹¹ and R¹² are each hydrogen, M is zirconium, Y is carbon, Q is chlorine, j is 2, and A is -(CH₂)₅-;

a metallocene compound of the formula (2a) wherein R¹ is methyl, R³ is tert-butyl, R², R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹ and R¹² are each hydrogen, R⁷ and R¹⁰ are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, j is 2, and A is -(CH₂)₅-;

a metallocene compound of the formula (2a) wherein R³ is trimethylsilyl, R¹, R², R⁴, R⁵, R⁷, R⁸, R⁹, R¹⁰ and R¹² are each hydrogen, R⁶ and R¹¹ are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, j is 2, and A is -(CH₂)₅-;

a metallocene compound of the formula (2a) wherein R³ is trimethylsilyl, R¹, R², R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹ and R¹² are each hydrogen, R⁷ and R¹⁰ are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, j is 2, and A is -(CH₂)₅-;

a metallocene compound of the formula (2a) wherein R³ is tert-butyl, R¹, R², R⁴, R⁵, R⁶, R⁸, R⁹, R¹¹ and R¹² are each hydrogen, R⁷ and R¹⁰ are each tert-butyl,

09857687, 060801

M is zirconium, Y is carbon, Q is chlorine, j is 2,
and A is $-(CH_2)_4-$;

- a metallocene compound of the formula (2a) wherein
 R^3 is 1,1-dimethylpropyl, R^1 , R^2 , R^4 , R^5 , R^6 , R^8 , R^9 ,
5 R^{11} and R^{12} are each hydrogen, R^7 and R^{10} are each
tert-butyl, M is zirconium, Y is carbon, Q is chlorine,
j is 2, and A is $-(CH_2)_5-$; and


- a metallocene compound of the formula (2a) wherein
 R^3 is tert-butyl, R^1 , R^2 , R^4 , R^5 , R^8 , R^9 and R^{12} are
10 each hydrogen, R^6 and R^7 are bonded to form -
 $(C(CH_3)_2CH_2CH_2C(CH_3)_2)-$ and thereby form a ring, R^{10}
and R^{11} are bonded to form $-(C(CH_3)_2CH_2CH_2C(CH_3)_2)-$
and thereby form a ring, M is zirconium, Y is carbon,
Q is chlorine, j is 2, and A is $-(CH_2)_4-$.

- 15 There is no specific limitation on the process for
preparing the metallocene compound represented by the
formula (1a) or (2a), and the compound can be prepared
by, for example, a process similar to the process for
preparing the metallocene compound represented by the
20 formula (1) or (2).


Next, the metallocene compound represented by the
formula (1b) or (2b) is described.

- A further embodiment of the metallocene compound
of the invention is represented by the following
25 formula (1b) or (2b).

09857687.060801



... (1b)



... (2b)

10

In the formula (1b) or (2b), each of R²¹ and R²² has the same meaning as that of R³ in the formula (1) or (2); each of R⁵ to R¹⁴ has the same meaning as that of R¹, R² or each of R⁴ to R¹⁴ in the formula (1) or (2); and A, Y, M, Q and j have the same meanings as those of A, Y, M, Q and j in the formula (1) or (2), respectively.

15

R²² is preferably a sterically bulky substituent group, more preferably a substituent group of 4 or

20

more carbon atoms.

Examples of the metallocene compounds represented by the formula (1b) or (2b) according to the invention are given below.

The ligand structure excluding MQ_j (metal part) in 25 the metallocene compound is divided into three parts

of Cp (cyclopentadienyl ring part), Bridge (bridge part) and Flu (fluorenyl ring part), and specific examples of these partial structures and specific examples of ligand structures formed by combination of

5 these partial structures are described first. Examples of Bridge (bridge part) and Flu (fluorenyl ring part) are the same as those previously described with respect to the metallocene compound represented by the formula (1) or (2).

10

09857687.060801







Examples of Cp






5

10

15

20

	a1
	a2
	a3
	a4
	a5
	a6

	a7
	a8
	a9
	a10
	a11

Examples of the ligand structures are described in the following table.

No.	Cp	Bridge	Flu
1	a 1	b 1	c 1
2	a 2	b 1	c 1
3	a 3	b 1	c 1
4	a 4	b 1	c 1
5	a 5	b 1	c 1
6	a 6	b 1	c 1
7	a 7	b 1	c 1
8	a 8	b 1	c 1
9	a 9	b 1	c 1
10	a 10	b 1	c 1
11	a 11	b 1	c 1
12	a 1	b 2	c 1
13	a 2	b 2	c 1
14	a 3	b 2	c 1
15	a 4	b 2	c 1
16	a 5	b 2	c 1
17	a 6	b 2	c 1
18	a 7	b 2	c 1
19	a 8	b 2	c 1
20	a 9	b 2	c 1
21	a 10	b 2	c 1
22	a 11	b 2	c 1
23	a 1	b 3	c 1
24	a 2	b 3	c 1
25	a 3	b 3	c 1
26	a 4	b 3	c 1
27	a 5	b 3	c 1
28	a 6	b 3	c 1
29	a 7	b 3	c 1
30	a 8	b 3	c 1
31	a 9	b 3	c 1
32	a 10	b 3	c 1
33	a 11	b 3	c 1
34	a 1	b 4	c 1
35	a 2	b 4	c 1
36	a 3	b 4	c 1
37	a 4	b 4	c 1
38	a 5	b 4	c 1
39	a 6	b 4	c 1
40	a 7	b 4	c 1
41	a 8	b 4	c 1
42	a 9	b 4	c 1
43	a 10	b 4	c 1
44	a 11	b 4	c 1
45	a 1	b 5	c 1

09857687.050801

No.	Cp	Bridge	Flu
46	a 2	b 5	c 1
47	a 3	b 5	c 1
48	a 4	b 5	c 1
49	a 5	b 5	c 1
50	a 6	b 5	c 1
51	a 7	b 5	c 1
52	a 8	b 5	c 1
53	a 9	b 5	c 1
54	a 10	b 5	c 1
55	a 11	b 5	c 1
56	a 1	b 6	c 1
57	a 2	b 6	c 1
58	a 3	b 6	c 1
59	a 4	b 6	c 1
60	a 5	b 6	c 1
61	a 6	b 6	c 1
62	a 7	b 6	c 1
63	a 8	b 6	c 1
64	a 9	b 6	c 1
65	a 10	b 6	c 1
66	a 11	b 6	c 1
67	a 1	b 7	c 1
68	a 2	b 7	c 1
69	a 3	b 7	c 1
70	a 4	b 7	c 1
71	a 5	b 7	c 1
72	a 6	b 7	c 1
73	a 7	b 7	c 1
74	a 8	b 7	c 1
75	a 9	b 7	c 1
76	a 10	b 7	c 1
77	a 11	b 7	c 1
78	a 1	b 8	c 1
79	a 2	b 8	c 1
80	a 3	b 8	c 1
81	a 4	b 8	c 1
82	a 5	b 8	c 1
83	a 6	b 8	c 1
84	a 7	b 8	c 1
85	a 8	b 8	c 1
86	a 9	b 8	c 1
87	a 10	b 8	c 1
88	a 11	b 8	c 1
89	a 1	b 9	c 1
90	a 2	b 9	c 1
91	a 3	b 9	c 1

09857687.060801

No.	Cp	Bridge	Flu
92	a 4	b 9	c 1
93	a 5	b 9	c 1
94	a 6	b 9	c 1
95	a 7	b 9	c 1
96	a 8	b 9	c 1
97	a 9	b 9	c 1
98	a 10	b 9	c 1
99	a 11	b 9	c 1
100	a 1	b 10	c 1
101	a 2	b 10	c 1
102	a 3	b 10	c 1
103	a 4	b 10	c 1
104	a 5	b 10	c 1
105	a 6	b 10	c 1
106	a 7	b 10	c 1
107	a 8	b 10	c 1
108	a 9	b 10	c 1
109	a 10	b 10	c 1
110	a 11	b 10	c 1
111	a 1	b 11	c 1
112	a 2	b 11	c 1
113	a 3	b 11	c 1
114	a 4	b 11	c 1
115	a 5	b 11	c 1
116	a 6	b 11	c 1
117	a 7	b 11	c 1
118	a 8	b 11	c 1
119	a 9	b 11	c 1
120	a 10	b 11	c 1
121	a 11	b 11	c 1
122	a 1	b 12	c 1
123	a 2	b 12	c 1
124	a 3	b 12	c 1
125	a 4	b 12	c 1
126	a 5	b 12	c 1
127	a 6	b 12	c 1
128	a 7	b 12	c 1
129	a 8	b 12	c 1
130	a 9	b 12	c 1
131	a 10	b 12	c 1
132	a 11	b 12	c 1
133	a 1	b 13	c 1
134	a 2	b 13	c 1
135	a 3	b 13	c 1
136	a 4	b 13	c 1
137	a 5	b 13	c 1

09857687 060801

No.	Cp	Bridge	Flu
138	a 6	b 13	c 1
139	a 7	b 13	c 1
140	a 8	b 13	c 1
141	a 9	b 13	c 1
142	a 10	b 13	c 1
143	a 11	b 13	c 1
144	a 1	b 14	c 1
145	a 2	b 14	c 1
146	a 3	b 14	c 1
147	a 4	b 14	c 1
148	a 5	b 14	c 1
149	a 6	b 14	c 1
150	a 7	b 14	c 1
151	a 8	b 14	c 1
152	a 9	b 14	c 1
153	a 10	b 14	c 1
154	a 11	b 14	c 1
155	a 1	b 15	c 1
156	a 2	b 15	c 1
157	a 3	b 15	c 1
158	a 4	b 15	c 1
159	a 5	b 15	c 1
160	a 6	b 15	c 1
161	a 7	b 15	c 1
162	a 8	b 15	c 1
163	a 9	b 15	c 1
164	a 10	b 15	c 1
165	a 11	b 15	c 1
166	a 1	b 1	c 2
167	a 2	b 1	c 2
168	a 3	b 1	c 2
169	a 4	b 1	c 2
170	a 5	b 1	c 2
171	a 6	b 1	c 2
172	a 7	b 1	c 2
173	a 8	b 1	c 2
174	a 9	b 1	c 2
175	a 10	b 1	c 2
176	a 11	b 1	c 2
177	a 1	b 2	c 2
178	a 2	b 2	c 2
179	a 3	b 2	c 2
180	a 4	b 2	c 2
181	a 5	b 2	c 2
182	a 6	b 2	c 2
183	a 7	b 2	c 2

09857587-060801

No.	Cp	Bridge	Flu
184	a 8	b 2	c 2
185	a 9	b 2	c 2
186	a 10	b 2	c 2
187	a 11	b 2	c 2
188	a 1	b 3	c 2
189	a 2	b 3	c 2
190	a 3	b 3	c 2
191	a 4	b 3	c 2
192	a 5	b 3	c 2
193	a 6	b 3	c 2
194	a 7	b 3	c 2
195	a 8	b 3	c 2
196	a 9	b 3	c 2
197	a 10	b 3	c 2
198	a 11	b 3	c 2
199	a 1	b 4	c 2
200	a 2	b 4	c 2
201	a 3	b 4	c 2
202	a 4	b 4	c 2
203	a 5	b 4	c 2
204	a 6	b 4	c 2
205	a 7	b 4	c 2
206	a 8	b 4	c 2
207	a 9	b 4	c 2
208	a 10	b 4	c 2
209	a 11	b 4	c 2
210	a 1	b 5	c 2
211	a 2	b 5	c 2
212	a 3	b 5	c 2
213	a 4	b 5	c 2
214	a 5	b 5	c 2
215	a 6	b 5	c 2
216	a 7	b 5	c 2
217	a 8	b 5	c 2
218	a 9	b 5	c 2
219	a 10	b 5	c 2
220	a 11	b 5	c 2
221	a 1	b 6	c 2
222	a 2	b 6	c 2
223	a 3	b 6	c 2
224	a 4	b 6	c 2
225	a 5	b 6	c 2
226	a 6	b 6	c 2
227	a 7	b 6	c 2
228	a 8	b 6	c 2
229	a 9	b 6	c 2

09857687.060001

No.	Cp	Bridge	Flu
230	a 10	b 6	c 2
231	a 11	b 6	c 2
232	a 1	b 7	c 2
233	a 2	b 7	c 2
234	a 3	b 7	c 2
235	a 4	b 7	c 2
236	a 5	b 7	c 2
237	a 6	b 7	c 2
238	a 7	b 7	c 2
239	a 8	b 7	c 2
240	a 9	b 7	c 2
241	a 10	b 7	c 2
242	a 11	b 7	c 2
243	a 1	b 8	c 2
244	a 2	b 8	c 2
245	a 3	b 8	c 2
246	a 4	b 8	c 2
247	a 5	b 8	c 2
248	a 6	b 8	c 2
249	a 7	b 8	c 2
250	a 8	b 8	c 2
251	a 9	b 8	c 2
252	a 10	b 8	c 2
253	a 11	b 8	c 2
254	a 1	b 9	c 2
255	a 2	b 9	c 2
256	a 3	b 9	c 2
257	a 4	b 9	c 2
258	a 5	b 9	c 2
259	a 6	b 9	c 2
260	a 7	b 9	c 2
261	a 8	b 9	c 2
262	a 9	b 9	c 2
263	a 10	b 9	c 2
264	a 11	b 9	c 2
265	a 1	b 10	c 2
266	a 2	b 10	c 2
267	a 3	b 10	c 2
268	a 4	b 10	c 2
269	a 5	b 10	c 2
270	a 6	b 10	c 2
271	a 7	b 10	c 2
272	a 8	b 10	c 2
273	a 9	b 10	c 2
274	a 10	b 10	c 2
275	a 11	b 10	c 2

09857687-060801

No.	Cp	Bridge	Flu
276	a 1	b 11	c 2
277	a 2	b 11	c 2
278	a 3	b 11	c 2
279	a 4	b 11	c 2
280	a 5	b 11	c 2
281	a 6	b 11	c 2
282	a 7	b 11	c 2
283	a 8	b 11	c 2
284	a 9	b 11	c 2
285	a 10	b 11	c 2
286	a 11	b 11	c 2
287	a 1	b 12	c 2
288	a 2	b 12	c 2
289	a 3	b 12	c 2
290	a 4	b 12	c 2
291	a 5	b 12	c 2
292	a 6	b 12	c 2
293	a 7	b 12	c 2
294	a 8	b 12	c 2
295	a 9	b 12	c 2
296	a 10	b 12	c 2
297	a 11	b 12	c 2
298	a 1	b 13	c 2
299	a 2	b 13	c 2
300	a 3	b 13	c 2
301	a 4	b 13	c 2
302	a 5	b 13	c 2
303	a 6	b 13	c 2
304	a 7	b 13	c 2
305	a 8	b 13	c 2
306	a 9	b 13	c 2
307	a 10	b 13	c 2
308	a 11	b 13	c 2
309	a 1	b 14	c 2
310	a 2	b 14	c 2
311	a 3	b 14	c 2
312	a 4	b 14	c 2
313	a 5	b 14	c 2
314	a 6	b 14	c 2
315	a 7	b 14	c 2
316	a 8	b 14	c 2
317	a 9	b 14	c 2
318	a 10	b 14	c 2
319	a 11	b 14	c 2
320	a 1	b 15	c 2
321	a 2	b 15	c 2

08857687.060801

No.	Cp	Bridge	Flu
322	a 3	b 15	c 2
323	a 4	b 15	c 2
324	a 5	b 15	c 2
325	a 6	b 15	c 2
326	a 7	b 15	c 2
327	a 8	b 15	c 2
328	a 9	b 15	c 2
329	a 10	b 15	c 2
330	a 11	b 15	c 2
331	a 1	b 1	c 3
332	a 2	b 1	c 3
333	a 3	b 1	c 3
334	a 4	b 1	c 3
335	a 5	b 1	c 3
336	a 6	b 1	c 3
337	a 7	b 1	c 3
338	a 8	b 1	c 3
339	a 9	b 1	c 3
340	a 10	b 1	c 3
341	a 11	b 1	c 3
342	a 1	b 2	c 3
343	a 2	b 2	c 3
344	a 3	b 2	c 3
345	a 4	b 2	c 3
346	a 5	b 2	c 3
347	a 6	b 2	c 3
348	a 7	b 2	c 3
349	a 8	b 2	c 3
350	a 9	b 2	c 3
351	a 10	b 2	c 3
352	a 11	b 2	c 3
353	a 1	b 3	c 3
354	a 2	b 3	c 3
355	a 3	b 3	c 3
356	a 4	b 3	c 3
357	a 5	b 3	c 3
358	a 6	b 3	c 3
359	a 7	b 3	c 3
360	a 8	b 3	c 3
361	a 9	b 3	c 3
362	a 10	b 3	c 3
363	a 11	b 3	c 3
364	a 1	b 4	c 3
365	a 2	b 4	c 3
366	a 3	b 4	c 3
367	a 4	b 4	c 3

09857687 060801

No.	Cp	Bridge	Flu
368	a 5	b 4	c 3
369	a 6	b 4	c 3
370	a 7	b 4	c 3
371	a 8	b 4	c 3
372	a 9	b 4	c 3
373	a 10	b 4	c 3
374	a 11	b 4	c 3
375	a 1	b 5	c 3
376	a 2	b 5	c 3
377	a 3	b 5	c 3
378	a 4	b 5	c 3
379	a 5	b 5	c 3
380	a 6	b 5	c 3
381	a 7	b 5	c 3
382	a 8	b 5	c 3
383	a 9	b 5	c 3
384	a 10	b 5	c 3
385	a 11	b 5	c 3
386	a 1	b 6	c 3
387	a 2	b 6	c 3
388	a 3	b 6	c 3
389	a 4	b 6	c 3
390	a 5	b 6	c 3
391	a 6	b 6	c 3
392	a 7	b 6	c 3
393	a 8	b 6	c 3
394	a 9	b 6	c 3
395	a 10	b 6	c 3
396	a 11	b 6	c 3
397	a 1	b 7	c 3
398	a 2	b 7	c 3
399	a 3	b 7	c 3
400	a 4	b 7	c 3
401	a 5	b 7	c 3
402	a 6	b 7	c 3
403	a 7	b 7	c 3
404	a 8	b 7	c 3
405	a 9	b 7	c 3
406	a 10	b 7	c 3
407	a 11	b 7	c 3
408	a 1	b 8	c 3
409	a 2	b 8	c 3
410	a 3	b 8	c 3
411	a 4	b 8	c 3
412	a 5	b 8	c 3
413	a 6	b 8	c 3

09857687 060801

No.	Cp	Bridge	Flu
414	a 7	b 8	c 3
415	a 8	b 8	c 3
416	a 9	b 8	c 3
417	a 10	b 8	c 3
418	a 11	b 8	c 3
419	a 1	b 9	c 3
420	a 2	b 9	c 3
421	a 3	b 9	c 3
422	a 4	b 9	c 3
423	a 5	b 9	c 3
424	a 6	b 9	c 3
425	a 7	b 9	c 3
426	a 8	b 9	c 3
427	a 9	b 9	c 3
428	a 10	b 9	c 3
429	a 11	b 9	c 3
430	a 1	b 10	c 3
431	a 2	b 10	c 3
432	a 3	b 10	c 3
433	a 4	b 10	c 3
434	a 5	b 10	c 3
435	a 6	b 10	c 3
436	a 7	b 10	c 3
437	a 8	b 10	c 3
438	a 9	b 10	c 3
439	a 10	b 10	c 3
440	a 11	b 10	c 3
441	a 1	b 11	c 3
442	a 2	b 11	c 3
443	a 3	b 11	c 3
444	a 4	b 11	c 3
445	a 5	b 11	c 3
446	a 6	b 11	c 3
447	a 7	b 11	c 3
448	a 8	b 11	c 3
449	a 9	b 11	c 3
450	a 10	b 11	c 3
451	a 11	b 11	c 3
452	a 1	b 12	c 3
453	a 2	b 12	c 3
454	a 3	b 12	c 3
455	a 4	b 12	c 3
456	a 5	b 12	c 3
457	a 6	b 12	c 3
458	a 7	b 12	c 3
459	a 8	b 12	c 3

09857687.050801

No.	Cp	Bridge	Flu
460	a 9	b 12	c 3
461	a 10	b 12	c 3
462	a 11	b 12	c 3
463	a 1	b 13	c 3
464	a 2	b 13	c 3
465	a 3	b 13	c 3
466	a 4	b 13	c 3
467	a 5	b 13	c 3
468	a 6	b 13	c 3
469	a 7	b 13	c 3
470	a 8	b 13	c 3
471	a 9	b 13	c 3
472	a 10	b 13	c 3
473	a 11	b 13	c 3
474	a 1	b 14	c 3
475	a 2	b 14	c 3
476	a 3	b 14	c 3
477	a 4	b 14	c 3
478	a 5	b 14	c 3
479	a 6	b 14	c 3
480	a 7	b 14	c 3
481	a 8	b 14	c 3
482	a 9	b 14	c 3
483	a 10	b 14	c 3
484	a 11	b 14	c 3
485	a 1	b 15	c 3
486	a 2	b 15	c 3
487	a 3	b 15	c 3
488	a 4	b 15	c 3
489	a 5	b 15	c 3
490	a 6	b 15	c 3
491	a 7	b 15	c 3
492	a 8	b 15	c 3
493	a 9	b 15	c 3
494	a 10	b 15	c 3
495	a 11	b 15	c 3
496	a 1	b 1	c 4
497	a 2	b 1	c 4
498	a 3	b 1	c 4
499	a 4	b 1	c 4
500	a 5	b 1	c 4
501	a 6	b 1	c 4
502	a 7	b 1	c 4
503	a 8	b 1	c 4
504	a 9	b 1	c 4
505	a 10	b 1	c 4

060801.7857860

No.	Cp	Bridge	Flu
506	a 11	b 1	c 4
507	a 1	b 2	c 4
508	a 2	b 2	c 4
509	a 3	b 2	c 4
510	a 4	b 2	c 4
511	a 5	b 2	c 4
512	a 6	b 2	c 4
513	a 7	b 2	c 4
514	a 8	b 2	c 4
515	a 9	b 2	c 4
516	a 10	b 2	c 4
517	a 11	b 2	c 4
518	a 1	b 3	c 4
519	a 2	b 3	c 4
520	a 3	b 3	c 4
521	a 4	b 3	c 4
522	a 5	b 3	c 4
523	a 6	b 3	c 4
524	a 7	b 3	c 4
525	a 8	b 3	c 4
526	a 9	b 3	c 4
527	a 10	b 3	c 4
528	a 11	b 3	c 4
529	a 1	b 4	c 4
530	a 2	b 4	c 4
531	a 3	b 4	c 4
532	a 4	b 4	c 4
533	a 5	b 4	c 4
534	a 6	b 4	c 4
535	a 7	b 4	c 4
536	a 8	b 4	c 4
537	a 9	b 4	c 4
538	a 10	b 4	c 4
539	a 11	b 4	c 4
540	a 1	b 5	c 4
541	a 2	b 5	c 4
542	a 3	b 5	c 4
543	a 4	b 5	c 4
544	a 5	b 5	c 4
545	a 6	b 5	c 4
546	a 7	b 5	c 4
547	a 8	b 5	c 4
548	a 9	b 5	c 4
549	a 10	b 5	c 4
550	a 11	b 5	c 4
551	a 1	b 6	c 4

09857687.060801

No.	Cp	Bridge	Flu
552	a 2	b 6	c 4
553	a 3	b 6	c 4
554	a 4	b 6	c 4
555	a 5	b 6	c 4
556	a 6	b 6	c 4
557	a 7	b 6	c 4
558	a 8	b 6	c 4
559	a 9	b 6	c 4
560	a 10	b 6	c 4
561	a 11	b 6	c 4
562	a 1	b 7	c 4
563	a 2	b 7	c 4
564	a 3	b 7	c 4
565	a 4	b 7	c 4
566	a 5	b 7	c 4
567	a 6	b 7	c 4
568	a 7	b 7	c 4
569	a 8	b 7	c 4
570	a 9	b 7	c 4
571	a 10	b 7	c 4
572	a 11	b 7	c 4
573	a 1	b 8	c 4
574	a 2	b 8	c 4
575	a 3	b 8	c 4
576	a 4	b 8	c 4
577	a 5	b 8	c 4
578	a 6	b 8	c 4
579	a 7	b 8	c 4
580	a 8	b 8	c 4
581	a 9	b 8	c 4
582	a 10	b 8	c 4
583	a 11	b 8	c 4
584	a 1	b 9	c 4
585	a 2	b 9	c 4
586	a 3	b 9	c 4
587	a 4	b 9	c 4
588	a 5	b 9	c 4
589	a 6	b 9	c 4
590	a 7	b 9	c 4
591	a 8	b 9	c 4
592	a 9	b 9	c 4
593	a 10	b 9	c 4
594	a 11	b 9	c 4
595	a 1	b 10	c 4
596	a 2	b 10	c 4
597	a 3	b 10	c 4

09857637-06001

No.	Cp	Bridge	Flu
598	a 4	b 10	c 4
599	a 5	b 10	c 4
600	a 6	b 10	c 4
601	a 7	b 10	c 4
602	a 8	b 10	c 4
603	a 9	b 10	c 4
604	a 10	b 10	c 4
605	a 11	b 10	c 4
606	a 1	b 11	c 4
607	a 2	b 11	c 4
608	a 3	b 11	c 4
609	a 4	b 11	c 4
610	a 5	b 11	c 4
611	a 6	b 11	c 4
612	a 7	b 11	c 4
613	a 8	b 11	c 4
614	a 9	b 11	c 4
615	a 10	b 11	c 4
616	a 11	b 11	c 4
617	a 1	b 12	c 4
618	a 2	b 12	c 4
619	a 3	b 12	c 4
620	a 4	b 12	c 4
621	a 5	b 12	c 4
622	a 6	b 12	c 4
623	a 7	b 12	c 4
624	a 8	b 12	c 4
625	a 9	b 12	c 4
626	a 10	b 12	c 4
627	a 11	b 12	c 4
628	a 1	b 13	c 4
629	a 2	b 13	c 4
630	a 3	b 13	c 4
631	a 4	b 13	c 4
632	a 5	b 13	c 4
633	a 6	b 13	c 4
634	a 7	b 13	c 4
635	a 8	b 13	c 4
636	a 9	b 13	c 4
637	a 10	b 13	c 4
638	a 11	b 13	c 4
639	a 1	b 14	c 4
640	a 2	b 14	c 4
641	a 3	b 14	c 4
642	a 4	b 14	c 4
643	a 5	b 14	c 4

09857687 060801

No.	Cp	Bridge	Flu
644	a 6	b 14	c 4
645	a 7	b 14	c 4
646	a 8	b 14	c 4
647	a 9	b 14	c 4
648	a 10	b 14	c 4
649	a 11	b 14	c 4
650	a 1	b 15	c 4
651	a 2	b 15	c 4
652	a 3	b 15	c 4
653	a 4	b 15	c 4
654	a 5	b 15	c 4
655	a 6	b 15	c 4
656	a 7	b 15	c 4
657	a 8	b 15	c 4
658	a 9	b 15	c 4
659	a 10	b 15	c 4
660	a 11	b 15	c 4
661	a 1	b 1	c 5
662	a 2	b 1	c 5
663	a 3	b 1	c 5
664	a 4	b 1	c 5
665	a 5	b 1	c 5
666	a 6	b 1	c 5
667	a 7	b 1	c 5
668	a 8	b 1	c 5
669	a 9	b 1	c 5
670	a 10	b 1	c 5
671	a 11	b 1	c 5
672	a 1	b 2	c 5
673	a 2	b 2	c 5
674	a 3	b 2	c 5
675	a 4	b 2	c 5
676	a 5	b 2	c 5
677	a 6	b 2	c 5
678	a 7	b 2	c 5
679	a 8	b 2	c 5
680	a 9	b 2	c 5
681	a 10	b 2	c 5
682	a 11	b 2	c 5
683	a 1	b 3	c 5
684	a 2	b 3	c 5
685	a 3	b 3	c 5
686	a 4	b 3	c 5
687	a 5	b 3	c 5
688	a 6	b 3	c 5
689	a 7	b 3	c 5

09857687.060801

No.	Cp	Bridge	Flu
690	a 8	b 3	c 5
691	a 9	b 3	c 5
692	a 10	b 3	c 5
693	a 11	b 3	c 5
694	a 1	b 4	c 5
695	a 2	b 4	c 5
696	a 3	b 4	c 5
697	a 4	b 4	c 5
698	a 5	b 4	c 5
699	a 6	b 4	c 5
700	a 7	b 4	c 5
701	a 8	b 4	c 5
702	a 9	b 4	c 5
703	a 10	b 4	c 5
704	a 11	b 4	c 5
705	a 1	b 5	c 5
706	a 2	b 5	c 5
707	a 3	b 5	c 5
708	a 4	b 5	c 5
709	a 5	b 5	c 5
710	a 6	b 5	c 5
711	a 7	b 5	c 5
712	a 8	b 5	c 5
713	a 9	b 5	c 5
714	a 10	b 5	c 5
715	a 11	b 5	c 5
716	a 1	b 6	c 5
717	a 2	b 6	c 5
718	a 3	b 6	c 5
719	a 4	b 6	c 5
720	a 5	b 6	c 5
721	a 6	b 6	c 5
722	a 7	b 6	c 5
723	a 8	b 6	c 5
724	a 9	b 6	c 5
725	a 10	b 6	c 5
726	a 11	b 6	c 5
727	a 1	b 7	c 5
728	a 2	b 7	c 5
729	a 3	b 7	c 5
730	a 4	b 7	c 5
731	a 5	b 7	c 5
732	a 6	b 7	c 5
733	a 7	b 7	c 5
734	a 8	b 7	c 5
735	a 9	b 7	c 5

09857687 060801

No.	Cp	Bridge	Flu
736	a 10	b 7	c 5
737	a 11	b 7	c 5
738	a 1	b 8	c 5
739	a 2	b 8	c 5
740	a 3	b 8	c 5
741	a 4	b 8	c 5
742	a 5	b 8	c 5
743	a 6	b 8	c 5
744	a 7	b 8	c 5
745	a 8	b 8	c 5
746	a 9	b 8	c 5
747	a 10	b 8	c 5
748	a 11	b 8	c 5
749	a 1	b 9	c 5
750	a 2	b 9	c 5
751	a 3	b 9	c 5
752	a 4	b 9	c 5
753	a 5	b 9	c 5
754	a 6	b 9	c 5
755	a 7	b 9	c 5
756	a 8	b 9	c 5
757	a 9	b 9	c 5
758	a 10	b 9	c 5
759	a 11	b 9	c 5
760	a 1	b 10	c 5
761	a 2	b 10	c 5
762	a 3	b 10	c 5
763	a 4	b 10	c 5
764	a 5	b 10	c 5
765	a 6	b 10	c 5
766	a 7	b 10	c 5
767	a 8	b 10	c 5
768	a 9	b 10	c 5
769	a 10	b 10	c 5
770	a 11	b 10	c 5
771	a 1	b 11	c 5
772	a 2	b 11	c 5
773	a 3	b 11	c 5
774	a 4	b 11	c 5
775	a 5	b 11	c 5
776	a 6	b 11	c 5
777	a 7	b 11	c 5
778	a 8	b 11	c 5
779	a 9	b 11	c 5
780	a 10	b 11	c 5
781	a 11	b 11	c 5

09857687-060801

No.	Cp	Bridge	Flu
782	a 1	b 12	c 5
783	a 2	b 12	c 5
784	a 3	b 12	c 5
785	a 4	b 12	c 5
786	a 5	b 12	c 5
787	a 6	b 12	c 5
788	a 7	b 12	c 5
789	a 8	b 12	c 5
790	a 9	b 12	c 5
791	a 10	b 12	c 5
792	a 11	b 12	c 5
793	a 1	b 13	c 5
794	a 2	b 13	c 5
795	a 3	b 13	c 5
796	a 4	b 13	c 5
797	a 5	b 13	c 5
798	a 6	b 13	c 5
799	a 7	b 13	c 5
800	a 8	b 13	c 5
801	a 9	b 13	c 5
802	a 10	b 13	c 5
803	a 11	b 13	c 5
804	a 1	b 14	c 5
805	a 2	b 14	c 5
806	a 3	b 14	c 5
807	a 4	b 14	c 5
808	a 5	b 14	c 5
809	a 6	b 14	c 5
810	a 7	b 14	c 5
811	a 8	b 14	c 5
812	a 9	b 14	c 5
813	a 10	b 14	c 5
814	a 11	b 14	c 5
815	a 1	b 15	c 5
816	a 2	b 15	c 5
817	a 3	b 15	c 5
818	a 4	b 15	c 5
819	a 5	b 15	c 5
820	a 6	b 15	c 5
821	a 7	b 15	c 5
822	a 8	b 15	c 5
823	a 9	b 15	c 5
824	a 10	b 15	c 5
825	a 11	b 15	c 5
826	a 1	b 1	c 6
827	a 2	b 1	c 6

09857687 060801

No.	Cp	Bridge	Flu
828	a 3	b 1	c 6
829	a 4	b 1	c 6
830	a 5	b 1	c 6
831	a 6	b 1	c 6
832	a 7	b 1	c 6
833	a 8	b 1	c 6
834	a 9	b 1	c 6
835	a 10	b 1	c 6
836	a 11	b 1	c 6
837	a 1	b 2	c 6
838	a 2	b 2	c 6
839	a 3	b 2	c 6
840	a 4	b 2	c 6
841	a 5	b 2	c 6
842	a 6	b 2	c 6
843	a 7	b 2	c 6
844	a 8	b 2	c 6
845	a 9	b 2	c 6
846	a 10	b 2	c 6
847	a 11	b 2	c 6
848	a 1	b 3	c 6
849	a 2	b 3	c 6
850	a 3	b 3	c 6
851	a 4	b 3	c 6
852	a 5	b 3	c 6
853	a 6	b 3	c 6
854	a 7	b 3	c 6
855	a 8	b 3	c 6
856	a 9	b 3	c 6
857	a 10	b 3	c 6
858	a 11	b 3	c 6
859	a 1	b 4	c 6
860	a 2	b 4	c 6
861	a 3	b 4	c 6
862	a 4	b 4	c 6
863	a 5	b 4	c 6
864	a 6	b 4	c 6
865	a 7	b 4	c 6
866	a 8	b 4	c 6
867	a 9	b 4	c 6
868	a 10	b 4	c 6
869	a 11	b 4	c 6
870	a 1	b 5	c 6
871	a 2	b 5	c 6
872	a 3	b 5	c 6
873	a 4	b 5	c 6

09257687 060801

No.	Cp	Bridge	Flu
874	a 5	b 5	c 6
875	a 6	b 5	c 6
876	a 7	b 5	c 6
877	a 8	b 5	c 6
878	a 9	b 5	c 6
879	a 10	b 5	c 6
880	a 11	b 5	c 6
881	a 1	b 6	c 6
882	a 2	b 6	c 6
883	a 3	b 6	c 6
884	a 4	b 6	c 6
885	a 5	b 6	c 6
886	a 6	b 6	c 6
887	a 7	b 6	c 6
888	a 8	b 6	c 6
889	a 9	b 6	c 6
890	a 10	b 6	c 6
891	a 11	b 6	c 6
892	a 1	b 7	c 6
893	a 2	b 7	c 6
894	a 3	b 7	c 6
895	a 4	b 7	c 6
896	a 5	b 7	c 6
897	a 6	b 7	c 6
898	a 7	b 7	c 6
899	a 8	b 7	c 6
900	a 9	b 7	c 6
901	a 10	b 7	c 6
902	a 11	b 7	c 6
903	a 1	b 8	c 6
904	a 2	b 8	c 6
905	a 3	b 8	c 6
906	a 4	b 8	c 6
907	a 5	b 8	c 6
908	a 6	b 8	c 6
909	a 7	b 8	c 6
910	a 8	b 8	c 6
911	a 9	b 8	c 6
912	a 10	b 8	c 6
913	a 11	b 8	c 6
914	a 1	b 9	c 6
915	a 2	b 9	c 6
916	a 3	b 9	c 6
917	a 4	b 9	c 6
918	a 5	b 9	c 6
919	a 6	b 9	c 6

09857687, 060301

No.	Cp	Bridge	Flu
920	a 7	b 9	c 6
921	a 8	b 9	c 6
922	a 9	b 9	c 6
923	a 10	b 9	c 6
924	a 11	b 9	c 6
925	a 1	b 10	c 6
926	a 2	b 10	c 6
927	a 3	b 10	c 6
928	a 4	b 10	c 6
929	a 5	b 10	c 6
930	a 6	b 10	c 6
931	a 7	b 10	c 6
932	a 8	b 10	c 6
933	a 9	b 10	c 6
934	a 10	b 10	c 6
935	a 11	b 10	c 6
936	a 1	b 11	c 6
937	a 2	b 11	c 6
938	a 3	b 11	c 6
939	a 4	b 11	c 6
940	a 5	b 11	c 6
941	a 6	b 11	c 6
942	a 7	b 11	c 6
943	a 8	b 11	c 6
944	a 9	b 11	c 6
945	a 10	b 11	c 6
946	a 11	b 11	c 6
947	a 1	b 12	c 6
948	a 2	b 12	c 6
949	a 3	b 12	c 6
950	a 4	b 12	c 6
951	a 5	b 12	c 6
952	a 6	b 12	c 6
953	a 7	b 12	c 6
954	a 8	b 12	c 6
955	a 9	b 12	c 6
956	a 10	b 12	c 6
957	a 11	b 12	c 6
958	a 1	b 13	c 6
959	a 2	b 13	c 6
960	a 3	b 13	c 6
961	a 4	b 13	c 6
962	a 5	b 13	c 6
963	a 6	b 13	c 6
964	a 7	b 13	c 6
965	a 8	b 13	c 6

09857687.060801

No.	Cp	Bridge	Flu
966	a 9	b 13	c 6
967	a 10	b 13	c 6
968	a 11	b 13	c 6
969	a 1	b 14	c 6
970	a 2	b 14	c 6
971	a 3	b 14	c 6
972	a 4	b 14	c 6
973	a 5	b 14	c 6
974	a 6	b 14	c 6
975	a 7	b 14	c 6
976	a 8	b 14	c 6
977	a 9	b 14	c 6
978	a 10	b 14	c 6
979	a 11	b 14	c 6
980	a 1	b 15	c 6
981	a 2	b 15	c 6
982	a 3	b 15	c 6
983	a 4	b 15	c 6
984	a 5	b 15	c 6
985	a 6	b 15	c 6
986	a 7	b 15	c 6
987	a 8	b 15	c 6
988	a 9	b 15	c 6
989	a 10	b 15	c 6
990	a 11	b 15	c 6
991	a 1	b 1	c 7
992	a 2	b 1	c 7
993	a 3	b 1	c 7
994	a 4	b 1	c 7
995	a 5	b 1	c 7
996	a 6	b 1	c 7
997	a 7	b 1	c 7
998	a 8	b 1	c 7
999	a 9	b 1	c 7
1000	a 10	b 1	c 7
1001	a 11	b 1	c 7
1002	a 1	b 2	c 7
1003	a 2	b 2	c 7
1004	a 3	b 2	c 7
1005	a 4	b 2	c 7
1006	a 5	b 2	c 7
1007	a 6	b 2	c 7
1008	a 7	b 2	c 7
1009	a 8	b 2	c 7
1010	a 9	b 2	c 7
1011	a 10	b 2	c 7

09857697-060801

No.	Cp	Bridge	Flu
1012	a 11	b 2	c 7
1013	a 1	b 3	c 7
1014	a 2	b 3	c 7
1015	a 3	b 3	c 7
1016	a 4	b 3	c 7
1017	a 5	b 3	c 7
1018	a 6	b 3	c 7
1019	a 7	b 3	c 7
1020	a 8	b 3	c 7
1021	a 9	b 3	c 7
1022	a 10	b 3	c 7
1023	a 11	b 3	c 7
1024	a 1	b 4	c 7
1025	a 2	b 4	c 7
1026	a 3	b 4	c 7
1027	a 4	b 4	c 7
1028	a 5	b 4	c 7
1029	a 6	b 4	c 7
1030	a 7	b 4	c 7
1031	a 8	b 4	c 7
1032	a 9	b 4	c 7
1033	a 10	b 4	c 7
1034	a 11	b 4	c 7
1035	a 1	b 5	c 7
1036	a 2	b 5	c 7
1037	a 3	b 5	c 7
1038	a 4	b 5	c 7
1039	a 5	b 5	c 7
1040	a 6	b 5	c 7
1041	a 7	b 5	c 7
1042	a 8	b 5	c 7
1043	a 9	b 5	c 7
1044	a 10	b 5	c 7
1045	a 11	b 5	c 7
1046	a 1	b 6	c 7
1047	a 2	b 6	c 7
1048	a 3	b 6	c 7
1049	a 4	b 6	c 7
1050	a 5	b 6	c 7
1051	a 6	b 6	c 7
1052	a 7	b 6	c 7
1053	a 8	b 6	c 7
1054	a 9	b 6	c 7
1055	a 10	b 6	c 7
1056	a 11	b 6	c 7
1057	a 1	b 7	c 7

09857687.060801

No.	Cp	Bridge	Flu
1058	a 2	b 7	c 7
1059	a 3	b 7	c 7
1060	a 4	b 7	c 7
1061	a 5	b 7	c 7
1062	a 6	b 7	c 7
1063	a 7	b 7	c 7
1064	a 8	b 7	c 7
1065	a 9	b 7	c 7
1066	a 10	b 7	c 7
1067	a 11	b 7	c 7
1068	a 1	b 8	c 7
1069	a 2	b 8	c 7
1070	a 3	b 8	c 7
1071	a 4	b 8	c 7
1072	a 5	b 8	c 7
1073	a 6	b 8	c 7
1074	a 7	b 8	c 7
1075	a 8	b 8	c 7
1076	a 9	b 8	c 7
1077	a 10	b 8	c 7
1078	a 11	b 8	c 7
1079	a 1	b 9	c 7
1080	a 2	b 9	c 7
1081	a 3	b 9	c 7
1082	a 4	b 9	c 7
1083	a 5	b 9	c 7
1084	a 6	b 9	c 7
1085	a 7	b 9	c 7
1086	a 8	b 9	c 7
1087	a 9	b 9	c 7
1088	a 10	b 9	c 7
1089	a 11	b 9	c 7
1090	a 1	b 10	c 7
1091	a 2	b 10	c 7
1092	a 3	b 10	c 7
1093	a 4	b 10	c 7
1094	a 5	b 10	c 7
1095	a 6	b 10	c 7
1096	a 7	b 10	c 7
1097	a 8	b 10	c 7
1098	a 9	b 10	c 7
1099	a 10	b 10	c 7
1100	a 11	b 10	c 7
1101	a 1	b 11	c 7
1102	a 2	b 11	c 7
1103	a 3	b 11	c 7

09857687.060801

No.	Cp	Bridge	Flu
1104	a 4	b 11	c 7
1105	a 5	b 11	c 7
1106	a 6	b 11	c 7
1107	a 7	b 11	c 7
1108	a 8	b 11	c 7
1109	a 9	b 11	c 7
1110	a 10	b 11	c 7
1111	a 11	b 11	c 7
1112	a 1	b 12	c 7
1113	a 2	b 12	c 7
1114	a 3	b 12	c 7
1115	a 4	b 12	c 7
1116	a 5	b 12	c 7
1117	a 6	b 12	c 7
1118	a 7	b 12	c 7
1119	a 8	b 12	c 7
1120	a 9	b 12	c 7
1121	a 10	b 12	c 7
1122	a 11	b 12	c 7
1123	a 1	b 13	c 7
1124	a 2	b 13	c 7
1125	a 3	b 13	c 7
1126	a 4	b 13	c 7
1127	a 5	b 13	c 7
1128	a 6	b 13	c 7
1129	a 7	b 13	c 7
1130	a 8	b 13	c 7
1131	a 9	b 13	c 7
1132	a 10	b 13	c 7
1133	a 11	b 13	c 7
1134	a 1	b 14	c 7
1135	a 2	b 14	c 7
1136	a 3	b 14	c 7
1137	a 4	b 14	c 7
1138	a 5	b 14	c 7
1139	a 6	b 14	c 7
1140	a 7	b 14	c 7
1141	a 8	b 14	c 7
1142	a 9	b 14	c 7
1143	a 10	b 14	c 7
1144	a 11	b 14	c 7
1145	a 1	b 15	c 7
1146	a 2	b 15	c 7
1147	a 3	b 15	c 7
1148	a 4	b 15	c 7
1149	a 5	b 15	c 7


09857687.060801

No.	Cp	Bridge	Flu
1150	a 6	b 15	c 7
1151	a 7	b 15	c 7
1152	a 8	b 15	c 7
1153	a 9	b 15	c 7
1154	a 10	b 15	c 7
1155	a 11	b 15	c 7

T08090"/8975860

According to the above table, the ligand structure of No. 331 means a combination of a1-b1-c3, so that when the metal part MQ_j is $ZrCl_2$, the following

5 metallocene compound is exemplified.



10

Specific examples of MQ_j include $ZrCl_2$, $ZrBr_2$, $ZrMe_2$, $Zr(OTs)_2$, $Zr(OMs)_2$, $Zr(OTf)_2$, $TiCl_2$, $TiBr_2$, $TiMe_2$, $Ti(OTs)_2$, $Ti(OMs)_2$, $Ti(OTf)_2$, $HfCl_2$, $HfBr_2$, $HfMe_2$, $Hf(OTs)_2$, $Hf(OMs)_2$ and $Hf(OTf)_2$.

15

Preferred examples of the metallocene compounds represented by the formula (1b) or (2b) according to the invention include:

20 a metallocene compound of the formula (1b) wherein R^{21} , R^{13} and R^{14} are each methyl, R^{22} is tert-butyl, R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , R^{11} and R^{12} are each hydrogen, M is zirconium, Y is carbon, Q is chlorine, and j is 2;

09857687-060801

a metallocene compound of the formula (1b) wherein R²¹, R¹³ and R¹⁴ are each methyl, R²² is tert-butyl, R⁵, R⁶, R⁸, R⁹, R¹¹ and R¹² are each hydrogen, R⁷ and R¹⁰ are each tert-butyl, M is zirconium, Y is carbon,

5 Q is chlorine, and j is 2;

a metallocene compound of the formula (1b) wherein R²¹, R¹³ and R¹⁴ are each methyl, R²² is tert-butyl, R⁵, R⁷, R⁸, R⁹, R¹⁰ and R¹² are each hydrogen, R⁶ and R¹¹ are each tert-butyl, M is zirconium, Y is carbon,

10 Q is chlorine, and j is 2;

a metallocene compound of the formula (2b) wherein R²¹ is methyl, R²² is tert-butyl, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, R¹¹ and R¹² are each hydrogen, M is zirconium, Y is carbon, Q is chlorine, j is 2, and A is -(CH₂)₅-;

15 and

a metallocene compound of the formula (2b) wherein R²¹ is methyl, R²² is tert-butyl, R⁵, R⁶, R⁸, R⁹, R¹¹ and R¹² are each hydrogen, R⁷ and R¹⁰ are each tert-butyl, M is zirconium, Y is carbon, Q is chlorine, j

20 is 2, and A is -(CH₂)₅-.

There is no specific limitation on the process for preparing the metallocene compound represented by the formula (1b) or (2b), and the compound can be prepared by, for example, the following process.

09867687-060801

In the process for preparing the metallocene compound according to the invention, the metallocene compound represented by the formula (1b) or (2b) is selectively prepared so as not to include an isomeric compound wherein R^1 and R^2 are adjacent to each other. To attain this purpose, it is necessary to selectively prepare the ligand precursor, etc. of the metallocene compound. Such a process is described with reference to the following example.




10 Process for preparing metallocene compound

The ligand precursor (7) used as starting material for preparing the metallocene compound represented by the formula (1b) can be selectively prepared through the following step (H) or (I).

15




0957637.000001

[H]



09857687-060801

[1]




09857687-060801


In the compounds shown in the above steps (H) and (I), R^5 to R^{14} , R^{21} , R^{22} and Y have the same meanings as those of R^5 to R^{14} , R^{21} , R^{22} and Y in the formula (1b), respectively, L is an alkali metal, and Z^1 and Z^2 may be the same or different and are each a halogen or an anionic ligand.

- With regard to the cyclopentadiene (19b), the precursor compound (23b) and the ligand precursor (7b), presence of isomers different in only the position of a double bond in the cyclopentadienyl ring can be thought, but only one example is shown. Each of them may be another isomer different in only the position of a double bond in the cyclopentadienyl ring or a mixture thereof.
- By the preparation of a precursor compound through the step (H) or (I), the precursor compound (13b) can be prepared without producing the following isomeric compound (15b) or (16b), and the ligand precursor (7b) can be prepared without producing the following isomeric compound (9b) or (10b).

09857687-060801




... (15b)




... (16b)

wherein R^{21} , R^{22} , R^{13} , R^{14} and Y have the same meanings as those of R^{21} , R^{22} , R^{13} , R^{14} and Y in the formula (1b), respectively.



... (9b)




... (10b)

wherein R^{21} , R^{22} , R^5 to R^{14} , and Y have the same meanings as those of R^{21} , R^{22} , R^5 to R^{14} , and Y in the formula (1b), respectively, and the cyclopentadienyl group may be another isomer different in only the




position of a double bond in the cyclopentadienyl ring or a mixture thereof.

The ligand precursor (8b) of the metallocene compound represented by the formula (2b) can be
5 selectively prepared through the following step (J) or (K).

09557667, 060001



[K]




- In the compounds shown in the above steps (J) and (K), R^5 to R^{14} , R^{21} , R^{22} , Y and A have the same meanings as those of R^5 to R^{14} , R^{21} , R^{22} , Y and A in the formula (2b), respectively, L is an alkali metal, 5 and Z^1 and Z^2 may be the same or different and are each a halogen or an anionic ligand.


- With regard to the cyclopentadiene (19b), the precursor compound (30b) and the ligand precursor (8b), presence of isomers different in only the position of 10 a double bond in the cyclopentadienyl ring can be thought, but only one example is shown. Each of them may be another isomer different in only the position of a double bond in the cyclopentadienyl ring or a mixture thereof.

- 15 By the preparation of a precursor compound through the step (J) or (K), the precursor compound (14b) can be prepared without producing the following isomeric compound (17b) or (18b), and the ligand precursor (8b) can be prepared without producing the following 20 isomeric compound (11b) or (12b).

0357687-060801




... (17b)




... (18b)

wherein R^{21} , R^{22} , Y and A have the same meanings as those of R^{21} , R^{22} , Y and A in the formula (2b), respectively.



... (11b)




... (12b)

- wherein R^{21} , R^{22} , R^5 to R^{12} , A and Y have the same meanings as those of R^{21} , R^{22} , R^5 to R^{12} , A and Y in the formula (2b), respectively, and the cyclopentadienyl group may be another isomer different in only the position of a double bond in the cyclopentadienyl ring or a mixture thereof.

The cyclopentadiene (19) that is a precursor common to the metallocene compounds represented by the formulas (1b) and (2b) can be selectively prepared through, for example, the following step (L).

5

[L]




10 In the compounds shown in the step (L), each of R²¹ and R²² has the same meaning as described in the formula (1b) or (2b), M¹ is an alkali metal or an alkaline earth metal, Z³ is the same as R²² or is a halogen or an anionic ligand, and e is a valence of M¹.

15 As another step for preparing the cyclopentadiene (19b), the following step (M) or (N) is also available. In the step (M) or (N), however, an isomer (20b) wherein R²¹ and R²² are adjacent to each other is occasionally produced as a by-product, and therefore,


20 the step (M) or (N) is employable only when the isomer (20b) is not produced owing to combination of R²¹ and R²², reaction conditions, etc.

[M]



5

[N]




10

In the compounds shown in the above steps (M) and (N), R^{21} and R^{22} have the same meanings as those of R^{21} and R^{22} in the formula (1b) or (2b), respectively, L is an alkali metal, and Z^1 is a halogen or an

15 anionic ligand.

When R^{22} is a substituent group represented by $\text{CR}^{15}\text{R}^{16}\text{R}^{17}$, the cyclopentadiene (19b) can be prepared also through the following step (O).

20 [O]



25

09657687, 060801

[illegible]

10

15

... (20b)

20

wherein R²¹ and R²² have the same meanings as those of R²¹ and R²² in the formula (1b) or (2b), respectively, and the cyclopentadienyl group may be another isomer different in only the position of a double bond in the cyclopentadienyl ring or a mixture thereof.

0583193 : 000001

5

In the first place, the ligand precursor

10

15

Examples of the alkali metals and the alkali metal hydrides used for the reaction include the same ones as used for preparing the metallocene compound from the ligand precursor represented by the formula (5) or (6).

20

In the next place, the di-alkali metal salt is allowed to react, in an organic solvent, with a compound represented by the following formula (43b):



- 5 wherein M is a metal selected from Group 4 of the periodic table, each Z may be the same or different and is selected from a halogen, an anionic ligand and a neutral ligand capable of coordination by a lone pair, and k is an integer of 3 to 6.

- 10 Thus, the metallocene compound represented by the formula (1b) or (2b) can be synthesized.

Preferred examples of the compounds represented by the formula (43b) include trivalent or tetravalent titanium fluoride, chloride, bromide or iodide;

- 15 tetravalent zirconium fluoride, chloride, bromide or iodide; tetravalent hafnium fluoride, chloride, bromide or iodide; and complexes of these compounds with ethers such as THF, diethyl ether, dioxane and 1,2-dimethoxyethane.

- 20 Examples of the organic solvents used include the same ones as previously described.

The reaction of the di-alkali metal salt with the compound represented by the formula (43b) is preferably an equimolar reaction, and can be carried

09857687-050801

out in the aforesaid organic solvent at a reaction temperature of -80 to 200°C.

The metallocene compound obtained by the reaction can be isolated and purified by, for example,

5 extraction, recrystallization or sublimation.

The metallocene compound prepared by the process of the invention contains no unnecessary isomer, so that when it is used as, for example, an olefin polymerization catalyst, obtainable are favorable
10 results such that an atactic polymer is hardly produced.

Olefin polymerization catalyst

A preferred embodiment of use of the metallocene compound of the invention as an olefin polymerization
15 catalyst is described below.

When the metallocene compound of the invention is used as an olefin polymerization catalyst, the catalyst comprises:

- (A) the metallocene compound,
- 20 (B) at least one compound selected from:
 - (B-1) an organometallic compound,
 - (B-2) an organoaluminum oxy-compound, and
 - (B-3) a compound which reacts with the metallocene compound (A) to form an ion pair,
- 25 and optionally,

0957687-060801


(C) a particle carrier.

The components (B) and (C) for forming the catalyst are described below.

5 (B-1) Organometallic compound

Examples of the organometallic compounds (B-1) used in the preparation of the ethylene/ α -olefin copolymer include the below-described organometallic compounds containing metals of Group 1, Group 2, Group 10 12 and Group 13 of the periodic table.

(B-1a) Organoaluminum compound represented by the following formula:



wherein R^a and R^b may be the same or different and are 15 each a hydrocarbon group of 1 to 15 carbon atoms, preferably 1 to 4 carbon atoms; X is a halogen atom; and m, n, p and q are numbers satisfying the conditions of $0 < m \leq 3$, $0 \leq n < 3$, $0 \leq p < 3$, $0 \leq q < 3$ and $m+n+p+q = 3$.

20 (B-1b) Alkyl complex compound comprising a metal of Group 1 of the periodic table and aluminum, which is represented by the following formula:



09257587.060801

wherein M^2 is Li, Na or K; and R^a is a hydrocarbon group of 1 to 15 carbon atoms, preferably 1 to 4 carbon atoms.

- (B-1c) Dialkyl compound containing a metal of
- 5 Group 2 or Group 12 of the periodic table, which is represented by the following formula:



- wherein R^a and R^b may be the same or different and are each a hydrocarbon group of 1 to 15 carbon atoms,
- 10 preferably 1 to 4 carbon atoms; and M^3 is Mg, Zn or Cd.


Examples of the organoaluminum compounds (B-1a) include:

an organoaluminum compound represented by the following formula:

- 15 $R^a_mAl(OR^b)_{3-m}$

wherein R^a and R^b may be the same or different and are each a hydrocarbon group of 1 to 15 carbon atoms, preferably 1 to 4 carbon atoms, and m is preferably a number satisfying the condition of $1.5 \leq m \leq 3$;

- 20 an organoaluminum compound represented by the following formula:




wherein R^a is a hydrocarbon group of 1 to 15 carbon atoms, preferably 1 to 4 carbon atoms, X is a halogen

00857587.060801

atom, and m is preferably a number satisfying the condition of $0 < m < 3$;


an organoaluminum compound represented by the following formula:



wherein R^a is a hydrocarbon group of 1 to 15 carbon atoms, preferably 1 to 4 carbon atoms, and m is preferably a number satisfying the condition of $2 \leq m < 3$;

and

10 an organoaluminum compound represented by the following formula:



wherein R^a and R^b may be the same or different and are each a hydrocarbon group of 1 to 15 carbon atoms,

15 preferably 1 to 4 carbon atoms, X is a halogen atom, and m, n and q are numbers satisfying the conditions of $0 < m \leq 3$, $0 \leq n < 3$, $0 \leq q < 3$ and $m+n+q = 3$.

Specific examples of the organoaluminum compounds (B-1a) include:

20 tri-n-alkylaluminums, such as trimethylaluminum, triethylaluminum, tri-n-butylaluminum, tripropylaluminum, tripentylaluminum, trihexylaluminum, trioctylaluminum and tridecylaluminum;

branched-chain trialkylaluminums, such as

25 triisopropylaluminum, triisobutylaluminum,

09857687.060801

tri-sec-butylaluminum, tri-tert-butylaluminum,
tri-2-methylbutylaluminum, tri-3-methylbutylaluminum,
tri-2-methylpentylaluminum, tri-3-methylpentylaluminum,
tri-4-methylpentylaluminum, tri-2-methylhexylaluminum,

- 5 tri-3-methylhexylaluminum and tri-2-ethylhexylaluminum;

tricycloalkylaluminums, such as
tricyclohexylaluminum and tricyclooctylaluminum;

- triarylaluminums, such as triphenylaluminum and
10 tritolylaluminum;

dialkylaluminum hydrides, such as
diisopropylaluminum hydride and diisobutylaluminum
hydride;

- alkenylaluminums represented by the formula (i-
15 $C_4H_9)_xAl_y(C_5H_{10})_z$ (wherein x, y and z are each a
positive number, and $z \geq 2x$) or the like, such as
isoprenylaluminum;

alkylaluminum alkoxides, such as isobutylaluminum
methoxide, isobutylaluminum ethoxide and

- 20 isobutylaluminum isopropoxide;

dialkylaluminum alkoxides, such as
dimethylaluminum methoxide, diethylaluminum ethoxide
and dibutylaluminum butoxide;

09657687-060801

alkylaluminum sesquialkoxides, such as ethylaluminum sesquiethoxide and butylaluminum sesquibutoxide;

- 5 partially alkoxyated alkylaluminums having an average composition, which are represented by $R^a_2.5Al(OR^b)_0.5$ or the like;

- alkylaluminum aryloxides, such as diethylaluminum phenoxide, diethylaluminum(2,6-di-t-butyl-4-methylphenoxide), ethylaluminumbis(2,6-di-t-butyl-4-methylphenoxide), diisobutylaluminum(2,6-di-t-butyl-4-methylphenoxide) and isobutylaluminumbis(2,6-di-t-butyl-4-methylphenoxide);
- 10

- dialkylaluminum halides, such as dimethylaluminum chloride, diethylaluminum chloride, dibutylaluminum chloride, diethylaluminum bromide and diisobutylaluminum chloride;
- 15

- alkylaluminum sesquihalides, such as ethylaluminum sesquichloride, butylaluminum sesquichloride and ethylaluminum sesquibromide,
- 20 partially halogenated alkylaluminums, e.g., alkylaluminum dihalides, such as ethylaluminum dichloride, propylaluminum dichloride and butylaluminum dibromide;

- dialkylaluminum hydrides, such as diethylaluminum hydride and dibutylaluminum hydride;
- 25

00657587 050001

partially hydrogenated alkylaluminums, e.g., alkylaluminum dihydrides, such as ethylaluminum dihydride and propylaluminum dihydride; and

partially alkoxyated and halogenated

- 5 alkylaluminums, such as ethylaluminum ethoxychloride, butylaluminum butoxychloride and ethylaluminum ethoxybromide.

Also employable are compounds analogous to the organoaluminum compound (B-1a). For example, there can

- 10 be mentioned organoaluminum compounds wherein two or more aluminum compounds are combined through a nitrogen atom, such as $(C_2H_5)_2AlN(C_2H_5)Al(C_2H_5)_2$.

Examples of the compounds (B-1b) include $LiAl(C_2H_5)_4$ and $LiAl(C_7H_{15})_4$.

- 15 Other compounds, such as methyl lithium, ethyllithium, propyllithium, butyllithium, methylmagnesium bromide, methylmagnesium chloride, ethylmagnesium bromide, ethylmagnesium chloride, propylmagnesium bromide, propylmagnesium chloride, 20 butylmagnesium bromide, butylmagnesium chloride, dimethylmagnesium, diethylmagnesium, dibutylmagnesium and butylethylmagnesium, are also employable as the organometallic compounds (B-1).

Combinations of compounds capable of forming the

- 25 above-mentioned organoaluminum compounds in the

09257687-060801

polymerization system, e.g., a combination of halogenated aluminum and alkylolithium and a combination of halogenated aluminum and alkylmagnesium, are also employable.

- 5 Of the organometallic compounds (B-1), the organoaluminum compounds are preferable.

The organometallic compounds (B-1) mentioned above are used singly or in combination of two or more kinds.

(B-2) Organoaluminum oxy-compound

- 10 The organoaluminum oxy-compound (B-2) used in the present invention may be conventional aluminoxane or such a benzene-insoluble organoaluminum oxy-compound as exemplified in Japanese Patent Laid-Open Publication No. 78687/1990.

- 15 The conventional aluminoxane can be prepared by, for example, the following processes, and is generally obtained as a hydrocarbon solvent solution.

- (1) An organoaluminum compound such as trialkylaluminum is added to a hydrocarbon medium
- 20 suspension of a compound containing adsorption water or a salt containing water of crystallization, e.g., magnesium chloride hydrate, copper sulfate hydrate, aluminum sulfate hydrate, nickel sulfate hydrate or cerous chloride hydrate, to allow the organoaluminum

09857687.060001

compound to react with the adsorption water or the water of crystallization.

- (2) Water, ice or water vapor is allowed to directly act on an organoaluminum compound such as
- 5 trialkylaluminum in a medium such as benzene, toluene, ethyl ether or tetrahydrofuran.

- (3) An organotin oxide such as dimethyltin oxide or dibutyltin oxide is allowed to react with an organoaluminum compound such as trialkylaluminum in a
- 10 medium such as decane, benzene or toluene.

- The aluminoxane may contain a small amount of an organometallic component. Further, it is possible that the solvent or the unreacted organoaluminum compound is distilled off from the recovered solution of
- 15 aluminoxane and the remainder is redissolved in a solvent or suspended in a poor solvent for aluminoxane.

- Examples of the organoaluminum compounds used for preparing the aluminoxane include the same organoaluminum compounds as previously exemplified
- 20 with respect to the organoaluminum compound (B-1a). Of these, preferable are trialkylaluminums and tricycloalkylaluminums. Particularly preferable is trimethylaluminum.

- The organoaluminum compounds are used singly or in
- 25 combination of two or more kinds.

00657587-060801

An aluminoxane prepared from the trimethylaluminum is referred as methylaluminoxane or MAO, and is the commonly used compound.

- Examples of the solvents used for preparing the
- 5 aluminoxane include aromatic hydrocarbons, such as benzene, toluene, xylene, cumene and cymene; aliphatic hydrocarbons, such as pentane, hexane, heptane, octane, decane, dodecane, hexadecane and octadecane; alicyclic hydrocarbons, such as cyclopentane, cyclohexane,
- 10 cyclooctane and methylcyclopentane; petroleum fractions, such as gasoline, kerosine and gas oil; and halogenated products of these aromatic, aliphatic and alicyclic hydrocarbons, particularly chlorinated or brominated products thereof. Also employable are
- 15 ethers such as ethyl ether and tetrahydrofuran. Of the solvents, particularly preferable are aromatic hydrocarbons and aliphatic hydrocarbons.

- The benzene-insoluble organoaluminum oxy-compound used in the present invention is preferably one
- 20 containing an Al component that is soluble in benzene at 60°C in an amount of usually not more than 10 %, preferably not more than 5 %, particularly preferably not more than 2 %, in terms of Al atom. That is, the benzene-insoluble organoaluminum oxy-compound is
- 25 preferably insoluble or sparingly soluble in benzene.

09857587.060801

The organoaluminum oxy-compound used in the present invention is, for example, an organoaluminum oxy-compound containing boron, which is represented by the following formula (i):

5



wherein R^c is a hydrocarbon group of 1 to 10 carbon atoms; and each R^d may be the same or different and is
10 a hydrogen atom, a halogen atom or a hydrocarbon group of 1 to 10 carbon atoms.

The organoaluminum oxy-compound containing boron, which is represented by the formula (i), can be prepared by allowing an alkylboronic acid represented
15 by the following formula (ii) to react with an organoaluminum compound in an inert solvent at a temperature of -80°C to room temperature for 1 minute to 24 hours under an inert gas atmosphere.

20



wherein R^c is the same group as described above.

Examples of the alkylboronic acids represented by the formula (ii) include methylboronic acid,
25 ethylboronic acid, isopropylboronic acid, n-

09857687.060801

propylboronic acid, n-butylboronic acid, isobutylboronic acid, n-hexylboronic acid, cyclohexylboronic acid, phenylboronic acid, 3,5-difluoroboronic acid, pentafluorophenylboronic acid and 3,5-bis(trifluoromethyl)phenylboronic acid. Of these, preferable are methylboronic acid, n-butylboronic acid, isobutylboronic acid, 3,5-difluorophenylboronic acid and pentafluorophenylboronic acid.

- 10 These alkylboronic acids are used singly or in combination of two or more kinds.

Examples of the organoaluminum compounds to be reacted with the alkylboronic acid include the same organoaluminum compounds as previously exemplified

15 with respect to the organoaluminum compound (B-1).

Of these, preferable are trialkylaluminums and tricycloalkylaluminums. Particularly preferable are trimethylaluminum, triethylaluminum and triisobutylaluminum. These organoaluminum compounds

20 are used singly or in combination of two or more kinds.

The organoaluminum oxy-compounds (B-2) mentioned above are used singly or in combination of two or more kinds.

- 25 (B-3) Compound which reacts with the metallocene compound (A) to form ion pair


00557587.060801

The compound (B-3) which reacts with the metallocene compound (A) to form an ion pair (referred to as an "ionizing ionic compound" hereinafter) includes Lewis acid, an ionic compound, a borane

- 5 compound and a carborane compound described in Japanese Patent Laid-Open Publications No. 501950/1989, No. 502036/1989, No. 179005/1991, No. 179006/1991, No. 207703/1991 and No. 207704/1991, U.S. Patent No. 5,321,106, etc.

- 10 The Lewis acid includes a compound represented by BR_3 (R is fluorine or a phenyl group which may have a substituent group such as fluorine, methyl or trifluoromethyl). Examples of such compounds include trifluoroboron, triphenylboron, tris(4-
- 15 fluorophenyl)boron, tris(3,5-difluorophenyl)boron, tris(4-fluoromethylphenyl)boron, tris(pentafluorophenyl)boron, tris(p-tolyl)boron, tris(o-tolyl)boron and tris(3,5-dimethylphenyl)boron.

- The ionizing ionic compound includes, for example,
- 20 a compound represented by the following formula (iii).



(iii)

09857637-060001

09857887 060801

10

15

20

25

triphenylphosphonium cation,

tris(methylphenyl)phosphonium cation and
tris(dimethylphenyl)phosphonium cation.

R^e is preferably carbenium cation, ammonium cation
or the like, particularly preferably

- 5 triphenylcarbenium cation, N,N-dimethylanilinium
cation or N,N-diethylanilinium cation.

Examples of the carbenium salts include
triphenylcarbeniumtetrphenylborate,

triphenylcarbeniumtetrakis(pentafluorophenyl)borate,

- 10 triphenylcarbeniumtetrakis(3,5-
dinitrofluoromethylphenyl)borate,

tris(4-

methylphenyl)carbeniumtetrakis(pentafluorophenyl)borat
e, and tris(3,5-

- 15 dimethylphenyl)carbeniumtetrakis(pentafluorophenyl)bor
ate.

Examples of the ammonium salts include a trialkyl-
substituted ammonium salt, a N,N-dialkylanilinium salt,
a dialkylammonium salt or a triarylphosphonium salt.

- 20 Examples of the trialkyl-substituted ammonium

salts include triethylammoniumtetrphenylborate,

tripropylammoniumtetrphenylborate,

tri(n-butyl)ammoniumtetrphenylborate,

trimethylammoniumtetrakis(p-tolyl)borate,

- 25 trimethylammoniumtetrakis(o-tolyl)borate,

09257587, 060001

- tri(n-butyl)ammoniumtetrakis(pentafluorophenyl)borate,
triethylammoniumtetrakis(pentafluorophenyl)borate,
tripropylammoniumtetrakis(pentafluorophenyl)borate,
tripropylammoniumtetrakis(2,4-dimethylphenyl)borate,
5 tri(n-butyl)ammoniumtetrakis(3,5-dimethylphenyl)borate,
tri(n-butyl)ammoniumtetrakis(4-
trifluoromethylphenyl)borate,
tri(n-butyl)ammoniumtetrakis(3,5-
ditrifluoromethylphenyl)borate and
10 tri(n-butyl)ammoniumtetrakis(o-tolyl)borate.

Examples of the N,N-dialkylanilinium salts include


- N,N-dimethylaniliniumtetraphenylborate,
N,N-dimethylaniliniumtetrakis(pentafluorophenyl)borate,
N,N-dimethylaniliniumtetrakis(3,5-
15 ditrifluoromethylphenyl)borate,
N,N-diethylaniliniumtetraphenylborate
N,N-diethylaniliniumtetrakis(pentafluorophenyl)borate,
N,N-diethylaniliniumtetrakis(3,5-
ditrifluoromethylphenyl)borate,
20 N,N-2,4,6-pentamethylaniliniumtetraphenylborate and
N,N-2,4,6-
pentamethylaniliniumtetrakis(pentafluorophenyl)borate.

Examples of the dialkylammonium salts include

- di(1-propyl)ammoniumtetrakis(pentafluorophenyl)borate
25 and dicyclohexylammoniumtetraphenylborate.


09357687 060801

Further employable are
 ferroceniumtetrakis(pentafluorophenyl)borate,
 triphenylcarbeniumpentaphenylcyclopentadienyl complex,
 N,N-diethylaniliniumpentaphenylcyclopentadienyl
 5 complex or a borate compound represented by the
 following formula (iv) or (v).



... (iv)

10 wherein Et is an ethyl group.



... (v)

Examples of the borane compounds include:

15 decaborane(14);

salts of anions, such as

bis(tri(n-butyl)ammonium)nonaborate,

09857687-060001

- bis(tri(n-butyl)ammonium)decaborate,
bis(tri(n-butyl)ammonium)undecaborate,
bis(tri(n-butyl)ammonium)dodecaborate,
bis(tri(n-butyl)ammonium)decachlorodecaborate and
5 bis(tri(n-butyl)ammonium)dodecachlorododecaborate; and
salts of metallic borane anions, such as tri(n-
butyl)ammoniumbis(dodecahydridododecaborate)cobaltate(
III) and bis(tri(n-butyl)ammonium)bis-
(dodecahydridododecaborate)nickelate(III).
- 10 Examples of the carborane compounds include:
salts of anions, such as 4-carbanonaborane(14),
1,3-dicarbanonaborane(13), 6,9-dicarbadeccaborane(14),
dodecahydrido-1-phenyl-1,3-dicarbanonaborane,
dodecahydrido-1-methyl-1,3-dicarbanonaborane,
15 undecahydrido-1,3-dimethyl-1,3-dicarbanonaborane,
7,8-dicarbaundecaborane(13), 2,7-
dicarbaundecaborane(13), undecahydrido-7,8-dimethyl-
7,8-dicarbaundecaborane, dodecahydrido-11-methyl-2,7-
dicarbaundecaborane,
20 tri(n-butyl)ammonium-1-carbadecaborate,
tri(n-butyl)ammonium-1-carbaundecaborate,
tri(n-butyl)ammonium-1-carbadodecaborate,
tri(n-butyl)ammonium-1-trimethylsilyl-1-
carbadeccaborate, tri(n-butyl)ammoniumbromo-1-
25 carbadodecaborate,

09857687, 060801

- tri(n-butyl) ammonium-6-carbadecaborate(14),
tri(n-butyl) ammonium-6-carbadecaborate(12),
tri(n-butyl) ammonium-7-carbaundecaborate(13),
tri(n-butyl) ammonium-7,8-dicarbaundecaborate(12),
5 tri(n-butyl) ammonium-2,9-dicarbaundecaborate(12),
tri(n-butyl) ammoniumdodecahydrido-8-methyl-7,9-
dicarbaundecaborate,
tri(n-butyl) ammoniumundecahydrido-8-ethyl-7,9-
dicarbaundecaborate,
10 tri(n-butyl) ammoniumundecahydrido-8-butyl-7,9-
dicarbaundecaborate,
tri(n-butyl) ammoniumundecahydrido-8-allyl-7,9-
dicarbaundecaborate,
tri(n-butyl) ammoniumundecahydrido-9-trimethylsilyl-
15 7,8-dicarbaundecaborate and
tri(n-butyl) ammoniumundecahydrido-4,6-dibromo-7-
carbaundecaborate; and
salts of metallic carborane anions, such as
tri(n-butyl) ammoniumbis(nonahydrido-1,3-
20 dicarbanonaborate) cobaltate(III),
tri(n-butyl) ammoniumbis(undecahydrido-7,8-
dicarbaundecaborate) ferrate(III),
tri(n-butyl) ammoniumbis(undecahydrido-7,8-
dicarbaundecaborate) cobaltate(III),

09357687-060801

- tri(n-butyl)ammoniumbis(undecahydrido-7,8-dicarbaundecaborate)nickelate(III),
- tri(n-butyl)ammoniumbis(undecahydrido-7,8-dicarbaundecaborate)cuprate(III),
- 5 tri(n-butyl)ammoniumbis(undecahydrido-7,8-dicarbaundecaborate)aurate(III),
- tri(n-butyl)ammoniumbis(nonahydrido-7,8-dimethyl-7,8-dicarbaundecaborate)ferrate(III),
- tri(n-butyl)ammoniumbis(nonahydrido-7,8-dimethyl-7,8-dicarbaundecaborate)chromate(III),
- 10 tri(n-butyl)ammoniumbis(tribromooctahydrido-7,8-dicarbaundecaborate)cobaltate(III),
- tris(tri(n-butyl)ammonium)bis(undecahydrido-7-carbaundecaborate)chromate(III),
- 15 bis(tri(n-butyl)ammonium)bis(undecahydrido-7-carbaundecaborate)manganate(IV),
- bis(tri(n-butyl)ammonium)bis(undecahydrido-7-carbaundecaborate)cobaltate(III) and
- bis(tri(n-butyl)ammonium)bis(undecahydrido-7-carbaundecaborate)nickelate(IV).
- 20

The ionizing ionic compounds (B-3) mentioned above are used singly or in combination of two or more kinds.

(C) Particle carrier

09857687-060801

- The particle carrier (C) that is optionally used in the invention is an inorganic or organic compound of granular or particulate solid having a particle diameter of 5 to 300 μm , preferably 10 to 200 μm . As
- 5 the inorganic compound, a porous oxide or chloride is preferable, and examples thereof include SiO_2 , Al_2O_3 , MgCl_2 , MgO , ZrO , TiO_2 , B_2O_3 , CaO , ZnO , BaO , ThO_2 , and mixtures containing them, such as $\text{SiO}_2\text{-MgO}$, $\text{SiO}_2\text{-Al}_2\text{O}_3$, $\text{SiO}_2\text{-TiO}_2$, $\text{SiO}_2\text{-V}_2\text{O}_5$, $\text{SiO}_2\text{-Cr}_2\text{O}_3$, $\text{SiO}_2\text{-MgCl}_2$, MgO-
- 10 MgCl_2 and $\text{SiO}_2\text{-TiO}_2\text{-MgO}$. Of these, preferable are those containing at least one component selected from the group consisting of SiO_2 and Al_2O_3 .

- In the inorganic oxides, small amounts of carbonate, sulfate, nitrate and oxide components, such
- 15 as Na_2CO_3 , K_2CO_3 , CaCO_3 , MgCO_3 , Na_2SO_4 , $\text{Al}_2(\text{SO}_4)_3$, BaSO_4 , KNO_3 , $\text{Mg}(\text{NO}_3)_2$, $\text{Al}(\text{NO}_3)_3$, Na_2O , K_2O and Li_2O , may be contained.

- As the particle carrier, an ion-exchangeable layered silicate is also employable. When the ion-
- 20 exchangeable layered silicate is used, the silicate functions as a carrier, and additionally, the amount of the organoaluminum oxy-compound used such as alkylaluminumoxane can be decreased by utilizing the ion-exchange properties and layered structure of the
- 25 silicate. Although the ion-exchangeable layered

silicate naturally occurs as a main component of a clay mineral, not only a natural one but also a synthetic one is employable. Examples of the ion-exchangeable layered silicates include kaolinite,

- 5 montmorillonite, hectorite, bentonite, smectite, vermiculite, synthetic mica and synthetic hectorite.

Although the properties of the particle carrier varies depending upon the type and the preparation process, the specific surface area is desired to be in
10 the range of 50 to 1000 m²/g, preferably 100 to 800 m²/g, and the pore volume is desired to be in the range of 0.3 to 3.0 cm³/g. The carrier is used after calcined at 80 to 1000°C, preferably 100 to 800°C, when needed.

- 15 The particle carrier (C) employable in the invention may be an organic compound of granular or particulate solid having a particle diameter of 5 to 300 μm. Examples of the organic compounds include polymers or copolymers produced using as a main
20 component an α-olefin of 2 to 14 carbon atoms, such as ethylene, propylene, 1-butene or 4-methyl-1-pentene; polymers or copolymers produced using as a main component vinylcyclohexane or styrene; and polar functional group-containing polymers obtained by
25 copolymerizing or graft polymerizing these polymers

09857687 1606001

with polar monomers such as acrylic acid, acrylic ester and maleic anhydride.

In the polymerization process, the catalyst components can be used in any way and in any order.

5 For example, the following processes are available.

(1) The metallocene compound (A) and at least one compound (B) selected from the organometallic compound (B-1), the organoaluminum oxy-compound (B-2) and the ionizing ionic compound (B-3) (referred to as a
10 "component (B)" simply hereinafter) are fed to the polymerization reactor in an arbitrary order.

(2) A catalyst obtained by previously contacting the metallocene compound (A) with the component (B) is fed to the polymerization reactor.

15 (3) A catalyst component obtained by previously contacting the metallocene compound (A) with the component (B) and the component (B) are fed to the polymerization reactor in an arbitrary order. In this case, the components (B) may be the same or different.

20 (4) A catalyst component wherein the metallocene compound (A) is supported on the particle carrier (C), and the component (B) are fed to the polymerization reactor in an arbitrary order.

(5) A catalyst wherein the metallocene compound
25 (A) and the component (B) are supported on the

09857587-060801

particle carrier (C) is fed to the polymerization reactor.

- (6) A catalyst component wherein the metallocene compound (A) and the component (B) are supported on the particle carrier (C) and the component (B) are fed to the polymerization reactor in an arbitrary order. In this case, the components (B) may be the same or different.

- (7) A catalyst component wherein the component (B) is supported on the particle carrier (C), and the metallocene compound (A) are added to the polymerization reactor in an arbitrary order.

- (8) A catalyst component wherein the component (B) is supported on the particle carrier (C), the metallocene compound (A) and the component (B) are added to the polymerization reactor in an arbitrary order. In this case, the components (B) may be the same or different.

- (9) A catalyst component obtained by previously contacting a catalyst wherein the metallocene compound (A) and the component (B) are supported on the particle carrier (C) with the component (B) is added to the polymerization reactor. In this case, the components (B) may be the same or different.

09857687.060601

(10) A catalyst component obtained by previously contacting a catalyst wherein the metallocene compound (A) and the component (B) are supported on the particle carrier (C) with the component (B), and the component (B) are added to the polymerization reactor in an arbitrary order. In this case, the components (B) may be the same or different.

Onto the solid catalyst component wherein the metallocene compound (A) and the component (B) are supported on the particle carrier (C), an olefin may be prepolymerized. In the solid catalyst component thus prepolymerized, a polyolefin produced as a prepolymer is contained in an amount of usually 0.1 to 1000 g, preferably 0.3 to 500 g, particularly preferably 1 to 200 g, based on 1 g of the solid catalyst component.

For the purpose of smoothly promoting the polymerization, an antistatic agent, an antifouling agent and the like may be used in combination or may be supported on the particle carrier.

Process for preparing polyolefin

In the process for preparing a polyolefin using the olefin polymerization catalyst according to the invention, the polymerization can be carried out as any of liquid phase polymerization such as solution

09857687.060801

polymerization or suspension polymerization and gas phase polymerization.

Examples of inert hydrocarbon solvents used in the liquid phase polymerization include aliphatic

- 5 hydrocarbons, such as propane, butane, pentane, hexane, heptane, octane, decane, dodecane and kerosine; alicyclic hydrocarbons, such as cyclopentane, cyclohexane and methylcyclopentane; aromatic hydrocarbons, such as benzene, toluene and xylene;
- 10 halogenated hydrocarbons, such as ethylene chloride, chlorobenzene and dichloromethane; and mixtures thereof. The α -olefin used for the polymerization may be per se used as a solvent.

- In the polymerization, the component (A) is used
- 15 in an amount of usually 10^{-8} to 10^{-2} mol, preferably 10^{-7} to 10^{-3} mol, based on 1 liter of the polymerization volume.

- The component (B-1) is used in such an amount that the molar ratio ((B-1)/(M)) of the component (B-1) to
- 20 the transition metal atom (M) in the component (A) becomes usually 0.01 to 5000, preferably 0.05 to 2000. The component (B-2) is used in such an amount that the molar ratio ((B-2)/(M)) of the aluminum atom in the component (B-2) to the transition metal atom (M) in
- 25 the component (A) becomes usually 10 to 5000,

0957687.060801

preferably 20 to 2000. The component (B-3) is used in such an amount that the molar ratio $\{(B-3)/(M)\}$ of the component (B-3) to the transition metal atom (M) in the component (A) becomes usually 1 to 10, preferably 1 to 5.

The temperature of polymerization of olefin using the olefin polymerization catalyst is in the range of usually -50 to $+200^{\circ}\text{C}$, preferably 0 to 170°C . The polymerization pressure is in the range of usually atmospheric pressure to 10 MPa (gage-pressure), preferably atmospheric pressure to 5 MPa (gage-pressure). The polymerization reaction can be carried out by any of batchwise, semi-continuous and continuous processes. It is possible to conduct the polymerization in two or more stages under different reaction conditions.

In the polymerization, the molecular weight of the resulting polymer or polymerization activity can be regulated by adding hydrogen in amount of about 0.01 to 100 NL based on 1 kg of the olefin.

In the present invention, as olefins used in the polymerization reaction preferable are those of 2 to 20 carbon atoms, particularly α -olefins of 2 to 10 carbon atoms. Example of the olefins include ethylene, propylene, 1-butene, 1-pentene, 1-hexene, 3-methyl-1-

- butene, 3-methyl-1-pentene, 3-ethyl-1-pentene, 4-methyl-1-pentene, 4-methyl-1-hexene, 4,4-dimethyl-1-hexene, 4,4-dimethyl-1-pentene, 4-ethyl-1-hexene, 3-ethyl-1-hexene, 1-octene, 1-decene, 1-dodecene, 1-tetradecene, 1-hexadecene, 1-octadecene, 1-eicosene, vinylcyclohexane and styrene.

- Further examples include dienes of 4 to 20 carbon atoms such as butadiene, 1,4-pentadiene, 1,5-hexadiene and 1,4-hexadiene, cyclicolefins such as
- 10 dicyclopentadiene, norbornene, methylnorbornene, tetracyclododecene and methyltetracyclododecene and silicon-containing olefins such as allyltrimethylsilane and vinyltrimethylsilane.

- Of the olefin polymerization catalysts according
- 15 to the invention, the catalyst containing the metallocene compound represented by the formula (1) or (2) is favorably used for copolymerization of at least 2 kinds of olefins.

- At least one of the olefins used is preferably an
- 20 α -olefin of 4 or less carbon atoms.

- The copolymerization of two or more olefins using the olefin polymerization catalyst of the invention has advantages such as high polymerization activity and good copolymerizability and is characterized in
- 25 that a copolymer of desired properties can be obtained.

An example of the copolymer obtained from two or more olefins is a copolymer comprising recurring units (U₁) derived from one α -olefin selected from α -olefins of 3 to 8 carbon atoms in amounts of 50 to 99.9 % by mol and recurring units (U₂) other than the recurring units (U₁), said recurring units (U₂) being derived from at least one α -olefin selected from α -olefins of 2 to 20 carbon atoms, in amounts of 50 to 0.1 % by mol.

Examples of the α -olefins of 3 to 8 carbon atoms include propylene, 1-butene, 1-pentene, 1-hexene, 3-methyl-1-butene, 3-methyl-1-pentene, 3-ethyl-1-pentene, 4-methyl-1-pentene, 4-methyl-1-hexene, 4,4-dimethyl-1-hexene, 4,4-dimethyl-1-pentene, 4-ethyl-1-hexene, 3-ethyl-1-hexene and 1-octene. Examples of the α -olefins of 2 to 20 carbon atoms include the same ones as described above.

Such a copolymer is, for example, a copolymer comprising propylene units in amounts of 50 to 99.5 % by mol and units of an α -olefin of 2 to 20 carbon atoms other than propylene in amounts of 50 to 0.5 % by mol.

The random copolymer comprising propylene units in amounts of 95 to 99.5 % by mol and units of an α -olefin of 2 to 20 carbon atoms other than propylene in amounts of 5 to 0.5 % by mol preferably has the

09857687-060801

- following properties: the pentad isotacticity as determined from ^{13}C -NMR spectrum measurement is not less than 80 %, preferably not less than 85 %; the proportion of 2,1-insertion and the proportion of 1,3-
- 5 insertion are each not more than 0.2 %, preferably not more than 0.1 %; the MFR is in the range of 0.01 to 1000 g/10 min, preferably 0.01 to 500 g/10 min; the molecular weight distribution (Mw/Mn) as calculated from molecular weights (Mw: weight-average molecular
- 10 weight, Mn: number-average molecular weight) measured by gel permeation chromatography (GPC) is in the range of 1 to 3, preferably 1 to 2.5, more preferably 1 to 2.3; and the quantity of a decane-soluble component (after the polymer is treated with n-decane at 150°C
- 15 for 2 hours and cooled to room temperature, the amount (weight %) of the polymer dissolved in the n-decane is measured) is not more than 2 % by weight, preferably not more than 1 % by weight.

- Of the olefin polymerization catalysts according
- 20 to the invention, the catalyst containing the metallocene compound represented by the formula (1a) or (2a) is favorably used for homopolymerization of an olefin.

- The homopolymerization of an α -olefin of 3 or more
- 25 carbon atoms using the olefin polymerization catalyst

of the invention is characterized in that an olefin polymer having high stereoregularity can be obtained and the polymer usually has high isotacticity.

- The homopolymer of an α -olefin of 3 or more carbon
- 5 atoms, particularly polypropylene, preferably has the following properties: the pentad isotacticity as determined from ^{13}C -NMR spectrum measurement is not less than 85 %, preferably not less than 90 %, more preferably not less than 95 %; the proportion of 2,1-
- 10 insertion and the proportion of 1,3-insertion are each not more than 0.2 %, preferably not more than 0.1 %, more preferably not more than 0.05 %; the melting point (T_m) as measured by differential scanning calorimetry (DSC) is not lower than 140°C, preferably
- 15 not lower than 150°C, more preferably not lower than 153°C; the MFR is in the range of 0.01 to 1000 g/10 min, preferably 0.01 to 500 g/10 min; the molecular weight distribution (M_w/M_n) as calculated from molecular weights measured by GPC is in the range of 1
- 20 to 3, preferably 1 to 2.5, more preferably 1 to 2.3; and the quantity of a decane-soluble component is not more than 2 % by weight, preferably not more than 1 % by weight, more preferably not more than 0.5 % by weight.

0857637.060801

Of the olefin polymerization catalysts according to the invention, the catalyst containing the metallocene compound represented by the formula (1b) or (2b) is favorably used for homopolymerization of an olefin or copolymerization of at least two kinds of olefins.

Of the polymers obtained by the use of such a catalyst, a homopolymer of an α -olefin of 3 to 8 carbon atoms, particularly polypropylene, preferably has the following properties: the pentad isotacticity as determined from ^{13}C -NMR spectrum measurement is not less than 85 %, preferably not less than 90 %, more preferably not less than 95 %; the proportion of 2,1-insertion and the proportion of 1,3-insertion are each not more than 0.2 %, preferably not more than 0.1 %, more preferably not more than 0.05 %; the melting point (T_m) as measured by DSC is not lower than 140°C, preferably not lower than 150°C, more preferably not lower than 153°C; the MFR is in the range of 0.01 to 1000 g/10 min, preferably 0.01 to 500 g/10 min; the molecular weight distribution (M_w/M_n) as calculated from molecular weights measured by GPC is in the range of 1 to 3, preferably 1 to 2.5, more preferably 1 to 2.3; and the quantity of a decane-soluble component is not more than 2 % by weight, preferably not more than

0957687, 060801

1 % by weight, more preferably not more than 0.5 % by weight.

An example of the copolymer obtained from two or more olefins using the catalyst containing the

- 5 metallocene compound represented by the formula (1b) or (2b) is a copolymer comprising recurring units (U₁) derived from one α -olefin selected from α -olefins of 3 to 8 carbon atoms in amounts of 50 to 99.9 % by mol and recurring units (U₂) other than the recurring
10 units (U₁), said recurring units (U₂) being derived from at least one α -olefin selected from α -olefins of 2 to 20 carbon atoms, in amounts of 50 to 0.1 % by mol.

- Such a copolymer is, for example, a copolymer comprising propylene units in amounts of 50 to 99.5 %
15 by mol and units of an α -olefin other than propylene in amounts of 50 to 0.5 % by mol.

- The copolymer comprising propylene units in amounts of 95 to 99.5 % by mol and units of an α -olefin of 2 to 20 carbon atoms other than propylene in
20 amounts of 5 to 0.5 % by mol preferably has the following properties: the pentad isotacticity as determined from ¹³C-NMR spectrum measurement is not less than 80 %, preferably not less than 85 %; the proportion of 2,1-insertion and the proportion of 1,3-
25 insertion are each not more than 0.2 %, preferably not

- more than 0.1 %; the MFR is in the range of 0.01 to 1000 g/10 min, preferably 0.01 to 500 g/10 min; the molecular weight distribution (Mw/Mn) as calculated from molecular weights measured by GPC is in the range
- 5 of 1 to 3, preferably 1 to 2.5, more preferably 1 to 2.3; and the quantity of a decane-soluble component is not more than 2 % by weight, preferably not more than 1 % by weight.

Polyolefin

- 10 The polyolefin according to the invention is a polyolefin comprising recurring units (U₁) derived from one α -olefin selected from α -olefins of 3 to 8 carbon atoms in amounts of 50 to 100 % by mol, preferably 65 to 100 % by mol, more preferably 80 to
- 15 100 % by mol, and recurring units (U₂) other than the recurring units (U₁), said recurring units (U₂) being derived from at least one olefin selected from α -olefins of 2 to 20 carbon atoms, in amounts of 50 to 0 % by mol, preferably 35 to 0 % by mol, more
- 20 preferably 20 to 0 % by mol.

Examples of the α -olefins of 3 to 8 carbon atoms and the α -olefins of 2 to 20 carbon atoms include the same ones as previously described.

- This polyolefin satisfies the following requisites
- 25 (i) to (iii):

09857687-060801

(i) the proportion of 2,1-insertion and the proportion of 1,3-insertion are each not more than 0.2 %, preferably not more than 0.1 %,

(ii) the molecular weight distribution (Mw/Mn) as
5 determined by (GPC) is in the range of 1 to 3, preferably 1 to 2.5, more preferably 1 to 2.3, and

(iii) the quantity of a decane-soluble component is not more than 2 % by weight, preferably not more than 1 % by weight.

10 The polyolefin preferably comprises recurring units derived from propylene in amounts of 50 to 99.5 % by mol, preferably 65 to 99.5 % by mol, more preferably 80 to 99.5 % by mol, and recurring units derived from at least one olefin selected from α -
15 olefins of 2 to 20 carbon atoms other than propylene in amounts of 50 to 0.5 % by mol, preferably 35 to 0.5 % by mol, more preferably 20 to 0.5 % by mol.

Such a polyolefin of the invention has excellent elastic modulus, impact resistance and transparency.

20 Another embodiment of the polyolefin of the invention is a homopolymer of one α -olefin selected from α -olefins of 3 to 8 carbon atoms.

Examples of the α -olefins of 3 to 8 carbon atoms include the same ones as previously described.

09857637.060001

This polyolefin satisfies the following requisites
(i) to (vi):

- (i) the pentad isotacticity as determined from
 ^{13}C -NMR spectrum measurement is not less than 85 %,
5 preferably not less than 90 %, more preferably not
less than 95 %,

(ii) the proportion of 2,1-insertion and the
proportion of 1,3-insertion are each not more than
0.2 %, preferably not more than 0.1 %, more preferably
10 not more than 0.05 %,

(iii) the MFR is in the range of 0.01 to 1000 g/10
min, preferably 0.01 to 500 g/10 min, more preferably
0.02 to 400 g/10 min,

(iv) the molecular weight distribution (M_w/M_n) as
15 determined by GPC is in the range of 1 to 3,
preferably 1 to 2.5, more preferably 1 to 2.3,

(v) the quantity of a decane-soluble component is
not more than 2 % by weight, preferably not more than
1 % by weight, more preferably not more than 0.5 % by
20 weight, and

(vi) the melting point (T_m) as measured by DSC is
not lower than 140°C, preferably not lower than 150°C,
more preferably not lower than 153°C.

The polyolefin is preferably a homopolymer of
25 propylene.

09857687-060801

Such a polyolefin of the invention has excellent elastic modulus, impact resistance and transparency.

- A further embodiment of the polyolefin of the invention is a polyolefin comprising recurring units
- 5 (U₁) derived from one α -olefin selected from α -olefins of 3 to 8 carbon atoms in amounts of 95 to 99.5 % by mol, preferably 95 to 99 % by mol, more preferably 95 to 98 % by mol, and recurring units (U₂) other than the recurring units (U₁), said recurring units (U₂)
- 10 being derived from at least one olefin selected from α -olefins of 2 to 20 carbon atoms, in amounts of 5 to 0.05 % by mol, preferably 5 to 1 % by mol, more preferably 5 to 2 % by mol.

- Examples of the α -olefins of 3 to 8 carbon atoms
- 15 and the α -olefins of 2 to 20 carbon atoms include the same ones as previously described.

This polyolefin satisfies the following requisites (i) to (vi):

- (i) the pentad isotacticity as determined from
- 20 ¹³C-NMR spectrum measurement is not less than 80 %, preferably not less than 85 %,

(ii) the proportion of 2,1-insertion and the proportion of 1,3-insertion are each not more than 0.2 %, preferably not more than 0.1 %,

0857697.060601

(iii) the MFR is in the range of 0.01 to 1000 g/10 min, preferably 0.01 to 500 g/10 min, more preferably 0.02 to 400 g/10 min,

(iv) the molecular weight distribution (M_w/M_n) as
5 determined by GPC is in the range of 1 to 3,
preferably 1 to 2.5, more preferably 1 to 2.3,

(v) the quantity of a decane-soluble component is
not more than 2 % by weight, preferably not more than
1 % by weight, more preferably not more than 0.5 % by
10 weight, and

(vi) the melting point (T_m) as measured by a
differential scanning calorimeter is not higher than
145°C, preferably not higher than 140°C.

The polyolefin preferably comprises recurring
15 units derived from propylene in amounts of 95 to
99.5 % by mol, preferably 95 to 99 % by mol, more
preferably 95 to 98 % by mol, and recurring units
derived from at least one olefin selected from α -
olefins of 2 to 20 carbon atoms other than propylene
20 in amounts of 5 to 0.5 % by mol, preferably 5 to 1 %
by mol, more preferably 5 to 2 % by mol.

Such a polyolefin of the invention has excellent
elastic modulus, impact resistance and transparency.

The polyolefin of the invention mentioned above
25 can be prepared by polymerizing or copolymerizing the

corresponding olefin under the above-mentioned conditions using the olefin polymerization catalyst containing the metallocene compound represented by the formula (1), (2), (1a), (2a), (1b) or (2b).

5

EFFECT OF THE INVENTION

The metallocene compound represented by the formula (1) or (2) according to the invention and the olefin polymerization catalyst containing this
10 metallocene compound have excellent olefin polymerization activity and are of industrially great value. The olefin copolymer obtained by the use of the catalyst, particularly a propylene random copolymer, has excellent elastic modulus, impact resistance and
15 transparency.

The metallocene compound represented by the formula (1a) or (2a) according to the invention and the olefin polymerization catalyst containing this metallocene compound have excellent olefin
20 polymerization activity and are of industrially great value. The poly- α -olefin obtained by the use of the catalyst, particularly polypropylene, has excellent elastic modulus, impact resistance and transparency.

The metallocene compound represented by the
25 formula (1b) or (2b) according to the invention and

09857587-060801

the olefin polymerization catalyst containing this metallocene compound have excellent olefin polymerization activity and are of industrially great value. The poly- α -olefin obtained by the use of the

5 catalyst, particularly polypropylene, has excellent elastic modulus, impact resistance and transparency. The olefin copolymer obtained by the use of the catalyst, particularly a propylene random copolymer, has excellent elastic modulus, impact resistance and

10 transparency.

The process for preparing a metallocene compound according to the invention is excellent as a process for selectively preparing a metallocene compound having a desirable specific structure, and is of

15 industrially great value.

The polyolefin according to the invention has excellent elastic modulus, impact resistance and transparency.

The polyolefin according to the invention can be

20 favorably used for nonwoven fabrics, films, sealants, industrial materials, transparent injection, block polymers, alloys, modifiers, etc., and can be broadly used specifically for hygienic materials, civil engineering materials, automobile parts, electrical

09857687.060801

appliances, food containers, packaging materials, miscellaneous goods, etc.

EXAMPLE

- 5 The present invention is further described with reference to the following examples, but it should be construed that the invention is in no way limited to those examples.

- 10 In the present invention, the melting point (T_m) of a polymer was determined as follows. Through differential scanning calorimetry (DSC), a polymer sample kept at 240°C for 10 minutes was cooled to 30°C, kept for 5 minutes and then heated at a rate of 10°C/min to obtain a crystal melting peak, from which
15 the melting point was calculated.

 The molecular weight (M_w , M_n) was measured by GPC (gel permeation chromatography).

- The quantity of a decane-soluble component was determined as follows. A polymer was treated with n-
20 decene at 150°C for 2 hours and then cooled to room temperature, and the quantity of the polymer (% by weight) dissolved in n-decane was measured.

- The stereoregularity (pentad isotacticity (mmmm), 2,1-insertion, 1,3-insertion) of a polymer was
25 determined from ^{13}C -NMR spectrum measurement.

0957687 060801
10090789786

The intrinsic viscosity (η) was measured in decalin at 135°C.

The MFR was measured after heating of a polymer at 230°C for 6 minutes.

5 Example 1

Synthesis of dimethylmethylen(3-tert-butyl-5-methylcyclopentadienyl)fluorenylzirconium dichloride
(1) Synthesis of 1-tert-butyl-3-methylcyclopentadiene

- To a solution obtained by adding 350 ml of
- 10 dehydrated diethyl ether to 450 ml (0.90 mol) of a tert-butylmagnesium chloride/diethyl ether solution (concentration: 2.0 mol/liter), a solution of 43.7 g (0.45 mmol) of 3-methylcyclopentenone in 150 ml of dehydrated diethyl ether was dropwise added in a
- 15 nitrogen atmosphere at 0°C with ice cooling, followed by stirring at room temperature for 15 hours. To the reaction solution, a solution of 80.0 g (1.50 mol) of ammonium chloride in 350 ml of water was dropwise added at 0°C with ice cooling. To the resulting
- 20 solution, 2500 ml of water was added, followed by stirring. Then, the organic phase was separated and washed with water. To the organic phase, 82 ml of a 10% hydrochloric acid aqueous solution was added at 0°C with ice cooling, followed by stirring at room
- 25 temperature for 6 hours. The organic phase was

09857687-060801

09857687 350301

- (2) Synthesis of 3-tert-butyl-1,6,6-trimethylfulvene
- To a solution of 13.0 g (95.6 mmol) of 1-tert-butyl-3-methylcyclopentadiene in 130 ml of dehydrated methanol, 55.2 g (950.4 mmol) of dehydrated acetone was dropwise added in a nitrogen atmosphere at 0°C with ice cooling, and 68.0 g (956.1 mmol) of pyrrolidine was further dropwise added, followed by stirring at room temperature for 4 days. After the reaction solution was diluted with 400 ml of diethyl ether, 400 ml of water was added. The organic phase was separated, washed with a 0.5N hydrochloric acid aqueous solution (150 ml x 4), water (200 ml x 3) and a saturated saline solution (150 ml), and then dried

over anhydrous magnesium sulfate. The drying agent was filtered, and from the filtrate the solvent was distilled off to obtain a liquid. The liquid was subjected to vacuum distillation (70-80°C/0.1 mmHg) to obtain 10.5 g of a yellow liquid. The analyzed values are given below.

¹H-NMR (270 MHz, in CDCl₃, based on TMS): δ 6.23 (s, 1H), 6.05 (d, 1H), 2.23 (s, 3H), 2.17 (d, 6H), 1.17 (s, 9H)

10 (3) Synthesis of 2-(3-tert-butyl-5-methylcyclopentadienyl)-2-fluorenylpropane

To a solution of 10.1 g (60.8 mmol) of fluorene in 300 ml of THF, 40 ml (61.6 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for 5 hours (dark brown solution). The solution was ice cooled again, and a solution of 11.7 g (66.5 mmol) of 3-tert-butyl-1,6,6-trimethylfulvene in 300 ml of THF was dropwise added in a nitrogen atmosphere. After stirring at room temperature for 14 hours, the resulting brown solution was ice cooled, and 200 ml of water was added. The organic phase extracted with diethyl ether and separated was dried over magnesium sulfate and then filtered. From the filtrate, the solvent was removed

09857687 060801

under reduced pressure to obtain an orangy brown oil. The oil was purified by silica gel column chromatography (developing solvent: hexane) to obtain 3.8 g of a yellow oil. The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 7.70 (d, 4H), 7.34-7.26 (m, 6H), 7.18-7.11 (m, 6H), 6.17 (s, 1H), 6.01 (s, 1H), 4.42 (s, 1H), 4.27 (s, 1H), 3.01 (s, 2H), 2.87 (s, 2H), 2.17 (s, 3H), 1.99 (s, 3H), 2.10 (s, 9H), 1.99 (s, 9H), 1.10 (s, 6H), 1.07 (s, 6H)

(4) Synthesis of dimethylmethylene(3-tert-butyl-5-methylcyclopentadienyl)fluorenylzirconium dichloride

To a solution of 1.14 g (3.3 mmol) of 2-(3-tert-butyl-5-methylcyclopentadienyl)-2-fluorenylpropane in 25 ml of diethyl ether, 5.0 ml (7.7 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, and the mixture was stirred at room temperature for 14 hours to obtain a pink slurry. To the slurry, 0.77 g (3.3 mmol) of zirconium tetrachloride was added at -78°C , and the mixture was stirred at -78°C for several hours, followed by further stirring at room temperature for 65 hours. The resulting dark brown slurry was filtered. The substance remaining on the filter was washed with

10 ml of diethyl ether and extracted with

09657687, 060801

dichloroethane to obtain a red solution. From the solution, the solvent was vacuum distilled off to obtain 0.53 g of a reddish orange solid. The analyzed values are given below.

- 5 $^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 8.11-8.02 (m, 3H), 7.82 (d, 1H), 7.56-7.45 (m, 2H), 7.23-7.17 (m, 2H), 6.08 (d, 1H), 5.72 (d, 1H), 2.59 (s, 3H), 2.41 (s, 3H), 2.30 (s, 3H), 1.08 (s, 9H)
- FD-MS: m/z = 500, 502, 504 (M^+)

10

Example 2Synthesis of cyclohexylidene(3-tert-butyl-5-methylcyclopentadienyl)fluorenylzirconium dichloride

(1) Synthesis of 3-tert-butyl-5-methyl-6,6-

15 pentamethylenefulvene

To 50 ml of dehydrated methanol, 0.5 g (3.68 mmol) of 1-tert-butyl-3-methylcyclopentadiene and 3.81 ml (36.8 mmol) of cyclohexanone were added, then 3.07 ml (36.8 mmol) of pyrrolidine was dropwise added at 0°C , 20 and the mixture was reacted at room temperature for 7 days. Then, 20 ml of water was added at 0°C . After extraction with ether, the organic phase was washed with water and successively dried over anhydrous magnesium sulfate. Then, the solvent was distilled off

09857687-060801
102090-28975860

to obtain 1.3 g of a light yellow solid. The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 6.26 (s, 1H), 6.10 (s, 1H), 2.71 (dd, 2H), 2.61 (dd, 2H), 2.27 (d, 3H), 1.80-1.61 (m, 6H), 1.17 (s, 9H)

(2) Synthesis of 1-(3-tert-butyl-5-methylcyclopentadienyl)-1-fluorenylcyclohexane

To a solution of 0.8 g (4.5 mmol) of fluorene in 40 ml of THF, 2.9 ml (4.6 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for 6 hours. To the resulting red solution, a solution of 1.0 g (4.8 mmol) of 3-tert-butyl-5-methyl-6,6-pentamethylenefulvene in 15 ml of THF was dropwise added in a nitrogen atmosphere with ice cooling. After stirring at room temperature for 16 hours, 30 ml of water was added. The organic phase extracted with diethyl ether and separated was dried over magnesium sulfate and then filtered. From the filtrate, the solvent was removed under reduced pressure to obtain a light yellow liquid. The liquid was passed through a silica gel column using hexane as an eluent. From the resulting hexane solution, the solvent was removed under reduced pressure to obtain

09857687-060001

1.3 g of a light yellow solid. The analyzed values are given below.

¹H-NMR (270 MHz, in CDCl₃, Based on TMS): 87.64 (d, 2H), 7.34-7.24 (m, 4H), 7.16-7.10 (m, 2H), 5.79 (s, 1H), 4.02 (s, 1H), 2.87-2.77 (s+s, 3H), 2.26-2.00 (m, 2H), 1.75-1.60 (s+s, 3H), 1.55-1.23 (m, 8H), 1.12 (d, 9H)

(3) Synthesis of cyclohexylidene(3-tert-butyl-5-methylcyclopentadienyl)fluorenylzirconium dichloride

- 10 To a solution of 1.3 g (3.3 mmol) of 1-(3-tert-butyl-5-methylcyclopentadienyl)-1-fluorenylcyclohexane in 40 ml of THF, 4.8 ml (6.8 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by
- 15 stirring at room temperature for 16 hours. From the reaction mixture, the solvent was removed under reduced pressure to obtain a reddish orange solid. To the solid, 150 ml of dichloromethane was added at -78°C, and they were stirred to give a solution. Then,
- 20 the solution was added to 10 ml of a dichloromethane suspension of 1.1 g (2.9 mmol) of zirconium tetrachloride (THF) 2-complex having been cooled to -78°C, and the mixture was stirred at -78°C for 6 hours, followed by further stirring at room temperature for
- 25 one day and night. From the reaction solution, the

solvent was removed under reduced pressure to obtain a vermilion solid. The solid was extracted with diethyl ether and subjected to sellaite filtration. The filtrate was concentrated to precipitate 18 mg of a reddish brown solid, and the solid was separated from the mother liquor. The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 8.10 (m, 2H), 7.90 (d, 1H), 7.76 (d, 1H), 7.56-7.46 (m, 2H), 7.28-7.18 (m, 2H), 6.07 (d, 1H), 5.72 (d, 1H), 3.73 (br, 1H), 3.34 (br, 1H), 2.55-2.33 (m, 2H), 2.27 (s, 3H), 2.05-1.64 (m, 6H), 1.08 (s, 9H)

FD-MS: m/z = 540, 542, 544 (M^+)

Reference Example

15 Synthesis of 3,6-di-tert-butylfluorene

(1) Synthesis of 4,4'-di-t-butylbiphenylmethane

A 300 ml two-necked flask was thoroughly purged with nitrogen. In the flask, 38.4 g (289 mmol) of AlCl_3 was placed, and 80 ml of CH_3NO_2 was added to give a solution (1). Separately, a 500 ml three-necked flask equipped with a dropping funnel and a magnetic stirrer was thoroughly purged with nitrogen. In the flask, 25.6 g (152 mmol) of diphenylmethane and 43.8 g (199 mmol) of 2,6-di-t-butyl-4-methylphenol were placed, and 80 ml of CH_3NO_2 was added to give a

- solution. With stirring, this solution was cooled with an ice bath. To the solution was dropwise added the solution (1) over a period of 35 minutes, and the reaction solution was stirred at 12°C for 1 hour. The
- 5 reaction solution was poured into 500 ml of ice water and extracted with 800 ml of hexane. The organic phase was washed with 600 ml of a 5% NaOH aqueous solution and dried over MgSO₄. Then, the MgSO₄ was filtered off, and the solvent was evaporated to obtain an oil. The
- 10 oil was cooled to -78°C to precipitate a solid. The solid was recovered by filtration, washed with 300 ml of EtOH and dried under reduced pressure to obtain 4,4'-di-t-butylldiphenylmethane (yield: 18.9 g).
- (2) Synthesis of 2,2'-diiodo-4,4'-di-t-butylldiphenylmethane
- 15 butylldiphenylmethane

- In a 200 ml flask equipped with a magnetic stirrer, 1.95 g (6.96 mmol) of 4,4'-di-t-butylldiphenylmethane, 0.78 g (3.48 mmol) of HIO₄, 1.55 g (6.12 mmol) of I₂ and 0.48 ml of concentrated H₂SO₄ were placed. Then,
- 20 17.5 ml of acetic acid and 3.75 ml of water were added, and the mixture was heated to 90°C with stirring and reacted for 5 hours. The reaction solution was poured into 50 ml of ice water and extracted with Et₂O. The organic phase was washed with 100 ml of a saturated
- 25 NaHSO₄ aqueous solution, and then Na₂CO₃ was added.

09857687-60801
108099-2895860

After stirring, the Na_2CO_3 was filtered off. The organic phase was washed with 800 ml of water, and Mg_2SO_4 was added to dry the organic phase. After the Mg_2SO_4 was filtered off, the solvent was distilled off

- 5 to obtain a yellow oil. The oil was purified by column chromatography to obtain 2,2'-diiodo-4,4'-di-t-butyl-
diphenylmethane (yield: 3.21 g).

(3) Synthesis of 3,6-di-t-butylfluorene

- In a 50 ml two-necked flask, 3.21 g (6.03 mmol) of
10 2,2'-diiodo-4,4'-di-t-butyl-
diphenylmethane was placed,
and 2.89 g (47.0 mmol) of a copper powder was added.
The mixture was heated to 230°C and reacted for 5
hours with stirring. After extraction with acetone,
the solvent was distilled off to obtain a reddish
15 brown oil. The oil was subjected to column
chromatography to obtain a light yellow oil. The
fractions containing the unreacted material was
subjected to column chromatography again to recover
the desired product only. The obtained product was
20 recrystallized from methanol to obtain a white solid
(yield: 1.08 g).

Example 3

09857687-060801

Synthesis of dimethylmethylene(3-tert-butyl-5-
methylcyclopentadienyl) (3,6-di-tert-
butylfluorenyl)zirconium dichloride

- (1) Synthesis of 2-(3-tert-butyl-5-
5 methylcyclopentadienyl)-2-(3,6-di-tert-
butylfluorenyl)propane

To a solution of 0.9 g (3.4 mmol) of 3,6-di-tert-
butylfluorene in 30 ml of THF, 2.1 ml (3.4 mmol) of a
hexane solution of n-butyllithium was dropwise added
10 in a nitrogen atmosphere with ice cooling, followed by
stirring at room temperature for 6 hours. To the
resulting red solution, a solution of 0.6 g (3.5 mmol)
of 3-tert-butyl-5,6,6-trimethylfulvene in 15 ml of THF
was dropwise added in a nitrogen atmosphere with ice
15 cooling, followed by stirring at room temperature for
12 hours. Then, 30 ml of water was added. The organic
phase extracted with diethyl ether and separated was
dried over magnesium sulfate and then filtered. From
the filtrate, the solvent was removed under reduced
20 pressure to obtain a solid. The solid was
recrystallized from hot methanol to obtain 1.2 g of a
light yellow solid. The analyzed values are given
below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 7.72 (d,
25 2H), 7.18-7.05 (m, 4H), 6.18-5.99 (s+s, 1H), 4.32-4.18

09857687, 060801

(s+s, 1H), 3.00-2.90 (s+s, 2H), 2.13-1.98 (t+s, 3H),
1.38 (s, 18H), 1.19 (s, 9H), 1.10 (d, 6H)

(2) Synthesis of dimethylmethylen(3-tert-butyl-5-methylcyclopentadienyl) (3,6-di-tert-

5 butylfluorenyl)zirconium dichloride

- To a solution of 1.3 g (2.8 mmol) of 2-(3-tert-butyl-5-methylcyclopentadienyl)-2-(3,6-di-tert-butylfluorenyl)propane in 40 ml of diethyl ether, 3.6 ml (5.8 mmol) of a hexane solution of n-butyllithium
- 10 was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for 16 hours. From the reaction mixture, the solvent was removed under reduced pressure to obtain a reddish orange solid. To the solid, 150 ml of dichloromethane
- 15 was added at -78°C, and they were stirred to give a solution. Then, the solution was added to a suspension of 1.0 g (2.7 mmol) of zirconium tetrachloride (THF) 2-complex in 10 ml of dichloromethane having been cooled to -78°C, and the mixture was stirred at -78°C
- 20 for 6 hours, followed by further stirring at room temperature for one day and night. From the reaction solution, the solvent was removed under reduced pressure to obtain an orange solid. The solid was extracted with toluene and subjected to sellaita
- 25 filtration. From the filtrate, the solvent was removed

09857687-060801

under reduced pressure, and the residue was recrystallized from diethyl ether to obtain 0.18 g of an orange solid. The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 7.98

- 5 (dd, 2H), 7.90 (d, 1H), 7.69 (d, 1H), 7.32-7.25 (m, 2H), 6.01 (d, 1H), 5.66 (d, 1H), 2.54 (s, 3H), 2.36 (s, 3H), 2.28 (s, 1H), 1.43 (d, 18H), 1.08 (s, 9H)

FD-MS: m/z = 612, 614, 616 (M^+)

10 Example 4

Synthesis of cyclohexylidene(3-tert-butyl-5-methylcyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride

(1) Synthesis of 1-(3-tert-butyl-5-

- 15 methylcyclopentadienyl)-1-(3,6-di-tert-butylfluorenyl)cyclohexane

To a solution of 0.81 g (2.91 mmol) of 3,6-di-tert-butylfluorene in 40 ml of THF, 1.91 ml (3.06 mmol) of a hexane solution of n-butyllithium was

- 20 dropwise added in a nitrogen atmosphere at 0°C , followed by stirring at room temperature for 16 hours. To the resulting solution, a solution of 0.69 g (3.20 mmol) of 3-tert-butyl-5-methyl-6-pentamethylenefulvene in 30 ml of THF was dropwise
25 added in a nitrogen atmosphere at 0°C , followed by

09857687-060801

stirring at room temperature for 16 hours, to perform reaction. After the reaction, 30 ml of water was added. The organic phase was extracted with ether and dried over anhydrous magnesium sulfate. From the resulting solution, the solvent was distilled off under reduced pressure to obtain 1.26 g of a yellow solid. The analyzed values are given below.

¹H-NMR (270 MHz, in CDCl₃, Based on TMS): 87.64 (d, 2H), 7.22 (d, 2H), 7.15 (d,d, 2H), 6.10, 5.76 (1H), 3.89 (s, 1H), 2.82-2.58 (2H), 1.70 (s, 3H), 1.38 (s, 18H), 1.09 (s, 9H), 2.26-1.25 (10H)

(2) Synthesis of cyclohexylidene(3-tert-butyl-5-methylcyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride

To a solution of 1.22 g (2.47 mmol) of 1-(3-tert-butyl-5-methylcyclopentadienyl)-1-(3,6-di-tert-butylfluorenyl)cyclohexane in 50 ml of THF, 3.39 ml (5.43 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for 16 hours. From the reaction mixture, the solvent was removed under reduced pressure to obtain a reddish orange solid. To the solid, a solution of 0.93 g (2.47 mmol) of zirconium tetrachloride (THF) 2-complex in 100 ml of dichloromethane having been cooled to -78°C

09857687-060801

was added. The mixture was stirred and reacted while the temperature of the mixture was allowed to naturally rise to room temperature. The resulting red suspension was subjected to sellaite filtration to

5 remove lithium chloride. Then, to the orange filtrate was added 10 ml of toluene, and the mixture was concentrated until a solid was precipitated, followed by cooling to -20°C . The precipitated solid was recovered and then recrystallized from toluene to

10 obtain 27 mg of a red solid. The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 8.02 (d, 1H), 7.97 (d, 1H), 7.76 (d, 1H), 7.62 (d, 1H), 7.33-7.29 (d,d, 2H), 6.01 (d, 1H), 5.66 (d, 1H), 3.69 (br,d,

15 1H), 3.29 (br,d, 1H), 2.25 (s, 3H), 2.54-1.53 (m, 8H), 1.44 (s, 9H), 1.43 (s, 9H), 1.07 (s, 9H)

FD-MS: m/z = 652, 654, 656 (M^+)

Example 5

- 20 Synthesis of dimethylmethylene(3-tert-butyl-5-methylcyclopentadienyl)(2,7-di-tert-butylfluorenyl)zirconium dichloride
- (1) Synthesis of 2-(3-tert-butyl-5-methylcyclopentadienyl)-2-(2,7-di-tert-
- 25 butylfluorenyl)propane

00557637-060801

To a solution of 0.9 g (3.4 mmol) of 2,7-di-tert-butylfluorene in 30 ml of THF, 2.1 ml (3.4 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for 6 hours. To the resulting red solution, a solution of 0.6 g (3.5 mmol) of 3-tert-butyl-5,6,6-trimethylfulvene in 15 ml of THF was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for 12 hours. Then, 30 ml of water was added. The organic phase extracted with diethyl ether and separated was dried over magnesium sulfate and then filtered. From the filtrate, the solvent was removed under reduced pressure to obtain 1.1 g of a crude product. The crude product was per se used for the next reaction without being purified.

(2) Synthesis of dimethylmethylene(3-tert-butyl-5-methylcyclopentadienyl)(2,7-di-tert-butylfluorenyl)zirconium dichloride

To a solution of 0.87 g (1.92 mmol) of 2-(3-tert-butyl-5-methylcyclopentadienyl)-2-(2,7-di-tert-butylfluorenyl)propane in 50 ml of THF, 2.88 ml (4.60 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for

- 16 hours. From the reaction mixture, the solvent was removed under reduced pressure to obtain a reddish orange solid. To the solid, a solution of 0.72 g (1.92 mmol) of zirconium tetrachloride (THF) 2-complex in
- 5 100 ml of dichloromethane having been cooled to -78°C was added. The mixture was stirred and reacted while the temperature of the mixture was allowed to naturally rise to room temperature. The resulting red suspension was subjected to sellaite filtration to
- 10 remove lithium chloride. Then, to the orange filtrate was added 10 ml of toluene, and the mixture was concentrated until a solid was precipitated, followed by cooling to -20°C . The precipitated solid was recovered and then recrystallized from toluene to
- 15 obtain 17 mg of a red solid. The analyzed values are given below.

- $^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 7.96 (d, 1H), δ 7.94 (s, 1H), δ 7.93 (d, 1H), 7.69 (s, 1H), 7.59 (d, 1H), 7.53 (d, 1H), 6.03 (d, 1H), 5.68 (d, 1H),
- 20 2.60 (s, 1H), 2.41 (s, 1H), 2.31 (s, 1H), 1.32 (s, 18H), 1.08 (s, 9H)

FD-MS: m/z = 612, 614, 616 (M^+)

Example 6

Synthesis of dimethylmethylene(3-tert-
butylcyclopentadienyl) (3,6-di-tert-
butylfluorenyl)zirconium dichloride

(1) Synthesis of 3-tert-butyl-6,6-dimethylfulvene

- 5 To a solution of 1.53 g (13 mmol) of tert-butylcyclopentadiene in 30 ml of THF, 9.0 ml (14 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night.
- 10 Then, 1.7 ml (16 mmol) of acetone was further added at -78°C, followed by stirring at room temperature for 2 days. To the reaction solution, water was added. After extraction with ether, the solvent was distilled off, and the residue was subjected to column
- 15 chromatography (silica gel, developing solvent: hexane) to obtain 2.00 g of a yellow liquid (yield: 95 %). The analyzed values are given below.
- $^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 6.53 (d, 2H), 6.14 (t, 1H), 2.16 (s, 3H), 2.14 (s, 3H), 1.20 (s,
- 20 9H)

The 3-tert-6,6-dimethylfulvene could be synthesized also by the following process.

- To a mixed solution of 1.40 g (11 mmol) of tert-butylcyclopentadiene, 8.4 ml (114 mmol) of acetone and
- 25 20 ml of methanol, 9.5 ml (114 mmol) of pyrrolidine

09857687, 060801

09857687-060801

was added with ice cooling, followed by stirring at room temperature for one night. To the reaction solution, 50 ml of water, 100 ml of ether and 3 ml of acetic acid were added with ice cooling. The separated organic phase was washed with water and dried over anhydrous sodium sulfate. After the solvent was distilled off, the residue was subjected to column chromatography (silica gel, developing solvent: hexane) to obtain 1.62 g of a yellow liquid (yield: 88 %).

(2) Synthesis of 2-(3-tert-butylcyclopentadienyl)-2-(3,6-di-tert-butylfluorenyl)propane

To a solution of 1.98 g (7.1 mmol) of 3,6-di-tert-butylfluorene in 40 ml of ether, 4.6 ml (7.5 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. To the resulting red solution, a solution of 1.56 g (9.6 mmol) of 3-tert-butyl-6,6-dimethylfulvene in 20 ml of ether was further dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. Then, 60 ml of water was added. The separated organic phase was dried over magnesium sulfate and then filtered. From the filtrate, the solvent was removed under reduced pressure to

obtain a solid. The solid was purified by column chromatography (silica gel, developing solvent: hexane) to obtain 1.35 g of a light yellow solid (yield: 43 %). The analyzed values are given below.

- 5 $^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 7.71 (t, 2H), 7.20-6.97 (m, 4H), 6.48-5.70 (m, 2H), 4.04-3.98 (m, 1H), 3.10 (d, 2H), 1.38 (s, 18H), 1.24-1.20 (m, 9H), 1.05 (s, 6H)

- (3) Synthesis of dimethylmethylene(3-tert-butylcyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride
- 10

To a solution of 1.01 g (2.3 mmol) of 2-(3-tert-butyl-cyclopentadienyl)-2-(3,6-di-tert-butylfluorenyl)propane in 50 ml of ether, 2.9 ml (4.7

- 15 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for 20 hours. To the resulting reddish orange reaction mixture having been cooled to -78°C , 0.85 g (2.3 mmol)
- 20 of zirconium tetrachloride (THF) 2-complex was added, followed by stirring at room temperature for one day and night. The resulting reaction mixture was subjected to seltite filtration. From the filtrate, the solvent was removed under reduced pressure, and
- 25 the residue was recrystallized from diethyl ether to

09557687.06001

obtain 0.91 g of an orange solid (yield: 67 %). The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 8.02 (d, 2H), 7.74-7.65 (d+d, 2H), 7.33 (d+d, 2H), 6.11 (t, 1H), 5.73 (t, 1H), 5.53 (t, 1H), 2.32 (s, 6H), 1.44 (s, 18H), 1.16 (s, 9H)

FD-MS: m/z = 598, 600, 602 (M^+)

Example 7

10 Synthesis of dimethylmethylene(3-(1-methyl-1-cyclohexyl)cyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride

(1) Synthesis of (1-methyl-1-cyclohexyl)cyclopentadiene

- 15 To a solution of 6.50 g (44.5 mmol) of cyclohexylfulvene in 60 ml of THF, 44.8 ml (51.1 mmol) of an ether solution of methylolithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night.
- 20 After the reaction solution was diluted with 100 ml of ether, 30 ml of water was added. The separated organic phase was washed with water and a saturated saline solution, then dried over magnesium sulfate and filtered. From the filtrate, the solvent was removed
- 25 under reduced pressure to obtain a liquid. The liquid

00357637.060801

was isolated and purified by column chromatography (silica gel, developing solvent: hexane) to obtain 2.72 g (16.76 mmol) of a colorless transparent liquid (yield: 38 %). The analyzed values are given below.

5 $^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS):

δ 6.58+6.42+6.28+6.18+6.00 (m+m+m+m+m, 3H), 2.95+2.86 (s+m, 2H), 1.90-0.80 (m, 10H), 1.10 (s, 3H)

(2) Synthesis of 3-(1-methyl-1-cyclohexyl)-6,6-dimethylfulvene

10 To a solution of 2.71 g (16.7 mmol) of (1-methyl-1-cyclohexyl)cyclopentadiene in 30 ml of methanol, 25 ml (340.5 mmol) of acetone and 2.8 ml (33.5 mmol) of pyrrolidine were added with ice cooling, followed by stirring at room temperature for 3 days. After the

15 reaction solution was diluted with 100 ml of ether, 50 ml of water was added. The organic phase was separated, washed with water and a saturated saline solution, then dried over anhydrous magnesium sulfate and filtered. From the filtrate, the solvent was removed

20 under reduced pressure to obtain a liquid. The liquid was isolated and purified by column chromatography (silica gel, developing solvent: hexane) to obtain 2.95 g (14.58 mmol) of a yellow liquid (yield: 87 %). The analyzed values are given below.

09357637 060801

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 7.80-6.16 (m, 3H), 2.18 (d, 6H), 2.25-0.80 (m, 14H), 1.23 (s, 3H)

- (3) Synthesis of 2-(3-(1-methyl-1-cyclohexyl)cyclopentadienyl)-2-(3,6-di-tert-butylfluorenyl)propane

- To a solution of 2.64 g (9.5 mmol) of 3,6-di-tert-butylfluorene in 45 ml of THF, 6.4 ml (10.4 mmol) of a hexane solution of n-butyllithium was dropwise added
- 10 in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. To the resulting red solution, a solution of 2.00 g (9.9 mmol) of 3-(1-methyl-1-cyclohexyl)-6,6-dimethylfulvene in 30 ml of THF was further dropwise added in a
- 15 nitrogen atmosphere with ice cooling, followed by stirring at room temperature for 3 days. After the reaction solution was diluted with 100 ml of ether, 50 ml of water was added. The separated organic phase was washed with water and a saturated saline solution,
- 20 then dried over magnesium sulfate and filtered. From the filtrate, the solvent was removed under reduced pressure to obtain a liquid. The liquid was isolated and purified by column chromatography (silica gel, developing solvent: hexane) to obtain 1.96 g (4.08

09857687 060801

mmol) of a white solid (yield: 43 %). The analyzed values are given below.

^1H -NMR (270 MHz, in CDCl_3 , Based on TMS):

δ 7.73+7.25-6.95 (d+m, 6H), 6.51+6.11+5.98+5.73 (s+s+s+s, 2H), 4.08+3.98 (d+s, 1H), 3.17+3.08+2.98 (s+s+s, 2H), 1.95-0.85 (m, 10H+3H+6H), 1.38 (s, 18H)

(4) Synthesis of dimethylmethylene(3-(1-methyl-1-cyclohexyl)cyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride

- 10 To a solution of 0.70 g (1.5 mmol) of 2-(3-(1-methyl-1-cyclohexyl)cyclopentadienyl)-2-(3,6-di-tert-butylfluorenyl)propane in 30 ml of diethyl ether, 1.9 ml (3.0 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. The solution was cooled to -78°C , and 0.53 g (1.4 mmol) of zirconium tetrachloride (THF) 2-complex was added, followed by stirring at room temperature for 3 days. The reaction solution was
- 20 subjected to sellaite filtration in a nitrogen atmosphere. From the resulting liquid, the solvent was removed under reduced pressure to obtain 0.80 g (1.25 mmol) of an orange solid (yield: 85 %). The analyzed values are given below.

09857687-060801

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 8.10-7.10 (m, 6H), 6.16+5.75+5.58 (m+m+m, 3H), 2.44-1.14 (m, 10H+3H+6H), 1.46 (s, 18H)

FD-MS: m/z = 638, 640, 642 (M^+)

5

Example 8

Synthesis of dimethylmethylene(3-tert-butylcyclopentadienyl)(1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-fluorenyl)zirconium dichloride

10

(1) Synthesis of 1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-fluorene

In a 500 ml three-necked flask purged with nitrogen, 9.72 g (58.6 mmol, 1 eq) of fluorene and

15

19.61 g (134 mmol, 2.3 eq) of 2,5-dimethyl-2,5-hexanediol were placed at room temperature. Then, 85 ml of dehydrated dichloromethane was added. After stirring by a magnetic stirrer, the mixture was cooled to -8°C with an ice bath (light brown slurry). To the

20

slurry, 38.9 g (292 mmol, 5.0 eq) of pulverized anhydrous aluminum chloride was added over a period of 70 minutes, followed by stirring at 0°C for 2 hours. The ice bath was removed, and the solution was stirred at room temperature for 19 hours (dark brown solution).

09857687-060801

After disappearance of fluorene was confirmed by gas chromatography, the dark brown solution was poured into 150 ml of ice water to perform quenching (yellowish brown slurry). After the soluble component

- 5 was extracted with 500 ml of diethyl ether, the organic phase was neutralized with a saturated sodium hydrogencarbonate aqueous solution and washed with water. The dispensed organic phase was dried over $MgSO_4$, then the $MgSO_4$ was filtered off, and from the
- 10 filtrate the solvent was vacuum distilled off by a rotary evaporator. The residue was transferred onto a Kiriyama funnel, washed 6 times with 10 ml of hexane and vacuum dried to obtain a white powder (12.0 g, yield: 53 %).

- 15 (2) Synthesis of 2-(3-tert-butylcyclopentadienyl)-2-(1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-fluorenyl)propane

To a solution of 1.55 g (4.0 mmol) of 1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-

- 20 octahydrodibenzo(b,h)-fluorene in 50 ml of THF, 2.6 ml (4.2 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. To the resulting red solution, a solution
- 25 of 0.97 g (6.0 mmol) of 3-tert-butyl-6,6-

09857637-060801

dimethylfulvene in 25 ml of THF was further dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. Then, 60 ml of water was added. The organic phase

- 5 extracted with ether and separated was dried over magnesium sulfate and then filtered. From the filtrate, the solvent was removed under reduced pressure to obtain a solid. The solid was purified by column chromatography (silica gel, developing solvent: hexane) to obtain 0.95 g of a light yellow solid (yield: 43 %). The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 7.54 (d, 2H), 7.10 (d, 2H), 6.55-5.68 (d+d, 2H), 4.06-4.02 (s+s, 1H), 3.19-3.06 (s+s, 2H), 1.67 (s, 8H), 1.36-1.20 (m, 33H), 1.00 (s, 6H)

- 15 (3) Synthesis of dimethylmethylene(3-tert-butylcyclopentadienyl)(1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-fluorenyl)zirconium dichloride

- 20 To a solution of 0.91 g (1.7 mmol) of 2-(3-tert-butyl-cyclopentadienyl)-2-(1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-fluorenyl)propane in 50 ml of ether, 2.1 ml (3.4 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling,
- 25

- followed by stirring at room temperature for 5 days.
To the resulting reddish orange reaction mixture
having been cooled to -78°C , 0.64 g (1.7 mmol) of
zirconium tetrachloride (THF) 2-complex was added,
5 followed by stirring at room temperature for 5 days.
The resulting reaction mixture was subjected to
sellaita filtration. From the filtrate, the solvent
was removed under reduced pressure, and the residue
was recrystallized from hexane to obtain 0.35 g of an
10 orange solid (yield: 30 %). The analyzed values are
given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 7.99 (s,
2H), 7.59 (d, 2H), 6.09 (t, 1H), 5.53 (t, 1H), 5.43 (t,
1H), 2.30 (s, 6H), 1.72 (s, 8H), 1.52-1.14 (m, 33H)

- 15 FD-MS: m/z = 706, 708, 710 (M^+)

Example 9

- Synthesis of dimethylmethylene(3-
trimethylsilylcyclopentadienyl)(1,1,4,4,7,7,10,10-
20 octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-
fluorenyl)zirconium dichloride

(1) Synthesis of 2-(cyclopentadienyl)-2-
(1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-
octahydrodibenzo(b,h)-fluorenyl)propane

09857637.060801
108090.28925860

In a 200 ml three-necked flask purged with nitrogen, 3.11 g (8.04 mmol, 1 eq) of 1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-fluorene was placed at room

- 5 temperature. Then, 40 ml of dehydrated THF was added, and the mixture was stirred by a magnetic stirrer to give a solution. The solution was cooled to 2°C with an ice bath (light yellow solution). To the solution, 5.2 ml (8.48 mmol, 1.05 eq) of n-BuLi (hexane
- 10 solution) was dropwise added over a period of 10 minutes, and 10 ml of dehydrated THF was further added. The ice bath was removed, and the mixture was stirred at room temperature for 22 hours (dark red slurry). After the slurry was cooled to 0°C with an ice bath, a
- 15 solution of 1.05 ml (8.54 mmol, 1.06 eq) of 6,6-dimethylfulvene in 10 ml of dehydrated THF was dropwise added over a period of 15 minutes (dark red solution). The ice bath was removed, and the solution was stirred at room temperature for 23 hours. The
- 20 resulting dark red brown solution was poured into 100 ml of a diluted hydrochloric acid solution to perform quenching. After the organic phase was washed with 100 ml of a saturated saline solution, the soluble component was extracted from the aqueous layer with 50
- 25 ml of diethyl ether. The soluble component and the

00857687-060801

dispensed organic phase were together dried over MgSO_4 , then the MgSO_4 was filtered off, and from the filtrate the solvent was vacuum distilled off by a rotary evaporator to obtain a yellowish orange solid. The

- 5 solid was purified by silica gel column chromatography (developing solvent: hexane) to obtain a white powder (2.70 g, yield: 68 %).

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 1.02, 1.04 (s, H, $-\text{CH}_3$ of Bridge), 1.18-1.36 (m, 24H, $-\text{CH}_3$ of OMOHDBFlu), 1.63-1.72 (m, 8H, $-\text{CH}_2$ of OMOHDBFlu), 3.08, 3.09, 3.19 (s, 2H, $-\text{CH}_2-$ of Cp), 3.97, 4.02 (s, 1H, 9-H of OMOHDBFlu), 5.90-6.97 (m, 2H, $-\text{CH}-$ of Cp), 6.95, 7.07, 7.54 (s, 4H, Ph-H of OMOHDBFlu); OMOHDBFlu = 1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-

- 15 octahydrodibenzo(b,h)-fluorenyl
(2) Synthesis of 2-(3-trimethylsilylcyclopentadienyl)-2-(1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-fluorenyl)propane

- In a 30 ml Schlenk flask purged with nitrogen,
20 0.66 g (1.34 mmol, 1 eq) of 2-(cyclopentadienyl)-2-(1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-fluorenyl)propane was placed at room temperature. Then, 10 ml of dehydrated THF was added, and the mixture was stirred by a magnetic
25 stirrer to give a solution. The solution was cooled

- with an ice bath (light brown solution). To the solution, 0.88 ml (1.43 mmol, 1.07 eq) of n-BuLi (hexane solution) was dropwise added over a period of 1 to 2 minutes. The ice bath was removed, and the
- 5 solution was stirred at room temperature for 66 hours (dark violet solution). After the solution was cooled with an ice bath, 0.8 ml (6.31 mmol, 4.71 eq) of chlorotrimethylsilane was dropwise added by a syringe (reddish brown solution). The ice bath was removed,
- 10 and the solution was stirred at room temperature for 2.5 hours. The resulting light yellow solution was poured into 50 ml of a diluted hydrochloric acid solution to perform quenching. After the soluble component was extracted with 30 ml of diethyl ether,
- 15 the organic phase was washed with a saturated saline solution. The organic phase was dried over MgSO_4 , then the MgSO_4 was filtered off, and from the filtrate the solvent was vacuum distilled off by a rotary evaporator to obtain a slightly yellow amorphous
- 20 product. The amorphous product was purified by silica gel column chromatography (developing solvent: hexane) to obtain 0.71 g of a white solid (yield: 93 %).

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ -0.02 (s, 9H, $-\text{Si}(\text{CH}_3)_3$), 1.06, 1.08 (s, 6H, $-\text{CH}_3$ of Bridge),

25 1.26-1.47 (m, 24H, $-\text{CH}_3$ of OMOHDBFlu), 1.60-1.71 (m,

09857687-060801

8H, -CH₂- of OMOHDBFlu), 3.33 (s, 1H, 1-H of Cp), 4.08 (s, 1H, 9-H of OMOHDBFlu), 5.97-6.91 (m, 2H, -CH- of fCp), 6.68, 7.46, 7.50, 7.56 (s, 4H, Ph-H of OMOHDBFlu)

- 5 (3) Synthesis of dimethylmethylene(3-trimethylsilylcyclopentadienyl)(1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-fluorenyl)zirconium dichloride

In a 50 ml Schlenk flask purged with nitrogen,

- 10 0.70 g (1.24 mmol, 1 eq) of 2-(3-trimethylsilylcyclopentadienyl)-2-(1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-fluorenyl)propane was placed at room temperature. Then, 23 ml of dehydrated diethyl ether was added, and the
- 15 mixture was stirred by a magnetic stirrer to give a solution. The solution was cooled with an ice bath (slightly yellow solution). To the solution, 1.58 ml (2.58 mmol, 2.08 eq) of n-BuLi (hexane solution) was dropwise added by a syringe. The ice bath was removed,
- 20 and the solution was stirred at room temperature for 20 hours (orangi red solution). From the solution, the solvent was vacuum distilled off, then 15 ml of dehydrated diethyl ether was added again, and the mixture was stirred by a magnetic stirrer to give a
- 25 solution. The solution was cooled with an ice bath

09857687-060801

- (orangy red solution). To the solution, 0.38 ml (0.62 mmol, 0.50 eq) of n-BuLi (hexane solution) was dropwise added by a syringe. The ice bath was removed, and the solution was stirred at room temperature for
- 5 20 hours (red solution). The solution was cooled with a dry ice/methanol bath, and to the solution was added 0.43 g (1.14 mmol, 0.92 eq) of zirconium tetrachloride (THF) 2-complex. The mixture was stirred for 23 hours while allowing the dry ice to naturally disappear and
- 10 the temperature of the mixture to naturally rise. From the resulting red slurry, the volatile component was vacuum distilled off. To the residue, 30 ml of dehydrated hexane was added, and the insoluble component was filtered. The solvent of the resulting
- 15 red solution was vacuum concentrated, and the obtained solution was stored in a refrigerator to obtain 0.28 g of a red plate solid (yield: 33 %).

- $^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 0.11 (s, 9H, $-\text{Si}(\text{CH}_3)_3$), 1.23-1.51 (m, 24H, $-\text{CH}_3$ of OMOHDBFlu),
- 20 1.73-1.75 (m, 8H, $-\text{CH}_2-$ of OMOHDBFlu), 2.33 (s, 6H, $-\text{CH}_3$ of Bridge), 5.49, 5.79, 6.30 (t, 3H, $-\text{CH}-$ of Cp), 7.60, 7.98 (s, 4H, Ph-H of OMOHDBFlu)

FD-MS: m/z = 722, 724, 726 (M^+)

- 25 Example 10

09857687-060801

Synthesis of dimethylmethylene(3-(1,1-
dimethylpropyl)cyclopentadienyl)(3,6-di-tert-
butylfluorenyl)zirconium dichloride

(1) Synthesis of 6-methyl-6-ethylfulvene

- 5 To a solution of 10.00 g (151.3 mmol) of cyclopentadiene in 30 ml of methanol, 13.6 ml (151.8 mmol) of methyl ethyl ketone and 12.8 ml (153.3 mmol) of pyrrolidine were added with ice cooling, followed by stirring at room temperature for one night. After
- 10 the reaction solution was diluted with 200 ml of ether, 100 ml of water was added. The organic phase was separated, washed with water and a saturated saline solution, then dried over anhydrous magnesium sulfate and filtered. From the filtrate, the solvent was
- 15 removed under reduced pressure to obtain a liquid. The liquid was subjected to vacuum distillation (75-82°C/20 mmHg) to obtain 9.20 g (76.55 mmol) of a yellow liquid (yield: 51 %). The analyzed values are given below.

- 20 ¹H-NMR (270 MHz, in CDCl₃, Based on TMS): δ6.50 (m, 4H), 2.55 (f, 2H), 2.20 (s, 3H), 1.18 (t, 3H)

(2) Synthesis of (1,1-dimethylpropyl)cyclopentadiene

- To a solution of 8.00 g (66.6 mmol) of 6-methyl-6-ethylfulvene in 40 ml of ether, 66.0 ml (75.2 mmol) of
- 25 an ether solution of methyllithium was dropwise added

09857687, 060801

- in an nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. Then, 30 ml of water was added. The separated organic phase was washed with water and a saturated saline solution, then dried over magnesium sulfate and filtered. From the filtrate, the solvent was removed under reduced pressure to obtain a liquid. The liquid was subjected to vacuum distillation (165°C/270 mmHg) to obtain 8.40 g (61.66 mmol) of a light yellow liquid (yield: 93 %).
- 10 The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS):

δ 6.55+6.41+6.26+6.14+5.96 (m+m+m+m+m, 3H), 2.94+2.88 (m+m, 2H), 1.48 (m, 2H), 1.12 (s, 6H), 0.72 (m, 3H)

(3) Synthesis of 3-(1,1-dimethylpropyl)-6,6-

- 15 dimethylfulvene

- To a solution of 3.00 g (22.0 mmol) of (1,1-dimethylpropyl)cyclopentadiene in 30 ml of methanol, 16.2 ml (220.4 mmol) of acetone and 3.7 ml (44.0 mmol) of pyrrolidine were added with ice cooling, followed by stirring at room temperature for one night. After the reaction solution was diluted with 100 ml of ether, 50 ml of water was added. The organic phase was separated, washed with water and a saturated saline solution, then dried over anhydrous magnesium sulfate and filtered. From the filtrate, the solvent was
- 25

09857687-060801

removed under reduced pressure to obtain a liquid. The liquid was subjected to vacuum distillation (100°C/1 mmHg) to obtain 1.85 g (10.49 mmol) of a yellow liquid (yield: 48 %). The analyzed values are given below.

- 5 $^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 6.52 (m, 2H), 6.13 (m, 1H), 2.18 (d, 6H), 1.52 (f, 2H), 1.18 (s, 6H), 0.80 (t, 3H)

- (4) Synthesis of 2-(3-(1,1-dimethylpropyl)cyclopentadienyl)-2-(3,6-di-tert-butylfluorenyl)propane
- 10

- To a solution of 2.14 g (7.7 mmol) of 3,6-di-tert-butylfluorene in 40 ml of THF, 5.0 ml (8.1 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by
- 15 stirring at room temperature for one night. To the resulting red solution, a solution of 1.81 g (10.3 mmol) of 3-(1,1-dimethylpropyl)-6,6-dimethylfulvene in 30 ml of THF was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at
- 20 room temperature for 3 days. After the reaction solution was diluted with 100 ml of ether, 50 ml of water was added. The separated organic phase was washed with water and a saturated saline solution, then dried over magnesium sulfate and filtered. From
- 25 the filtrate, the solvent was removed under reduced

09857687-060801

pressure to obtain a liquid. The liquid was isolated and purified by column chromatography (silica gel, developing solvent: hexane) to obtain 2.06 g (4.53 mmol) of a white solid (yield: 59 %). The analyzed

5 values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS):

87.72+7.20-6.95 (s+m, 6H), 6.42+6.08+5.92+5.72 (s+s+s+s, 2H), 4.05 (d, 1H), 3.13+2.98+2.88 (s+s+s, 2H), 1.52 (m, 2H), 1.38 (s, 18H), 1.19+1.13 (d+s, 6H), 1.08 (d, 6H),

10 0.82 (m, 3H)

(5) Synthesis of dimethylmethylene(3-(1,1-dimethylpropyl)cyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride

- To a solution of 0.82 g (1.8 mmol) of 2-(3-(1,1-
- 15 dimethylpropyl)cyclopentadienyl)-2-(3,6-di-tert-butylfluorenyl)propane in 30 ml of diethyl ether, 2.3 ml (3.8 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for
- 20 one night. The solution was cooled to -78°C , and 0.66 g (1.8 mmol) of zirconium tetrachloride (THF) 2-complex was added, followed by stirring at room temperature for one night. The reaction solution was subjected to sellaite filtration in a nitrogen
- 25 atmosphere. From the resulting liquid, the solvent was

09857637.060801

removed under reduced pressure. To the residue, 10 ml of hexane was added, and the mixture was cooled to perform crystallization and thereby obtain 0.38 g (0.62 mmol) of a red solid (yield: 34 %). The analyzed

5 values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS):

8.02+7.70, 7.30 (t+m+m, 6H), 6.10+5.75+5.52 (t+t+t, 3H), 2.32 (d, 6H), 1.46 (s, 18H), 1.40 (f, 2H), 1.20+1.10 (s+s, 6H), 0.65 (t, 3H)

10 FD-MS: m/z = 612, 614, 616 (M^+)

Example 11

Synthesis of dimethylmethylene(3-(1-ethyl-1-methylpropyl)cyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride

15 (1) Synthesis of 6,6-diethylfulvene

To a solution of 22.00 g (332.8 mmol) of cyclopentadiene in 35 ml of methanol, 36.0 ml (665.1 mmol) of diethyl ketone and 28.0 ml (335.5 mmol) of pyrrolidine were added with ice cooling, followed by stirring at room temperature for one night. After the reaction solution was diluted with 200 ml of ether, 100 ml of water was added. The organic phase was separated, washed with water and a saturated saline solution, then dried over anhydrous magnesium sulfate

25

09857687.060801

and filtered. From the filtrate, the solvent was removed under reduced pressure to obtain a liquid. The liquid was subjected to vacuum distillation (78-83°C/4 mmHg) to obtain 36.50 g (271.94 mmol) of a yellow

- 5 liquid (yield: 82 %). The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 6.50 (m, 4H), 2.55 (f, 4H), 1.18 (t, 6H)

- (2) Synthesis of (1-ethyl-1-methylpropyl)cyclopentadiene
- 10

To a solution of 8.00 g (59.6 mmol) of 6,6-diethylfulvene in 35 ml of ether, 60.0 ml (68.4 mmol) of an ether solution of methylolithium was dropwise added in a nitrogen atmosphere with ice cooling,

- 15 followed by stirring at room temperature for one night. Then, 30 ml of water was added. The separated organic phase was washed with water and a saturated saline solution, then dried over magnesium sulfate and filtered. From the filtrate, the solvent was removed
- 20 under reduced pressure to obtain a liquid. The liquid was subjected to vacuum distillation (92°C/40 mmHg) to obtain 5.50 g (36.6 mmol) of a light yellow liquid (yield: 61 %). The analyzed values are given below.

09857697-060801
108890-28929860

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 6.60-5.90 (m, 3H), 2.94+2.88 (f+f, 2H), 1.48 (m, 4H), 1.08 (s, 3H), 0.72 (m, 6H)

(3) Synthesis of 3-(1-ethyl-1-methylpropyl)-6,6-

5 dimethylfulvene

- To a solution of 2.50 g (16.6 mmol) of (1-ethyl-1-methylpropyl)cyclopentadiene in 20 ml of methanol, 8.4 ml (114.4 mmol) of acetone and 2.8 ml (33.5 mmol) of pyrrolidine were added with ice cooling, followed by
- 10 stirring at room temperature for one night. After the reaction solution was diluted with 100 ml of ether, 50 ml of water was added. The organic phase was separated, washed with water and a saturated saline solution, then dried over anhydrous magnesium sulfate and
- 15 filtered. From the filtrate, the solvent was removed under reduced pressure to obtain a liquid. The liquid was isolated and purified by column chromatography (silica gel, developing solvent: hexane) to obtain 2.90 g (15.24 mmol) of a yellow liquid (yield: 92 %).
- 20 The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 6.50 (m, 2H), 6.11 (m, 1H), 2.13 (d, 6H), 1.50 (f, 4H), 1.09 (d, 3H), 0.78 (m, 6H)

09867687-060801

(4) Synthesis of 2-(3-(1-ethyl-1-methylpropyl)cyclopentadienyl)-2-(3,6-di-tert-butylfluorenyl)propane

- To a solution of 1.93 g (6.9 mmol) of 3,6-di-tert-butylfluorene in 30 ml of THF, 4.7 ml (7.6 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. To the resulting red solution, a solution of 1.70 g (8.9 mmol) of 3-(1-ethyl-1-methylpropyl)-6,6-dimethylfulvene in 10 ml of THF was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for 5 days. After the reaction solution was diluted with 100 ml of ether, 50 ml of water was added. The separated organic phase was washed with water and a saturated saline solution, then dried over magnesium sulfate and filtered. From the filtrate, the solvent was removed under reduced pressure to obtain a liquid. The liquid was isolated and purified by column chromatography (silica gel, developing solvent: hexane) to obtain 1.20 g (2.56 mmol) of a white solid (yield: 37 %). The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS):

- 87.72+7.20-6.95 (s+m, 6H), 6.42+6.08+5.92+5.72 (s+s+s+s,

2H), 4.05 (d, 1H), 3.13+2.98+2.88 (s+s+s, 2H), 1.52 (m, 4H), 1.38 (s, 18H), 1.09, 1.06 (m,m, 9H), 0.80 (m, 6H)

(5) Synthesis of dimethylmethylene(3-(1-ethyl-1-methylpropyl)cyclopentadienyl)(3,6-di-tert-

5 butylfluorenyl)zirconium dichloride

- To a solution of 0.70 g (1.5 mmol) of 2-(3-(1-ethyl-1-methylpropyl)cyclopentadienyl)-2-(3,6-di-tert-butylfluorenyl)propane in 35 ml of diethyl ether, 1.9 ml (3.1 mmol) of a hexane solution of n-butyllithium
- 10 was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. The solution was cooled to -78°C, and 0.55 g (1.5 mmol) of zirconium tetrachloride (THF) 2-complex was added, followed by stirring at room
- 15 temperature for one night. The reaction solution was subjected to sellaite filtration in a nitrogen atmosphere. From the resulting liquid, the solvent was removed under reduced pressure. To the residue, 5 ml of hexane was added, and the mixture was cooled to
- 20 perform crystallization and thereby obtain 0.33 g (0.52 mmol) of a red solid (yield: 35 %). The analyzed values are given below.

¹H-NMR (270 MHz, in CDCl₃, Based on TMS):

δ8.00+7.70, 7.30 (t+m+m, 6H), 6.09+5.74+5.52 (t+t+t,

09857687-060801

3H), 2.31 (m, 6H), 1.46 (s, 18H), 1.27 (m, 4H), 1.10 (m, 3H), 0.64 (m, 6H)

FD-MS: m/z = 626, 628, 630 (M^+)

5 Example 12

Synthesis of dimethylmethylene(3-(1,1,3-trimethylbutyl)cyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride

- (1) Synthesis of 6-methyl-6-isobutylfulvene
- 10 To a solution of 10.00 g (151.3 mmol) of cyclopentadiene in 30 ml of methanol, 18.9 ml (151.1 mmol) of methyl isobutyl ketone and 12.8 ml (153.3 mmol) of pyrrolidine were added with ice cooling, followed by stirring at room temperature for one night.
- 15 After the reaction solution was diluted with 100 ml of ether, 50 ml of water was added. The organic phase was separated, washed with water and a saturated saline solution, then dried over anhydrous magnesium sulfate and filtered. From the filtrate, the solvent was
- 20 removed under reduced pressure to obtain a liquid. The liquid was subjected to vacuum distillation (83-88°C/10 mmHg) to obtain 15.80 g (106.58 mmol) of a yellow liquid (yield: 71 %). The analyzed values are given below.

00857627-060801

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 6.50 (m, 4H), 2.42 (d, 2H), 2.19 (s, 3H), 1.96 (m, 1H), 0.93 (d, 6H)

(2) Synthesis of (1,1,3-trimethylbutyl)cyclopentadiene

5 To a solution of 8.00 g (54.0 mmol) of 6-methyl-6-isobutylfulvene in 30 ml of ether, 54.0 ml (61.6 mmol) of an ether solution of methyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for 4 days.

10 Then, 30 ml of water was added. The separated organic phase was washed with water and a saturated saline solution, then dried over magnesium sulfate and filtered. From the filtrate, the solvent was removed under reduced pressure to obtain a liquid. The liquid
15 was subjected to vacuum distillation ($120^\circ\text{C}/25\text{ mmHg}$) to obtain 7.10 g (43.2 mmol) of a light yellow liquid (yield: 80 %).

(3) Synthesis of 3-(1,1,3-trimethylbutyl)-6,6-dimethylfulvene

20 To a solution of 3.00 g (18.3 mmol) of (1,1,3-trimethylbutyl)cyclopentadiene in 30 ml of methanol, 13.4 ml (182.5 mmol) of acetone and 3.1 ml (36.6 mmol) of pyrrolidine were added with ice cooling, followed by stirring at room temperature for one night. After

09857687-060801

the reaction solution was diluted with 100 ml of ether, 50 ml of water was added. The organic phase was separated, washed with water and a saturated saline solution, then dried over anhydrous magnesium sulfate and filtered. From the filtrate, the solvent was removed under reduced pressure to obtain a liquid. The liquid was subjected to vacuum distillation (130°C/1 mmHg) to obtain 3.50 g (17.1 mmol) of a yellow liquid (yield: 94 %). The analyzed values are given below.

- 10 ¹H-NMR (270 MHz, in CDCl₃, Based on TMS): δ 6.50 (m, 2H), 6.11 (m, 1H), 2.15 (d, 6H), 1.52 (m, 1H), 1.42 (d, 2H), 1.17 (s, 6H), 0.81 (d, 6H)
- (4) Synthesis of 2-(3-(1,1,3-trimethylbutyl)cyclopentadienyl)-2-(3,6-di-tert-butylfluorenyl)propane
- 15

- To a solution of 2.16 g (7.8 mmol) of 3,6-di-tert-butylfluorene in 35 ml of THF, 5.0 ml (8.2 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. To the resulting red solution, a solution of 2.16 g (10.6 mmol) of 3-(1,1,3-trimethylbutyl)-6,6-dimethylfulvene in 10 ml of THF was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for 5 days. After the reaction
- 25

0957687-050801

solution was diluted with 100 ml of ether, 50 ml of water was added. The separated organic phase was washed with water and a saturated saline solution, then dried over magnesium sulfate and filtered. From

- 5 the filtrate, the solvent was removed under reduced pressure to obtain a liquid. The liquid was isolated and purified by column chromatography (silica gel, developing solvent: hexane) to obtain 2.80 g (5.80 mmol) of a white solid (yield: 74 %). The analyzed
- 10 values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS):

δ 7.71+7.14-6.95 (s+m, 6H), 6.42+6.08+5.92+5.72 (s+s+s+s, 2H), 4.05 (d, 1H), 3.13+2.98+2.88 (s+s+s, 2H), 1.62 (m, 1H), 1.45 (m, 2H), 1.38 (s, 18H), 1.22+1.18+1.06

- 15 (s+s+m, 12H), 0.80 (m, 6H)

(5) Synthesis of dimethylmethylene(3-(1,1,3-trimethylbutyl)cyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride

- To a solution of 0.87 g (1.8 mmol) of 2-(3-(1,1,3-trimethylbutyl)cyclopentadienyl)-2-(3,6-di-tert-butylfluorenyl)propane in 35 ml of diethyl ether, 2.3 ml (3.7 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for
- 20
- 25 one night. The solution was cooled to -78°C , and 0.67

0000072897886

g (1.8 mmol) of zirconium tetrachloride (THF) 2-complex was added, followed by stirring at room temperature for 2 days. The reaction solution was subjected to sellaite filtration in a nitrogen

- 5 atmosphere. From the resulting liquid, the solvent was removed under reduced pressure to obtain 0.6 g (0.93 mmol) of a red solid (yield: 52 %). The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS):

- 10 δ 8.00+7.70, 7.30 (t+m+m, 6H), 6.06+5.69+5.49 (t+t+t, 3H), 2.28 (m, 6H), 1.41 (s, 18H), 1.42-0.64 (m, 9H), 0.59 (m, 6H)

FD-MS: m/z = 640, 642, 644 (M^+)

15 Example 13

Synthesis of dimethylmethylene(3-trimethylsilylcyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride

- (1) Synthesis of 2-(cyclopentadienyl)-2-(3,6-di-tert-butylfluorenyl)propane
- 20 butylfluorenyl)propane

To a solution of 3.0 g (10.8 mmol) of 3,6-di-tert-butylfluorene in 40 ml of THF, 7.0 ml (11.3 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by

25 stirring at room temperature for 6 hours. From the

09857687 060801
108000 28925860

- reaction mixture, the solvent was removed under reduced pressure, and the residue was washed with pentane and dried to obtain a white solid. To a solution of the solid in 30 ml of THF, a solution of
- 5 1.4 g (13.2 mmol) of 6,6-dimethylfulvene in 30 ml of THF was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring for 5 hours. Then, 30 ml of water was added. The organic phase extracted with diethyl ether and separated was dried over
- 10 magnesium sulfate and filtered. From the filtrate, the solvent was removed under reduced pressure to obtain a solid. The solid was recrystallized from methanol to obtain 2.9 g of a slightly yellow solid. The analyzed values are given below.
- 15 $^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 7.73 (s, 2H), 7.20-6.98 (m, 4H), 6.95-5.93 (m, 3H), 4.06 (d, 1H), 3.13 (d, 2H), 1.39 (s, 18H), 1.07 (d, 6H)
- (2) Synthesis of 2-(3-trimethylsilylcyclopentadienyl)-2-(3,6-di-tert-butylfluorenyl)propane
- 20 In a 50 ml Schlenk flask purged with nitrogen, 1.44 g (3.74 mmol, 1 eq) of 2-(cyclopentadienyl)-2-(3,6-di-tert-butylfluorenyl)propane was placed at room temperature. Then, 20 ml of dehydrated THF was added, and the mixture was stirred by a magnetic stirrer to
- 25 give a solution. The solution was cooled with an ice

0957697, 090801

- bath (light yellowish orange solution). To the solution, 2.5 ml (1.63 mmol, 1.09 eq) of n-BuLi (hexane solution) was dropwise added. The ice bath was removed, and the solution was stirred at room temperature for 19 hours (dark red solution). The solution was cooled with an ice bath, and to the solution, 2.7 ml (21.3 mmol, 5.70 eq) of chlorotrimethylsilane was dropwise added by a syringe. The ice bath was removed, and the solution was stirred at room temperature for 3 hours. The resulting yellow solution was poured into 80 ml of a diluted hydrochloric acid solution to perform quenching. After the soluble component was extracted with 100 ml of diethyl ether, the organic phase was washed with 50 ml of a saturated saline solution. The organic phase was dried over MgSO_4 , then the MgSO_4 was filtered off, and from the filtrate the solvent was vacuum distilled off by a rotary evaporator to obtain a light yellow solid. The solid was washed with 50 ml of methanol and vacuum dried to obtain 1.44 g a light creamy powder (yield: 84 %).

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ -0.01 (s, 9H, -Si(CH₃)₃), 1.35, 1.39 (s, 18H, tBu of 3, 6-tBu₂Flu), 1.37, 1.41 (s, 6H, -CH₃ of Bridge), 3.34 (s, 1H, 1-H of Cp), 4.14 (s, 1H, 9-H of 3, 6-tBu₂Flu),

6.01, 6.58, 6.87 (m, 3H, -CH- of Cp), 6.71-7.72 (m, 6H, Ph-H of 3, 6-tBu₂Flu)

(3) Synthesis of dimethylmethylene(3-trimethylsilylcyclopentadienyl)(3,6-di-tert-

5 butylfluorenyl)zirconium dichloride

In a 50 ml Schlenk flask purged with nitrogen, 1.32 g (2.89 mmol, 1 eq) of 2-(3-trimethylsilylcyclopentadienyl)-2-(3,6-di-tert-butylfluorenyl)propane was placed at room temperature.

- 10 Then, 30 ml of dehydrated diethyl ether was added, and the mixture was stirred by a magnetic stirrer to give a solution. The solution was cooled with an ice bath (creamy solution). To the solution, 3.9 ml (6.36 mmol, 2.20 eq) of n-BuLi (hexane solution) was dropwise
- 15 added by a syringe. The ice bath was removed, and the mixture was stirred at room temperature for 27 hours (yellowish orange slurry). The slurry was cooled with a dry ice/methanol bath, and thereto was added 1.09 g (2.89 mmol, 1.00 eq) of zirconium tetrachloride (THF)
- 20 2-complex. The mixture was stirred for 22 hours while allowing the dry ice to naturally disappear and the temperature of the mixture to naturally rise to room temperature. From the resulting reddish orange slurry, the volatile component was vacuum distilled off. To
- 25 the residue, 50 ml of dehydrated hexane was added, and

00857637.060301

then the insoluble component was filtered through a filter. To the orange powder remaining on the filter, 10 ml of dehydrated dichloromethane was added to filter the soluble component. From the resulting red solution, the solvent was vacuum distilled off to obtain an orange solid (0.74 g, yield: 42 %).

¹H-NMR (270 MHz, in CDCl₃, Based on TMS): δ0.12 (s, 9H, -Si(CH₃)₃), 1.44 (s, 18H, tBu of 3, 6-tBu₂Flu), 2.35 (s, 6H, -CH₃ of Bridge), 5.61, 5.96, 6.33 (t, 3H, -CH- of Cp), 7.32, 7.33 (d, 2H, 1, 8-H of 3, 6-tBu₂Flu), 7.70 (m, 2H, 2, 7-H of 3, 6-tBu₂Flu), 8.01 (s, 2H, 4, 5-H of 3, 6-tBu₂Flu)

FD-MS: m/z = 614, 616, 618 (M⁺)

15 Example 14

Synthesis of dimethylmethylene(3-(1,1-dimethylbutyl)cyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride

(1) Synthesis of 6-methyl-6-propylfulvene

- 20 To a solution of 10.00 g (151.3 mmol) of cyclopentadiene in 40 ml of methanol, 18.6 ml (174.2 mmol) of methyl propyl ketone and 4.5 ml (54.7 mmol) of pyrrolidine were added with ice cooling, followed by stirring at room temperature for one night. After 25 the reaction solution was diluted with 100 ml of ether,

09857687, 0660801

50 ml of water was added. The organic phase was separated, washed with water and a saturated saline solution, then dried over anhydrous magnesium sulfate and filtered. From the filtrate, the solvent was

- 5 removed under reduced pressure to obtain a liquid. The liquid was subjected to vacuum distillation (70°C/1 mmHg) to obtain 12.30 g (91.64 mmol) of a yellow liquid (yield: 61 %). The analyzed values are given below.

- 10 ¹H-NMR (270 MHz, in CDCl₃, Based on TMS): δ6.55 (m, 4H), 2.56 (m, 2H), 2.23 (t, 3H), 1.67 (m, 2H), 1.00 (m, 3H)

(2) Synthesis of (1,1-dimethylbutyl)cyclopentadiene

- To a solution of 7.00 g (52.2 mmol) of 6-methyl-6-
15 propylfulvene in 40 ml of THF, 50.3 ml (57.3 mmol) of an ether solution of methyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. After the reaction solution was diluted with 100 ml of ether, 30
20 ml of water was added. The separated organic phase was washed with water and a saturated saline solution, then dried over magnesium sulfate and filtered. From the filtrate, the solvent was removed under reduced pressure to obtain a liquid. The liquid was subjected
25 to vacuum distillation (75°C/5-7 mmHg) to obtain 6.40

09857687, 060801

g (42.6 mmol) of a light yellow liquid (yield: 82 %).

The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS):

δ 6.55+6.41+6.26+6.14+5.96 (m+m+m+m+m, 3H), 2.94+2.88

5 (m+m, 2H), 1.48 (m, 2H), 1.12 (s, 6H), 1.00-0.80 (m, 5H)

(3) Synthesis of 3-(1,1-dimethylbutyl)-6,6-dimethylfulvene

To a solution of 3.00 g (20.0 mmol) of (1,1-dimethylbutyl)cyclopentadiene in 30 ml of methanol, 14.6 ml (198.8 mmol) of acetone and 2.5 ml (29.9 mmol) of pyrrolidine were added with ice cooling, followed by stirring at room temperature for 3 days. After the reaction solution was diluted with 100 ml of ether, 50 ml of water was added. The organic phase was separated, washed with water and a saturated saline solution, then dried over anhydrous magnesium sulfate and filtered. From the filtrate, the solvent was removed under reduced pressure to obtain a liquid. The liquid was isolated and purified by column chromatography (silica gel, developing solvent: hexane) to obtain 2.70 g (14.19 mmol) of a yellow liquid (yield: 71 %). The analyzed values are given below.

09857687.060801

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 6.51 (m, 2H), 6.11 (m, 1H), 2.15 (d, 6H), 1.44 (m, 2H), 1.26-1.10 (m, 2H), 1.15 (s, 6H), 0.85 (t, 3H)

(4) Synthesis of 2-(3-(1,1-

- 5 dimethylbutyl)cyclopentadienyl)-2-(3,6-di-tert-butylfluorenyl)propane

To a solution of 1.70 g (6.1 mmol) of 3,6-di-tert-butylfluorene in 40 ml of THF, 3.9 ml (6.4 mmol) of a hexane solution of n-butyllithium was dropwise added
10 in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. To the resulting red solution, a solution of 1.22 g (6.4 mmol) of 3-(1,1-dimethylbutyl)-6,6-dimethylfulvene in 35 ml of THF was dropwise added in a nitrogen
15 atmosphere with ice cooling, followed by stirring at room temperature for one night. After the reaction solution was diluted with 100 ml of ether, 50 ml of water was added. The separated organic phase was washed with water and a saturated saline solution,
20 then dried over magnesium sulfate and filtered. From the filtrate, the solvent was removed under reduced pressure to obtain a liquid. The liquid was isolated and purified by column chromatography (silica gel, developing solvent: hexane) to obtain 1.73 g (3.69

mmol) of an oily liquid (yield: 61 %). The analyzed values are given below.

¹H-NMR (270 MHz, in CDCl₃, Based on TMS):

87.71+7.16-6.95 (s+m, 6H), 6.42-5.70 (m, 2H), 4.03 (d,

5 1H), 3.12+3.03+2.94 (s+s+s, 2H), 1.38 (s, 18H),
1.27+1.18 (m+d, 10H), 1.06 (s, 6H), 0.92 (m, 3H)

(5) Synthesis of dimethylmethylene(3-(1,1-dimethylbutyl)cyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride

- 10 To a solution of 0.60 g (1.3 mmol) of 2-(3-(1,1-dimethylbutyl)cyclopentadienyl)-2-(3,6-di-tert-butylfluorenyl)propane in 50 ml of diethyl ether, 1.6 ml (2.6 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice
- 15 cooling, followed by stirring at room temperature for 3 days. The solution was cooled to -78°C, and 0.46 g (1.2 mmol) of zirconium tetrachloride (THF) 2-complex was added, followed by stirring at room temperature for 4 days. The reaction solution was subjected to
- 20 sellaita filtration in a nitrogen atmosphere. From the resulting liquid, the solvent was removed under reduced pressure. To the residue, 15 ml of hexane was added, and the mixture was cooled to perform crystallization and thereby obtain 0.33 g (0.53 mmol)

03857687-060801

of a red solid (yield: 43 %). The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS):

5 δ 8.01+7.70, 7.30 (t+m+m, 6H), 6.07+5.72+5.50 (t+t+t, 3H), 2.31 (d, 6H), 1.44 (s, 18H), 1.42-0.80 (m, 10H), 0.76 (t, 3H)

FD-MS: m/z = 626, 628, 630 (M^+)

Example 15

10 Synthesis of dimethylmethylene(3-tert-
butylcyclopentadienyl) (2,7-di-tert-
butylfluorenyl)zirconium dichloride

(1) Synthesis of 2-(3-tert-butyl-5-methylcyclopentadienyl)-2-(2,7-di-tert-butylfluorenyl)propane
15

To a solution of 2.45 g (8.80 mmol) of 2,7-di-tert-butylfluorene in 50 ml of THF, 5.67 ml (9.24 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere at 0°C ,
20 followed by stirring at room temperature overnight. To the resulting solution, a solution of 2.85 g (17.6 mmol) of 3-tert-butyl-6,6-dimethylfulvene in 30 ml of THF was successively dropwise added in a nitrogen atmosphere at 0°C , followed by stirring at room
25 temperature overnight to perform reaction. After the

09857687:060801

reaction, 30 ml of water was added. The organic phase was extracted with ether and dried over anhydrous magnesium sulfate. From the resulting solution, the solvent was distilled off to obtain a crude yellow solid. The solid was washed with methanol to obtain 2.77 g of a powdery white solid (yield: 71.5 %). The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 7.56 (d, 2H), 7.33-7.12 (4H), 6.59-5.68 (2H), 4.14-4.05 (1H), 3.21-3.04 (2H), 1.29 (s, 18H), 1.01 (s, 6H)

(2) Synthesis of dimethylmethylene(3-tert-butylcyclopentadienyl)(2,7-di-tert-butylfluorenyl)zirconium dichloride

To a solution of 1.0 g (2.27 mmol) of 2-(3-tert-butylcyclopentadienyl)-2-(2,7-di-tert-butylfluorenyl)propane in 50 ml of diethyl ether, 2.9 ml (4.65 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere at -78°C .

With stirring, the temperature of the mixture was

allowed to naturally rise to room temperature, and the reaction was performed overnight to obtain a red solution. The solution was cooled to -78°C again, and 0.86 g (2.27 mmol) of zirconium tetrachloride (THF) 2-complex was added in a nitrogen atmosphere. The

mixture was stirred and reacted while the temperature

09857697.060801

of the mixture was allowed to naturally rise to room temperature. The resulting red suspension was subjected to sellalite filtration to remove a white solid. Then, the orange filtrate was concentrated and dried to obtain a crude red solid. The solid was recrystallized from 5 ml of toluene to obtain 113 mg of a red solid. The analyzed values are given below.

¹H-NMR (270 MHz, in CDCl₃, Based on TMS): δ8.00-7.95 (2H), 7.72-7.58 (4H), 6.12 (t, 1H), 5.60 (t, 1H), 5.56 (t, 1H), 2.36 (s, 6H), 1.34 (s, 18H), 1.14 (s, 9H)

FD-MS: m/z = 598, 600, 602 (M⁺)

Example 16

15 Synthesis of diphenylmethylene(3-trimethylsilylcyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride

(1) Synthesis of 1-(cyclopentadienyl)-1-(3,6-di-tert-butylfluorenyl)diphenylmethane

20 To a solution of 2.5 g (9.0 mmol) of 3,6-di-tert-butylfluorene in 40 ml of THF, 6.1 ml (9.8 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for 4 hours. The
25 resulting solution was ice cooled again, and thereto

was dropwise added a solution of 2.5 g (10.8 mmol) of 6,6-diphenylfulvene in 30 ml of THF in a nitrogen atmosphere, followed by stirring at room temperature for 5 hours. Then, 50 ml of water was added. The

- 5 organic phase extracted with diethyl ether and separated was dried over magnesium sulfate and then filtered. From the filtrate, the solvent was removed under reduced pressure to obtain a solid. The solid was recrystallized from methanol to obtain 3.4 g of a
- 10 slightly yellow solid. The analyzed values are given below.

¹H-NMR (270 MHz, in CDCl₃, Based on TMS): δ 7.47 (s, 2H), 7.28 (br, 4H), 7.07-7.01 (br, 10H), 6.51-6.18 (m, 3H), 5.46+5.41 (s+s, 1H), 2.94+2.86 (s+s, 2H), 1.30 (s,

- 15 18H)

(2) Synthesis of 1-(3-trimethylsilylcyclopentadienyl)-1-(3,6-di-tert-butylfluorenyl)diphenylmethane

To a solution of 0.45 g (0.88 mmol) of 1-(cyclopentadienyl)-1-(3,6-di-tert-

- 20 butylfluorenyl)diphenylmethane in 30 ml of THF, 0.54 ml (0.97 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for 16 hours. After the resulting solution was cooled to -
- 25 78°C, a solution of 0.22 ml (1.76 mmol) of

09857687-050804

chlorotrimethylsilane in 10 ml of THF was slowly added, followed by stirring at room temperature for 6 hours. To the reaction solution, 20 ml of water was added to terminate the reaction. The resulting solution was

5 subjected to extraction with diethyl ether, then dried over anhydrous magnesium sulfate and vacuum evaporated to dryness to obtain a yellow solid. The solid was washed with a small amount of methanol and dried under reduced pressure to obtain 0.42 g of an opaque white

10 solid (yield: 81.8 %). The analyzed values are given below.

¹H-NMR (270 MHz, in CDCl₃, Based on TMS): 87.80 (t, 2H), 7.63 (dd, 2H), 7.31 (ddd, 2H), 6.99 (dd, 1H), 6.50 (t, 1H), 6.44 (dd, 1H), 1.80 (d, 6H), 1.41 (d, 18H), .(1.12 (s, 9H)

15

(3) Synthesis of diphenylmethylene(3-trimethylsilylcyclopentadienyl) (3,6-di-tert-butylfluorenyl)zirconium dichloride

To a solution of 0.58 g (1.14 mmol) of 1-(3-trimethylsilylcyclopentadienyl)-1-(3,6-di-tert-butylfluorenyl)diphenylmethane in 40 ml of THF, 1.47 ml (2.40 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for

20

25 8 hours. From the reaction mixture, the solvent was

09857687, 060801

removed under reduced pressure to obtain an reddish orange solid. To the solid, 100 ml of dichloromethane was added at -78°C , and they were stirred to give a solution. Then, the solution was added to a suspension of 0.44 g (1.02 mmol) of zirconium tetrachloride (THF) 2-complex in 5 ml of dichloromethane having been cooled to -78°C , followed by stirring at -78°C for 4 hours. The solution was slowly heated and stirred at room temperature for one day and night. From the reaction solution, the solvent was removed under reduced pressure to obtain a yellowish brown solid. The solid was extracted with hexane and subjected to sellaite filtration. The filtrate was concentrated under reduced pressure and kept at -25°C to obtain an orange solid. The solid was washed with a small amount of diethyl ether to obtain 0.19 g of a reddish orange solid. The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 7.80 (t, 2H), 7.63 (dd, 2H), 7.31 (ddd, 2H), 6.99 (dd, 1H), 6.50 (t, 1H), 6.44 (dd, 1H), 1.80 (d, 6H), 1.41 (d, 18H), 1.12 (s, 9H)

FD-MS: $m/z = 738, 740, 742 (M^+)$

Example 17

Synthesis of diphenylmethylene(3-phenylcyclopentadienyl) (1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-fluorenyl)zirconium dichloride

5 (1) Synthesis of phenylcyclopentadiene

To 160 ml (120 mmol) of a THF solution of phenylmagnesium chloride, a solution of 8.38 ml (100 mmol) of 2-cyclopentenone in 70 ml of THF was dropwise added with ice cooling. The mixture was stirred at 0°C for 1 hour and then further stirred at room temperature for 1 hour. Then, 200 ml of an ammonium chloride saturated aqueous solution was added. To the reaction solution, diethyl ether was added to perform extraction. The resulting ether solution was dried over magnesium sulfate, and the solvent was distilled off to obtain of a crude product of phenylcyclopentenol as a gold liquid (17.5 g). In a glass tube oven, 6 g of the crude product was placed, and the product was heated at 180 to 190°C for 1 hour at atmospheric pressure, then cooled to room temperature and slowly heated (finally) to 195°C under reduced pressure (1 to 4 mmHg). As a result, 2.5 g of a white crystal was sublimed (51.3 %).

¹H-NMR (270 MHz, in CDCl₃, Based on TMS): δ{7.58 (dd), 7.50 (dd), 7.47-7.10 (m), 5H}, {6.94 (dt), 6.89

09857587-060801

(p), 6.65 (p), 7.58 (m), 6.43 (m), 3.38 (t), 3.19 (t), 5H)}

(2) Synthesis of 3,6,6-triphenylfulvene

- A solution of 2.5 g (17.6 mmol) of
- 5 phenylcyclopentadiene in 30 ml of toluene was ice cooled, and thereto was dropwise added 13.0 ml (21.1 mmol) of a hexane solution of n-butyllithium. The resulting white slurry was stirred at room temperature for one night. From the slurry, the solvent was
- 10 filtered off to give a THF solution (brown solution). To the solution, a solution of 3.2 g (17.6 mmol) of benzophenone in 10 ml of THF was added, followed by stirring at room temperature for one night. After addition of water, the mixture was subjected to
- 15 extraction with diethyl ether and dried over magnesium sulfate. Then, the ether was distilled off to obtain a red viscous liquid. The liquid was purified by a silica gel column to obtain a red solid.

- $^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ {7.81
- 20 (d), 7.61 (d), 7.56-7.24 (m), 15H}, 7.04 (dd, 1H), 6.59 (t, 1H), 6.46 (dd, 1H)

(3) Synthesis of 1-(3-phenylcyclopentadienyl)-1-(1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-fluorenyl)diphenylmethane

09857687-060801

- To a solution of 1.0 g (2.59 mmol) of 1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-fluorene in 30 ml of THF, 1.75 ml (2.85 mmol) of a hexane solution of n-butyllithium
- 5 was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for 4 hours. Then, a solution of 0.92 g (3.11 mmol) of 3,6,6-triphenylfulvene in 10 ml of THF was slowly added at room temperature, followed by stirring for 15
- 10 hours. To the reaction solution, 20 ml of water was added to terminate the reaction. The resulting solution was subjected to extraction with diethyl ether, then dried over anhydrous magnesium sulfate and vacuum evaporated to dryness to obtain a yellow solid.
- 15 The solid was washed twice with a small amount of methanol and dried under reduced pressure to obtain 1.24 g of an opaque white solid (yield: 69.1 %).
- (4) Synthesis of diphenylmethene(3-phenylcyclopentadienyl) (1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-fluorenyl)zirconium dichloride
- 20

- To a solution of 1.20 g (1.73 mmol) of 1-(3-phenylcyclopentadienyl)-1-(1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-fluorenyl)diphenylmethane in 30 ml of THF, 2.23 ml
- 25

09357637-060301

- (3.63 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for 8 hours. From the reaction mixture, the solvent was removed under reduced pressure to obtain a reddish orange solid. To the solid, 100 ml of dichloromethane was added at -78°C , and they were stirred to give a solution. Then, the solution was added to a suspension of 0.59 g (1.56 mmol) of titanium tetrachloride (THF) 2-complex in 5 ml of dichloromethane having been cooled to -78°C , followed by stirring at -78°C for 4 hours. The resulting solution was slowly heated and stirred at room temperature for one day and night. From the reaction solution, the solvent was removed under reduced pressure to obtain a yellowish brown solid. The solid was extracted with hexane and subjected to sellaite filtration. The filtrate was concentrated under reduced pressure, and a small amount of diethyl ether was added to produce an orange precipitate. The mother liquor was removed, and the pressure was reduced to obtain 3 mg of a reddish orange solid (yield: 2.3 %). The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 8.07 (d, 2H), 8.01 (d, 2H), 7.89 (d, 2H), 7.48 (tt, 2H), 7.33

09857687, 060801

(p, 5H), 7.26 (s, 3H), 7.18 (m, 2H), 6.49 (m, 1H),
6.24 (d, 2H), 5.74 (t, 1H), 5.66 (t, 1H), 1.73-1.52 (m,
6H), 1.47 (s, 3H), 1.42 (s, 3H), 1.39 (s, 6H), 1.24 (d,
3H), 0.97 (d, 6H), 0.84 (d, 6H)

5 FD-MS: m/z = 850, 852, 854 (M^+)

Example 18

Synthesis of diphenylmethylene(3-

trimethylsilylcyclopentadienyl) (1,1,4,4,7,7,10,10-

10 octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-

fluorenyl)zirconium dichloride

(1) Synthesis of 1-(cyclopentadienyl)-1-

(1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-
octahydrodibenzo(b,h)-fluorenyl)diphenylmethane

- 15 In a 200 ml three-necked flask purged with
nitrogen, 2.64 g (6.83 mmol, 1 eq) of
1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-
octahydrodibenzo(b,h)-fluorene was placed at room
temperature. Then, 40 ml of dehydrated THF was added,
20 and the mixture was stirred by a magnetic stirrer to
give a solution. The solution was cooled with an ice
bath (light yellow solution). To the solution, 4.6 ml
(7.50 mmol, 1.10 eq) of a hexane solution of n-BuLi
25 the ice bath was removed, and the solution was stirred

09357687-060801

- at room temperature for 23 hours (dark red solution). The solution was cooled to 1°C with an ice bath, and to the solution, a solution of 2.06 (8.94 mmol, 1.31 eq) of 6,6-diphenylfulvene in 20 ml of dehydrated THF
- 5 was dropwise added over a period of 20 minutes (dark red slurry). The ice bath was removed, and the solution was stirred at room temperature for 65 hours. The resulting dark reddish brown solution was poured into 100 ml of a diluted hydrochloric acid solution to
- 10 perform quenching. From the aqueous layer, the soluble component was extracted with diethyl ether, and the organic phase was washed with 100 ml of a saturated saline solution. The dispensed organic phase was dried over MgSO₄, then the MgSO₄ was filtered off, and from
- 15 the filtrate the solvent was vacuum distilled off by a rotary evaporator to obtain an orangy yellow amorphous product. The amorphous product was washed with methanol, then filtered and dried in a vacuum disiccator to obtain 3.31 g of a slightly yellow
- 20 powder (yield: 79 %).

¹H-NMR (270 MHz, in CDCl₃, Based on TMS): 8.86-1.40 (m, 24H, -CH₃ of OMOHDBFlu), 1.60-1.62 (m, 8H, -CH₂- of OMOHDBFlu), 2.8-3.1 (br, 2H, -CH₂- of Cp), 5.37, 5.42 (s, 1H, 9-H of OMOHDBFlu), 6.0-6.6 (br, 3H,

09857687-060001

-CH- of Cp), 6.9-7.5 (br, 14H, Ph-H of OMOHDBFlu, Ph-H of Bridge)

- (2) Synthesis of 1-(3-trimethylsilylcyclopentadienyl)-
1-(1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-
5 octahydrodibenzo(b,h)-fluorenyl)diphenylmethane

- In a 30 ml Schlenk flask purged with nitrogen,
0.92 g (1.48 mmol, 1 eq) of 1-(cyclopentadienyl)-1-
(1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-
octahydrodibenzo(b,h)-fluorenyl)diphenylmethane was
10 placed at room temperature. Then, 20 ml of dehydrated
THF was added, and the mixture was stirred by a
magnetic stirrer to give a solution. The solution was
cooled with an ice bath (light orangy brown solution).
To the solution, 1.0 ml (1.63 mmol, 1.10 eq) of a
15 hexane solution of n-BuLi was dropwise added. Then,
the ice bath was removed, and the solution was stirred
at room temperature for 18 hours (dark red solution).
The solution was cooled with an ice bath, and to the
solution, 1.05 ml (8.28 mmol, 5.59 eq) of
20 chlorotrimethylsilane was dropwise added by a syringe
(dark brown solution). The ice bath was removed, and
the solution was stirred at room temperature for 3
hours. The resulting dark brown solution was poured
into 50 ml of a diluted hydrochloric acid solution to
25 perform quenching. After the soluble component was

09857687, 060801

- extracted with 30 ml of diethyl ether, the organic phase was washed with 50 ml of a saturated saline solution. The organic phase was dried over MgSO_4 , then the MgSO_4 was filtered off, and from the filtrate the
- 5 solvent was vacuum distilled off by a rotary evaporator to obtain a yellowish brown amorphous product. The amorphous product was purified by silica gel column chromatography (developing solvent: hexane:dichloromethane = 19:1) to obtain 0.62 g a
- 10 light yellow amorphous product (yield: 61 %).
- $^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ -0.22 (s, 9H, $-\text{Si}(\text{CH}_3)_3$), 0.86-1.31 (m, 24H, $-\text{CH}_3$ of OMOHDBFlu), 1.60-1.62 (m, 8H, $-\text{CH}_2-$ of OMOHDBFlu), 3.20 (br, 1H, 1-H of Cp), 5.52 (s, 1H, 9-H of
- 15 OMOHDBFlu), 6.3 (br, 2H, $-\text{CH}-$ of Cp), 6.8-7.7 (br, 14H, Ph-H of OMOHDBFlu, Ph-H of Bridge)
- (3) Synthesis of diphenylmethylene(3-trimethylsilylcyclopentadienyl)(1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-
- 20 fluorenyl)zirconium dichloride
- In a 50 ml Schlenk flask purged with nitrogen, 0.62 g (0.90 mmol, 1 eq) of 1-(3-trimethylsilylcyclopentadienyl)-1-(1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-
- 25 fluorenyl)diphenylmethane was placed at room

09857687.060801

- temperature. Then, 15 ml of dehydrated diethyl ether was added, and the mixture was stirred by a magnetic stirrer to give a solution. The solution was cooled with an ice bath (yellow solution). To the solution,
- 5 1.25 ml (2.04 mmol, 2.27 eq) of n-BuLi (hexane solution) was dropwise added by a syringe. Then, the ice bath was removed, and the solution was stirred at room temperature for 22 hours (orange slurry). The slurry was cooled with a dry ice/methanol bath, and
- 10 thereto was added 20.32 g (0.86 mmol, 0.95 eq) of zirconium tetrachloride (THF) 2-complex. The mixture was stirred for 24 hours while allowing the dry ice to naturally disappear and the temperature of the mixture to naturally rise to room temperature. From the
- 15 resulting dark brown slurry, the volatile component was vacuum distilled off. To the residue, 50 ml of dehydrated hexane was added, and then the insoluble component was filtered through a filter. The solvent of the resulting orangy brown solution was vacuum
- 20 concentrated, and the obtained solution was stored in a refrigerator to obtain 0.20 g of a pink powder (yield: 28 %).

- $^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 0.12 (s, H, $-\text{Si}(\text{CH}_3)_3$), 0.82-1.49 (m, 24H, $-\text{CH}_3$ of OMOHDBFlu),
- 25 1.58-1.70 (m, 8H, $-\text{CH}_2-$ of OMOHDBFlu), 5.49, 5.77,

09857687-060801

6.34 (t, H, -CH- of Cp), 6.16, 6.18, 8.04 (s, 4H, Ph-H of OMOHDBFlu), 7.27-8.01 (m, 10H, Ph-H of Bridge)

FD-MS: m/z = 846, 848, 850 (M^+)

5 Example 19

Synthesis of methylphenylmethylene(3-tert-butylcyclopentadienyl) (3,6-di-tert-butylfluorenyl)zirconium dichloride

(1) Synthesis of 3-tert-butyl-6,6-methylphenylfulvene

- 10 To a solution of 3.78 g (30.9 mmol) of tert-butylcyclopentadiene in 35 ml of THF, 20.0 ml (32.6 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for
- 15 8 hours. To the resulting solution, a solution of 3.73 g (31.0 mmol) of acetophenone in 10 ml of THF was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. After the reaction solution was diluted
- 20 with 100 ml of ether, 50 ml of water was added. The separated organic phase was washed with water and a saturated saline solution, then dried over magnesium sulfate and filtered. From the filtrate, the solvent was removed under reduced pressure to obtain a liquid.
- 25 The liquid was isolated and purified by column

09857687 060801

chromatography (silica gel, developing solvent: hexane) to obtain 1.70 g (7.58 mmol) of a red liquid (yield: 25 %). The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 7.39 (m,

5H), 6.63+6.53+6.23+6.16+5.81 (m+m+m+m+m, 3H), 2.50 (d, 3H), 1.23+1.15 (s+s, 9H)

(2) Synthesis of 1-phenyl-1-(3-tert-butylcyclopentadienyl)-1-(3,6-di-tert-butylfluorenyl)ethane

- 10 To a solution of 1.92 g (6.9 mmol) of 3,6-di-tert-butylfluorene in 30 ml of THF, 4.4 ml (7.2 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. To the
- 15 resulting red solution, a solution of 1.70 g (7.6 mmol) of 3-tert-butyl-6,6-methylphenylfulvene in 40 ml of THF was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. After the reaction solution
- 20 was diluted with 100 ml of ether, 50 ml of water was added. The separated organic phase was washed with water and a saturated saline solution, then dried over magnesium sulfate and filtered. From the filtrate, the solvent was removed under reduced pressure to obtain a
- 25 solid. The solid was reslurried with 50 ml of methanol,

09057607-050801

and the resulting slurry was filtered to obtain 1.0 g (1.99 mmol) of a white solid (yield: 29 %). The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS):

- 5 87.71+7.63 (d+d, 5H),
7.40+7.28+7.10+6.90+6.69+6.46+5.94 (t+t+m+d+d+s+m, 8H),
4.86 (s, 1H), 3.13+3.05+2.96+2.88 (s+s+s+s, 2H), 1.35 (d, 18H), 1.20 (d, 9H), 1.00 (s, 3H)

- (3) Synthesis of methylphenylmethylene(3-tert-butylcyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride
- 10

To a solution of 0.53 g (1.1 mmol) of 1-phenyl-1-(3-tert-butylcyclopentadienyl)-1-(3,6-di-tert-butylfluorenyl)ethane in 50 ml of ether, 1.4 ml (2.3

- 15 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for 2 days. To the resulting reddish orange reaction mixture having been cooled to -78°C , 0.41 g (1.1 mmol)
- 20 of zirconium tetrachloride (THF) 2-complex was added, and the mixture was stirred at room temperature for 3 days. The resulting reaction mixture was subjected to sellait filtration. From the filtrate, the solvent was removed under reduced pressure, and the residue
- 25 was recrystallized from diethyl ether to obtain 0.20 g

09867507-060801

of an orange solid (yield: 28 %). The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 8.03 (dd, 2H), 7.89-7.38 (m, 7H), 6.96 (dd, 1H), 6.09 (t, 1H), 6.07 (d, 1H), 5.68 (t, 1H), 5.65 (t, 1H), 2.46 (s, 3H), 1.47 (s, 9H), 1.37 (s, 9H), 1.22 (s, 9H)

FD-MS: m/z = 660, 662, 664 (M^+)

Example 20

10 Synthesis of diethylmethylen(3-tert-butylcyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride

(1) Synthesis of 3-tert-butyl-6-diethylfulvene

- To a THF solution of 1.53 g (13 mmol) of tert-butylcyclopentadiene, 9.0 ml (14 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. Then, 1.7 ml (16 mmol) of 3-pentanone was further added at -78°C , followed by stirring at room temperature for 2 days.
- To the reaction solution, water was added. The mixture was subjected to extraction with ether, then the solvent was distilled off, and the residue was subjected to column chromatography (silica gel, developing solvent: hexane) to obtain 1.50 g of a

yellow liquid (yield: 63 %). The analyzed values are given below.

- $^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 6.52 (qd, 2H), 6.11 (t, 1H), 2.53 (qd, 4H), 1.20 (s, 9H),
- 5 1.17-1.12 (m, 6H)

(2) Synthesis of 2-(3-tert-butylcyclopentadienyl)-3-(3,6-di-tert-butylfluorenyl)pentane

- To a solution of 1.99 g (7.1 mmol) of 3,6-di-tert-butylfluorene in 30 ml of THF, 4.6 ml (7.5 mmol) of a
- 10 hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. To the resulting red solution, a solution of 1.50 g (7.9 mmol) of 3-tert-butyl-6,6-diethylfulvene in 30 ml of
- 15 THF was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. After the reaction solution was diluted with 100 ml of ether, 50 ml of water was added. The separated organic phase was washed with water and a
- 20 saturated saline solution, then dried over magnesium sulfate and filtered. From the filtrate, the solvent was removed under reduced pressure to obtain a liquid. The liquid was isolated and purified by column chromatography (silica gel, developing solvent:

09857687-060801

hexane) to obtain 2.34 g (4.99 mmol) of a white solid (yield: 70 %). The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS):

87.65+7.26-7.12 (d+m, 6H), 6.12-5.60 (m, 2H), 4.06 (d, 1H), 2.80 (s, 2H), 1.80 (m, 4H), 1.38 (s, 18H), 1.08 (s, 9H), 0.66 (m, 6H)

(3) Synthesis of diethylmethylene(3-tert-butylcyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride

- 10 To a solution of 0.74 g (1.7 mmol) of 3-(3-tert-butyl-cyclopentadienyl)-3-(3,6-di-tert-butylfluorenyl)pentane in 50 ml of ether, 2.2 ml (3.6 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice
- 15 cooling, followed by stirring at room temperature for 2 days. To the resulting reddish orange reaction mixture having been cooled to -78°C , 0.66 g (1.7 mmol) of zirconium tetrachloride (THF) 2-complex was added, followed by stirring at room temperature for one day
- 20 and night. The resulting reaction mixture was subjected to seltait filtration. From the filtrate, the solvent was removed under reduced pressure, and the residue was recrystallized from hexane to obtain 0.44 g of an orange solid (yield: 40 %). The analyzed
- 25 values are given below.

09257687-050801

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 8.00 (s, 2H), 7.70 (d, 1H), 7.64 (d, 1H), 7.32 (d, 1H), 7.31 (d, 1H), 6.10 (t, 1H), 5.71 (t, 1H), 5.50 (t, 1H), 2.76 (q, 4H), 1.43 (s, 18H), 1.26 (t, 6H), 1.14 (s, 9H)

5 FD-MS: m/z = 626, 628, 630 (M^+)

Example 21

Synthesis of cyclohexylidene(3-trimethylsilylcyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride

10 (1) Synthesis of 1-(cyclopentadienyl)-1-(3,6-di-tert-butylfluorenyl)cyclohexane

In a 200 ml two-necked flask purged with nitrogen, 1.96 g (7.04 mmol, 1 eq) of 3,6-di-tert-butylfluorene
15 was placed at room temperature. Then, 40 ml of dehydrated THF was added, and the mixture was stirred by a magnetic stirrer to give a solution. The solution was cooled with an ice bath (colorless transparent solution). To the solution, 5.0 ml (8.15 mmol, 1.16
20 eq) of a hexane solution of $n\text{-BuLi}$ was dropwise added over a period of 5 minutes. Then, the ice bath was removed, and the solution was stirred at room temperature for 21 hours (red solution). After the solution was cooled with an ice bath, a solution of

0957687-060801
T02090-2892960

- 1.37 g (9.37 mmol, 1.33 eq) of 6-cyclohexylfulvene in 5 ml of dehydrated THF was dropwise added over a period of 10 minutes. The ice bath was removed, and the solution was stirred at room temperature for 42
- 5 hours. The resulting brownish red solution was poured into 50 ml of a diluted hydrochloric acid solution to perform quenching. The soluble component was extracted from the aqueous layer with 100 ml of diethyl ether, and the organic phase was washed with 80 ml of a
- 10 saturated saline solution. The dispensed organic phase was dried over MgSO_4 , then the MgSO_4 was filtered off, and from the filtrate the solvent was vacuum distilled off by a rotary evaporator to obtain a brownish yellow solid. The solid was purified by silica gel column
- 15 chromatography (developing solvent: hexane) to obtain 1.31 g of a white solid (yield: 44 %).

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 1.23-1.87 (br, 10H, $-\text{CH}_2-$ of Bridge), 1.38 (s, 18H, tBu of 3, 6-tBu₂Flu), 2.81, 3.02 (m, 2H, $-\text{CH}_2-$ of Cp), 3.83, 20 3.85 (s, 1H, 9-H of 3, 6-tBu₂Flu), 5.91, 5.96, 6.30, 6.43, 6.56 (m, 4H, $-\text{CH}-$ of Cp), 7.08 (s, 2H, 1, 8-H of 3, 6-tBu₂Flu), 7.13-7.19 (m, 2H, 2, 7-H of 3, 6-tBu₂Flu), 7.66 (s, 2H, 4, 5-H of 3, 6-tBu₂Flu)

- (2) Synthesis of 1-(3-trimethylsilylcyclopentadienyl)-
- 25 1-(3,6-di-tert-butylfluorenyl)cyclohexane

09557587.060801

09557687-060801

In a 30 ml Schlenk flask purged with nitrogen, 0.86 g (2.02 mmol, 1 eq) of 1-(cyclopentadienyl)-1-(3,6-di-tert-butylfluorenyl)cyclohexane was placed at room temperature. Then, 12 ml of dehydrated THF was added, and the mixture was stirred by a magnetic stirrer to give a solution. The solution was cooled with an ice bath (colorless transparent solution). To the solution, 1.4 ml (2.28 mmol, 1.13 eq) of n-BuLi (hexane solution) was dropwise added. Then, the ice bath was removed, and the solution was stirred at room temperature for 19 hours. The solution was cooled with an ice bath, and to the solution, 1.6 ml (12.6 mmol, 6.24 eq) of chlorotrimethylsilane was dropwise added by a syringe. The ice bath was removed, and the solution was stirred at room temperature for 4 hours. The resulting yellow solution was poured into 50 ml of a diluted hydrochloric acid solution to perform quenching. After the soluble component was extracted with 70 ml of diethyl ether, the organic phase was washed with 50 ml of a saturated saline solution. The organic phase was dried over MgSO_4 , then the MgSO_4 was filtered off, and from the filtrate the solvent was vacuum distilled off by a rotary evaporator to obtain a yellow amorphous product. The amorphous product was purified by silica gel column chromatography

(developing solution: hexane) to obtain 0.46 g a white amorphous product (yield: 46 %).

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ -0.03 (s, 9H, $-\text{Si}(\text{CH}_3)_3$), 1.11-2.20 (br, 10H, $-\text{CH}_2-$ of

- 5 Bridge), 1.36, 1.38, 1.40 (s, 18H, tBu of 3, 6-tBu₂Flu), 3.20 (s, 1H, 1-H of Cp), 3.85, 3.87 (s, 1H, 9-H of 3, 6-tBu₂Flu), 5.94-6.52 (m, 3H, $-\text{CH}-$ of Cp), 6.68-7.67 (m, 6H, Ph-H of 3, 6-tBu₂Flu)

(3) Synthesis of cyclohexylidene(3-

- 10 trimethylsilylcyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride

In a 30 ml Schlenk flask purged with nitrogen, 0.46 g (0.93 mmol, 1 eq) of 1-(3-

trimethylsilylcyclopentadienyl)-1-(3,6-di-tert-

- 15 butylfluorenyl)cyclohexane was placed at room temperature. Then, 10 ml of dehydrated diethyl ether was added, and the mixture was stirred by a magnetic stirrer to give a solution. The solution was cooled with an ice bath (colorless transparent solution). To
20 the solution, 1.25 ml (2.04 mmol, 2.19 eq) of a hexane solution of n-BuLi was dropwise added by a syringe. Then, the ice bath was removed, and the solution was stirred at room temperature for 22 hours (reddish brown solution). The slurry was cooled with a dry
25 ice/methanol bath, and thereto was added 0.35 g (0.92

09857687-060801

mmol, 0.99 eq) of zirconium tetrachloride (THF) 2-complex. The mixture was stirred for 24 hours while allowing the dry ice to naturally disappear and the temperature of the mixture to naturally rise to room temperature. From the resulting dark orange slurry, the volatile component was vacuum distilled off. To the residue, 40 ml of dehydrated hexane was added, and then the insoluble component was filtered through a filter. To the orangy brown powder remaining on the filter, 5 ml of dehydrated dichloromethane was added to filter the soluble component. From the resulting red solution, the solvent was vacuum distilled off to obtain 0.34 g of an orange solid (yield: 57 %).

¹H-NMR (270 MHz, in CDCl₃, Based on TMS): 80.12 (s, 9H, -Si(CH₃)₃), 1.44, 1.45 (s, 18H, tBu of 3, 6-tBu₂Flu), 1.68-3.32 (br, 10H, -CH₂- of Bridge), 5.62, 5.96, 6.33 (t, 3H, -CH- of Cp), 7.34, 7.34 (d, 2H, 1, 8-H of 3, 6-tBu₂Flu), 7.61, 7.65 (d, 2H, 2, 7-H of 3, 6-tBu₂Flu), 8.02 (s, 2H, 4, 5-H of 3, 6-tBu₂Flu)

FD-MS: m/z = 654, 656, 658 (M⁺)

Example 22

Synthesis of cyclopentylidene(3-tert-butylcyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride

(1) Synthesis of 3-tert-butyl-6,6-cyclopentylfulvene

To a THF solution of 1.53 g (13 mmol) of tert-butylcyclopentadiene, 9.0 ml (14 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. Then, 1.4 ml (16 mmol) of cyclopentanone was added at -78°C, followed by stirring at room temperature for 2 days. To the reaction solution, water was added. The mixture was subjected to extraction with ether, then the solvent was distilled off, and the residue was subjected to column chromatography (silica gel, developing solvent: hexane) to obtain 1.18 g of a yellow liquid (yield: 50 %). The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 6.48 (dd, 1H), 6.38 (dd, 1H), 6.00 (t, 1H), 2.78-2.73 (m, 4H), 1.80-1.75 (m, 4H), 1.19 (s, 9H)

(2) Synthesis of 1-(3-tert-butylcyclopentadienyl)-1-(3,6-di-tert-butylfluorenyl)cyclopentane

To a solution of 1.59 g (5.7 mmol) of 3,6-di-tert-butylfluorene in 30 ml of THF, 3.7 ml (6.0 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. To the

09857587-060801

resulting red solution, a solution of 1.18 g (6.3 mmol) of 3-tert-butyl-6,6-cyclopentylfulvene in 30 ml of THF was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room

- 5 temperature for one night. After the reaction solution was diluted with 100 ml of ether, 50 ml of water was added. The separated organic phase was washed with water and a saturated saline solution, then dried over magnesium sulfate and filtered. From the filtrate, the
- 10 solvent was removed under reduced pressure to obtain a liquid. The liquid was isolated and purified by column chromatography (silica gel, developing solvent: hexane) to obtain 1.52 g (3.26 mmol) of a white solid (yield: 57 %). The analyzed values are given below.

- 15 $^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS):
8.60+7.37-7.08 (s+m, 6H), 5.77-5.45 (m, 2H), 4.02 (m, 1H), 2.65-2.33 (m, 2H), 1.38 (s, 18H), 2.20-0.80 (m, 17H)

- (3) Synthesis of cyclopentylidene(3-tert-butylcyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride
- 20

- To a solution of 0.58 g (1.3 mmol) of 1-(3-tert-butyl-cyclopentadienyl)-1-(3,6-di-tert-butylfluorenyl)cyclopentane in 50 ml of ether, 2.2 ml
- 25 (3.6 mmol) of a hexane solution of n-butyllithium was

09257567-060901

- dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for 2 days. After the reaction suspension was filtered, 0.40 g (0.9 mmol) of the resulting solid was suspended in 50 ml of ether. The suspension was cooled to -78°C , and to the suspension, 0.33 g (0.9 mmol) of zirconium tetrachloride (THF) 2-complex was added, followed by stirring at room temperature for 5 days. The resulting reaction mixture was subjected to sellaite filtration.
- 10 From the filtrate, the solvent was removed under reduced pressure, and the residue was recrystallized from ether to obtain 0.12 g of an orange solid (yield: 15 %). The analyzed values are given below.

- $^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): 88.01 (d, 2H), 7.56 (d+d, 2H), 7.32 (d+d, 2H), 6.08 (t, 1H), 5.66 (t, 1H), 5.47 (t, 1H), 3.20-3.10 (m, 2H), 2.80-2.60 (m, 2H), 2.10-2.00 (m, 4H), 1.44 (s, 18H), 1.14 (s, 9H)

FD-MS: m/z = 624, 626, 628 (M^+)

20

Example 23

Synthesis of cyclohexylidene(3-(1,1-dimethylpropyl)cyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride

09857687-060801

(1) Synthesis of 3-(1,1-dimethylpropyl)-6,6-cyclohexylfulvene

- To a solution of 3.00 g (29.4 mmol) of (1,1-dimethylpropyl)cyclopentadiene in 30 ml of methanol,
- 5 6.1 ml (58.9 mmol) of cyclohexanone and 4.9 ml (58.7 mmol) of pyrrolidine were added with ice cooling, followed by stirring at room temperature for one night. After the reaction solution was diluted with 100 ml of ether, 50 ml of water was added. The organic phase was
- 10 separated, washed with water and a saturated saline solution, then dried over anhydrous magnesium sulfate and filtered. From the filtrate, the solvent was removed under reduced pressure to obtain a liquid. The liquid was isolated and purified by column
- 15 chromatography (silica gel, developing solvent: hexane) to obtain 2.00 g (9.24 mmol) of a yellow liquid (yield: 31 %). The analyzed values are given below.

- ¹H-NMR (270 MHz, in CDCl₃, Based on TMS): δ6.54 (m,
- 20 2H), 6.16 (m, 1H), 2.61+1.72 (m+m, 10H), 1.50 (f, 2H), 1.15 (s, 6H), 0.77 (t, 3H)

(2) Synthesis of 1-(3-(1,1-dimethylpropyl)cyclopentadienyl)-1-(3,6-di-tert-butylfluorenyl)cyclohexane

09857687.050801

09857637, 060801

To a solution of 2.38 g (8.5 mmol) of 3,6-di-tert-butylfluorene in 40 ml of THF, 5.7 ml (9.2 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. To the resulting red solution, a solution of 2.00 g (9.2 mmol) of 3-(1,1-dimethylpropyl)-6,6-dimethylfulvene in 30 ml of THF was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. After the reaction solution was diluted with 100 ml of ether, 50 ml of water was added. The separated organic phase was washed with water and a saturated saline solution, then dried over magnesium sulfate and filtered. From the filtrate, the solvent was removed under reduced pressure to obtain a liquid. The liquid was isolated and purified by column chromatography (silica gel, developing solvent: hexane) to obtain 1.88 g (3.80 mmol) of a white solid (yield: 45 %). The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS):

δ 7.62+7.20-7.10 (s+m, 6H), 6.85-6.55 (m, 2H), 3.83 (m, 1H), 2.75+2.65 (s+s, 2H), 2.15-1.00 (m, 12H), 1.38 (s, 18H), 1.08 (d, 6H), 0.75 (m, 3H)

(3) Synthesis of cyclohexylidene(3-(1,1-dimethylpropyl)cyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride

- To a solution of 0.70 g (1.4 mmol) of 1-(3-(1,1-dimethylpropyl)cyclopentadienyl)-1-(3,6-di-tert-butylfluorenyl)cyclohexane in 35 ml of diethyl ether, 1.8 ml (2.9 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere with ice cooling, followed by stirring at room temperature for one night. The resulting solution was cooled to -78°C, and 0.52 g (1.4 mmol) of zirconium tetrachloride (THF) 2-complex was added, followed by stirring at room temperature for one night. The reaction solution was subjected to sellaita filtration in a nitrogen atmosphere. From the resulting liquid, the solvent was removed under reduced pressure. To the residue, 10 ml of hexane was added, and the mixture was cooled. The resulting reaction solution was subjected to sellaita filtration, and the filtrate was concentrated to obtain 0.45 g (0.70 mmol) of a reddish brown solid (yield: 48 %). The analyzed values are given below.

¹H-NMR (270 MHz, in CDCl₃, Based on TMS): 8.02-7.10 (m, 6H), 6.10-4.40 (m, 3H), 1.46 (s, 18H), 2.90-0.70 (m, 12H), 0.65 (t, 3H)

FD-MS: m/z = 652, 654, 656 (M^+)

Example 24

Synthesis of cyclopentylidene(3-tert-

- 5 butylcyclopentadienyl)(1,1,4,4,7,7,10,10-octamethyl-
1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-
fluorenyl)zirconium dichloride

(1) Synthesis of 3-tert-butyl-6,6-tetramethylenefulvene

- 10 To 50 ml of dehydrated methanol, 3.0 g (24.4 mmol) of 3-tert-butylcyclopentadiene and 3.24 ml (36.6 mmol) of cyclopentanone were added at 0°C, and 3.06 ml (36.6 mmol) of pyrrolidine was dropwise added at 0°C, followed by stirring at room temperature for 3 days.
- 15 Then, 20 ml of water was added at 0°C, and the mixture was subjected to extraction with ether. The organic phase was washed with water and dried over anhydrous magnesium sulfate. Then, the solvent was distilled off to obtain a crude orange liquid.
- 20 The liquid was purified by column chromatography (silica, hexane) to obtain 1.6 g of a desired yellow product (yield: 35.7 %). The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 6.50-

- 25 6.01 (3H), 2.77 (m, 4H), 1.78 (m, 4H), 1.20 (s, 9H)

09657687-060801

(2) Synthesis of 1-(3-tert-butylcyclopentadienyl)-1-(1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-fluorenyl)cyclopentane

- To a solution of 2.32 g (6.02 mmol) of
- 5 1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-fluorene in 40 ml of THF, 10.1 ml (6.32 mmol) of a hexane solution of n-butyllithium was dropwise added in a nitrogen atmosphere at 0°C, followed by stirring at room temperature overnight. To
- 10 the resulting solution, a solution of 1.64 g (8.71 mmol) of 3-tert-butyl-6,6-tetramethylenefulvene in 30 ml of THF was dropwise added in a nitrogen atmosphere at 0°C, followed by stirring at room temperature overnight to perform reaction. After the reaction, 30
- 15 ml of water was added, and the mixture was subjected to extraction with ether. The organic phase was dried over anhydrous magnesium sulfate. From the resulting solution, the solvent was distilled off under reduced pressure to obtain a crude yellow solid.
- 20 The solid was recrystallized from hexane to obtain 2.72 g of a desired product (yield: 78.7 %). The analyzed values are given below.
- ¹H-NMR (270 MHz, in CDCl₃, Based on TMS): δ 7.47-7.25 (4H), 5.88-5.46 (2H), 4.03-3.98 (1H), 2.70-0.94
- 25 (44H)

D857687-060001

(3) Synthesis of cyclopentylidene(3-tert-butylcyclopentadienyl)(1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-fluorenyl)zirconium dichloride

- 5 To a solution of 0.95 g (1.66 mmol) of 1-(3-tert-butylcyclopentadienyl)-1-(1,1,4,4,7,7,10,10-octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-fluorenyl)cyclopentane in 15 ml of THF, 2.12 ml (3.39 mmol) of a hexane solution of n-butyllithium was
- 10 dropwise added in a nitrogen atmosphere with ice cooling. The mixture was reacted overnight while allowing the temperature of the mixture to naturally rise to room temperature, to obtain a red solution. The solution was cooled to -78°C again, and 0.60 g
- 15 (1.60 mmol) of zirconium tetrachloride (THF) 2-complex was added in a nitrogen atmosphere. The mixture was reacted overnight while allowing the temperature of the mixture to naturally rise to room temperature similarly to the above. The resulting red suspension
- 20 was subjected to sellaite filtration to remove a white solid. Then, the red filtrate was concentrated and dried to obtain a crude red solid. The solid was recrystallized from 5 ml of diethyl ether to obtain 116 mg of a red solid. The analyzed values are given
- 25 below.

09657687-050801

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS): δ 7.98 (2H), 7.45 (d, 2H), 6.05 (t, 1H), 5.48 (t, 1H), 5.37 (t, 1H), 3.48 (m, 4H), 2.68 (m, 4H), 2.06-0.99 (36H)
FD-MS: m/z = 732, 734, 736 (M^+)

5

Example 25

Bulk copolymerization of propylene and ethylene using
dimethylmethylene(3-tert-butyl-5-
methylcyclopentadienyl)fluorenylzirconium dichloride

- 10 In a 50 ml two-necked flask thoroughly purged with nitrogen, 0.72 mmol (in terms of aluminum) of silica-supported methylaluminoxane was suspended in 20 ml of heptane. To the suspension, a toluene solution of 0.65 mg (1.3 μmol) of the reddish orange solid obtained in
- 15 Example 1 was added, then triisobutylaluminum (0.33 mmol) and triethylaluminum (1.0 mmol) were added as alkylaluminum, and they were stirred for 30 minutes to give a catalyst suspension.

- 20 A 2000 ml autoclave thoroughly purged with nitrogen was charged with 400 g of propylene and 2NL of an ethylene gas, and the catalyst suspension was added to perform polymerization at 60°C for 60 minutes under a pressure of 3.0 to 3.5 MPa. Thereafter, methanol was added to terminate the polymerization,

09657637.060001

- and propylene was purged of, to obtain a polymer. The polymer was dried under vacuum at 80°C for 6 hours. The quantity of the polymer obtained was 127 g. This polymer had Tm of 128°C, MFR of 5.5 g/10 min and a
- 5 decane-soluble component quantity of 0.2 % by weight.

Example 26

- Bulk copolymerization of propylene and ethylene using
dimethylmethylen(3-tert-butyl-5-
10 methylcyclopentadienyl)fluorenylzirconium dichloride

- Copolymerization of propylene and ethylene was carried out in the same manner as in Example 25, except that the charge of ethylene was changed to 3 NL. The quantity of the polymer obtained was 146 g. This
- 15 polymer had Tm of 124°C, MFR of 5.5 g/10 min and a decane-soluble component quantity of 0.3 % by weight.

Example 27

- Bulk copolymerization of propylene and ethylene using
dimethylmethylen(3-tert-butyl-5-
20 methylcyclopentadienyl)fluorenylzirconium dichloride

- Polymerization was carried out in the same manner as in Example 25, except that the silica-supported methylaluminoxane was used in an amount of 0.52 mmol
- 25 in terms of aluminum, and only the triethylaluminum

(1.3 mmol) was used as alkylaluminum. The quantity of the polymer obtained was 79 g. This polymer had Tm of 124°C, MFR of 7.5 g/10 min and a decane-soluble component quantity of 0.2 % by weight.

5

Example 28

Bulk copolymerization of propylene and ethylene using
dimethylmethylene(3-tert-butyl-5-
methylcyclopentadienyl)fluorenylzirconium dichloride

- 10 Copolymerization of propylene and ethylene was carried out in the same manner as in Example 25, except that 0.5 NL of hydrogen was added. The quantity of the polymer obtained was 49 g. This polymer had Tm of 120°C, MFR of 65 g/10 min and a decane-soluble
- 15 component quantity of 0.2 % by weight.

Example 29

Bulk copolymerization of propylene and ethylene using
dimethylmethylene(3-tert-butyl-5-
20 methylcyclopentadienyl)(2,7-di-tert-
butylfluorenyl)zirconium dichloride

- Copolymerization of propylene and ethylene was carried out in the same manner as in Example 25, except that 0.8 mg of the orange solid obtained in
- 25 Example 5 was used. The quantity of the polymer

obtained was 97 g. This polymer had Tm of 126°C, MFR of 2.0 g/10 min and a decane-soluble component quantity of 0.2 % by weight.

5 Example 30

Bulk copolymerization of propylene and ethylene using
dimethylmethylen(3-tert-butyl-5-
methylcyclopentadienyl) (2,7-di-tert-
butylfluorenyl)zirconium dichloride

- 10 Copolymerization of propylene and ethylene was carried out in the same manner as in Example 29, except that the charge of ethylene was changed to 4 NL. The quantity of the polymer obtained was 142 g. This polymer had Tm of 116°C, MFR of 4.1 g/10 min and a
- 15 decane-soluble component quantity of 0.3 % by weight.

Example 31

Bulk copolymerization of propylene and ethylene using
cyclohexylidene(3-tert-butyl-5-
20 methylcyclopentadienyl)fluorenylzirconium dichloride

- Copolymerization of propylene and ethylene was carried out in the same manner as in Example 25, except that 0.7 mg of the reddish brown solid obtained in Example 2 was used. The quantity of the polymer
- 25 obtained was 89 g. This polymer had Tm of 126°C, MFR

0857587.060801

of 13.0 g/10 min and a decane-soluble component quantity of 0.2 % by weight.

Example 32

- 5 Bulk copolymerization of propylene and ethylene using
 cyclohexylidene(3-tert-butyl-5-
 methylcyclopentadienyl)fluorenylzirconium dichloride

 Copolymerization of propylene and ethylene was carried out in the same manner as in Example 31,
10 except that the charge of ethylene was changed to 3 NL. The quantity of the polymer obtained was 107 g. This polymer had Tm of 122°C, MFR of 18.0 g/10 min and a decane-soluble component quantity of 0.5 % by weight.

- 15 Example 33

Bulk copolymerization of propylene and ethylene using
 cyclohexylidene(3-tert-butyl-5-
 methylcyclopentadienyl)(3,6-di-tert-
 butylfluorenyl)zirconium dichloride

- 20 Copolymerization of propylene and ethylene was carried out in the same manner as in Example 25, except that 1.3 mg of the reddish brown solid obtained in Example 4 was used, and the charge of ethylene was changed to 4 NL. The quantity of the polymer obtained
25 was 297 g. This polymer had Tm of 141°C, MFR of 58

09857687-060801

g/10 min and a decane-soluble component quantity of 0.3 % by weight.

Example 34

- 5 Bulk copolymerization of propylene and ethylene using
cyclohexylidene(3-tert-butyl-5-
methylcyclopentadienyl)(3,6-di-tert-
butylfluorenyl)zirconium dichloride

- Copolymerization of propylene and ethylene was
10 carried out in the same manner as in Example 33,
except that the charge of ethylene was changed to 5 NL.
The quantity of the polymer obtained was 284 g. This
polymer had Tm of 137°C, MFR of 97 g/10 min and a
decane-soluble component quantity of 0.6 % by weight.

15

Example 35

- Bulk copolymerization of propylene and ethylene using
cyclohexylidene(3-tert-butyl-5-
methylcyclopentadienyl)(3,6-di-tert-
20 butylfluorenyl)zirconium dichloride

- Copolymerization of propylene and ethylene was
carried out in the same manner as in Example 33,
except that the charge of ethylene was changed to 5 NL,
and the polymerization temperature was changed to 50°C.
25 The quantity of the polymer obtained was 262 g. This

09657687 060804
108080 287286

- polymer had Tm of 137°C, MFR of 115 g/10 min, Mw of 112000, Mn of 62000, Mw/Mn of 1.8 and a decane-soluble component quantity of 0.8 % by weight. As the stereoregularity of the polymer, the mmmm was 95.7 %, the proportion of 2,1-insertion was 0.02 %, and the proportion of 1,3-insertion was 0.18 %.

Example 36

- Bulk copolymerization of propylene and ethylene using
10 cyclohexylidene(3-tert-butyl-5-
methylcyclopentadienyl)(3,6-di-tert-
butylfluorenyl)zirconium dichloride

- Copolymerization of propylene and ethylene was carried out in the same manner as in Example 33,
15 except that the charge of ethylene was changed to 5 NL, and 0.5 NL of hydrogen was added. The quantity of the polymer obtained was 205 g. This polymer had Tm of 131°C, MFR of 310 g/10 and a decane-soluble component quantity of 1.0 % by weight. As the stereoregularity
20 of the polymer, the mmmm was 95.0 %, the proportion of 2,1-insertion was 0.03 %, and the proportion of 1,3-insertion was 0.20 %.

Example 37

09557687.060801

Pressure solution polymerization of propylene and 1-butene using dimethylmethylene(3-tert-butyl-5-methylcyclopentadienyl)fluorenylzirconium dichloride

- A 2000 ml polymerization apparatus thoroughly
- 5 purged with nitrogen was charged with 900 ml of dry hexane and 30 g of 1-butene at ordinary temperature. Then, the internal temperature of the polymerization apparatus was raised to 70°C, and the apparatus was pressurized to 0.7 MPa with propylene. To the
- 10 polymerization apparatus, a catalyst solution obtained by adding 0.9 mmol (in terms of aluminum) of methylaluminoxane (available from Albemarle Co.) to a toluene solution of 1.0 mg (2 μ mol) of the reddish orange solid obtained in Example 1 and
- 15 triisobutylaluminum (1.0 mmol) were added, and polymerization was conducted for 30 minutes with maintaining the internal temperature at 70°C and the propylene pressure at 0.7 MPa. Thereafter, methanol was added to terminate the polymerization. After the
- 20 pressure was released, a polymer was precipitated from the polymer solution with methanol and dried under vacuum at 130°C for 12 hours. The quantity of the polymer obtained was 9.95 g. This polymer had T_m of 102.7°C and an intrinsic viscosity (η) of 0.89 dl/g.

Example 38

Polymerization was carried out in the same manner as in Example 37, except that the charge of 1-butene was changed to 60 g. The quantity of the polymer obtained was 7.31 g. This polymer had T_m of 73.6°C and an intrinsic viscosity (η) of 0.94 dl/g.

Example 39

09857687-060801

A 2000 ml polymerization apparatus thoroughly
10 purged with nitrogen was charged with 750 ml of dry hexane and 40 g of 1-butene at ordinary temperature. Then, the internal temperature of the polymerization apparatus was raised to 50°C, and the apparatus was pressurized to 0.7 MPa with propylene. To the
15 polymerization apparatus, a catalyst solution obtained by adding 1.35 mmol (in terms of aluminum) of methylaluminumoxane (available from Albemarle Co.) to a toluene solution of 1.5 mg (3 μ mol) of the reddish orange solid obtained in Example 1 and
20 triisobutylaluminum (1.0 mmol) were added, and polymerization was conducted for 30 minutes with maintaining the internal temperature at 50°C and the propylene pressure at 0.7 MPa. Thereafter, methanol was added to terminate the polymerization. After the
25 pressure was released, a polymer was precipitated from

the polymer solution with methanol and dried under vacuum at 130°C for 12 hours. The quantity of the polymer obtained was 30.0 g. This polymer had T_m of 108.1°C and an intrinsic viscosity (η) of 2.13 dl/g.

5

Example 40

Polymerization was carried out in the same manner as in Example 39, except that the charge of dry hexane was changed to 700 ml, and the charge of 1-butene was
10 changed to 60 g. The quantity of the polymer obtained was 39.0 g. This polymer had T_m of 80.0°C and an intrinsic viscosity (η) of 1.83 dl/g.

Example 41

15 A 1000 ml polymerization apparatus thoroughly purged with nitrogen was charged with 830 ml of dry hexane and 70 ml of 1-butene at ordinary temperature. Then, the internal temperature of the polymerization apparatus was raised to 40°C, and the apparatus was
20 pressurized to 0.5 MPa with propylene. To the polymerization apparatus, a catalyst solution obtained by adding 1.35 mmol (in terms of aluminum) of methylaluminumoxane (available from Albemarle Co.) to a toluene solution of 1.5 mg (3 μ mol) of the reddish
25 orange solid obtained in Example 1 and

09557687, 060801

triisobutylaluminum (1.0 mmol) were added, and polymerization was conducted for 40 minutes with maintaining the internal temperature at 40°C and the propylene pressure at 0.5 MPa. Thereafter, methanol
5 was added to terminate the polymerization. After the pressure was released, a polymer was precipitated from the polymer solution with methanol and dried under vacuum at 130°C for 12 hours. The quantity of the polymer obtained was 25.5 g. This polymer had T_m of
10 100.7°C and an intrinsic viscosity (η) of 3.41 dl/g.

Example 42

Polymerization was carried out in the same manner as in Example 41, except that the charge of dry hexane
15 was changed to 810 ml, and the charge of 1-butene was changed to 90 ml. The quantity of the polymer obtained was 23.8 g. This polymer had T_m of 90.6°C and an intrinsic viscosity (η) of 3.56 dl/g.

20 Examples 43 - 46

Films were prepared from the sample polymers obtained in Examples 39 to 42, and properties of the films were measured.

Preparation of film and properties thereof

09857587 050801

On a press plate, an aluminum sheet of 0.1 mm thickness, a polyethylene terephthalate (PET) sheet and an aluminum sheet of 0.1 mm thickness from the center of which a square of 15cmx15cm had been cut away

- 5 were superposed in this order, and on the center (cut portion) of the aluminum sheet, 3.3 g of a sample polymer was placed. Then, a PET sheet, an aluminum plate and a press plate were further superposed in this order.

- 10 The sample polymer interposed between the press plates was placed in a hot press at 200°C and preheated for about 7 minutes. In order to remove bubbles from the sample polymer, an operation of pressure-application (50 kg/cm²-G)/pressure-release
- 15 was repeated several times. Then, the pressure was finally increased to 100 kg/cm²-G, and the sample polymer was heated for 2 minutes under pressure. After the pressure was released, the press plates were taken out of the pressing machine, then transferred into a
- 20 different pressing machine wherein the pressing zone was maintained at 0°C, and cooled under a pressure of 100 kg/cm²-G for 4 minutes. After the pressure was released, the sample polymer was taken out. Thus, a film having a uniform thickness of about 0.15 to 0.17

09857687-060801

mm was obtained. The properties of the film are set forth in Table 1.

The properties of the film were measured in the following manner.

5 1. Heat sealing temperature ($^{\circ}\text{C}$)

Films were heat sealed by a heat sealer at a given temperature for 1 second under a load of 2 kg/cm^2 to obtain a specimen having a width of 15 mm. The specimen was peeled at a peel rate of 20 mm/min and a
10 peel angle of 180°C . The temperature wherein the peel resistance was 300 g, was taken as a heat sealing temperature.

2. Anti-blocking properties (mN/cm)

Two films superposed upon each other were allowed
15 to adhere under the following conditions, and the anti-blocking properties were measured in accordance with ASTM-D1893.

The measurement was made after the films were allowed to stand for 24 hours under the adhesion
20 conditions of 50°C and a load of 10 kg.

3. ΔHaze (%)

Using a specimen of 1 mm thickness, the haze was measured by a digital haze meter DH-20D manufactured by Nippon Denshoku Kogyo K.K.

09057587.060801

After a heat treatment of the specimen at 80°C for 3 days, the haze was further measured in the same manner as described above. The difference in haze before and after the heat treatment was taken as Δ Haze.

5 4. Static friction coefficient

The static friction coefficient was measured in accordance with ASTM-D1894.

5. Film impact strength (KJ/m)

The film impact strength was measured at 23°C in accordance with ASTM-D3420.

Table 1

Sample polymer	Ex. 43 Polymer obtained in Ex. 39	Ex. 44 Polymer obtained in Ex. 40	Ex. 45 Polymer obtained in Ex. 41	Ex. 46 Polymer obtained in Ex. 42
Heat sealing starting temperature (°C)	110	83	100	90
Anti-blocking properties (mN/cm)	3	18	1	15
Δ Haze (%)	0.5	0.2	0.4	0.2
Static friction coefficient	0.9	1.4	1	1.2
Film impact strength (KJ/m)	10.1	5.7	8.7	8.5

09857687-060801

Comparative Example 1

Bulk copolymerization of propylene and ethylene using
dimethylsilylenebis(2-methyl-4,5-
benzoindenyl)zirconium dichloride

- 5 Copolymerization of propylene and ethylene was carried out in the same manner as in Example 27, except that 0.8 mg of dimethylsilylenebis(2-methyl-4,5-benzoindenyl)zirconium dichloride was used as metallocene, and the charge of ethylene was changed to
- 10 4 NL. The quantity of the polymer obtained was 112 g. This polymer had Tm of 132°C, MFR of 7 g/10 min, Mw/Mn of 2.9 and a decane-soluble component quantity of 0.7 % by weight. As the stereoregularity of the polymer, the minimum was 90.4 %, the proportion of 2,1-
- 15 insertion was 0.79 %, and the proportion of 1,3-insertion was 0.11 %, so that the proportion of 2,1-insertion was high.

Comparative Example 2

- 20 Bulk copolymerization of propylene and ethylene using
dimethylsilylenebis(2-methyl-4,5-
benzoindenyl)zirconium dichloride

- Copolymerization of propylene and ethylene was carried out in the same manner as in Example 27,
- 25 except that 0.8 mg of dimethylsilylenebis(2-methyl-

09857687-060801

4,5-benzoindenyl)zirconium dichloride was used as metallocene, and the charge of ethylene was changed to 8 NL. The quantity of the polymer obtained was 145 g. This polymer had Tm of 120°C, MFR of 14 g/10 min, Mw/Mn of 3.4 and a decane-soluble component quantity of 1.1 % by weight. As the stereoregularity of the polymer, the mmmm was 88.8 %, the proportion of 2,1-insertion was 0.69 %, and the proportion of 1,3-insertion was 0.31 %, so that the proportion of 2,1-insertion was high.

Comparative Example 3

Properties of random PP prepared using Ziegler-Natta catalyst

Properties of commercially available random PP (trade name: F637, available from Grand Polymer Co.) obtained by the use of a magnesium chloride-supported titanium catalyst are as follows. This polymer had Tm of 142°C, MFR of 6 g/10 min, Mw/Mn of 6.0 and a decane-soluble component quantity of 8.0 % by weight, and the value of Mw/Mn was large. As the stereoregularity of the polymer, the mmmm was 91.1 %, and none of the 2,1-insertion and the 1,3-insertion were detected.

Comparative Example 4

Properties of thermally decomposed product of
random PP prepared using Ziegler-Natta catalyst

- Commercially available random PP (trade name: F637,
5 available from Grand Polymer Co.) obtained by the use
of a magnesium chloride-supported titanium catalyst
was thermally decomposed under the conditions of 400°C
and 100 minutes. Properties of the thus thermally
decomposed polymer are as follows. This polymer had Tm
10 of 140°C, MFR of 1000 g/10 min, Mw/Mn of 2.3 and a
decane-soluble component quantity of 22 % by weight,
and the decane-soluble component quantity was large.
As the stereoregularity of the polymer, the mmmm was
92.0 %, and none of the 2,1-insertion and the 1,3-
15 insertion were detected.

Example 47

- Normal pressure polymerization of propylene using
dimethylmethylen(3-tert-butyl-5-
20 methylcyclopentadienyl) (2,7-di-tert-
butylfluorenyl) zirconium dichloride

- A 500 ml glass polymerization apparatus thoroughly
purged with nitrogen was charged with 250 ml of dry
toluene, and then propylene was bubbled to saturate
25 the apparatus. Thereafter, a catalyst solution

09357607 060801

- obtained by adding 5 mmol (in terms of aluminum) of methylaluminumoxane (available from Albemarle Co.) to a toluene solution of 2.35 mg (3.8 μ mol) of the red solid obtained in Example 5 was added. With stirring,
- 5 polymerization was conducted at 25°C for 60 minutes while propylene was bubbled. Thereafter, methanol and a small amount of hydrochloric acid were added to terminate the polymerization. The resulting polymer was filtered, washed with methanol and dried under
- 10 vacuum at 80°C for 6 hours. The quantity of the polymer obtained was 0.50 g. This polymer had Tm of 140°C.

Example 48

- 15 Normal pressure polymerization of propylene using
dimethylmethylene(3-tert-butyl-5-
methylcyclopentadienyl) (2,7-di-tert-
butylfluorenyl)zirconium dichloride

- Polymerization was carried out in the same manner
- 20 as in Example 47, except that 10.3 mg (16.75 μ mol) of the red solid obtained in Example 5 was used, and the polymerization temperature was changed to 50°C. The quantity of the polymer obtained was 6.2 g. This polymer had Tm of 138°C.

Example 49

Normal pressure polymerization of propylene using
cyclohexylidene(3-tert-butyl-5-
methylcyclopentadienyl)(3,6-di-tert-
5 butylfluorenyl)zirconium dichloride

- A 500 ml glass polymerization apparatus thoroughly
purged with nitrogen was charged with 250 ml of dry
toluene, and then propylene was bubbled to saturate
the apparatus. Thereafter, a catalyst solution
10 obtained by adding 5 mmol (in terms of aluminum) of
methylaluminumoxane (available from Albemarle Co.) to a
toluene solution of 3.27 mg (5.0 μ mol) of the red
solid obtained in Example 4 was added. With stirring,
polymerization was conducted at 25°C for 30 minutes
15 while propylene was bubbled. Thereafter, methanol and
a small amount of hydrochloric acid were added to
terminate the polymerization. The resulting polymer
was filtered, washed with methanol and dried under
vacuum at 80°C for 6 hours. The quantity of the
20 polymer obtained was 0.9 g. This polymer had T_m of
155°C.

Example 50

- Normal pressure polymerization of propylene using
25 cyclohexylidene(3-tert-butyl-5-

09857687-060801

methylcyclopentadienyl)(3,6-di-tert-
butylfluorenyl)zirconium dichloride

Polymerization was carried out in the same manner as in Example 49, except that the polymerization

- 5 temperature was changed to 50°C. The quantity of the polymer obtained was 4.9 g. This polymer had T_m of 144°C.

Example 51

- 10 Normal pressure polymerization of propylene using
cyclohexylidene(3-tert-butyl-5-
methylcyclopentadienyl)fluorenylzirconium dichloride

- A 500 ml glass polymerization apparatus thoroughly purged with nitrogen was charged with 250 ml of dry
15 toluene, and then propylene was bubbled to saturate the apparatus. Thereafter, a catalyst solution obtained by adding 5 mmol (in terms of aluminum) of methylaluminumoxane (available from Albemarle Co.) to a toluene solution of 2.71 mg (5.0 μmol) of the reddish
20 brown solid obtained in Example 2 was added. With stirring, polymerization was conducted at 25°C for 15 minutes while propylene was bubbled. Thereafter, methanol and a small amount of hydrochloric acid were added to terminate the polymerization. The resulting
25 polymer was filtered, washed with methanol and dried

09857687.060001

under vacuum at 80°C for 6 hours. The quantity of the polymer obtained was 1.3 g. This polymer had Tm of 145°C.

5 Example 52

Normal pressure polymerization of propylene using
cyclohexylidene(3-tert-butyl-5-
methylcyclopentadienyl)fluorenylzirconium dichloride

- Polymerization was carried out in the same manner
10 as in Example 51, except that the polymerization
temperature was changed to 50°C. The quantity of the
polymer obtained was 3.8 g. This polymer had Tm of
139°C.

15 Example 53

Normal pressure polymerization of propylene using
dimethylmethylene(3-(1-methyl-1-
cyclohexyl)cyclopentadienyl)(3,6-di-tert-
butylfluorenyl)zirconium dichloride

- 20 Polymerization of propylene was carried out in the
same manner as in Example 47, except that 9.61 mg (5
μmol) of the orange solid obtained in Example 7 was
used. The quantity of the polymer obtained was 0.3 g.
This polymer had Tm of 147°C.

Example 54

Normal pressure polymerization of propylene using
dimethylmethylen(3-(1-methyl-1-
cyclohexyl)cyclopentadienyl) (3,6-di-tert-
5 butylfluorenyl)zirconium dichloride

Polymerization was carried out in the same manner
as in Example 53, except that the polymerization
temperature was changed to 50°C. The quantity of the
polymer obtained was 0.2 g. This polymer had Tm of
10 134°C.

Example 55

Normal pressure polymerization of propylene using
dimethylmethylen(3-tert-
15 butylcyclopentadienyl) (1,1,4,4,7,7,10,10-octamethyl-
1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-
fluorenyl)zirconium dichloride

Polymerization of propylene was carried out in the
same manner as in Example 47, except that 1.7 mg (2.5
20 µmol) of the orange solid obtained in Example 8 was
used. The quantity of the polymer obtained was 0.3 g.
This polymer had Tm of 143°C.

Example 56

00557527-1060801

- Normal pressure polymerization of propylene using
dimethylmethylene(3-tert-
butylcyclopentadienyl)(1,1,4,4,7,7,10,10-octamethyl-
1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-
5 fluorenyl)zirconium dichloride

Polymerization was carried out in the same manner as in Example 55, except that the polymerization temperature was changed to 50°C. The quantity of the polymer obtained was 0.4 g. This polymer had Tm of
10 140°C.

Example 57

- Normal pressure polymerization of propylene using
dimethylmethylene(3-
15 trimethylsilylcyclopentadienyl)(1,1,4,4,7,7,10,10-
octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-
fluorenyl)zirconium dichloride

Polymerization of propylene was carried out in the same manner as in Example 47, except that 3.7 mg (5
20 μmol) of the red plate solid obtained in Example 9 was used. The quantity of the polymer obtained was 0.5 g. This polymer had Tm of 137°C.

Example 58

09357687-060801

- Normal pressure polymerization of propylene using
dimethylmethylen(3-
trimethylsilylcyclopentadienyl) (1,1,4,4,7,7,10,10-
octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-
5 fluorenyl)zirconium dichloride
- Polymerization was carried out in the same manner
as in Example 57, except that the polymerization
temperature was changed to 50°C. The quantity of the
polymer obtained was 1.1 g. This polymer had Tm of
10 142°C.

Example 59

- Normal pressure polymerization of propylene using
dimethylmethylen(3-(1,1-
15 dimethylpropyl)cyclopentadienyl) (3,6-di-tert-
butylfluorenyl)zirconium dichloride

- Polymerization of propylene was carried out in the
same manner as in Example 47, except that 3.07 mg (5
μmol) of the red solid obtained in Example 10 was used,
20 and the polymerization time was changed to 45 minutes.
The quantity of the polymer obtained was 1.1 g. This
polymer had Tm of 150°C.

Example 60

0857687 060801
10090 297586

Normal pressure polymerization of propylene using
dimethylmethylene (3-(1,1-
dimethylpropyl)cyclopentadienyl) (3,6-di-tert-
butylfluorenyl)zirconium dichloride

- 5 Polymerization was carried out in the same manner
as in Example 59, except that the polymerization
temperature was changed to 50°C. The quantity of the
polymer obtained was 0.74 g. This polymer had Tm of
138°C.

10

Example 61

Normal pressure polymerization of propylene using
dimethylmethylene (3-(1-ethyl-1-
methylpropyl)cyclopentadienyl) (3,6-di-tert-
butylfluorenyl)zirconium dichloride

15

Polymerization of propylene was carried out in the
same manner as in Example 47, except that 3.15 mg (5
μmol) of the orange solid obtained in Example 11 was
used. The quantity of the polymer obtained was 0.13 g.

- 20 This polymer had Tm of 142°C.

Example 62

Normal pressure polymerization of propylene using
dimethylmethylene (3-(1-ethyl-1-

09857687-060601

methylpropyl)cyclopentadienyl) (3,6-di-tert-
butylfluorenyl)zirconium dichloride

- Polymerization was carried out in the same manner as in Example 61, except that the polymerization
- 5 temperature was changed to 50°C. The quantity of the polymer obtained was 0.02 g. This polymer had Tm of 123°C.

Example 63

- 10 Normal pressure polymerization of propylene using
dimethylmethylene(3-(1,1,3-
trimethylbutyl)cyclopentadienyl) (3,6-di-tert-
butylfluorenyl)zirconium dichloride

- Polymerization of propylene was carried out in the
- 15 same manner as in Example 47, except that 3.22 mg (5 μmol) of the reddish brown solid obtained in Example 12 was used. The quantity of the polymer obtained was 0.62 g. This polymer had Tm of 146°C.

20 Example 64

Normal pressure polymerization of propylene using
dimethylmethylene(3-(1,1,3-
trimethylbutyl)cyclopentadienyl) (3,6-di-tert-
butylfluorenyl)zirconium dichloride

09857667-060001

- Polymerization was carried out in the same manner as in Example 63, except that the polymerization temperature was changed to 50°C. The quantity of the polymer obtained was 1.2 g. This polymer had Tm of
- 5 136°C.

Example 65

- Normal pressure polymerization of propylene using
dimethylmethylene(3-(1,1-
10 dimethylbutyl)cyclopentadienyl)(3,6-di-tert-
butylfluorenyl)zirconium dichloride

- Polymerization of propylene was carried out in the same manner as in Example 47, except that 3.14 mg (5 μmol) of the red solid obtained in Example 14 was used.
- 15 The quantity of the polymer obtained was 1.67 g. This polymer had Tm of 149°C.

Example 66

- Normal pressure polymerization of propylene using
20 dimethylmethylene(3-(1,1-
dimethylbutyl)cyclopentadienyl)(3,6-di-tert-butyl-
fluorenyl)zirconium dichloride

- Polymerization was carried out in the same manner as in Example 65, except that the polymerization
- 25 temperature was changed to 50°C. The quantity of the

09557687 060801

polymer obtained was 1.2 g. This polymer had T_m of 137°C.

Example 67

- 5 Normal pressure polymerization of propylene using dimethylmethylene(3-tert-butylcyclopentadienyl)(2,7-di-tert-butylfluorenyl)zirconium dichloride

Polymerization of propylene was carried out in the same manner as in Example 47, except that 3.0 mg (5 μ mol) of the red solid obtained in Example 15 was used. The quantity of the polymer obtained was 1.27 g. This polymer had T_m of 140°C.

Example 68

- 15 Normal pressure polymerization of propylene using dimethylmethylene(3-tert-butylcyclopentadienyl)(2,7-di-tert-butylfluorenyl)zirconium dichloride

Polymerization was carried out in the same manner as in Example 67, except that the polymerization temperature was changed to 50°C. The quantity of the polymer obtained was 5.11 g. This polymer had T_m of 137°C.

Example 69

09557687-060801

Normal pressure polymerization of propylene using
diphenylmethylen(3-
phenylcyclopentadienyl)(1,1,4,4,7,7,10,10-octamethyl-
1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-
5 fluorenyl)zirconium dichloride

- Polymerization of propylene was carried out in the same manner as in Example 47, except that 4.27 mg (5 μ mol) of the reddish orange solid obtained in Example 17 was used. The quantity of the polymer obtained was 10 0.08 g. This polymer had Tm of 105°C.

Example 70

- Normal pressure polymerization of propylene using
diphenylmethylen(3-
15 trimethylsilylcyclopentadienyl)(1,1,4,4,7,7,10,10-
octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-
fluorenyl)zirconium dichloride

- Polymerization of propylene was carried out in the same manner as in Example 47, except that 4.05 mg (5 μ mol) of the pink powder obtained in Example 18 was 20 used. The quantity of the polymer obtained was 0.18 g. This polymer had Tm of 139°C.

Example 71

09557687-060801

Normal pressure polymerization of propylene using
diphenylmethylene(3-
trimethylsilylcyclopentadienyl)(1,1,4,4,7,7,10,10-
octamethyl-1,2,3,4,7,8,9,10-octahydridibenzo(b,h)-
5 fluorenyl)zirconium dichloride

- Polymerization was carried out in the same manner
as in Example 70, except that the polymerization
temperature was changed to 50°C. The quantity of the
polymer obtained was 0.64 g. This polymer had Tm of
10 139°C.

Example 72

Normal pressure polymerization of propylene using
methylphenylmethylene(3-tert-
15 butylcyclopentadienyl)(3,6-di-tert-
butylfluorenyl)zirconium dichloride

- Polymerization of propylene was carried out in the
same manner as in Example 47, except that 3.32 mg (5
μmol) of the orange solid obtained in Example 19 was
20 used, and the polymerization time was changed to 45
minutes. The quantity of the polymer obtained was 1.16
g. This polymer had Tm of 144°C.

Example 73

09857687.060801

Normal pressure polymerization of propylene using
methylphenylmethylene(3-tert-
butylcyclopentadienyl) (3,6-di-tert-
butylfluorenyl)zirconium dichloride

- 5 Polymerization was carried out in the same manner as in Example 72, except that the polymerization temperature was changed to 50°C. The quantity of the polymer obtained was 8.65 g. This polymer had Tm of 144°C.

10

Example 74

Normal pressure polymerization of propylene using
diethylmethylene(3-tert-butylcyclopentadienyl) (3,6-di-
tert-butylfluorenyl)zirconium dichloride

15

Polymerization of propylene was carried out in the same manner as in Example 47, except that 3.14 mg (5 μ mol) of the orange solid obtained in Example 20 was used. The quantity of the polymer obtained was 0.83 g. This polymer had Tm of 150°C.

20

Example 75

Normal pressure polymerization of propylene using
diethylmethylene(3-tert-butylcyclopentadienyl) (3,6-di-
tert-butylfluorenyl)zirconium dichloride

09557587-060801

- Polymerization was carried out in the same manner as in Example 74, except that the polymerization temperature was changed to 50°C. The quantity of the polymer obtained was 3.15 g. This polymer had Tm of
- 5 143°C.

Example 76

- Normal pressure polymerization of propylene using cyclohexylidene(3-trimethylsilylcyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride
- 10 di-tert-butylfluorenyl)zirconium dichloride
- Polymerization of propylene was carried out in the same manner as in Example 47, except that 3.3 mg (5 μmol) of the orange solid obtained in Example 21 was used. The quantity of the polymer obtained was 0.58 g.
- 15 This polymer had Tm of 141°C.

Example 77

- Normal pressure polymerization of propylene using cyclohexylidene(3-trimethylsilylcyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride
- 20 di-tert-butylfluorenyl)zirconium dichloride
- Polymerization was carried out in the same manner as in Example 76, except that the polymerization temperature was changed to 50°C. The quantity of the polymer obtained was 0.8 g. This polymer had Tm of
- 25 139°C.

09857687-060801

Example 78

Normal pressure polymerization of propylene using
cyclopentylidene(3-tert-butylcyclopentadienyl) (3,6-di-
5 tert-butylfluorenyl)zirconium dichloride

Polymerization of propylene was carried out in the same manner as in Example 47, except that 3.13 mg (5 μ mol) of the orange solid obtained in Example 22 was used. The quantity of the polymer obtained was 0.3 g.

10 This polymer had Tm of 146°C.

Example 79

Normal pressure polymerization of propylene using
cyclopentylidene(3-tert-butylcyclopentadienyl) (3,6-di-
15 tert-butylfluorenyl)zirconium dichloride

Polymerization was carried out in the same manner as in Example 78, except that the polymerization temperature was changed to 50°C. The quantity of the polymer obtained was 3.1 g. This polymer had Tm of

20 143°C.

Example 80

Normal pressure polymerization of propylene using
cyclohexylidene(3-(1,1-

0957587, 060801
100902, 2827860

dimethylpropyl)cyclopentadienyl)(3,6-di-tert-
butylfluorenyl)zirconium dichloride

- Polymerization of propylene was carried out in the same manner as in Example 47, except that 3.28 mg (5 μ mol) of the reddish brown solid obtained in Example 23 was used. The quantity of the polymer obtained was 0.37 g. This polymer had Tm of 143°C.

Example 81

- 10 Normal pressure polymerization of propylene using
cyclohexylidene(3-(1,1-
dimethylpropyl)cyclopentadienyl)(3,6-di-tert-
butylfluorenyl)zirconium dichloride

- Polymerization was carried out in the same manner as in Example 80, except that the polymerization temperature was changed to 50°C. The quantity of the polymer obtained was 0.19 g. This polymer had Tm of 129°C.

20 Example 82

- Normal pressure polymerization of propylene using
cyclopentylidene(3-tert-
butylcyclopentadienyl)(1,1,4,4,7,7,10,10-octamethyl-
1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-
25 fluorenyl)zirconium dichloride

09857687.060801

Polymerization of propylene was carried out in the same manner as in Example 47, except that 3.67 mg (5 μ mol) of the red solid obtained in Example 24 was used. The quantity of the polymer obtained was 0.33 g.

5

Example 83

Normal pressure polymerization of propylene using
cyclopentylidene(3-tert-
butylcyclopentadienyl)(1,1,4,4,7,7,10,10-octamethyl-
10 1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-
fluorenyl)zirconium dichloride

Polymerization was carried out in the same manner as in Example 82, except that the polymerization temperature was changed to 50°C. The quantity of the
15 polymer obtained was 0.37 g.

Example 84

Bulk polymerization of propylene using
cyclohexylidene(3-tert-butyl-5-
20 methylcyclopentadienyl)fluorenylzirconium dichloride

In a 50 ml two-necked flask thoroughly purged with nitrogen, 2.0 mmol (in terms of aluminum) of silica-supported methylaluminoxane was suspended in 20 ml of heptane. To the suspension, a toluene solution of 1.1
25 mg (2 μ mol) of the reddish brown solid obtained in

09857687-060801

Example 2 was added, then triisobutylaluminum (1 mmol) was added, and they were stirred for 30 minutes to give a catalyst suspension.

- A 2000 ml autoclave thoroughly purged with
- 5 nitrogen was charged with 500 g of propylene, and the catalyst suspension was added to perform polymerization at 70°C for 40 minutes under a pressure of 3.0 to 3.5 MPa. Thereafter, methanol was added to terminate the polymerization, and propylene was purged
- 10 of, to obtain a polymer. The polymer was dried under vacuum at 80°C for 6 hours. The quantity of the polymer obtained was 103 g. This polymer had Tm of 139°C, MFR of 1.2 g/10 min, Mw of 348000, Mn of 184000, Mw/Mn of 1.9 and a decane-soluble component quantity
- 15 of 0.5 % by weight.

Example 85

Bulk polymerization of propylene using cyclohexylidene(3-tert-butyl-5-

- 20 methylcyclopentadienyl)fluorenylzirconium dichloride

Polymerization of propylene was carried out in the same manner as in Example 84, except that 2 NL of hydrogen was added. The quantity of the polymer obtained was 55 g. This polymer had Tm of 141°C, MFR

25 of 1000 g/10 min, Mw of 69000, Mn of 30000, Mw/Mn of

09857687.050801

2.3 and a decane-soluble component quantity of 0.8 % by weight. As the stereoregularity of the polymer, the mmum was 85.8 %, the proportion of 2,1-insertion was 0.08 %, and the proportion of 1,3-insertion was 0.02 %.

5

Example 86

Bulk polymerization of propylene using
cyclohexylidene(3-tert-butyl-5-
methylcyclopentadienyl)(3,6-di-tert-
butylfluorenyl)zirconium dichloride

10

Polymerization of propylene was carried out in the same manner as in Example 84, except that 1.3 mg (2 μ mol) of the red solid obtained in Example 4 was used.

The quantity of the polymer obtained was 49 g. This

15 polymer had Tm of 155°C, MFR of 1.6 g/10 min, Mw of 357000, Mn of 193000, Mw/Mn of 1.8 and a decane-soluble component quantity of 0.3 % by weight.

Example 87

20

Bulk polymerization of propylene using
cyclohexylidene(3-tert-butyl-5-
methylcyclopentadienyl)(3,6-di-tert-
butylfluorenyl)zirconium dichloride

Polymerization of propylene was carried out in the

25 same manner as in Example 86, except that 1 NL of

09857587-060801

- hydrogen was added. The quantity of the polymer obtained was 328 g. This polymer had T_m of 156°C , MFR of 150 g/10 min, M_w of 117000, M_n of 52000, M_w/M_n of 2.3 and a decane-soluble component quantity of 0.1 % by weight. As the stereoregularity of the polymer, the mmmm was 95.6 %, and none of the 2,1-insertion and the 1,3-insertion were detected.

Example 88

- 10 Bulk polymerization of propylene using
 cyclohexylidene(3-tert-butyl-5-
 methylcyclopentadienyl)(3,6-di-tert-
 butylfluorenyl)zirconium dichloride

- Polymerization of propylene was carried out in the same manner as in Example 86, except that 1 NL of hydrogen was added, and the polymerization temperature was changed to 60°C . The quantity of the polymer obtained was 252 g. This polymer had T_m of 158°C , MFR of 210 g/10 min, M_w of 97000, M_n of 45000, M_w/M_n of 2.1 and a decane-soluble component quantity of 0.1 % by weight. As the stereoregularity of the polymer, the mmmm was 97.0 %, and none of the 2,1-insertion and the 1,3-insertion were detected.

- 25 Example 89

Bulk polymerization of propylene using
cyclohexylidene(3-tert-butyl-5-
methylcyclopentadienyl) (3,6-di-tert-
butylfluorenyl)zirconium dichloride

- 5 Polymerization of propylene was carried out in the same manner as in Example 86, except that 0.5 NL of hydrogen was added, and triethylaluminum (1 mmol) was used instead of triisobutylaluminum (1 mmol). The quantity of the polymer obtained was 295 g. This
- 10 polymer had Tm of 157°C, MFR of 42 g/10 min, Mw of 147000, Mn of 71000, Mw/Mn of 2.1 and a decane-soluble component quantity of 0.1 % by weight.

Example 90

- 15 Bulk polymerization of propylene using
dimethylmethylene(3-tert-butyl-5-
methylcyclopentadienyl) (2,7-di-tert-
butylfluorenyl)zirconium dichloride

- Polymerization of propylene was carried out in the
- 20 same manner as in Example 84, except that 1.2 mg (2 μmol) of the red solid obtained in Example 5 was used. The quantity of the polymer obtained was 41 g. This polymer had Tm of 141°C, MFR of 0.05 g/10 min, Mw of 524000, Mn of 274000, Mw/Mn of 1.9 and a decane-
- 25 soluble component quantity of 0.1 % by weight. As the

stereoregularity of the polymer, the minimum was 88.4 %, the proportion of 2,1-insertion was 0.04 %, and the proportion of 1,3-insertion was 0.07 %.

5 Example 91

Bulk polymerization of propylene using
dimethylmethylen(3-(1-methyl-1-
cyclohexyl)cyclopentadienyl)(3,6-di-tert-
butylfluorenyl)zirconium dichloride

- 10 Polymerization of propylene was carried out in the same manner as in Example 84, except that 4.5 mg (7 μ mol) of the orange solid obtained in Example 7 was used. The quantity of the polymer obtained was 33 g. This polymer had Tm of 146°C, MFR of 60 g/10 min, Mw
- 15 of 115000, Mn of 67000, Mw/Mn of 1.7 and a decane-soluble component quantity of 0.7 % by weight.

Example 92

Bulk polymerization of propylene using
dimethylmethylen(3-(1-methyl-1-
cyclohexyl)cyclopentadienyl)(3,6-di-tert-
butylfluorenyl)zirconium dichloride

- 20 Polymerization of propylene was carried out in the same manner as in Example 91, except that 1 NL of
- 25 hydrogen was added. The quantity of the polymer

09857587.060601

obtained was 24 g. This polymer had Tm of 153°C, MFR of 400 g/10 min, Mw of 59000, Mn of 30000, Mw/Mn of 2.0 and a decane-soluble component quantity of 1.0 % by weight.

5

Example 93

Bulk polymerization of propylene using
dimethylmethylen(3-tert-
butylcyclopentadienyl) (1,1,4,4,7,7,10,10-octamethyl-
10 1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-
fluorenyl)zirconium dichloride

Polymerization of propylene was carried out in the same manner as in Example 84, except that 1.0 mg (1.4 μmol) of the orange solid obtained in Example 8 was
15 used. The quantity of the polymer obtained was 30 g. This polymer had Tm of 149°C and MFR of 190 g/10 min.

Example 94

Bulk polymerization of propylene using
20 dimethylmethylen(3-tert-
butylcyclopentadienyl) (1,1,4,4,7,7,10,10-octamethyl-
1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-
fluorenyl)zirconium dichloride

Polymerization of propylene was carried out in the
25 same manner as in Example 93, except that 0.3 NL of

09557537.060801
105090.782586

hydrogen was added. The quantity of the polymer obtained was 183 g. This polymer had T_m of 153°C and MFR of 1000 g/10 min.

5 Example 95

Bulk polymerization of propylene using

dimethylmethylene(3-

trimethylsilylcyclopentadienyl)(1,1,4,4,7,7,10,10-

octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-

10 fluorenyl)zirconium dichloride

Polymerization of propylene was carried out in the same manner as in Example 84, except that 10.68 mg (0.94 μmol) of the red plate solid obtained in Example 9 was used. The quantity of the polymer obtained was 4

15 g. This polymer had T_m of 136°C.

Example 96

Bulk polymerization of propylene using

dimethylmethylene(3-

20 trimethylsilylcyclopentadienyl)(1,1,4,4,7,7,10,10-

octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-

fluorenyl)zirconium dichloride

Polymerization of propylene was carried out in the same manner as in Example 95, except that 0.3 NL of

09857687.060801

hydrogen was added. The quantity of the polymer obtained was 64 g. This polymer had Tm of 143°C.

Example 97

- 5 Bulk polymerization of propylene using
 dimethylmethylen(3-(1,1-
 dimethylpropyl)cyclopentadienyl)(3,6-di-tert-
 butylfluorenyl)zirconium dichloride

10 Polymerization of propylene was carried out in the
 same manner as in Example 84, except that 0.68 mg (1.1
 μ mol) of the red solid obtained in Example 10 was used.
 The quantity of the polymer obtained was 54 g. This
 polymer had Tm of 151°C.

- 15 Example 98
 Bulk polymerization of propylene using
 dimethylmethylen(3-(1,1-
 dimethylpropyl)cyclopentadienyl)(3,6-di-tert-
 butylfluorenyl)zirconium dichloride

20 Polymerization of propylene was carried out in the
 same manner as in Example 97, except that 0.3 NL of
 hydrogen was added. The quantity of the polymer
 obtained was 91 g. This polymer had Tm of 151°C.

- 25 Example 99

09857687.060801
108090.28975860

Bulk polymerization of propylene using
dimethylmethylen(3-(1-ethyl-1-
methylpropyl)cyclopentadienyl) (3,6-di-tert-
butylfluorenyl)zirconium dichloride

- 5 Polymerization of propylene was carried out in the same manner as in Example 84, except that 0.68 mg (1.1 μ mol) of the red solid obtained in Example 11 was used. The quantity of the polymer obtained was 12 g. This polymer had Tm of 147°C.

10

Example 100

Bulk polymerization of propylene using
dimethylmethylen(3-(1-ethyl-1-
methylpropyl)cyclopentadienyl) (3,6-di-tert-butyl-
fluorenyl)zirconium dichloride

15

Polymerization of propylene was carried out in the same manner as in Example 99, except that 0.3 NL of hydrogen was added. The quantity of the polymer obtained was 34 g. This polymer had Tm of 152°C.

20

Example 101

Bulk polymerization of propylene using
dimethylmethylen(3-(1,1-
dimethylbutyl)cyclopentadienyl) (3,6-di-tert-
butylfluorenyl)zirconium dichloride

25

09557687.060801

- Polymerization of propylene was carried out in the same manner as in Example 84, except that 0.68 mg (1.1 μ mol) of the red solid obtained in Example 14 was used. The quantity of the polymer obtained was 29 g. This
- 5 polymer had Tm of 147°C and MFR of 350 g/10 min.

Example 102

- Bulk polymerization of propylene using
dimethylmethylen(3-(1,1-
10 dimethylbutyl)cyclopentadienyl) (3,6-di-tert-
butylfluorenyl)zirconium dichloride

- Polymerization of propylene was carried out in the same manner as in Example 101, except that 0.3 NL of hydrogen was added. The quantity of the polymer
- 15 obtained was 43 g. This polymer had Tm of 150°C and MFR of 1000 g/10 min.

Example 103

- Bulk polymerization of propylene using
20 dimethylmethylen(3-tert-butylcyclopentadienyl) (2,7-
di-tert-butylfluorenyl)zirconium dichloride

Polymerization of propylene was carried out in the same manner as in Example 84, except that 1.3 mg (2 μ mol) of the red solid obtained in Example 15 was used.

09857587.060801

The quantity of the polymer obtained was 42 g. This polymer had Tm of 137°C and MFR of 1000 g/10 min.

Example 104

- 5 Bulk polymerization of propylene using
dimethylmethylen(3-tert-butylcyclopentadienyl) (2,7-
di-tert-butylfluorenyl)zirconium dichloride

Polymerization of propylene was carried out in the same manner as in Example 103, except that 0.3 NL of
10 hydrogen was added. The quantity of the polymer obtained was 84 g. This polymer had Tm of 138°C and MFR of 1000 g/10 min.

Example 105

- 15 Bulk polymerization of propylene using
diphenylmethylen(3-
trimethylsilylcyclopentadienyl) (1,1,4,4,7,7,10,10-
octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-
fluorenyl)zirconium dichloride

20 Polymerization of propylene was carried out in the same manner as in Example 84, except that 0.68 mg (0.8 μmol) of the pink powder obtained in Example 18 was used. The quantity of the polymer obtained was 6 g. This polymer had Tm of 141°C.

Example 106

- Bulk polymerization of propylene using
diphenylmethylene(3-
trimethylsilylcyclopentadienyl)(1,1,4,4,7,7,10,10-
5 octamethyl-1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-
fluorenyl)zirconium dichloride

- Polymerization of propylene was carried out in the
same manner as in Example 105, except that 0.3 NL of
hydrogen was added. The quantity of the polymer
10 obtained was 49 g. This polymer had Tm of 146°C.

Example 107

- Bulk polymerization of propylene using
methylphenylmethylene(3-tert-
15 butylcyclopentadienyl)(3,6-di-tert-
butylfluorenyl)zirconium dichloride

- Polymerization of propylene was carried out in the
same manner as in Example 84, except that 0.68 mg (2
μmol) of the orange solid obtained in Example 19 was
20 used. The quantity of the polymer obtained was 87 g.
This polymer had Tm of 144°C.

Example 108

- Bulk polymerization of propylene using
25 methylphenylmethylene(3-tert-

09657687 060801
108090 28975860

butylcyclopentadienyl)(3,6-di-tert-
butylfluorenyl)zirconium dichloride

Polymerization of propylene was carried out in the same manner as in Example 107, except that 0.3 NL of

- 5 hydrogen was added. The quantity of the polymer obtained was 148 g. This polymer had Tm of 146°C.

Example 109

Bulk polymerization of propylene using

- 10 diethylmethylene(3-tert-butylcyclopentadienyl)(3,6-di-
tert-butylfluorenyl)zirconium dichloride

Polymerization of propylene was carried out in the same manner as in Example 84, except that 0.68 mg (1.1 μmol) of the orange solid obtained in Example 20 was

- 15 used. The quantity of the polymer obtained was 50 g. This polymer had Tm of 149°C.

Example 110

Bulk polymerization of propylene using

- 20 diethylmethylene(3-tert-butylcyclopentadienyl)(3,6-di-
tert-butylfluorenyl)zirconium dichloride

Polymerization of propylene was carried out in the same manner as in Example 109, except that 0.3 NL of hydrogen was added. The quantity of the polymer

- 25 obtained was 89 g. This polymer had Tm of 152°C.

09857687.060801

Example 111

Bulk polymerization of propylene using
cyclohexylidene(3-trimethylsilylcyclopentadienyl) (3,6-
5 di-tert-butylfluorenyl)zirconium dichloride

Polymerization of propylene was carried out in the same manner as in Example 84, except that 0.68 mg (1 μ mol) of the orange solid obtained in Example 21 was used. The quantity of the polymer obtained was 20 g.

- 10 This polymer had Tm of 139°C.

Example 112

Bulk polymerization of propylene using
cyclohexylidene(3-trimethylsilylcyclopentadienyl) (3,6-
15 di-tert-butylfluorenyl)zirconium dichloride

Polymerization of propylene was carried out in the same manner as in Example 111, except that 0.3 NL of hydrogen was added. The quantity of the polymer obtained was 43 g. This polymer had Tm of 141°C, MFR
20 of 1000 g/10 min and a decane-soluble component quantity of 0.5 % by weight.

Example 113

09857687.060801

Bulk polymerization of propylene using
cyclopentylidene(3-tert-butylcyclopentadienyl) (3,6-di-
tert-butylfluorenyl)zirconium dichloride

- Polymerization of propylene was carried out in the
- 5 same manner as in Example 84, except that 0.68 mg (1.1 μ mol) of the orange solid obtained in Example 17 was used. The quantity of the polymer obtained was 49 g. This polymer had Tm of 149°C and MFR of 190 g/10 min.

10 Example 114

Bulk polymerization of propylene using
cyclopentylidene(3-tert-butylcyclopentadienyl) (3,6-di-
tert-butylfluorenyl)zirconium dichloride

- Polymerization of propylene was carried out in the
- 15 same manner as in Example 113, except that 0.3 NL of hydrogen was added. The quantity of the polymer obtained was 118 g. This polymer had Tm of 151°C and MFR of 1000 g/10 min.

20 Example 115

Bulk polymerization of propylene using
cyclohexylidene(3-(1,1-
dimethylpropyl)cyclopentadienyl) (3,6-di-tert-
butylfluorenyl)zirconium dichloride

0957637 060301

Polymerization of propylene was carried out in the same manner as in Example 84, except that 0.68 mg (1 μ mol) of the reddish brown solid obtained in Example 23 was used. The quantity of the polymer obtained was 3 g. This polymer had Tm of 141°C.

Example 116

Bulk polymerization of propylene using
cyclohexylidene(3-(1,1-
10 dimethylpropyl)cyclopentadienyl)(3,6-di-tert-
butylfluorenyl)zirconium dichloride

Polymerization of propylene was carried out in the same manner as in Example 115, except that 0.3 NL of hydrogen was added. The quantity of the polymer
15 obtained was 47 g. This polymer had Tm of 150°C.

Example 117

Bulk polymerization of propylene using
cyclopentylidene(3-tert-
20 butylcyclopentadienyl)(1,1,4,4,7,7,10,10-octamethyl-
1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-
fluorenyl)zirconium dichloride

Polymerization of propylene was carried out in the same manner as in Example 84, except that 0.68 mg (0.9 μ mol) of the red solid obtained in Example 24 was used.
25

09857697.060801

The quantity of the polymer obtained was 3 g. This polymer had Tm of 143°C.

Example 118

- 5 Bulk polymerization of propylene using
 cyclopentylidene(3-tert-
 butylcyclopentadienyl)(1,1,4,4,7,7,10,10-octamethyl-
 1,2,3,4,7,8,9,10-octahydrodibenzo(b,h)-
 fluorenyl)zirconium dichloride
- 10 Polymerization of propylene was carried out in the same manner as in Example 117, except that 0.3 NL of hydrogen was added. The quantity of the polymer obtained was 87 g. This polymer had Tm of 152°C.
- 15 Comparative Example 5
 Bulk polymerization of propylene using
 dimethylsilylenebis(2-methyl-4,5-
 benzoindenyl)zirconium dichloride
- 20 Polymerization of propylene was carried out in the same manner as in Example 84, except that 0.8 mg of dimethylsilylenebis(2-methyl-4,5-benzoindenyl)zirconium dichloride was used as metallocene. The quantity of the polymer obtained was 150 g. This polymer had Tm of 145°C, MFR of 16 g/10
- 25 min, Mw/Mn of 2.1 and a decane-soluble component

09857687-060801

- quantity of 0.4 % by weight. As the stereoregularity of the polymer, the mmmm was 93.0 %, the proportion of 2,1-insertion was 0.75 %, the proportion of 1,3-insertion was 0.06 %, and the proportion of the 2,1-insertion was high.

Comparative Example 6

Bulk polymerization of propylene using
dimethylsilylenebis(2-methyl-4-phenylindenyl)zirconium
dichloride

- Polymerization of propylene was carried out in the same manner as in Example 84, except that 0.7 mg of dimethylsilylenebis(2-methyl-4-phenylindenyl)zirconium dichloride was used as metallocene. The quantity of the polymer obtained was 163 g. This polymer had Tm of 150°C, MFR of 1 g/10 min, Mw/Mn of 2.5 and a decane-soluble component quantity of 0.6 % by weight. As the stereoregularity of the polymer, the mmmm was 95.9 %, the proportion of 2,1-insertion was 0.80 %, the proportion of 1,3-insertion was 0.05 %, and the proportion of the 2,1-insertion was high.

Comparative Example 7

Properties of homo-PP prepared using Ziegler-Natta
catalyst

- Properties of commercially available homo-PP (trade name: J700, available from Grand Polymer Co.) obtained by the use of a magnesium chloride-supported titanium catalyst are as follows. This polymer had Tm
- 5 of 161°C, MFR of 11 g/10 min, Mw/Mn of 5.2 and a decane-soluble component quantity of 2.0 % by weight, and the value of Mw/Mn was large. As the stereoregularity of the polymer, the minimum was 95.0 %, and none of the 2,1-insertion and the 1,3-insertion
- 10 were detected.

Comparative Example 8

Properties of thermally decomposed product of homo-PP prepared using Ziegler-Natta catalyst

- 15 Commercially available homo-PP (trade name: J700, available from Grand Polymer Co.) obtained by the use of a magnesium chloride-supported titanium catalyst was thermally decomposed under the conditions of 400°C and 100 minutes. Properties of the thus thermally
- 20 decomposed polymer are as follows. This polymer had Tm of 160°C, MFR of 1000 g/10 min, Mw/Mn of 2.3 and a decane-soluble component quantity of 15 % by weight, and the decane-soluble component quantity was large. As the stereoregularity of the polymer, the minimum was

00857637-060801

94.9 %, and none of the 2,1-insertion and the 1,3-insertion were detected.

Example 119

- 5 Normal pressure polymerization of propylene using
 dimethylmethylene(3-tert-butyl-5-
 methylcyclopentadienyl) (3,6-di-tert-
 butylfluorenyl)zirconium dichloride

- A 500 ml glass polymerization apparatus thoroughly
- 10 purged with nitrogen was charged with 250 ml of dry
 toluene, and then the apparatus was purged with
 propylene. Then, a catalyst solution obtained by
 adding 5 mmol (in terms of aluminum) of
 methylaluminumoxane (available from Albemarle Co.) to a
- 15 toluene solution of 3.1 mg (5 μ mol) of the orange
 solid obtained in Example 3 was added. With stirring,
 polymerization was conducted at 25°C for 30 minutes
 while propylene was bubbled. Thereafter, methanol and
 a small amount of hydrochloric acid were added to
- 20 terminate the polymerization. The resulting polymer
 was filtered, washed with methanol and dried under
 vacuum at 80°C for 6 hours. The quantity of the
 polymer obtained was 0.7 g. This polymer had T_m of
 155°C.

Example 120

Normal pressure polymerization of propylene using
dimethylmethylene(3-tert-butyl-5-
methylcyclopentadienyl)(3,6-di-tert-
5 butylfluorenyl)zirconium dichloride

- Polymerization was carried out in the same manner as in Example 119, except that the polymerization temperature was changed to 50°C. The quantity of the polymer obtained was 1.6 g. This polymer had Tm of
- 10 144°C.

Example 121

- Normal pressure polymerization of propylene using
dimethylmethylene(3-tert-butyl-5-
15 methylcyclopentadienyl)fluorenylzirconium dichloride

- A 500 ml glass polymerization apparatus thoroughly purged with nitrogen was charged with 250 ml of dry toluene, and then propylene was bubbled to saturate the apparatus. Thereafter, a catalyst solution
- 20 obtained by adding 5 mmol (in terms of aluminum) of methylaluminoxane (available from Albemarle Co.) to a toluene solution of 2.51 mg (5.0 μ mol) of the reddish orange solid obtained in Example 1 was added. With stirring, polymerization was conducted at 25°C for 10
- 25 minutes while propylene was bubbled. Thereafter,

methanol and a small amount of hydrochloric acid were added to terminate the polymerization. The resulting polymer was filtered, washed with methanol and dried under vacuum at 80°C for 6 hours. The quantity of the polymer obtained was 0.9 g. This polymer had Tm of 146°C.

Example 122

Normal pressure polymerization of propylene using
10 dimethylmethylene(3-tert-butyl-5-
methylcyclopentadienyl)fluorenylzirconium dichloride

Polymerization was carried out in the same manner as in Example 121, except that the polymerization temperature was changed to 50°C. The quantity of the
15 polymer obtained was 0.9 g. This polymer had Tm of 134°C.

Example 123

Bulk polymerization of propylene using
20 dimethylmethylene(3-tert-butyl-5-
methylcyclopentadienyl)fluorenylzirconium dichloride

In a 50 ml two-necked flask thoroughly purged with nitrogen, 2.0 mmol (in terms of aluminum) of silica-supported methylaluminoxane was suspended in 20 ml of
25 heptane. To the suspension, a toluene solution of 1.0

09857687-050801
1-2208-7897-586

mg (2 μ mol) of the reddish orange solid obtained in Example 1 was added, then triisobutylaluminum (1 mmol) was added, and they were stirred for 30 minutes to give a catalyst suspension.

- 5 A 2000 ml autoclave thoroughly purged with nitrogen was charged with 500 g of propylene, and the catalyst suspension was added to perform polymerization at 70°C for 40 minutes under a pressure of 3.0 to 3.5 MPa. Thereafter, methanol was added to
- 10 terminate the polymerization, and propylene was purged of, to obtain a polymer. The polymer was dried under vacuum at 80°C for 6 hours. The quantity of the polymer obtained was 102 g. This polymer had Tm of 139°C, MFR of 0.7 g/10 min, Mw of 406000, Mn of 197000,
- 15 Mw/Mn of 2.1 and a decane-soluble component quantity of 0.1 % by weight.

Example 124

- 20 Bulk polymerization of propylene using
dimethylmethylen(3-tert-butyl-5-
methylcyclopentadienyl)fluorenylzirconium dichloride

- Polymerization of propylene was carried out in the same manner as in Example 123, except that 1 NL of hydrogen was added. The quantity of the polymer
- 25 obtained was 69 g. This polymer had Tm of 142°C, MFR

00657687-060801

- of 22 g/10 min, Mw of 185000, Mn of 80000, Mw/Mn of 2.3 and a decane-soluble component quantity of 0.4 % by weight. As the stereoregularity of the polymer, the *mmmm* was 86.9 %, the proportion of 2,1-insertion was 0.02 %, and the proportion of 1,3-insertion was 0.05 %.

Example 125

- 10 Bulk polymerization of propylene using
dimethylmethylene(3-tert-butyl-5-
methylcyclopentadienyl) (3,6-di-tert-
butylfluorenyl)zirconium dichloride

- 15 Polymerization of propylene was carried out in the same manner as in Example 123, except that 1.1 mg (1.8 μ mol) of the orange solid obtained in Example 3 was used. The quantity of the polymer obtained was 90 g. This polymer had Tm of 154°C, MFR of 1.8 g/10 min, Mw of 321000, Mn of 154000, Mw/Mn of 2.3 and a decane-soluble component quantity of 0.1 % by weight.

20 Example 126

Bulk polymerization of propylene using
dimethylmethylene(3-tert-butyl-5-
methylcyclopentadienyl) (3,6-di-tert-
butylfluorenyl)zirconium dichloride

0985787.060801
108090.289586

Polymerization of propylene was carried out in the same manner as in Example 125, except that 1 NL of hydrogen was added. The quantity of the polymer obtained was 135 g. This polymer had Tm of 156°C, MFR of 350 g/10 min, Mw of 82000, Mn of 37000, Mw/Mn of 2.2 and a decane-soluble component quantity of 0.2 % by weight. As the stereoregularity of the polymer, the mmmm was 94.8 %, and none of the 2,1-insertion and the 1,3-insertion were detected.

10

Comparative Example 9

Synthesis of dimethylmethylene(3-tert-butyl-5-methylcyclopentadienyl)fluorenylzirconium dichloride containing isomer

15 (1) Synthesis of 2,6,6-trimethylfulvene

To 130 ml of dehydrated methanol, 22.6 g (283 mmol) of methylcyclopentadiene and 8.50 ml (116 mmol) of acetone were added, then 14.5 ml (174 mmol) of pyrrolidine was dropwise added at 0°C, and the mixture was reacted at room temperature for one night. Then, 10 ml (180 mmol) of acetic acid was added at 0°C. The mixture was diluted with ether and water and then subjected to extraction. Then, the organic phase was separated, washed with water and dried over anhydrous

0057687-060801

magnesium sulfate to obtain 12.9 g of a brown liquid.
The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS, main peak): δ 6.49 (d, 1H), 6.32 (d, 1H), 6.17 (s, 1H), 2.14 (s, 3H), 2.13 (s, 3H), 2.06 (s, 3H)

(2) Synthesis of 1-tert-butyl-3-methylcyclopentadiene

In a 300 ml flask purged with nitrogen, 2.86 g (23.8 mmol) of trimethylfulvene synthesized in the above step (1) and 80 ml of dry ether were placed.

- 10 Then, 17 ml (23.8 mmol) of a methylolithium/ether solution (concentration: 1.4 mol/liter) was dropwise added at -78°C , and the mixture was reacted at room temperature for 2 days. Then, 20 ml of an ammonium chloride saturated aqueous solution was added, and the
- 15 organic phase was separated, washed with water, washed with a sodium chloride saturated aqueous solution and dried over anhydrous magnesium sulfate. Thereafter, the solvent was distilled off, and the residue was purified by column chromatography (silica gel,
- 20 developing solvent: hexane) to obtain 2.04 g of a brown liquid. The analyzed values are given below.

$^1\text{H-NMR}$ (270 MHz, in CDCl_3 , Based on TMS, main peak): δ 6.31+6.13+5.94+5.87 (s+s+t+d, 2H), 3.04+2.95 (s+s, 2H), 2.17+2.09 (s+s, 3H), 1.27 (d, 9H)

0957687 060901
10890 7897556

Peaks derived from proton of an isomer were observed in the vicinity of δ 5.5 and 5.1. From the integral value of proton, the ratio of the presence between the main product and the by-product proved to be about 8:1.

(3) Synthesis of dimethylmethylene(3-tert-butyl-5-methylcyclopentadienyl)fluorenylzirconium dichloride

Dimethylmethylene(3-tert-butyl-5-methylcyclopentadienyl)fluorenylzirconium dichloride

- 10 was synthesized in the same manner as in the steps (3) and (4) of Example 1, except that 1-tert-butyl-3-methylcyclopentadiene containing an isomer obtained in the step (2) was used.

- 15 Peaks derived from proton of an isomer were observed in the vicinity of δ 7.4 and 6.1. From the integral value of proton, the ratio of the presence between the main product and the by-product proved to be about 8:1.

20 Comparative Example 10

Bulk polymerization of propylene using
dimethylmethylene(3-tert-butyl-5-
methylcyclopentadienyl)fluorenylzirconium dichloride
containing isomer

09857687.060801

- Polymerization of propylene was carried out in the same manner as in Example 84, except that dimethylmethylene(3-tert-butyl-5-methylcyclopentadienyl)fluorenylzirconium dichloride
- 5 containing an isomer obtained in Comparative Example 9 was used. The quantity of the polymer obtained was 89 g. This polymer had Tm of 138°C, Mw of 394000 and Mn of 197000. The decane-soluble component quantity was 2.5 % by weight and was large.

10

Comparative Example 11


- Bulk polymerization of propylene using
dimethylmethylene(3-tert-butyl-5-
methylcyclopentadienyl)fluorenylzirconium dichloride
- 15 containing isomer

- Polymerization of propylene was carried out in the same manner as in Comparative Example 10, except that 2 NL of hydrogen was added. The quantity of the polymer obtained was 54 g. This polymer had Tm of
- 20 140°C, MFR of 130 g/10 min, Mw of 135000 and Mn of 34000. The decane-soluble component quantity was 4.5 % by weight and was large.

09857687 060801

What is claimed is:



1. A metallocene compound represented by the following formula (1) or (2):



wherein R³ is selected from a hydrocarbon group and a
 15 silicon-containing hydrocarbon group; R¹, R², R⁴, R⁵,
 R⁶, R⁷, R⁸, R⁹, R¹⁰, R¹¹, R¹², R¹³ and R¹⁴ may be the
 same or different and are each selected from a
 hydrogen atom, a hydrocarbon group and a silicon-
 containing hydrocarbon group; of the groups indicated
 20 by R¹ to R¹², neighboring groups may be bonded to form
 a ring; in case of the formula (1), a group selected
 from R¹, R⁴, R⁵ and R¹² may be bonded to R¹³ or R¹⁴ to
 form a ring; A is a divalent hydrocarbon group of 2 to
 20 carbon atoms which may contain an unsaturated bond
 25 and/or an aromatic ring; A may contain two or more

cyclic structures including a ring formed by A in cooperation with Y; Y is a carbon atom or a silicon atom; M is a metal selected from Group 4 of the periodic table; j is an integer of 1 to 4; Q is selected from a halogen atom, a hydrocarbon group, an anionic ligand and a neutral ligand capable of coordination by a lone pair; and when j is 2 or greater, each Q may be the same or different.

2. A metallocene compound represented by the following formula (1a) or (2a):



20


... (1a)

... (2a)


wherein R³ is selected from a hydrocarbon group and a silicon-containing hydrocarbon group; R¹, R², R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, R¹¹, R¹², R¹³ and R¹⁴ may be the same or different and are each selected from a

- hydrogen atom, a hydrocarbon group and a silicon-containing hydrocarbon group; in case of a compound of the formula (1a), when R^3 is a tert-butyl group or a trimethylsilyl group and when R^{13} and R^{14} are methyl groups or phenyl groups at the same time, R^6 and R^{11} are not hydrogen atoms at the same time; of the groups indicated by R^1 to R^{12} , neighboring groups may be bonded to form a ring; in case of the formula (1a), a group selected from R^1 , R^4 , R^5 and R^{12} may be bonded to R^{13} or R^{14} to form a ring; A is a divalent hydrocarbon group of 2 to 20 carbon atoms which may contain an unsaturated bond and/or an aromatic ring; A may contain two or more cyclic structures including a ring formed by A in cooperation with Y; Y is a carbon atom or a silicon atom; M is a metal selected from Group 4 of the periodic table; j is an integer of 1 to 4; Q is selected from a halogen atom, a hydrocarbon group, an anionic ligand and a neutral ligand capable of coordination by a lone pair; and when j is 2 or greater, each Q may be the same or different.
- 5
- 10
- 15
- 20

3. A metallocene compound represented by the following formula (1b) or (2b):



... (1b)



... (2b)

10

wherein R^{21} and R^{22} may be the same or different and are each selected from a hydrocarbon group and a silicon-containing hydrocarbon group; R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , R^{11} , R^{12} , R^{13} and R^{14} may be the same or

15

different and are each selected from a hydrogen atom, a hydrocarbon group and a silicon-containing hydrocarbon group; of the groups indicated by R^5 to R^{12} , neighboring groups may be bonded to form a ring;

20

A is a divalent hydrocarbon group of 2 to 20 carbon atoms which may contain an unsaturated bond and/or an aromatic ring; A may contain two or more cyclic structures including a ring formed by A in cooperation with Y; M is a metal selected from Group 4 of the periodic table; Y is a carbon atom or a silicon atom;

25


j is an integer of 1 to 4; Q is selected from a

halogen atom, a hydrocarbon group, an anionic ligand and a neutral ligand capable of coordination by a lone pair; and when j is 2 or greater, each Q may be the same or different.

5


4. A process for preparing a metallocene compound, comprising selectively preparing a metallocene compound represented by the following formula (1b) or (2b) so as not to include an isomeric compound represented by the following formula (3b), (4b), (5b) or (6b);

15



20

... (1b)



... (2b)


- wherein R^{21} and R^{22} may be the same or different and are each selected from a hydrocarbon group and a silicon-containing hydrocarbon group; R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , R^{11} , R^{12} , R^{13} and R^{14} may be the same or

25


00557687.060001

- different and are each selected from a hydrogen atom, a hydrocarbon group and a silicon-containing hydrocarbon group; of the groups indicated by R^5 to R^{12} , neighboring groups may be bonded to form a ring;
- 5 A is a divalent hydrocarbon group of 2 to 20 carbon atoms which may contain an unsaturated bond and/or an aromatic ring; A may contain two or more cyclic structures including a ring formed by A in cooperation with Y; M is a metal selected from Group 4 of the
- 10 periodic table; Y is a carbon atom or a silicon atom; j is an integer of 1 to 4; Q is selected from a halogen atom, a hydrocarbon group, an anionic ligand and a neutral ligand capable of coordination by a lone pair; and when j is 2 or greater, each Q may be the
- 15 same or different;

20




... (3b)




... (4b)

25

09857687.060601



... (5b)




... (6b)


wherein R²¹, R²², R⁵ to R¹⁴, A, M, Y, Q and j have the same meanings as those of R²¹, R²², R⁵ to R¹⁴, A, M, Y, Q and j in the formula (1b) or (2b), respectively.

5. The process for preparing a metallocene compound as claimed in claim 4, wherein a ligand precursor represented by the following formula (7b) or (8b) is selectively prepared so as not to include an isomeric compound represented by the following formula (9b), (10b), (11b) or (12b), and the resulting ligand precursor is used as a material to selectively prepare the metallocene compound represented by the formula (1b) or (2b);

5




... (7b)




... (8b)

- 10 wherein R²¹, R²², R⁵ to R¹⁴, A and Y have the same meanings as those of R²¹, R²², R⁵ to R¹⁴, A and Y in the formula (1b) or (2b), respectively; and the cyclopentadienyl group may be another isomer different in only the position of a double bond in the
- 15 cyclopentadienyl ring or a mixture thereof;

20




... (9b)




... (10b)

25

09557587-060801




... (11b)




... (12b)

- 10 wherein R²¹, R²², R⁵ to R¹⁴, A and Y have the same meanings as those of R²¹, R²², R⁵ to R¹⁴, A and Y in the formula (1b) or (2b), respectively; and the cyclopentadienyl group may be another isomer different in only the position of a double bond in the
- 15 cyclopentadienyl ring or a mixture thereof.

6. A process for preparing a metallocene compound as claimed in claim 5, wherein a precursor compound represented by the following formula (13b) or
- 20 (14b) is selectively prepared so as not to include an isomeric compound represented by the following formula (15b), (16b), (17b) or (18b), and the resulting precursor compound is used as a material to selectively prepare the ligand precursor represented
- 25 by the formula (7b) or (7b);




5 ... (13b)




... (14b)

wherein R²¹, R²², R¹³, R¹⁴, Y and A have the same meanings as those of R²¹, R²², R¹³, R¹⁴, Y and A in the formula (1b) or (2b), respectively;


10




15 (15a)



(16b)



(17b)



(18b)

wherein R²¹, R²², R¹³, R¹⁴, Y and A have the same meanings as those of R²¹, R²², R¹³, R¹⁴, Y and A in the formula (1b) or (2b), respectively.


20

7. A process for preparing a metallocene compound as claimed in claim 6, wherein cyclopentadiene represented by the following formula (19b) is selectively prepared so as not to include an isomeric compound represented by the following formula

25

(20b), and the resulting cyclopentadiene is used as a material to selectively prepare the precursor compound represented by the formula (13b) or (14b);

5



... (19b)

wherein R²¹ and R²² have the same meanings as those of R²¹ and R²² in the formula (1b) or (2b), respectively; and the cyclopentadienyl group may be another isomer different in only the position of a double bond in the cyclopentadienyl ring or a mixture thereof;

15



... (20b)

wherein R²¹ and R²² have the same meanings as those of R²¹ and R²² in the formula (1b) or (2b), respectively; and the cyclopentadienyl group may be another isomer different in only the position of a double bond in the cyclopentadienyl ring or a mixture thereof.

8. An olefin polymerization catalyst comprising the metallocene compound of any one of claims 1 to 3.

9. An olefin polymerization catalyst comprising:

(A) the metallocene compound of any one of claims

1 to 3, and

(B) at least one compound selected from:

5 (B-1) an organometallic compound,

(B-2) an organoaluminum oxy-compound, and

(B-3) a compound which reacts with the
metallocene compound (A) to form an ion pair.

10 10. An olefin polymerization catalyst comprising
the olefin polymerization catalyst of claim 9 and (C)
a particle carrier.

11. A process for preparing a polyolefin,
15 comprising polymerizing or copolymerizing an olefin in
the presence of the olefin polymerization catalyst of
any one of claims 8 to 10.

12. The process for preparing a polyolefin as
20 claimed in claim 11, wherein the metallocene compound
(A) is the metallocene compound represented by the
formula (1) or (2), and at least 2 kinds of olefins
are copolymerized.

09557587-060801

13. The process for preparing a polyolefin as claimed in claim 11, wherein the metallocene compound (A) is the metallocene compound represented by the formula (1a) or (2a), and a single olefin is

5 polymerized.

14. A polyolefin which comprises recurring units (U₁) derived from one α -olefin selected from α -olefins of 3 to 8 carbon atoms in amounts of 50 to 100 % by
10 mol and recurring units (U₂) other than the recurring units (U₁), said recurring units (U₂) being derived from at least one olefin selected from α -olefins of 2 to 20 carbon atoms, in amounts of 50 to 0 % by mol, and has the following properties:

15 (i) the proportion of 2,1-insertion and the proportion of 1,3-insertion are each not more than 0.2 %,

(ii) the molecular weight distribution (Mw/Mn) as determined by gel permeation chromatography is in the
20 range of 1 to 3, and

(iii) the quantity of a decane-soluble component is not more than 2 % by weight.

15. The polyolefin as claimed in claim 14, which
25 comprises recurring units derived from propylene in

09857687.060001

amounts of 50 to 99.5 % by mol and recurring units derived from at least one olefin selected from α -olefins of 2 to 20 carbon atoms other than propylene in amounts of 50 to 0.5 % by mol.

5

16. A polyolefin which is a homopolymer of one α -olefin selected from α -olefins of 3 to 8 carbon atoms and has the following properties:

- (i) the pentad isotacticity as determined from
10 ^{13}C -NMR spectrum measurement is not less than 85 %,
- (ii) the proportion of 2,1-insertion and the proportion of 1,3-insertion are each not more than 0.2 %,
- (iii) the melt flow rate (measured at 230°C under
15 a load of 2.16 kg in accordance with ASTM D1238) is in the range of 0.01 to 1000 g/10 min,
- (iv) the molecular weight distribution (M_w/M_n) as determined by gel permeation chromatography is in the range of 1 to 3,
- 20 (v) the quantity of a decane-soluble component is not more than 2 % by weight, and
- (vi) the melting point (T_m) as measured by a differential scanning calorimeter is not lower than 140°C.

25

09857687-060801
100090-28975860

17. The polyolefin as claimed in claim 16, which is a homopolymer of propylene.

18. A polyolefin which comprises recurring units
5 (U₁) derived from one α -olefin selected from α -olefins of 3 to 8 carbon atoms in amounts of 95 to 99.5 % by mol and recurring units (U₂) other than the recurring units (U₁), said recurring units (U₂) being derived from at least one olefin selected from α -olefins of 2
10 to 20 carbon atoms, in amounts of 5 to 0.05 % by mol, and has the following properties:

- (i) the pentad isotacticity as determined from ¹³C-NMR spectrum measurement is not less than 80 %,
- (ii) the proportion of 2,1-insertion and the
15 proportion of 1,3-insertion are each not more than 0.2 %,
- (iii) the melt flow rate (measured at 230°C under a load of 2.16 kg in accordance with ASTM D1238) is in the range of 0.01 to 1000 g/10 min,
- 20 (iv) the molecular weight distribution (Mw/Mn) as determined by gel permeation chromatography is in the range of 1 to 3,
- (v) the quantity of a decane-soluble component is not more than 2 % by weight, and

09857687.060801

(vi) the melting point (T_m) as measured by a differential scanning calorimeter is not higher than 145°C.

- 5 19. The polyolefin as claimed in claim 18, which
comprises recurring units derived from propylene in
amounts of 95 to 99.5 % by mol and recurring units
derived from at least one olefin selected from α -
olefins of 2 to 20 carbon atoms other than propylene
10 in amounts of 5 to 0.5 % by mol.

09857687-060801


ABSTRACT

The metallocene compound according to the invention and the olefin polymerization catalyst containing the compound are intended to produce a catalyst capable of preparing an isotactic polymer with a high polymerization activity. The metallocene compound contains a substituted cyclopentadienyl group and a (substituted) fluorenyl group and has a structure wherein these groups are bridged by a hydrocarbon group or the like. The process for preparing a metallocene compound according to the invention is intended to selectively prepare a specific metallocene compound so as not to produce an isomer, and in this process an intermediate product is synthesized by a specific method. The process for preparing a polyolefin according to the invention is intended to prepare a polyolefin having excellent impact resistance and transparency, and this process comprises homopolymerizing an α -olefin of 3 to 8 carbon atoms or copolymerizing an olefin of 3 to 8 carbon atoms and another α -olefin in the presence of an olefin polymerization catalyst containing the above-mentioned metallocene compound.

09557687-060801

Fig. 1

Transition metal component



- M: metal of Group 4 of the periodic table
 R³: hydrocarbon group, silicon-containing hydrocarbon group
 R¹, R², R⁴ - R¹⁴: hydrogen, hydrocarbon group, silicon-containing hydrocarbon group
 Y: carbon or silicon
 A: divalent hydrocarbon group
 Q: halogen, hydrocarbon group or the like
 j: integer of 1 to 4

Organometallic component

(Organometallic compound)

(Organoaluminum oxy-compound)

(Ionizing ionic compound)

(Co)polymerization
of olefin

Third component

(Carrier)

Japanese Language Declaration

(日本語宣言書)

Supplemental Priority Data Sheet

Additional prior foreign applications:

Number (番号)	Country (国名)	Day/Month/Year Filed (出願年月日)	Priority Not Claimed (優先権主張なし)
2000-250387	Japan	21/Aug./2000	claimed <input checked="" type="checkbox"/> Yes
2000-250390	Japan	21/Aug./2000	claimed <input checked="" type="checkbox"/> Yes
2000-250391	Japan	21/Aug./2000	claimed <input checked="" type="checkbox"/> Yes <input type="checkbox"/> <input type="checkbox"/>

Additional provisional applications:

Application Number (出願番号)	Filing Date (出願日)

Additional U.S. applications:

Application Number (出願番号)	Filing Date (出願日)	Status: Patented, Pending, Abandoned (現況: 特許許可済、係属中、放棄済)

Dkt. No. ZU-403**DECLARATION AND POWER OF ATTORNEY FOR PATENT APPLICATION**

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled METALLOCENE COMPOUND, PROCESS FOR PREPARING METALLOCENE COMPOUND, OLEFIN POLYMERIZATION CATALYST, PROCESS FOR PREPARING POLYOLEFIN, AND POLYOLEFIN

(check one) ☒ is attached hereto ☐ was filed on October 5, 2000 as Application Serial No. PCT/JP00/06945 and was amended on _____ (if applicable)

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37, Code of Federal Regulations, §1.56.

I hereby claim foreign priority benefits under Title 35, United States Code §119 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

Prior Foreign Application(s)		Priority Claimed	
288838/1999	Japan	8/Oct./1999	<input checked="" type="checkbox"/> YES <input type="checkbox"/> NO
(NUMBER)	(COUNTRY)	(DAY/MONTH/YEAR FILED)	
288839/1999	Japan	8/Oct./1999	<input checked="" type="checkbox"/> YES <input type="checkbox"/> NO
(NUMBER)	(COUNTRY)	(DAY/MONTH/YEAR FILED)	
288840/1999	Japan	8/Oct./1999	<input checked="" type="checkbox"/> YES <input type="checkbox"/> NO
(NUMBER)	(COUNTRY)	(DAY/MONTH/YEAR FILED)	

Continued on the attached sheet.

I hereby claim the benefit under Title 35, United States Code, §120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, §1.56 which occurred between the filing date of the prior application and the national or PCT international filing date of this applications:

(APPLICATION SERIAL NO.)	(FILING DATE)	(STATUS)
		(PATENTED, PENDING, ABANDONED)
(APPLICATION SERIAL NO.)	(FILING DATE)	(STATUS)
		(PATENTED, PENDING, ABANDONED)

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorneys and/or agents to prosecute this application and transact all business in the Patent and Trademark Office connected therewith:

Leonard W. Sherman	Reg. No. 19,636	Alan Holler	Reg. No. 29,266
Edwin A. Shalloway	Reg. No. 19,967	Karl Hoback	Reg. No. 23,026
Richard A. Steinkamp	Reg. No. 26,588	Robert L. Haines	Reg. No. 35,533
Perry Carvellas	Reg. No. 19,637		

SEND CORRESPONDENCE TO:

DIRECT TELEPHONE CALLS TO:

SHERMAN & SHALLOWAY
413 North Washington Street
Alexandria, Virginia 22314

(703) 549-2282

I further declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine and imprisonment, or both, under Section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or document or any patent issuing thereon.

Full name of sole or first inventor 1-0 Koji KAWAI
GIVEN NAME MIDDLE NAME FAMILY NAME
 Inventor's signature Koji Kawai
 Date of signature April 27, 2001
 Residence Waki-cho, Kuga-gun, Yamaguchi, Japan JPX
CITY STATE OR PROVINCE COUNTRY
 Citizenship Japanese
 Post Office Address c/o MITSUI CHEMICALS, INC., 1-2, Waki 6-chome, Waki-cho
(insert complete mailing address, including country) Kuga-gun, Yamaguchi 740-0061, Japan
 Full name of second inventor 2-0 Masahiro YAMASHITA
GIVEN NAME MIDDLE NAME FAMILY NAME
 Inventor's signature Masahiro Yamashita
 Date of signature April 27, 2001
 Residence Waki-cho, Kuga-gun, Yamaguchi, Japan JPX
CITY STATE OR PROVINCE COUNTRY
 Citizenship Japanese
 Post Office Address c/o MITSUI CHEMICALS, INC., 1-2, Waki 6-chome, Waki-cho,
(insert complete mailing address, including country) Kuga-gun, Yamaguchi 740-0061, Japan
 Full name of third inventor 3-0 Yasushi TOHI
GIVEN NAME MIDDLE NAME FAMILY NAME
 Inventor's signature Yasushi Tohi
 Date of signature April 27, 2001
 Residence Waki-cho, Kuga-gun, Yamaguchi, Japan JPX
CITY STATE OR PROVINCE COUNTRY
 Citizenship Japanese
 Post Office Address c/o MITSUI CHEMICALS, INC., 1-2, Waki 6-chome, Waki-cho,
(insert complete mailing address, including country) Kuga-gun, Yamaguchi 740-0061, Japan
 Full name of fourth inventor 4-0 Nobuo KAWAHARA
GIVEN NAME MIDDLE NAME FAMILY NAME
 Inventor's signature Nobuo Kawahara
 Date of signature April 27, 2001
 Residence Waki-cho, Kuga-gun, Yamaguchi, Japan JPX
CITY STATE OR PROVINCE COUNTRY
 Citizenship Japanese
 Post Office Address c/o MITSUI CHEMICALS, INC., 1-2, Waki 6-chome, Waki-cho,
(insert complete mailing address, including country) Kuga-gun, Yamaguchi 740-0061, Japan

50
Full name of
fifth inventor

Kenji

MICHIE

GIVEN NAME

MIDDLE NAME

FAMILY NAME

Inventor's signature

Kenji

Michie

Date of signature

April 27, 2001

Residence

Waki-cho, Kuga-gun, Yamaguchi, Japan

CITY

STATE OR PROVINCE

COUNTRY

Japanese

Citizenship

Post Office Address
(insert complete mailing
address, including country)

c/o MITSUI CHEMICALS, INC., 1-2, Waki 6-chome, Waki-cho,

Kuga-gun, Yamaguchi 740-0061, Japan

60
Full name of
sixth inventor

Hiromu

KANHEYOSHI

GIVEN NAME

MIDDLE NAME

FAMILY NAME

Inventor's signature

Hiromu

Kaneyoshi

Date of signature

April 27, 2001

Residence

Waki-cho, Kuga-gun, Yamaguchi, Japan

CITY

STATE OR PROVINCE

COUNTRY

Japanese

Citizenship

Post Office Address
(insert complete mailing
address, including country)

c/o MITSUI CHEMICALS, INC., 1-2, Waki 6-chome, Waki-cho,

Kuga-gun, Yamaguchi 740-0061, Japan

Full name of
seventh inventor

Ryoji

MORI

GIVEN NAME

MIDDLE NAME

FAMILY NAME

Inventor's signature

Ryoji

Mori

Date of signature

April 27, 2001

Residence

Waki-cho, Kuga-gun, Yamaguchi, Japan

CITY

STATE OR PROVINCE

COUNTRY

Japanese

Citizenship

Post Office Address
(insert complete mailing
address, including country)

c/o MITSUI CHEMICALS, INC., 1-2, Waki 6-chome, Waki-cho,

Kuga-gun, Yamaguchi 740-0061, Japan

Full name of
eighth inventor

GIVEN NAME

MIDDLE NAME

FAMILY NAME

Inventor's signature

Date of signature

Residence

CITY

STATE OR PROVINCE

COUNTRY

Citizenship

Post Office Address
(insert complete mailing
address, including country)